## INTERNATIONAL STANDARD



Second edition 2004-08-01

### Steel flat products for pressure purposes — Technical delivery conditions —

Part 5: Weldable fine grain steels, iTeh STthermomechanically rolled

(St produits plats en acier pour service sous pression — Conditions techniques de livraison —

Partie 5: Acters soudables à grains fins, laminés thermomécaniquement https://standards.iteh.av/catalog/standards/sist/id0cf145-159-49e6-8a58e55960987017/iso-9328-5-2004



Reference number ISO 9328-5:2004(E)

#### PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

### iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 9328-5:2004</u> https://standards.iteh.ai/catalog/standards/sist/fd0cf145-1f59-49e6-8a58e55960987017/iso-9328-5-2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

### Contents

Foreword iv					
Introdu	ntroductionv				
1	Scope	1			
2	Normative references	1			
3	Terms and definitions	1			
4 4.1 4.2	Classification and designation Classification Designation	1			
5 5.1 5.2 5.3	Information to be supplied by the purchaser Mandatory information Options Example for ordering	2 2			
6 6.1 6.2	Requirements	3			
6.3 6.4 6.5	Delivery condition ch. STANDARD PREVIEW Chemical composition Mechanical properties (standards.itch.ai) Surface condition	3 4 4			
6.6 6.7 6.8 6.9	Internal soundness	4 4 4			
7 7.1 7.2 7.3	Inspection Types of inspection and inspection documents Tests to be carried out Retests	5 5 5			
8	Sampling	5			
9	Test methods	5			
10	Marking	5			
Annex	A (normative) Chemical composition and mechanical properties of products delivered in accordance with European design codes	6			
Annex	B (normative) Chemical composition and mechanical properties of products delivered in accordance with ASME type design codes1	0			
Annex	C (informative) Steel designations in accordance with this part of ISO 9328 and designation of comparable steel grades in national or regional standards	4			
Bibliog	Jraphy1	5			

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9328-5 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 10, *Steel for pressure purposes*.

This second edition of ISO 9328-5 is a newly elaborated part of ISO 9328. The first edition (ISO 9328-5:1991) has been cancelled and replaced by ISO 9328-7.ndards.iteh.ai)

ISO 9328 consists of the following parts, under the general title *Steel flat products for pressure purposes* — *Technical delivery conditions*:

https://standards.iteh.ai/catalog/standards/sist/fd0cf145-1f59-49e6-8a58e55960987017/iso-9328-5-2004

- Part 1: General requirements
- Part 2: Non-alloy and alloy steels with specified elevated temperature properties
- Part 3: Weldable fine grain steels, normalized
- Part 4: Nickel-alloy steels with specified low temperature properties
- Part 5: Weldable fine grain steels, thermomechanically rolled
- Part 6: Weldable fine grain steels, quenched and tempered
- Part 7: Stainless steels

NOTE The clauses marked with a point (•) contain information relating to agreements which shall be made at the time of enquiry and order. The clauses marked by two points (••) contain information relating to agreements that may be made at the time of enquiry and order.

#### Introduction

This part of ISO 9328 was newly elaborated on the basis of European Standard EN 10028-5:1996 including additional steel grades. In comparison with EN 10028-5, it takes into consideration partly deviating and additional requirements, thus offering the possibility of specifying products in accordance with European design codes and ASME type design codes.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 9328-5:2004</u> https://standards.iteh.ai/catalog/standards/sist/fd0cf145-1f59-49e6-8a58e55960987017/iso-9328-5-2004

## iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 9328-5:2004</u> https://standards.iteh.ai/catalog/standards/sist/fdl0cf145-1f59-49e6-8a58e55960987017/iso-9328-5-2004

# Steel flat products for pressure purposes — Technical delivery conditions —

### Part 5: Weldable fine grain steels, thermomechanically rolled

#### 1 Scope

This part of ISO 9328 specifies the requirements for flat products for pressure equipment, made of thermomechanically rolled weldable fine grain steels as specified in Tables A.1 and B.1. The steels are not suitable for hot forming.

Until now, no sufficient data for the standardization of the elevated temperature properties of these steels are available. If their use at such temperatures is intended, the conditions for this shall be specially agreed upon between the interested parties.

The requirements and definitions of ISO 9328-1 also apply to this part of ISO 9328.

NOTE Fine grain steels are understood to be steels with a ferritic grain size of 6 or finer when tested in accordance with ISO 643.

#### ISO 9328-5:2004

https://standards.iteh.ai/catalog/standards/sist/fd0cf145-1f59-49e6-8a58-

#### 2 Normative references e55960987017/iso-9328-5-2004

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4948-1:1982, Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition

ISO 4948-2:1981, Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics

ISO 9328-1:2003, Steel plates and strips for pressure purposes — Technical delivery conditions — Part 1: General requirements

ISO 10474:1991, Steel and steel products — Inspection documents

#### 3 Terms and definitions

For the purpose of this document the terms and definitions given in ISO 9328-1 apply.

#### 4 Classification and designation

#### 4.1 Classification

In accordance with ISO 4948-1 and ISO 4948-2, all steel grades covered by in this part of ISO 9328 are alloyed special steels.

#### 4.2 Designation

See ISO 9328-1.

This part of ISO 9328 covers the steel grades specified in Annexes A and B in four series:

a) basic series (P...M, PT...M);

- b) series with low temperature properties down to 40 °C (P...ML1, PT...ML1);
- c) series with low temperature properties down to 50 °C (P...ML2 grades of Annex A only);
- d) series with low temperature properties down to 60 °C (PT...ML3 grades of Annex B only).

NOTE 1 Steel grades in Annex A are classified according to their yield strength; steel grades in Annex B are classified according to their tensile strength.

NOTE 2 Information on the designation of comparable steel grades in national or regional standards is given in Annex C.

#### 5 Information to be supplied by the purchaser

#### 5.1 Mandatory information

See ISO 9328-1.

### (standards.iteh.ai)

iTeh STANDARD PREVIEW

Additionally, for steel grades in accordance with Annex B, the test direction for the impact test shall be agreed upon (see Clause 9 and Table B.4, footnote a). ISO 9328-5:2004

#### 5.2 Options

https://standards.iteh.ai/catalog/standards/sist/fd0cf145-1f59-49e6-8a58e55960987017/iso-9328-5-2004

A number of options is specified in this part of ISO 9328. These are listed below under a) to e). Additionally, the relevant options of ISO 9328-1 apply. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the products shall be supplied in accordance with the basic specification (see ISO 9328-1).

- a) carbon equivalent value (see 6.3.3);
- b) decreased minimum Al<sub>total</sub> content (see Table B.1, footnote b);
- c) increased maximum carbon content for the grade PT550ML1 (see Table B.1, footnote c);
- d) increased maximum silicon content for the grade PT550M (see Table B.1, footnote d);
- e) other test requirements for the impact test (see Table B.4, footnote b).

#### 5.3 Example for ordering

10 plates with nominal dimensions, thickness = 50 mm, width = 2 000 mm, length = 10 000 mm, made of a steel grade with the name P355ML2 as specified in ISO 9328-5, inspection document 3.1.B as specified in ISO 10474:1991 is designated as follows:

#### 10 plates - 50 × 2 000 × 10 000 - ISO 9328-5 P355ML2 - Inspection document 3.1.B

#### 6 Requirements

#### 6.1 Steelmaking process

See ISO 9328-1.

#### 6.2 Delivery condition

The products complying with this part of ISO 9328 are supplied in the thermomechanically rolled condition.

#### 6.3 Chemical composition

**6.3.1** The requirements in Table A.1 and Table B.1 apply for the chemical composition according to the cast analysis.

**6.3.2** The product analysis may deviate from the specified values of the cast analysis given in Table A.1 and Table B.1 by the values given in Table 1.

**6.3.3** •• For steel grades covered by this part of ISO 9328, a carbon equivalent value according to Table A.2 (steel grades in Annex A) or Table B.2 (steel grades in Annex B) may be agreed upon at the time of enquiry and order.

Element	Specified value in the cast site analysis according to Tables A.1 and B.1	ermissible deviation <sup>a</sup> of the product analysis
	% by mass <sub>ISO 9328-5:2004</sub>	% by mass
С	https://standards.iteh.ai/20talog/standards/sist/fd0	cf145-1f59-49e6-8a58- + 0,02
Si	e55960987017/iso-9328-5-2 ≤ 0,75	+ 0,06
Mn	≤ 1,70	+ 0,10
Р	≤ 0,030	+ 0,005
S	≼ 0,015	+ 0,003
3	$>$ 0,015 to $\leqslant$ 0,030	+ 0,005
AI	≥ 0,020	- 0,005
N	≤ 0,020	+ 0,002
Мо	≤ 0,20	+ 0,03
Nb	≤ 0,05	+ 0,01
Ni	≤ 0,50	+ 0,05
Ti	≤ 0,05	+ 0,01
V	≤ 0,10	+ 0,01
$Cr + Cu + Mo^b$	≤ 0,60	+ 0,10
$V + Nb + Ti^b$	≤ 0,15	+ 0,03

## Table 1 — Permissible deviations of the chemical composition from the results of the product analysis from the specified values applicable to the cast analysis

<sup>a</sup> If several product analyses are carried out on one cast, and the contents of an individual element, as determined, lie outside the permissible range of the chemical composition specified for the cast analysis, then it is allowed either to exceed the permissible maximum value or fall short of the permissible minimum value, but not both for one cast.

Only specified for grades in Annex A..

b

#### 6.4 Mechanical properties

The values given in Tables A.3 and A.4 as well as in Tables B.3 and B.4 apply (see also ISO 9328-1).

#### 6.5 Surface condition

See ISO 9328-1.

#### 6.6 Internal soundness

See ISO 9328-1.

#### 6.7 Weldability

**6.7.1** The steels specified in this part of ISO 9328 shall be suitable for welding processes in current use (see NOTE to 6.7.2).

**6.7.2** The manufacturer shall, if requested, provide the purchaser with data on suitable welding conditions determined on the basis of weld procedure tests.

With increasing product thickness and strength level, cold cracking can occur. Cold cracking is caused by the following factors in combination:

- the amount of diffusible hydrogen in the weld metal; The second secon
- brittle structure of the heat-affected zone (standards.iteh.ai)
- tensile stress concentrations in the welded joint.

ISO 9328-5:2004

When using recommendations as laid down in appropriate documents, et. g., 4EN-1011-1 and EN 1011-2 or IIS/IIW-382-71, the recommended welding conditions and the various welding ranges of the steel grades can be determined depending on the product thickness, the applied welding energy, the design requirements, the electrode efficiency, the welding process and the weld metal properties.

NOTE Excessive post-weld heat treatment (PWHT) conditions may decrease the mechanical properties. When, on stress relieving, the intended time-temperature parameter

$$P = T_{\rm s} (20 + \lg t) \times 10^{-3}$$

where

- $T_{\rm s}$  is the stress relieving temperature in Kelvin and
- *t* is holding time in hours

exceeds the critical P value of  $P_{crit} = 17$  (steel grades in accordance with Annex A) or, where regarded as necessary in the case of Annex B steel grades, the purchaser should, in his enquiry and order, inform the manufacturer accordingly and, where appropriate, tests on simulated post-weld heat-treated samples may be agreed upon in order to check whether after such a treatment the properties specified in this part of ISO 9328 can still be regarded as valid.

#### 6.8 Dimensions and tolerances

See ISO 9328-1.

#### 6.9 Calculation of mass

See ISO 9328-1.

#### 7 Inspection

#### 7.1 Types of inspection and inspection documents

See ISO 9328-1.

#### 7.2 Tests to be carried out

See ISO 9328-1.

#### 7.3 Retests

See ISO 9328-1.

#### 8 Sampling

See ISO 9328-1.

•• For the impact test, deviating from ISO 9328-1:2003, Table 3, footnote c, the preparation of test pieces taken from the mid-thickness may be agreed upon at the time of enquiry and order. In this case, test temperatures and minimum impact energy values shall also be agreed.

## 9 Test methods iTeh STANDARD PREVIEW

See ISO 9328-1.

## (standards.iteh.ai)

• Impact tests for verification of impact energy values in Tables A.4 and B.4 shall be carried out on transverse test pieces (steel grades in accordance with Annex A) of on test pieces specified in the order (steel grades in accordance with Annex B//See Table B.4 footnote a) ds/sist/fd0cf145-1f59-49e6-8a58e55960987017/iso-9328-5-2004

### 10 Marking

See ISO 9328-1.