INTERNATIONAL STANDARD

ISO 22608

First edition 2004-07-01

Protective clothing — Protection against liquid chemicals — Measurement of repellency, retention, and penetration of liquid pesticide formulations through protective clothing materials

Teh ST Vêtements de protection — Protection contre les produits chimiques liquides — Mesurage de la répulsion, de la rétention et de la pénétration des formulations de pesticides liquides à travers les matériaux des vêtements de protection

ISO 22608:2004 https://standards.iteh.ai/catalog/standards/sist/164b545d-1ecb-4cf8-afce-76e86ee741f4/iso-22608-2004



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22608:2004 https://standards.iteh.ai/catalog/standards/sist/164b545d-1ecb-4cf8-afce-76e86ee741f4/iso-22608-2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents		Page
Forev	word	iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	2
5 5.1 5.2 5.3	Apparatus Apparatus and materials for contamination of test specimen Apparatus for analysis using Method A Apparatus and materials for analysis using Method B	3 3
6	Test specimens	6
7	Selection of analytical technique	7
8 8.1 8.2 8.3 8.4	Preparation of test apparatus and materials Calibration of the pipettor Preparation of test assembly A.N.D.A.R.D. PREVIEW Conditioning of test specimen Testing temperature (Standards.iteh.ai)	7 7 8 8
9 9.1 9.2	Method A Contamination of test specimen ISO 22608:2004 Calculation https://standards.iteh.ai/catalog/standards/sist/164b545d-1ecb-4cf8-afce-	8 8 8
10 10.1 10.2 10.3 10.4 10.5 10.6	Method B	9 9 10
11	Precision and bias	11
12	Test report	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 22608 was prepared by Technical Committee ISO/TC 94, *Personal safety — Protective clothing and equipment*, Subcommittee SC 13, *Protective clothing*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22608:2004 https://standards.iteh.ai/catalog/standards/sist/164b545d-1ecb-4cf8-afce-76e86ee741f4/iso-22608-2004

Introduction

The health and safety of workers involved in the mixing, loading and application of liquid pesticides can be affected by dermal exposure to liquid pesticide formulations. Use of protective clothing can assist in minimizing the danger of contact with potentially harmful pesticides. Nonporous materials that provide excellent protection to the user are usually not suitable for many environments where there is a potential for heat stress. Therefore, garments made of porous materials that can provide a balance between risk from pesticide exposure and user comfort can be used as personal protective equipment (PPE) for workers.

The movement of liquid pesticides through these materials is primarily due to penetration through spaces between fibres and interstices between yarns. As these materials provide protection either by repelling or retaining liquid pesticide, the measurement of these properties are also important. This test method is used to measure repellency, retention, and penetration of liquid pesticides through protective clothing materials.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22608:2004 https://standards.iteh.ai/catalog/standards/sist/164b545d-1ecb-4cf8-afce-76e86ee741f4/iso-22608-2004

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22608:2004

https://standards.iteh.ai/catalog/standards/sist/164b545d-1ecb-4cf8-afce-76e86ee741f4/iso-22608-2004

Protective clothing — Protection against liquid chemicals — Measurement of repellency, retention, and penetration of liquid pesticide formulations through protective clothing materials

1 Scope

This International Standard specifies a test method to measure repellency, retention and penetration of a known volume of liquid pesticide when applied to protective clothing material. No external hydrostatic or mechanical pressure is applied to the test specimen during or after the application of the liquid pesticide.

The degree of contamination depends on numerous factors such as type of exposure, application technique, and pesticide formulation. As the level of exposure can vary considerably, this method is designed to rate relative performance of personal protective equipment (PPE) materials at two levels of contamination. Low level of contamination is achieved by applying 0,1 ml liquid formulation and high level by applying 0,2 ml.

This test method does not measure resistance to permeation or degradation.

This test method is suitable for field strength and concentrated pesticide formulations. This method may not be suitable for testing protective clothing materials against volatile pesticides formulations.

This International Standard is applicable to the evaluation of materials that are new or those that have undergone treatment such as laundering, or simulated abrasion. Details of the treatment shall be reported. This test method can also be used to determine the resistance provided by protective clothing materials against penetration of new pesticide formulations.

76e86ee741f4/iso-22608-2004

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2859-1:1999, Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3 1

analytical technique

procedure whereby the concentration of the test chemical in a collection medium is quantitatively determined

NOTE The procedure selected is based on the test liquid to be analysed. Applicable techniques include, but are not limited to, gas chromatography, high pressure liquid chromatography, gravimetric analysis, and radionuclide tagging/detection counting.

3.2

coated fabric

flexible material composed of a textile fabric and an adherent polymeric or other material applied to one or both surfaces

© ISO 2004 – All rights reserved

3.3

test liquid

mixture of raw materials, including but not limited to, active ingredients, inert ingredients and a base solvent used in pesticide formulation

NOTE Additional ingredients could include emulsifiers and surfactants. Solvents used in the formulation could be water, isopropyl alcohol, or petroleum distillate. Solid materials (powders, granules, etc.) may be dissolved or emulsified to form a liquid or suspension. These formulations may be ready to use or concentrates that require dilution to field strength.

3.4

penetration

flow of a chemical through closures, porous materials, seams, and holes or other imperfections in a protective clothing material on a non-molecular level

permeation

process by which a chemical moves through a protective clothing material on a molecular level

NOTE Permeation involves

- sorption of molecules of the chemical into the contacted (outside) surface of a material, a)
- diffusion of the sorbed molecules in the material, and b)
- desorption of the molecules from the opposite (inside) surface of the material. C)

3.6

liquid retention

liquid retained in the protective clothing material under the conditions of this test

3.7

(standards.iteh.ai)

protective clothing material

any material or combination of materials used in an item of clothing for the purpose of isolating parts of the body from a potential hazard https://standards.itch.ai/catalog/standards/sist/164b545d-1ecb-4cf8-afce-76e86ee741f4/iso-22608-2004

For the purposes of this International Standard, protective clothing materials include those materials used in the construction of the suit or clothing that serve as the primary barrier for the wearer. Protective clothing materials do not include materials used in the construction of integral visors, gloves, and footwear.

3.8

liquid repellency

characteristic to resist wetting and penetration by a liquid

Principle

A test liquid is applied using a pipettor to the surface of the test assembly, which consists of single or multiple layer protective clothing material (test specimen) and an absorbent paper backed by polyethylene film (collector layer).

After a specified time, another absorbent paper backed by polyethylene film (top layer) is placed on the surface of the test specimen to remove the remaining liquid.

The top layer, contaminated test specimen and the collector layer are separated.

The amount of test liquid in each layer is measured either by gravimetric analysis (weighing) or by other appropriate analytical techniques.

Method A is a gravimetric method that measures the mass of the test liquid in each layer, whereas Method B is an analytical method that requires extraction of the test liquid and measures the mass of the active ingredient.

Data is obtained to calculate percent repellency, pesticide retention, and penetration.

5 Apparatus

5.1 Apparatus and materials for contamination of test specimen

5.1.1 Test liquid, to contaminate the test specimen.

Magnetic or other stirrer shall be used for liquids that may settle during application.

5.1.2 Pipettor, with disposable pipette tip, mounted on a support stand, for pipetting (0.1 ± 0.002) ml of liquid for low contamination level and (0.2 ± 0.004) ml for high contamination level (see Figure 1).

Multidispensing shall not be used for test liquids that may settle during application.

NOTE Liquid viscosity, user experience and temperature can affect accuracy and precision. Additional information on selection of pipettor can be obtained from the manufacturer.

5.1.3 Test specimen holder, consisting of a base plate $100 \text{ mm} \times 100 \text{ mm}$ (see Figure 2) and a cover plate $100 \text{ mm} \times 100 \text{ mm}$ with a $60 \text{ mm} \times 60 \text{ mm}$ opening in the centre (see Figure 3).

The test specimen holder is made of polymethyl methacrylate (4 mm thickness) or other suitable material. The mass of the cover plate shall be 30 g to 35 g.

- **5.1.4** Timer, accurate to nearest 1 s.
- **5.1.5 Absorbent paper**, two 80 mm × 80 mm squares backed by polyethylene film per test specimen, one square of which is used to measure penetration, and the other to measure repellency, both having the following characteristics¹⁾: (standards.iteh.ai)
- base mass: 160 g/m^2

ISO 22608:2004

— thickness https://standards.iteh.a590alpm/sat/53 kParland 1710 um at 10 kPa-

76e86ee741f4/iso-22608-2004

typical water absorption value 75 mg/cm²

Substitutions are not recommended, because due to differences in sorptive properties; use of absorbent papers other than that specified may affect the test results.

- **5.1.6 Container**, to discard contaminated materials.
- 5.2 Apparatus for analysis using Method A
- **5.2.1 Balance**, accurate to the nearest 0,001 g.
- 5.2.1 Tweezers.
- 5.3 Apparatus and materials for analysis using Method B
- **5.3.1 Solvent**, appropriate for extraction of pesticide.

NOTE Selection of the solvent is dependent on the test liquid and the analytical method used. A minimum extraction efficiency of 95 % is required. Procedure to calculate extraction efficiency is given in 10.2. Solvent with high volatility may not be appropriate, as there may be evaporation loss during handling operations.

© ISO 2004 – All rights reserved

-

¹⁾ Benchkote® Plus is the trade name of a polyethylene-backed absorbent paper manufactured by Whatman, available through scientific product suppliers or directly from Whatman (www.whatman.com). This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.