
**Glass in building — Fire-resistant glazed
assemblies containing transparent or
translucent glass, for use in building**

*Verre dans la construction — Ensembles vitrés résistant au feu, comportant
du verre transparent ou translucide, pour utilisation dans le bâtiment*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9051:2001

[https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-
c73830f1fb01/iso-9051-2001](https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-c73830f1fb01/iso-9051-2001)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9051:2001

<https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-c73830f1fb01/iso-9051-2001>

© ISO 2001

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 9051 was prepared by Technical Committee ISO/TC 160, *Glass in building*, Subcommittee SC 2, *Use considerations*.

This second edition cancels and replaces the first edition (ISO 9051:1990) of which it constitutes a minor revision.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 9051:2001](https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-c73830f1fb01/iso-9051-2001)

<https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-c73830f1fb01/iso-9051-2001>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9051:2001

<https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-c73830f1fb01/iso-9051-2001>

Glass in building — Fire-resistant glazed assemblies containing transparent or translucent glass, for use in building

1 Scope

This International Standard specifies the classification and marking of transparent and translucent glass products, which will be described in future International Standards on basic or processed glass products, in assemblies for use in building and intended to provide some degree of fire-resistance.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 834-1:1999, *Fire-resistance tests — Elements of building construction — Part 1: General requirements*

ISO 3009, *Fire resistance tests — Elements of building construction — Glazed elements*

3 Fire-resistance characteristics of glazed assemblies

Glass is a non-combustible material and therefore will not contribute to or propagate fire.

If affected by heat, glass may fracture by thermal shock or may soften and then not be held by the frame. Only certain types of glazed assemblies are, therefore, recognized as fire-resisting. The ability of glazed assemblies to resist fire depends on the type of glass product, glazing method, frame type, pane size, fixing method and the type of construction surrounding the glazed area.

Some transparent and translucent glazed assemblies can meet requirements for stability and integrity (RE), and in some cases insulation (REI, where R is for resistance, E for integrity and I for insulation).

Not only is the possibility of direct propagation of fire and smoke through openings caused by glass breakage to be considered for fire protection precautions, it may also be necessary to take into account the heat transmitted through the glazed assembly, which may still be intact, as such heat may cause ignition of combustible materials.

4 Classes

As glazed assemblies perform differently in case of fire, the type shall be classified into one of the following categories.

a) Class RE

Glazed assemblies of fire-resistance according to class RE under the fire conditions as defined in ISO 834-1 provide, for a given time, stability and integrity. The temperature of the unexposed side is not taken into account.

b) Class REI

Glazed assemblies of fire-resistance according to class REI under the fire conditions as defined in ISO 834-1 provide, for a given time, stability, integrity and insulation.

5 Frame, glass, glazing material and surrounding construction

The frame, glazing material and surrounding construction shall be such that the glazed assembly as a whole corresponds to the test report.

Glazings of class RE could, for example, contain

- glass blocks,
 - glass with a low coefficient of thermal expansion, or glass ceramics,
 - glass toughened by thermal or chemical treatment,
 - wired glass,
 - flat glass in small panes, or
 - laminated glass,
- <https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-c73830f1fb01/iso-9051-2001>

in single or multiple glazings.

Glazings of class REI could, for example, contain

- some types of glass blocks, or
- some types of laminated glazings in single or multiple glazings.

6 Test requirements

6.1 Specimens

A specimen, for the purposes of this International Standard, is a complete glazed assembly.

6.2 Installation

The fixing of the specimen into the furnace opening shall be in accordance with ISO 3009.

6.3 Procedure

The test procedure shall be in accordance with ISO 3009, and for the temperature of the unexposed side (class REI), see ISO 834-1:1999, subclause 5.5.12, with at least one thermocouple for the measurement of the maximum temperature on the glazing.

6.4 Criteria

A glazed assembly for fire-resistance class RE shall meet the integrity requirements of ISO 3009 (see Table 1).

A glazed assembly for fire-resistance class REI shall meet both the integrity requirements of ISO 3009 and the insulation requirements of ISO 834-1 (see Table 1).

7 Test report

The test report shall state the following information:

- a) name of test laboratory;
- b) name of sponsor(s);
- c) date of tests;
- d) name(s) of manufacturer(s) and trade name(s) (if any) of the major components of the glazed assembly;
- e) details of materials, construction and conditioning of the assembly tested;
- f) description of the fixings between the assembly tested and the test frame or surround;
- g) side exposed to heat;
- h) test result as determined by the furnace time/pressure chart and temperature curves, and the time(s) at which particular criteria in 6.4 are no longer satisfied;
- i) any other relevant observations;
- j) fire-resistance class(es) RE and/or REI and code number(s) according to Table 1.

Table 1 — Fire-resistance time

Code number	Resistance time min
15	15 to 29
30	30 to 44
45	45 to 59
60	60 to 89
90	90 to 119
120	120 or more

8 Marking

If marking is essential, the following particulars shall be indelibly and distinctly marked on every glazed assembly, in a position which is visible to anyone requiring the information:

- a) manufacturer's name or trademark;
- b) the number of this International Standard, i.e. ISO 9051;
- c) fire-resistance class RE and/or REI;
- d) code number(s) for the resistance time(s).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9051:2001

<https://standards.iteh.ai/catalog/standards/sist/4b7d7231-66ba-40d7-b4c5-c73830f1fb01/iso-9051-2001>

ICS 81.040.20

Price based on 3 pages