INTERNATIONAL STANDARD



Third edition 2005-10-15

Implants for surgery — Metallic materials —

Part 5: Wrought cobalt-chromium-tungstennickel alloy

iTeh STANDARD PREVIEW Implants chirurgicaux — Produits à base de métaux — Stratie 5: Ailiage corroyé à base de cobalt, de chrome, de tungstène et

de nickel ISO 5832-5:2005 https://standards.iteh.ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-8bbe50d8a817/iso-5832-5-2005



Reference number ISO 5832-5:2005(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 5832-5:2005

https://standards.iteh.ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-8bbe50d8a817/iso-5832-5-2005

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5832-5 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.

This third edition cancels and replaces the second edition (ISO 5832-5:1993), which has been technically revised. (standards.iteh.ai)

ISO 5832 consists of the following parts, under the general title *Implants for surgery* — *Metallic materials*:

- Part 1: Wrought stainless steel ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-8bbe50d8a817/iso-5832-5-2005
- Part 2: Unalloyed titanium
- Part 3: Wrought titanium 6-aluminium 4-vanadium alloy
- Part 4: Cobalt-chromium-molybdenum casting alloy
- Part 5: Wrought cobalt-chromium-tungsten-nickel alloy
- Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy
- Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy
- Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy
- Part 9: Wrought high nitrogen stainless steel
- Part 11: Wrought titanium 6-aluminium 7-niobium alloy
- Part 12: Wrought cobalt-chromium-molybdenum alloy

Introduction

No known surgical implant material has ever been shown to be completely free of adverse reactions in the human body. However, long-term clinical experience of the use of the material referred to in this part of ISO 5832 has shown that an acceptable level of biological response can be expected, if the material is used in appropriate applications.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 5832-5:2005 https://standards.iteh.ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-8bbe50d8a817/iso-5832-5-2005

Implants for surgery — Metallic materials —

Part 5: Wrought cobalt-chromium-tungsten-nickel alloy

1 Scope

This part of ISO 5832 specifies the characteristics of, and corresponding test methods for, wrought cobaltchromium-tungsten-nickel alloy for use in the manufacture of surgical implants.

NOTE The tensile properties of a sample obtained from a finished product made of this alloy might not necessarily comply with those specified in this part of ISO 5832.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 643, Steels — Micrographic determination of the apparent grain size

ISO 4967:1998, Steel — Determination of <u>icontent_of_nonmetallic</u> inclusions — Micrographic method using standard diagrams https://standards.iteh.ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-

ISO 6892, Metallic materials — Tensile testing at ambient temperature

3 Chemical composition

The analysis of a representative sample of the alloy when determined as specified in Clause 6 shall comply with the chemical composition specified in Table 1.

Element	Compositional limits mass fraction %	
Chromium	19 to 21	
Tungsten	14 to 16	
Nickel	9 to 11	
Iron	≤ 3	
Carbon	≼ 0,15	
Silicon	≤ 1	
Manganese	≤ 2	
Sulfur	0,03	
Phosphorus	0,04	
Cobalt	Balance	

Table 1 — Chemical composition

4 Microstructure

4.1 Grain size index

Samples shall be prepared and etched for examination by any recognized technique. The grain size measured in accordance with ISO 643 shall be 5 or finer.

NOTE ISO 643 is given as a reference even though the material dealt with in this part of ISO 5832 is not iron-based.

4.2 Inclusion content

A longitudinal sample suitably polished shall be examined in accordance with ISO 4967, Method A, and shall not exhibit inclusions in excess of those specified in Table 2.

Type of inclusion	Inclusion content: thin ^a	
A — Sulfides	1	
B — Aluminates	3	
C — Silicates	1	
D — Oxides (globular)	3	
a Thick inclusions are allowed until 0,5-RD PREVIEW		

Table 2 — Inclusion content limits

(standards.iteh.ai)

5 Tensile properties

<u>ISO 5832-5:2005</u>

https://standards.iteh.ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-

The tensile properties of the alloy, determined as specified in Clause 6, shall be in accordance with the requirements of Table 3.

The level of mechanical properties for material in other than the annealed condition shall be specified in the purchase order.

Condition	Tensile strength	0,2 % offset proof stress	Percentage elongation
	MPa	MPa	%
Annealed	≥ 860	≥ 310	≥ 30

Table 3 — Tensile properties

6 Test methods

The test methods to be used in determining compliance with the requirements of this part of ISO 5832 shall be those given in Table 4.

Representative test pieces for the determination of tensile properties shall be prepared in accordance with ISO 6892.

Requirement	Relevant clause or subclause	Test methods
Chemical composition	Clause 3	Recognized analytical procedures (ISO methods where these exist)
Tensile properties	Clause 5	ISO 6892
Grain size	4.1	ISO 643
Inclusion content	4.2	ISO 4967

Table 4 — Test methods

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 5832-5:2005

https://standards.iteh.ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-8bbe50d8a817/iso-5832-5-2005

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 5832-5:2005 https://standards.iteh.ai/catalog/standards/sist/e040c5ea-e691-4117-b14e-8bbe50d8a817/iso-5832-5-2005

ICS 11.040.40 Price based on 3 pages