



Designation: A 476 – 90 (Reapproved 1997)

Standard Specification for Ductile Iron Castings for Paper Mill Dryer Rolls^{1,2}

This standard is issued under the fixed designation A 476; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers ductile iron castings for use in pressure containing paper mill dryer rolls at temperatures up to 450°F.

1.2 No precise quantitative relationship can be stated between the properties of the iron in various locations of the same casting or between the properties of a casting and those of a test specimen cast from the same iron (see Appendix X1).

1.3 A complete metric companion to Specification A 476 has been developed—A 476M; therefore, no metric equivalents are presented in this specification.

2. Referenced Documents

2.1 ASTM Standards:

- A 644 Terminology Relating to Iron Castings³
- E 8 Test Methods for Tension Testing of Metallic Materials⁴
- E 10 Test Method for Brinell Hardness of Metallic Materials⁴
- E 94 Guide for Radiographic Testing⁵
- E 446 Reference Radiographs for Steel Castings Up to 2 in. (51 mm) in Thickness⁵

3. Terminology

3.1 Definitions for many terms common to iron castings are found in Terminology A 644.

4. Ordering Information

4.1 Orders for material purchased to the requirements of this specification should include the following information:

- 4.1.1 Quantity,
- 4.1.2 Specification number and date of issue,
- 4.1.3 Description of casting by pattern number or drawing,
- 4.1.4 Heat treatment, if required (see 5.1),
- 4.1.5 Type of test coupon (see 8.2),

- 4.1.6 Certification, if required (see 12.1),
- 4.1.7 Marking location (see 13.1), and
- 4.1.8 Additional requirements.

5. Heat Treatment

5.1 The castings may be stress relieved at a temperature not to exceed 1200°F.

6. Mechanical Properties

6.1 The iron represented by test coupons shall conform to tensile requirements prescribed in Table 1.

6.2 The yield strength prescribed in Table 1 may be determined by any of the approved procedures described in 7.3 of Test Methods E 8.

6.3 The Brinell hardness of the material shall be a minimum of 201 HB. Hardness tests shall be conducted in accordance with Test Method E 10, using a 3000-kgf load. The test may be made on either the casting or on a test coupon representing the casting.

7. Workmanship, Finish, and Appearance

7.1 The castings shall conform to the dimensions on the drawings furnished by the purchaser, or if no drawing has been provided, to the dimensions predicated by the pattern supplied by the purchaser. Surfaces of the castings shall be free of adhering sand. Runners, risers, fins, and other extraneous metal shall be removed.

8. Sampling

8.1 Test coupons shall be poured from the same iron as the castings represented.

8.2 Test coupons shall be cast either to the “Y” block size and shape shown in Fig. 1 or to the dimensions of the 1-in. keel block shown in Fig. 2. The type of test coupon and, when selected, the size of the “Y” block shall be specified by the purchaser.

8.3 The test coupons shall be cast in open molds made of suitable core sand with a minimum 1½ in. of sand for the 1-in. size and 3 in. of sand for the 3-in. size. The coupons shall be left in the mold until black.

8.4 Table 2 shows the equivalent geometrical shapes with various dimensions and the equivalent “Y” block, based on cooling rates, and may be used as a guide for selection of the proper “Y” block to be specified to represent the casting.

¹ This specification is under the jurisdiction of ASTM Committee A-4 on Iron Castings and is the direct responsibility of Subcommittee A04.02 on Malleable and Ductile Iron Castings.

Current edition approved Sept. 28, 1990. Published November 1990. Originally published as A 476 – 62 T. Last previous edition A 476 – 70 (1976).

² For ASME Boiler and Pressure Vessel Code Applications see related Specifications SA-467 in Section II of that Code.


³ Annual Book of ASTM Standards, Vol 01.02.

⁴ Annual Book of ASTM Standards, Vol 03.01.

⁵ Annual Book of ASTM Standards, Vol 03.03.

TABLE 1 Tensile Requirements


Test Coupon Section Thickness	1 in.	3 in.
Tensile strength, min, ksi	80	80
Yield strength, min, ksi	60	60
Elongation in 2 in., min, %	3.0	1.0



"Y" Block Size

Dimensions	"Y" Block Size	
	For Castings of Thickness 1/2 in. to 1 1/2 in.	For Castings of Thickness of 1 1/2 in. and Over
	in.	in.
A	1	3
B	1 1/8	5
C	3	4
D	6	8
E	7	7
	approx	approx

FIG. 1 "Y" Blocks for Test Coupons



NOTE—The length of keel block shall be 6 in.

FIG. 2 Keel Block for Test Coupons

8.5 When the castings are heat treated, the test coupons shall be heat treated with the castings they represent.

9. Tension Test


9.1 Tension test specimens shall be obtained from test coupons shown in either Fig. 1 or Fig. 2, and machined to the dimensions shown in Fig. 3. Test coupons cast as "Y" blocks (Fig. 1) shall be sectioned as shown in Fig. 4.

9.2 One tension test shall be performed for each casting.

9.3 If any specimen shows defective machining or flaws, it may be discarded and another substituted from the same casting represented.

TABLE 2 Equivalent Geometric Shapes Corresponding to "Y" Blocks

"Y" Block Size, in.	Infinite Plate Thickness, in.	Round Diameter, in.	Cube Edge, in.
1	0.9	1.75	2.75
3	1.6	3.1	4.8



NOTE—The gage length and fillets shall be as shown, but the ends may be of any shape to fit the holders of the testing machine in such a way that the load shall be axial. The reduced section shall have a gradual taper from the ends toward the center, with the ends 0.003 to 0.005 in. larger in diameter than the center.

FIG. 3 Standard Round Tension Test Specimen with 2-in. Gage Length

9.4 If an apparently sound test specimen fails to conform to the tensile requirements, two retests may be made. If either retest fails to conform to the requirements specified, the castings shall be rejected.

10. Repairs

10.1 Castings made to this specification that leak on subsequent hydrostatic testing may be repaired by using threaded plugs provided the following requirements are met.

10.1.1 No welding or brazing shall be permitted.

10.1.2 The diameter of the plug shall not exceed the diameter of a standard 2-in. iron pipe size pipe plug.

10.1.3 The plugs, where practical, shall conform in all dimensions to the standard iron pipe size pipe plugs. In addition, they shall have full thread engagement corresponding to the thickness of the repaired section. Where a tapered plug is impractical because of the excess wall thickness in terms of plug diameter and coincident thread engagement, other types of plugs may be used provided both full thread engagement and effective sealing against pressure are obtained. Where possible the ends of the plugs should be ground smooth after installation to conform to the inside and outside contours of the cylinder.

10.1.4 The material from which the plug is manufactured shall conform in all respects to this specification.

10.1.5 The area adjacent to the drilled hole should be examined radiographically in accordance with Guide E 94. The area examined shall meet the requirements of Severity Level 3 of Reference Radiographs E 446.

10.1.6 The thickness of any repaired section in relation to the size of plug used shall be not less than that given in Table 3.

10.1.7 The minimum radius of curvature of the repaired section of the cylinder in relation to the size of plug used shall be not less than that given in Table 4.

10.1.8 A repaired area may consist of a maximum of three plugs with a spacing such that the distance between adjacent