



SLOVENSKI STANDARD SIST ISO 589:2005

01-november-2005

fb]`dfYa c[`E`8 c`c Yj Ub`Y`W`cHbY`j`U` Y

Hard coal -- Determination of total moisture

Houille -- Détermination de l'humidité totale

ITEH STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: ISO 589:2003

[SIST ISO 589:2005](https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbaf6149022/sist-iso-589-2005)

<https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbaf6149022/sist-iso-589-2005>

ICS:

73.040

Premogi

Coals

SIST ISO 589:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 589:2005

<https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbafc149022/sist-iso-589-2005>

INTERNATIONAL STANDARD

**ISO
589**

Third edition
2003-11-15

Hard coal — Determination of total moisture

Houille — Détermination de l'humidité totale

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 589:2005](https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbaf6149022/sist-iso-589-2005)

<https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbaf6149022/sist-iso-589-2005>



Reference number
ISO 589:2003(E)

© ISO 2003

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 589:2005

<https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbafc149022/sist-iso-589-2005>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope.....	1
2 Normative references	1
3 Terms and definitions.....	1
4 Principle	2
4.1 Method A (two-stage methods)	2
4.2 Method B (single-stage methods)	2
5 Reagent	2
6 Apparatus.....	2
7 Sample.....	3
7.1 General	3
7.2 Sampling and sample preparation	3
7.3 Precautions against loss of moisture	3
7.4 Moisture determination with on-site treatment (method A only)	4
7.5 Moisture determination without on-site treatment (methods A and B)	4
8 Procedure.....	4
8.1 Methods A 1 and A 2 (two-stage methods)	4
8.2 Methods B (single-stage method)	6
9 Precision	7
9.1 Repeatability limit	7
9.2 Reproducibility critical difference	7
10 Test report.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 589 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 589:1981), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 589:2005

<https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbaf6149022/sist-iso-589-2005>

Introduction

Moisture is an important parameter in respect of coal quality.

The moisture content of coal is not an absolute value and conditions for its determination have to be standardized. Results given by the different methods specified here should be comparable within the limits of the tolerance quoted.

The determination of the total moisture content of hard coals is always to be considered in close connection with sampling. Therefore this International Standard has been prepared in close relationship with the series ISO 13909, *Hard coal and coke — Mechanical sampling*.

A major problem with the preparation of test samples for the determination of moisture is the risk of bias due to inadvertent loss of moisture. This is dependent on the tightness of the sealing of sampling containers, the level of moisture content in the sample, the ambient conditions, the type of coal and the reduction and division procedures used. This is described in detail in ISO 13909-4.

Depending on the mass, the nominal top size and the facilities available where samples are taken, it is possible to dry the sample directly after sampling (air-drying), then to reduce the particle size and prepare a test sample for determination of moisture in the air-dried sample. Alternatively, the whole sample may be transported to the laboratory and the total moisture determined.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 589:2005](https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbafc149022/sist-iso-589-2005)

<https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbafc149022/sist-iso-589-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 589:2005

<https://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbafc149022/sist-iso-589-2005>

Hard coal — Determination of total moisture

1 Scope

This International Standard describes two methods for the determination of the total moisture content of hard coals. Depending on the coal rank, there may be systematic differences between the results obtained by applying different methods on subsamples of the same sample. Methods using a nitrogen atmosphere are suitable for all hard coals; methods with drying in air are only suitable for hard coals not susceptible to oxidation.

NOTE The term “not susceptible to oxidation” cannot be defined easily. Usually, coals very high in rank are not oxidized under the conditions described in this standard. For all other types of coal this has to be verified by experiments.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1213-2, *Solid mineral fuels — Vocabulary — Part 2: Terms relating to sampling, testing and analysis*

[SIST ISO 589:2005](http://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbafc149022/sist-iso-589-2005)

ISO 1988, *Hard coal — Sampling*
<http://standards.iteh.ai/catalog/standards/sist/bf83189c-9f63-4bbc-bba3-cbbafc149022/sist-iso-589-2005>

ISO 11722, *Solid mineral fuels — Hard coal — Determination of moisture in the general analysis test sample by drying in nitrogen*

ISO 13909-1:2001, *Hard coal and coke — Mechanical sampling — Part 1: General introduction*

ISO 13909-2:2001, *Hard coal and coke — Mechanical sampling — Part 2: Coal — Sampling from moving streams*

ISO 13909-3:2001, *Hard coal and coke — Mechanical sampling — Part 3: Coal — Sampling from stationary lots*

ISO 13909-4:2001, *Hard coal and coke — Sampling — Part 4: Coal — Preparation of test samples*

ISO 13909-8:2001, *Hard coal and coke — Mechanical sampling — Part 8: Methods of testing for bias*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1213-2 apply.