

SLOVENSKI STANDARD SIST EN 1824:2011

01-oktober-2011

Nadomešča: SIST EN 1824:1999

Materiali za označevanje vozišča - Terenski preskusi

Road marking materials - Road trials

Straßenmarkierungsmaterialien - Feldprüfungen

iTeh STANDARD PREVIEW Produits de marquage routier - Essais routiers (standards.iteh.ai)

Ta slovenski standard je istoveten z:IST ENEN: 4824:2011 https://standards.iteh.ai/catalog/standards/sist/a19364c3-5307-4c7d-b37d-

d282e428e1ae/sist

<u>ICS:</u>

93.080.20 Materiali za gradnjo cest

Road construction materials

SIST EN 1824:2011

en

SIST EN 1824:2011

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 1824:2011 https://standards.iteh.ai/catalog/standards/sist/a19364c3-5307-4c7d-b37dd282e428e1ae/sist-en-1824-2011

SIST EN 1824:2011

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 1824

June 2011

ICS 93.080.20

Supersedes EN 1824:1998

English Version

Road marking materials - Road trials

Produits de marquage routier - Essais routiers

Straßenmarkierungsmaterialien - Feldprüfungen

This European Standard was approved by CEN on 22 April 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovania, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

SIST EN 1824:2011 https://standards.iteh.ai/catalog/standards/sist/a19364c3-5307-4c7d-b37dd282e428e1ae/sist-en-1824-2011



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Ref. No. EN 1824:2011: E

EN 1824:2011 (E)

Contents

Forewo	ord	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Test sites and conditions	4
5	Organization of road trials	7
6	Application of road marking materials1	0
7	Measurements related to performance1	1
8	Individual test report for road marking material1	4
Annex	A (normative) Köppen classification1	5
Annex	B (normative) Measurement of the number of wheel passages and the percentage of heavy vehicles1	7
Annex	C (normative) Determination of the rate of application and the rate of consumption of materia during application2	1
Annex	D (normative) Drying time determination2	4
Annex	E (normative) Meteorological determinations during application	5
Annex	F (normative) Removability	7
Annex	G (normative) Determination of wear index rds.iteh.ai)	8
Annex	H (informative) Model of test report	0
Bibliog	raphyhttps://standarda.itab.ai/catalog/standarda/sist/a19364c3-5307-4c7d-b37d3	2
	d282e428e1ae/sist-en-1824-2011	

Foreword

This document (EN 1824:2011) has been prepared by Technical Committee CEN/TC 226 "Road equipment", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2011, and conflicting national standards shall be withdrawn at the latest by December 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1824:1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

The Annexes A to G of this European Standard are normative and Annex H is informative.

This European Standard is one of a package of inter-related European Standards with a common date of withdrawal (dow) fixed on December 2011 (including the request of an extension for the co-existence period):

SIST EN 1824:2011

- EN 1790, Road marking materials Preformed road markings,
- EN 1824, Road marking materials Road trials,
- EN 1871, Road marking materials Paint, thermoplastic and cold plastic materials Specifications,
- EN 12802, Road marking materials Laboratory methods for identification,
- EN 13197, Road marking materials Wear simulator Turntable,
- EN 13212, Road marking materials Requirements for factory production control,
- EN 13459, Road marking materials Sampling and testing.

1 Scope

This document specifies the requirements for conducting road trials for road marking materials intended for use in both permanent and temporary road marking. Details are given for test sites, for the application of road marking materials on the test sites, for the parameters to be measured and the frequency of the measurements and for the presentation of the results in the form of a test report.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1436, Road marking materials — Road marking performance for road users

EN 13036-1, Road and airfield surface characteristics — Test methods — Part 1: Measurement of pavement surface macrotexture depth using a volumetric patch technique

3 Terms and definitions

For the purpose of this document, the following terms and definitions apply.

3.1

roll-over

(standards.iteh.ai)

number of wheels passing over a point of a road surface within a specified period of time

SIST EN 1824:2011

3.2 https://standards.iteh.ai/catalog/standards/sist/a19364c3-5307-4c7d-b37duseful rate of application

quantity, expressed in g×m⁻², of drop-on and/or non-drop materials which have adhered to the road marking substrate, when lines are done

3.3

rate of consumption during application

quantity, expressed in g×m², of drop-on or injection materials at the exit of the guns of the application equipment

3.4

percentage of heavy vehicles

ratio between the number of heavy vehicles and the number of all vehicles circulating on the test site

4 Test sites and conditions

4.1 General

Test sites shall be arranged at suitable locations in accordance with 4.2 to 4.5. The test results may depend on test field location, climate, road surface and traffic which shall be described according to 4.2 to 4.6.

4.2 Test sites characteristics and location

The test site shall be located in an area which belongs to one of the climatic classes defined in 4.3.

The test site shall consist of a field, where the road marking materials are to be applied, with extra space at both ends. The roads used for test sites should be straight and flat and without junctions, substantial obstacles to daylight, sources of frequent dirt (quarries, field exits, etc.) or tracked vehicles.

NOTE It is desirable to have additional areas at the roadsides in order to allow safe working conditions and convenient operation of application with road marking equipment.

The percentage of heavy vehicles on the test site shall be 10 % to 25 % of all vehicles.

The location of the test site shall be indicated in the test report.

4.3 Climatic conditions and classes

Climatic classes (see Table 1) are defined according to the Köppen classification and the use of winter maintenance.

Köppen classification shall be determined according to Annex A.

Winter maintenance is defined by the number of times that snowplough have operated on the test field during the road trials. Winter maintenance is applicable if this number is equal to or greater than 20 and shall be considered only for the Köppen zone Cfb.

Climatic Class	Climatic zone according to Köppen
iTeh ST ^{C1} (S	TANDARD PREVIEW tandards.iteh.æi)
C2 https://standards.iteh	SIST EN 1824:2011 Cfb without Winter maintenance ai/catalog/standards/sist/a19364c3-5307-4c7d-b37d- 1282c428c1ac/sist-en-1824-2011
C3	Cfb with Winter maintenance Dfb Dsb
C4	Csa Bsh Cfa Csb

Table 1 – Test Field climatic classes

4.4 Road surface conditions and classes

Road trials shall be carried out on asphaltic road surfaces of an age of 1 year or more, which are in good condition and not in need of repair for the duration of the road trials and are not damaged by the presence of wheel tracks, fissures, cracks or similar. Highly porous surfaces shall be avoided.

NOTE 1 Road trials on cement concrete surfaces do not give repeatable results because of on-going chemical reactions.

NOTE 2 Road trials on highly porous surfaces do not give comparable results due to the draining properties.

At the commencement of a road trial, a road surface report of the road trial shall be available. The test surface report shall include a general description of the road surface and an account of the texture depth (MTD: mean texture depth), determined in accordance with EN 13036-1.

The MTD shall be measured at several locations on the test field. The number of measurements depends on the test field length. Measurements shall be carried out, at least, at three transversal locations and repeated every 30 m on the test field. The transversal measurements locations are in the centre of the carriageway, near the right and left edge line.

The averaged mean texture depth is derived from these measurements. The standard deviation shall be less than 0,15 mm.

NOTE 3 The averaged texture depth may also be directly determined in accordance with EN ISO 13473-1. Depending to the averaged measured texture depth, the test field roughness is described in term of roughness class according to Table 2.

(standards.iteh.ai)

Table 2 – Test field roughness classes

Roughness classi/ca	aAveraged measured texture depth7d
RG1	≤ 0,60 mm
RG2	> 0,60 mm and \leq 0,90 mm
RG3	> 0,90 mm and \leq 1,20 mm
RG4	> 1,20 mm

NOTE 4 The texture depth has an influence on the result of road trials, at least for materials applied in thin layers.

4.5 Roll-over classes

The volume of traffic shall be such as to ensure that one or more measurement areas with the desired roll-over class can be selected (see 7.2).

At the termination of a road trial, a traffic report for the duration of the road trial should be made available. The traffic report shall include the roll-over classes according to Table 3, determined on the measurement area(s) in accordance with Annex B.

Roll-over class	Number of wheel passages		
ТО	≤ 50 000		
T1	Between 50 000 and 60 000		
Τ2	100 000 \pm 20 %		
P0	≤ 50 000		
P1	Between 50 000 and 60 000		
P2	100 000 \pm 20 %		
P3	200 000 \pm 20 %		
P4	500 000 ± 20 %		
P5	1 000 000 \pm 20 %		
P5.5	1 500 000 ± 10 %		
P6	2 000 000 ± 10 %		
NOTE The roll-over classes T0, T1 and T2 are for materials intended for temporary road markings, while the roll-over classes P0 to P6 are for materials intended for permanent road markings.			

Table 3 – Roll-over classes

The traffic report should further include the percentage of heavy vehicles together with an indication of the counting method used.

A vehicle is considered a heavy vehicle if its maximum gross mass is above 7500 kg.

4.6 Studded tyres classes

iTeh STANDARD PREVIEW

For road trial sites where studded tyres are used to a significant degree, this shall be indicated on the test report.

NOTE From general experience, such traffic conditions can be relevant to the erosion of road markings.

https://standards.iteh.ai/catalog/standards/sist/a19364c3-5307-4c7d-b37dd282e428e1ae/sist-en-1824-2011

5 Organization of road trials

5.1 Duration

A road trial shall include at least one full climatic cycle of one year for materials intended for permanent road marking and up to 6 months for materials intended for temporary road marking.

In some cases, test markings may fall below the performance requirements of the road authority. In these cases, it may be necessary for the markings to be removed.

5.2 Transverse and longitudinal application patterns

5.2.1 General

Road marking materials shall be applied in patterns of lines either transverse or longitudinal to the road.

When a long (more than 40 cm) measurement area is necessary, the transverse pattern cannot be used.

When both the transverse and longitudinal patterns are used on the same test site, they shall be used on separate parts of that test site.

5.2.2 Transverse pattern

At least three lines shall be applied for each road marking material. The distance between two adjacent lines should be at least 0,35 m and the width at least 0,15 m as shown in Figure 1. The application could be done across one or two lanes.

EN 1824:2011 (E)



NOTE Lines of the same material need not be adjacent.

Figure 1 – Example of a transverse pattern showing a measurement column

5.2.3 Longitudinal pattern

Lines are applied in transverse rows and longitudinal columns. For each of the road marking materials there shall be one line in each column containing measurement areas (see 7.2.2.3).

The lines should be at least 0,13 m wide and at least 1 m long as shown in Figure 2. Unmarked space between the lines is a minimum of 0,5 m in the longitudinal direction.



Key

- 6 columns 1
- 2 4 rows
- 3 centre line
- 4 Lane 1
- 5 edge line

- axis of measurement column 6
- 7 Measurement column
- 8 Measurement areas
- 9 Measurement point for the determination of the number of wheel passages



6 Application of road marking materials

6.1 General

In case of longitudinal pattern, the application shall be done in the direction of the traffic.

NOTE The test results depend on various factors related to the application of the road marking materials, i.e. application method, quantities applied, weather conditions, etc.

6.2 Periods for application

Road marking materials shall be applied when the weather conditions are as defined in 6.3.

NOTE The participating parties can agree to include one or more periods for application. One period can, for instance, be for materials intended for use as temporary road markings and another for materials intended for use as permanent road markings. There are practical advantages to having the period(s) as short as possible.

For temporary road marking materials, the application period shall be such that the required number of wheel passages is obtained, and the subsequent measurements carried out, prior to or after winter conditions.

6.3 Conditions suitable for application

Conditions shall be deemed suitable when:

- iTeh STANDARD PREVIEW
- a) the road surface appears to be dry and dew is not being formed; (standards.iteh.ai)
- b) the road surface temperature is within limits agreed upon by the participating parties;

SIST EN 1824:2011

c) the wind speed is less than the maximum agreed upon by the participating parties d

282e428e1ae/sist-en-1824-2011

Special road marking materials can be applied in other weather conditions, which shall be noted in the individual test report (see Clause 8).

EXAMPLE The road surface temperature is at least 3 $^{\circ}$ C above the dew point of the air, the road surface temperature is between 10 $^{\circ}$ C and 50 $^{\circ}$ C and the maximum wind speed is less than 10 m×s⁻¹.

6.4 Technical specification for application

Prior to the commencement of the road trials, the applicant shall submit to the test authority the application instructions of the road marking material.

NOTE 1 The application instructions will include preparation methods (such as how to melt a thermoplastic material), what type of application to use (e.g. extrusion of a thermoplastic material), any particular road marking equipment required, the pattern of application (e.g. plain or a certain type of structure), the rate(s) of application (in grams per square metre), what drop-on materials to add, their rate(s) of application and the method to use.

Whenever possible the road marking material shall be applied using self-propelled road marking equipment, and drop-on materials shall be applied mechanically.

NOTE 2 Most materials, except preformed materials, can be applied using self-propelled road marking equipment; this ensures better repeatability of the application.

NOTE 3 The road marking equipment used can either be those put to general commercial use or special road marking equipment. The road marking equipment can be operated by the usual crews or by staff at the test site.

If the test authority and the applicant agree to test road marking equipment prior to the application of a road marking material, the rate of application of marking materials and of drop-on materials shall be adjusted and the rate of application applied verified in accordance with Annex C. A road marking equipment shall be