



Designation: D 1791 – 93 (Reapproved 1998)

Standard Test Method for Accelerated Aging of Liquid Water-Emulsion Floor Polishes¹

This standard is issued under the fixed designation D 1791; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the storage stability of liquid water-emulsion floor polishes.

1.2 Storage for 30 days at 52°C (125°F), while not a guarantee of one year stability at 21°C (70°F), is believed to be a more reliable indicator of storage stability than similar tests of shorter duration.

NOTE 1—The 60° specular gloss on black glass determined by Test Method D 1455, may be used to confirm this observation. A substantial difference in gloss between aged and unaged samples is an indication of instability. A shelf stability of one year can be reasonably expected of the material in question if duplicate samples remain unchanged for 30 days at 52 ± 1.1°C (125 ± 2°F). If one or both duplicates show more than slight viscosity increases or slight creaming, other evidence of stability must be sought.

1.3 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 1455 Test Method for 60° Specular Gloss of Emulsion Floor Polish²

3. Significance and Use

3.1 This test method is not absolute but does give an indication of the useful shelf-life of a liquid water-emulsion floor polish. Will indicate whether a polish will gel or remain a usable liquid over the desired storage life of the product. It should be noted that polishes of different composition types will vary in useful storage life under identical storage conditions.

¹ This test method is under the jurisdiction of ASTM Committee D-21 on Polishes and is the direct responsibility of Subcommittee D21.03 on Chemical and Physical Testing.

Current edition approved Nov. 15, 1993. Published January 1994. Originally published as D 1791 – 60 T. Last previous edition D 1791 – 87.

² *Annual Book of ASTM Standards*, Vol 15.04.

4. Apparatus

4.1 *Flint Glass Bottles*, 4-oz (125 mL) capacity.³

4.2 *Drying Oven*, capable of maintaining the temperature of the emulsion samples at 52 ± 1.1°C (125 ± 2°F).

5. Sample

5.1 The sample shall be thoroughly representative of the material in question, and the portion used for the test shall be thoroughly representative of the sample itself.

5.2 Test samples shall be prepared in duplicate for each material in question.

6. Procedure

6.1 Transfer 100 mL of the emulsion to a clean, dry test bottle and hand tighten the screw cap.

6.2 Place the test set or series inverted in a drying oven capable of maintaining the temperature of the emulsions at 52 ± 1.1°C (125 ± 2°F).

6.3 Observe the samples daily for the first 14 days and thereafter twice weekly (for example, Monday and Thursday) for the remainder of the 30-day storage period. Samples should be examined as rapidly as possible with a minimum of agitation, and returned to the oven. *Do not loosen the cap.*

7. Report

7.1 The report shall include the following recorded at the time of each observation on a suitable data sheet:

7.1.1 Date.

7.1.2 Number of days in test.

7.1.3 Condition of the emulsion using the following symbols:

7.1.3.1 OK = no visible change (Note 1).

7.1.3.2 SV = slightly viscous.

7.1.3.3 V = viscous.

7.1.3.4 G = gelled.

7.1.3.5 Cr = creamed.

7.1.3.6 Sep = other types of liquid phase separation.

7.1.3.7 Sed = sedimentation of solid matter.

³ These bottles are available from Fisher Scientific. Request Catalog 86, 02—883BA.