



# SLOVENSKI STANDARD

## oSIST prEN 855:2012

01-januar-2012

---

### Polimerne cevi in cevni priključki - S plastomernim tekstilom ojačene hidravlične vrste - Specifikacija

Plastics hoses and hose assemblies - Thermoplastics textile reinforced hydraulic type - Specification

Kunststoffschläuche und -schlauchleitungen - Kunststoff-Hydraulikschläuche mit Textileinlage - Spezifikation

Tuyaux et flexibles en plastique - Type hydraulique en thermoplastiques à armature de textile - Spécification

**ITh STANDARD PREVIEW**  
(standards.iteh.ai)  
oSIST prEN 855:2012  
<https://standards.iteh.ai/catalog/standards/sist/b7a70870-82a0-4b6f-bf2c-95b32647782b/osist-pr-en-855-2012>

**Ta slovenski standard je istoveten z: prEN 855 rev**

---

#### **ICS:**

23.040.70      Gumene cevi in armature      Hoses and hose assemblies

**oSIST prEN 855:2012**

**en,fr**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN 855:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/b7a70870-82a0-4b6f-bf2c-95b32647782b/osist-pren-855-2012>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN 855 rev**

October 2011

ICS 23.040.70

Will supersede EN 855:1996

English Version

## Plastics hoses and hose assemblies - Thermoplastics textile reinforced hydraulic type - Specification

Tuyaux et flexibles en plastique - Type hydraulique en thermoplastiques à armature de textile - Spécification

Kunststoffschläuche und -schlauchleitungen - Kunststoff-Hydraulikschläuche mit Textileinlage - Spezifikation

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 218.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

Page

Foreword.....	3
1 Scope .....	3
2 Normative references .....	3
3 Types of hoses.....	4
4 Materials and construction .....	4
4.1 Hose .....	4
4.2 Hose assemblies.....	4
5 Dimensions.....	4
5.1 Diameters and concentricity.....	4
5.2 Length .....	5
5.2.1 Hoses .....	5
5.2.2 Hose assemblies.....	5
6 Requirements .....	6
6.1 Hydrostatic requirements .....	6
6.2 Minimum bend radius.....	6
6.3 Impulse test requirements.....	7
6.4 Leakage of hose assemblies .....	7
6.5 Cold flexibility .....	7
6.6 Fluid resistance.....	7
6.7 Ozone resistance .....	8
6.8 Electrical conductivity.....	8
7 Designation .....	8
8 Marking .....	8
8.1 Hoses .....	8
8.2 Hose assemblies.....	8
Annex A (normative) Method of test for electrical conductivity .....	10

iteh STANDARD PREVIEW  
(standards.iteh.ai)

oSIST prEN 855:2012

<https://standards.iteh.ai/catalog/standards/sist/b7a70870-82a0-4b6f-b12c-95b32647782b/osist-pren-855-2012>

## Foreword

This document (prEN 855:2011) has been prepared by Technical Committee CEN/TC 218 "Rubber and plastics hoses and hose assemblies", the secretariat of which is held by BSI.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 855:1996.

## 1 Scope

This European Standard specifies requirements for two types of textile reinforced thermoplastics hoses and hose assemblies with maximum working pressure in the range of 69 bar to 345 bar. The hoses are suitable for use with

- petroleum and synthetic based hydraulic fluids at temperatures ranging from -40 °C to +100 °C;
- water based hydraulic fluids at temperatures ranging from 0 °C to +70 °C.

The Standard does not include requirements for end fittings. It is limited to the performance of hoses assemblies.

NOTE 1 Operating temperatures in excess of 100 °C may materially reduce the life of the hose.

NOTE 2 Requirements for hydraulic hoses for underground mining are standardised in separate standards.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 1402, *Rubber and plastics hoses and hose assemblies – Hydrostatic testing*

EN ISO 4671, *Rubber and plastics hoses and hose assemblies – Methods of measurement of dimensions of hoses and the lengths of hose assemblies*

EN ISO 4672, *Rubber and plastics hoses – Sub-ambient temperature flexibility tests*

EN ISO 6803, *Rubber or plastics hoses and hose assemblies – Hydraulic pressure impulse test without flexing*

EN ISO 7326, *Rubber and plastics hoses – Assessment of ozone resistance under static conditions*

ISO 1817, *Rubber, vulcanized – Determination of the effect of liquids*

## prEN 855:2011 (E)

### 3 Types of hoses

Two types of hoses, Types R7 and R8, are specified distinguished by their maximum pressure (see table 4).

### 4 Materials and construction

#### 4.1 Hose

The hose shall consist of a seamless thermoplastics lining resistant to hydraulic fluids, with a suitable synthetic fibre reinforcement and a thermoplastics cover resistant to hydraulic fluids and the weather.

#### 4.2 Hose assemblies

Hose assemblies shall only be manufactured with those hose fittings whose functionality has been verified in all tests according to this standard.

### 5 Dimensions

#### 5.1 Diameters and concentricity

When measured in accordance with EN ISO 4671, the diameters of the hose shall comply with the values given in table 1.

iTech STANDARD PREVIEW  
(standards.iteh.ai)

Table 1 — Diameters of hoses

Nominal bore	Internal diameter				Maximum outside diameter	
	Type R7		Type R8		Type R7	Type R8
	min.	max.	min.	max.		
5	4,9	5,4	4,6	5,4	11,4	14,6
6	6,5	7,0	6,2	7,0	13,7	16,8
8	8,0	8,5	-	-	15,6	-
10	9,6	10,3	9,3	10,3	18,4	20,3
12	12,9	13,5	12,3	13,5	22,5	24,6
16	16,0	16,7	15,6	16,7	25,8	29,8
19	19,1	19,8	18,6	19,8	28,6	33,0
25	25,5	26,4	25,0	26,4	34,7	38,6

When measured in accordance with EN ISO 4671, the concentricity of hoses shall comply with the values given in table 2.

**Table 2 — Concentricity of hoses**

Nominal bore	Maximum variation in wall thickness
	Between internal diameter and outside diameter
Up to and including 6	0,8
Over 6 and including 19	1,0
Over 19	1,3

## 5.2 Length

### 5.2.1 Hoses

The hoses shall be supplied in lengths as specified by the purchaser, subject to a tolerance on the specified lengths of  $\pm 2\%$ .

When no specific hoses lengths have been ordered, the percentages of different lengths in any given delivery shall be as follows:

- over 20 m : not less than 80 % of total length;
- over 10 m to 20 m : not more than 20 % of total length;
- 1 m to 10 m : not more than 3 % of total length.

No hose length shall be less than 1 m.

### 5.2.2 Hose assemblies

The tolerances on the length of hose assemblies shall comply with the values given in table 3.

**Table 3 — Tolerances of length of hose assemblies**

Hose assembly length	Tolerances
Up to and including 630	+ 7
	- 3
Over 630 and including 1250	+ 12
	- 4
Over 1250 and including 2500	+ 20
	- 6

## 6 Requirements

### 6.1 Hydrostatic requirements

**6.1.1** When tested in accordance with EN ISO 1402, the maximum working pressure, the proof pressure and burst pressure of the hose and hose assemblies shall comply with the values given in table 4.

**Table 4 — Maximum working pressure, proof pressure and burst pressure**

Nominal bore	Maximum working pressure bar <sup>1)</sup>		Proof pressure bar		Burst pressure bar	
	Type		Type		Type	
	R7	R8	R7	R8	R7	R8
5	205	345	410	690	820	1380
6	190	345	380	690	760	1380
8	170	-	340	-	680	-
10	155	275	310	550	620	1100
12	135	240	270	480	540	960
16	100	190	200	380	400	760
19	86	155	172	310	344	620
25	69	138	138	275	276	550

<sup>1)</sup> 1 bar = 0,1 MPa

**6.1.2** When tested in accordance with EN ISO 1402, the change in length of hose at the maximum working pressure shall not exceed  $\pm 3\%$ .

### 6.2 Minimum bend radius

When bent to the minimum bend radius in table 5 measured on the inside of the bend, the flatness shall not exceed 10 % of the original outside diameter.

Measure the hose outside diameter with a calliper before bending the hose. Bend the hose to the minimum bend radius and measure the flatness with the calliper.



Table 5 — Minimum bend radius

Nominal bore	Minimum bend radius
5	90
6	100
8	115
10	125
12	180
16	205
19	240
25	300

### 6.3 Impulse test requirements

**6.3.1** The impulse test shall be in accordance with EN ISO 6803. The test temperature shall be 100 °C-

**6.3.2** For type R7 hose, when tested at impulse pressure equal to 125 % of the maximum working pressure, the hose shall withstand a minimum of 150 000 impulse cycles.

For type R8 hose, when tested at impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 200 000 impulse cycles.

**6.3.3** There shall be no leakage or other malfunction before reaching the specified number of cycles.

**6.3.4** This test shall be considered a destructive test and the test piece shall be thrown away.

### 6.4 Leakage of hose assemblies

When tested in accordance with EN ISO 1402 there shall be no leakage or evidence of failure. This test shall be considered a destructive test and the test piece shall be thrown away.

### 6.5 Cold flexibility

When tested in accordance with method B of EN ISO 4672 at a temperature of -40 °C there shall be no cracking of the lining or cover. The test piece shall not leak or crack when subjected to a proof pressure test after regaining ambient temperature.

### 6.6 Fluid resistance

When tested in accordance with ISO 1817, the lining and cover, immersed in Oil No. 3 for 72 h at a temperature of 100 °C, shall show shrinkage not greater than 15 % nor volume swelling greater than 35 %.

NOTE If the resistance against synthetic or water based hydraulic fluids is to be tested, the test fluid and the test procedure can be specified as agreed between manufacturer and user.

**prEN 855:2011 (E)****6.7 Ozone resistance**

When tested in accordance with Method 1 or 2 of EN ISO 7326, depending on the nominal bore of the hose, no cracking or deterioration of the cover shall be visible under x2 magnification.

**6.8 Electrical conductivity**

When tested in accordance with annex A, hoses shall not show a leakage greater than 50  $\mu$ A.

**7 Designation**

Hoses shall be designated as the following example.

Designation of a Type R7 thermoplastics textile reinforced hydraulic hose and a nominal bore of 10:

Hose EN 855 – R7 10

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

**8 Marking****8.1 Hoses**

<https://standards.iteh.ai/catalog/standards/sist/b7a70870-82a0-4b6f-bf2c-95b32647782b/osist-pren-855-2012>

Hoses shall be marked at a maximum spacing of 500 mm with at least the following information:

- a) the manufacturer's name or identification, e. g. XXX;
- b) the number of this European Standard "EN 855";
- c) type, e. g. R7;
- d) nominal bore, e. g. 16;
- e) quarter and last two digits of year of manufacture, e. g. 4Q96.

EXAMPLE: XXX/EN 855/R7/16/4Q96

NOTE Other information, as agreed between the purchaser and the manufacturer, can be included, if requested.

**8.2 Hose assemblies**

Hose assemblies shall be marked with at least the following information:

- a) the manufacturer's name or identification, e. g. XXX;
- b) maximum working pressure of the assemblies, in bar e. g. 100;