



Designation: C 1567 – 04

Standard Test Method for Determining the Potential Alkali-Silica Reactivity of Combinations of Cementitious Materials and Aggregate (Accelerated Mortar-Bar Method)¹

This standard is issued under the fixed designation C 1567; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method permits detection within 16 days of the potential for deleterious alkali-silica reaction of combinations of cementitious materials and aggregate in mortar bars. The cementitious materials are composed of various proportions of hydraulic cement, pozzolans and ground granulated blast-furnace slag.

1.2 The test results are only valid for the specific combinations of pozzolan, slag, and reactive aggregates tested.

1.3 This test is not suitable for evaluating the potential for deleterious reaction of combinations of hydraulic cement and aggregate (that is, in the absence of pozzolans or ground granulated blast-furnace slag).

1.4 The values stated in SI units are to be regarded as standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. A specific precautionary statement is given in the section on Reagents.*

2. Referenced Documents

2.1 ASTM Standards:²

- C 109/C 109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)
- C 125 Terminology Relating to Concrete and Concreting Aggregates
- C 150 Specification for Portland Cement
- C 151 Test Method for Autoclave Expansion of Portland Cement

- C 305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency
- C 490 Practice for Use of Apparatus for the Determination of Length Change of Hardened Cement Paste, Mortar, and Concrete
- C 494/C 494M Specification for Chemical Admixtures for Concrete
- C 511 Specification for Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes
- C 618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use as a Mineral Admixture in Concrete
- C 670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
- C 989 Specification for Ground Granulated Blast-Furnace Slag for Use in Concrete and Mortars
- C 1240 Specification for Silica Fume for Use as a Mineral Admixture in Hydraulic-Cement Concrete, Mortar or Grout
- C 1260 Test Method for Potential Alkali Reactivity of Aggregates (Mortar-Bar Method)
- C 1293 Test Method for Concrete Aggregates by Determination of Length Change of Concrete Due to Alkali-Silica Reaction
- C 1437 Test Method for Determining Flow of Hydraulic Cement Mortar
- D 1193 Specification for Reagent Water
- E 11 Specification for Wire-Cloth and Sieves for Testing Purposes

3. Definitions

3.1 For definitions of terms used in this test method, refer to Terminology C 125.

4. Significance and Use

4.1 This test method provides a means for evaluating the ability of pozzolans and ground granulated blast-furnace slag to control deleterious internal expansion due to alkali-silica reaction when used with an aggregate intended for use in

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.26 on Chemical Reactions.

Current edition approved July 1, 2004. Published August 2004.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

concrete. It is based on the Accelerated Test Method developed at the National Building Research Institute (NBRI) in the Republic of South Africa (1-4).³

4.2 Results obtained using this test method may overestimate the reactivity of some types of aggregates if used in service with the same pozzolans or slag and hydraulic cement of low alkali content.

4.3 Different levels of pozzolan and ground granulated blast-furnace slag may require testing to determine the amount required to reduce expansion to an acceptable level. Pozzolans and ground granulated blast-furnace slag may be tested separately or in combination.

4.4 It is recommended to test the same aggregate and hydraulic cement (without pozzolans and slag) using Test Method C 1260.

4.5 This test method may underestimate the expansion of cementitious systems containing pozzolans with an alkali content > 4.0 % sodium oxide equivalent (7-9). It is recommended that such materials be tested using Test Method C 1293.

5. Apparatus

5.1 The apparatus shall conform to Practice C 490, except as follows:

5.2 *Sieves*—Square hole, woven-wire cloth sieves, shall conform to Specification E 11.

5.3 *Mixer, Paddle, and Mixing Bowl*—Mixer, paddle, and mixing bowl shall conform to the requirements of Practice C 305, except that the clearance between the lower end of the paddle and the bottom of the bowl shall be 5.1 ± 0.3 mm.

5.4 *Tamper and Trowel*—The tamper and trowel shall conform to Test Method C 109/C 109M.

5.5 *Containers*—The containers shall be of such a nature that the bars can be totally immersed in either the water or 1N sodium hydroxide (NaOH) solution. The containers shall be made of material that can withstand prolonged exposure to 80°C and must be resistant to a 1N NaOH solution (see Note 1). The containers must be so constructed that when used for storing specimens, the loss or gain of moisture is prevented by tight-fitting covers, by sealing, or both (see Note 2). The bars in the solution must be placed and supported so that the solution has access to the entire surface of each bar; therefore, ensure that the specimens do not touch the sides of the container or each other. The specimens, if stood upright in the solution, shall not be supported by the metal gage stud.

NOTE 1—The NaOH solution corrodes glass or metal containers.

NOTE 2—Some microwave-proof food storage containers made of polypropylene or high-density polyethylene have been found to be acceptable.

5.6 *Oven, or Water Bath*—A convection oven or water bath with temperature control maintaining $80.0 \pm 2.0^\circ\text{C}$.

6. Reagents

6.1 *Sodium Hydroxide (NaOH)*—USP or technical grade may be used, provided the Na^+ and OH^- concentrations are shown by chemical analysis to lie between 0.99N and 1.01N.

³ The boldface numbers in parentheses refer to a list of references at the end of the text.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type IV of Specification D 1193.

6.3 *Sodium Hydroxide Solution*—Each litre of solution shall contain 40.0 g of NaOH dissolved in 900 mL of water, and shall be diluted with additional distilled or deionized water to obtain 1.0 L of solution. The volume proportion of sodium hydroxide solution to mortar bars in a storage container shall be 4 ± 0.5 volumes of solution to 1 volume of mortar bars. The volume of a mortar bar may be taken as 184 mL. Include sufficient test solution to ensure complete immersion of the mortar bars.

6.3.1 **Warning**—Before using NaOH, review: (1) the safety precautions for using NaOH; (2) first aid for burns; and (3) the emergency response to spills, as described in the manufacturer's Material Safety Data Sheet or other reliable safety literature. NaOH can cause very severe burns and injury to unprotected skin and eyes. Suitable personal protective equipment must always be used. These include full-face shields, rubber aprons, and gloves impervious to NaOH. Gloves must be checked periodically for pinholes.

7. Conditioning

7.1 Maintain the temperature of the molding room and dry materials at not less than 20°C and not more than 27.5°C. The temperature of the mixing water, and of the moist closet or moist room, shall not vary from 23°C by more than 2°C.

7.2 Maintain the relative humidity of the molding room at not less than 50 %. The moist closet or room shall conform to Specification C 511.

7.3 Maintain the storage oven or water bath in which the specimens are stored at a temperature of $80.0 \pm 2.0^\circ\text{C}$.

8. Sampling and Preparation of Test Specimens

8.1 *Selection of Aggregate*—Process materials proposed for use as fine aggregate in concrete as described in 8.2 with a minimum of crushing. Process materials proposed for use as coarse aggregate in concrete by crushing to produce as nearly as practical a graded product from which a sample can be obtained. Grade the sample as prescribed in Table 1. The sample shall represent the composition of the coarse aggregate as proposed for use.

8.1.1 When a given quarried material is proposed for use both as coarse and as fine aggregate, test only a selection of the fine aggregate, unless there is reason to expect that the coarse aggregate has a different composition than the fine aggregate. If such a difference is expected and if the differences might significantly affect expansion due to reaction with the alkalis

TABLE 1 Grading Requirements

Sieve Size		Mass, %
Passing	Retained on	
4.75 mm (No. 4)	2.36 mm (No. 8)	10
2.36 mm (No. 8)	1.18 mm (No. 16)	25
1.18 mm (No. 16)	600 μm (No. 30)	25
600 μm (No. 30)	300 μm (No. 50)	25
300 μm (No. 50)	150 μm (No. 100)	15