



Designation: A737/A737M – 99 (Reapproved 2004)

Standard Specification for Pressure Vessel Plates, High-Strength, Low-Alloy Steel¹

This standard is issued under the fixed designation A737/A737M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers high-strength low-alloy steel plates for service in welded pressure vessels and piping components.

1.2 This material is particularly intended for piping and pressure vessel applications where high strength and improved toughness are required.

1.3 Two grades, designated B and C, are covered by this specification. Grade B provides a minimum yield strength of 50 ksi [345 MPa]. Grade C provides a minimum yield strength of 60 ksi [415 MPa].

1.4 The maximum thickness of plates is limited only by the capacity of the chemical composition and heat treatment to meet the specified mechanical property requirements. Individual manufacturers should be consulted on thickness limitations since current industry limitations have not been ascertained to date.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 *ASTM Standards*:³

A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels³

A435/A435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates³

A577/A577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates³

A578/A578M Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications

3. General Requirements and Ordering Information

3.1 Material supplied to this specification shall conform to the requirements of Specification **A20/A20M**. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions and mass, quality, repair of defects, marking, loading, etc.

3.2 Specification **A20/A20M** also establishes the rules for compliance to the ordering information when purchasing material to this specification.

3.3 Certain supplementary requirements considered suitable for use with this specification are listed at the end of the specification. These include some of the standardized supplementary requirements listed in Specification **A20/A20M** as well as additional ones unique to this specification.

4. Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification **A20/A20M**.

5. Heat Treatment

5.1 The material shall be normalized by heating to a suitable temperature which produces an austenitic structure, but not exceeding 1700°F [925°C], holding a sufficient time to attain uniform heat throughout the material, and cooling in air.

5.2 If approved by the purchaser, cooling rates faster than air cooling are permitted for improvement of strength or toughness, provided the plates are subsequently tempered in the temperature range from 1100 to 1300°F [595 to 705°C].

5.3 If the purchaser elects to perform the required heat treatment, the material shall be accepted on the basis of mill tests made from test coupons heat treated in accordance with the purchase order requirements. If the test coupon heat-treatment requirements are not indicated on the purchase order, the manufacturer shall heat treat the test coupons under

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.11 on Steel for Boilers and Pressure Vessels.

Current edition approved Sept. 1, 2004. Published September 2004. Originally approved in 1976. Last previous edition approved in 1999 as A737/A737M – 99. DOI: 10.1520/A0737_A0737M-99R04.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-737 in Section II of that code.

³ *Annual Book of ASTM Standards*, Vol 01.04.