
**Toplotnoizolacijski proizvodi za opremo stavb in industrijske inštalacije -
Proizvodi iz ekspandiranega perlita (EPB) in vermikulita (EV) - Specifikacija**

Thermal insulation products for building equipment and industrial installations - Factory made expanded perlite (EP) and exfoliated vermiculite (EV) products - Specification

Wärmedämmstoffe für die Haustechnik und für betriebstechnische Anlagen - Werkmäßig hergestellte Produkte aus Blähperlite (EP) und expandiertem Vermiculit (EV) - Spezifikation

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en perlite expansée (EP) et en vermiculite exfoliée (EV) - Spécification

Ta slovenski standard je istoveten z: EN 15501:2013

ICS:

91.100.60	Materiali za toplotno in zvočno izolacijo	Thermal and sound insulating materials
-----------	---	--

SIST EN 15501:2013**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 15501:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/3ff28610-237c-4b5d-a727-1b9f8db04952/sist-en-15501-2013>

EUROPEAN STANDARD

EN 15501

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2013

ICS 91.100.60

English Version

Thermal insulation products for building equipment and industrial installations - Factory made expanded perlite (EP) and exfoliated vermiculite (EV) products - Specification

Produits isolants thermiques pour l'équipement du bâtiment et les installations industrielles - Produits manufacturés en perlite expansée (EP) et en vermiculite exfoliée (EV) - Spécification

Wärmedämmstoffe für die Haustechnik und für betriebstechnische Anlagen - Werkmäßig hergestellte Produkte aus Bläherlit (EP) und expandiertem Vermiculit (EV) - Spezifikation

This European Standard was approved by CEN on 10 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	5
1 Scope	7
2 Normative references	7
3 Terms, definitions, symbols, units and abbreviated terms	8
3.1 Terms and definitions	8
3.1.1 Terms and definitions as given in EN ISO 9229:2007	8
3.1.2 Additional terms and definitions	9
3.2 Symbols, units and abbreviated terms	10
3.2.1 Symbols and units	10
3.2.2 Abbreviated terms	11
4 Requirements	11
4.1 General.....	11
4.2 For all applications	12
4.2.1 Thermal conductivity.....	12
4.2.2 Dimensions and tolerances	12
4.2.3 Dimensional stability	13
4.2.4 Reaction to fire.....	13
4.2.5 Durability characteristics	13
4.3 For specific applications.....	14
4.3.1 General.....	14
4.3.2 Maximum service temperature	14
4.3.3 Minimum service temperature	14
4.3.4 Compressive stress or compressive strength	15
4.3.5 Trace quantities of water soluble ions and the pH value	15
4.3.6 Water vapour diffusion resistance	15
4.3.7 Short term water absorption by partial immersion	15
4.3.8 Dangerous substances	15
4.3.9 Continuous glowing combustion.....	16
5 Test methods.....	16
5.1 Sampling	16
5.2 Conditioning.....	16
5.3 Testing	16
5.3.1 General.....	16
5.3.2 Thermal conductivity.....	18
5.3.3 Maximum service temperature	19
5.3.4 Reaction to fire.....	19
6 Designation code	19
7 Evaluation of conformity.....	20
7.1 General.....	20
7.2 Initial Type Testing	20
7.3 Factory Production Control	20
8 Marking and labelling	20
Annex A (normative) Factory production control.....	21
Annex B (normative) Special conditions for the determination of organic content	24
B.1 Principle	24
B.2 Apparatus	24
B.3 Procedure	24

B.4	Calculation and expression of results	24
B.5	Test report.....	25
Annex C	(informative) Preparation of the test specimens to measure thermal conductivity	26
C.1	Preparation of the test specimens to measure thermal conductivity	26
C.2	Ageing.....	26
Annex D	(informative) Product specific details for mounting and fixing for reaction to fire testing	27
Annex E	(informative) Additional properties	31
E.1	General	31
E.2	Coefficient of thermal expansion.....	31
E.3	Apparent and true porosity	31
E.4	Air flow resistance.....	31
E.5	Creep in compression.....	31
E.6	Permeability to gases.....	31
E.7	Bending strength.....	31
E.8	Apparent density	31
Annex ZA	(informative) Clauses of this European Standard addressing the provisions of the EU Construction Products Directive	33
ZA.1	Scope and relevant characteristics	33
ZA.2	Procedures for attestation of conformity of factory made expanded perlite and exfoliated vermiculite products	35
ZA.2.1	Systems of attestation of conformity	35
ZA.2.2	EC certificate and declaration of conformity.....	37
ZA.3	CE Marking and labelling.....	38
Bibliography	41

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Figures

Figure ZA.1	— Example of CE marking information.....	40
-------------	--	----

Tables

Table 1	— Dimensional tolerances.....	12
Table 2	— Levels for maximum service temperatures.....	14
Table 3	— Levels for compressive stress at 10 % deformation or compressive strength	15
Table 4	— Test methods, test specimens and conditions	17
Table A.1	— Minimum product testing frequencies.....	21
Table A.2	— Minimum product testing frequencies for the reaction to fire characteristics	23
Table D.1	— Product parameters for EP / EV - flat products when tested as placed on the market or in standard test configuration of assemblies.....	27
Table D.2	— Installation Parameters for EP / EV - flat products as placed on the market.....	28
Table D.3	— Product parameters for EP / EV - pipe insulation products, as placed on the market.....	28
Table D.4	— Installation Parameters for EP / EV - pipe insulation products, as placed on the market.....	29
Table D.5	— Installation Parameters for EP / EV - flat products in standard test configuration of assemblies simulating end-use applications	29

EN 15501:2013 (E)

Table E.1 — Test methods, test specimens, and conditions.....	32
Table ZA.1— Relevant clauses	34
Table ZA.2 — System(s) of attestation of conformity	35
Table ZA.3.1 — Assignment of evaluation of conformity tasks for products under system 1 for reaction to fire and system 3 for other characteristics.....	36
Table ZA.3.2 — Assignment of evaluation of conformity tasks for products under system 3 or system 3 combined with system 4 for reaction to fire	37

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 15501:2013](https://standards.iteh.ai/catalog/standards/sist/3ff28610-237c-4b5d-a727-1b9f8db04952/sist-en-15501-2013)

<https://standards.iteh.ai/catalog/standards/sist/3ff28610-237c-4b5d-a727-1b9f8db04952/sist-en-15501-2013>

Foreword

This document (EN 15501:2013) has been prepared by Technical Committee CEN/TC 88 “Thermal insulating materials and products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2013, and conflicting national standards shall be withdrawn at the latest by October 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

Locally responsible authorities and contracting entities, who are bound by EU Directives to specify their requirements using European harmonised product standards, are allowed to demand additional properties outside the provisions of this standard if this is technically necessary because of prevailing operational conditions of the building equipment or the industrial installation projected or because of safety regulations.

This European Standard contains six annexes:

- Annex A (normative), Factory production control
- Annex B (normative), Special conditions to be used for the determination of organic content
- Annex C (informative), Preparation of the test specimens to measure thermal conductivity
- Annex D (informative), Product specific details for mounting and fixing for reaction to fire testing

NOTE This annex will be transferred to Annex A of EN 15715 when this document is being revised.

- Annex E (informative), Additional properties
- Annex ZA (informative), Clauses of this European Standard addressing the provisions of the EU Construction Products Directive

This document includes a bibliography.

This European Standard is one of a series of standards for insulation products used in building equipment and industrial installations, but this standard can be used in other areas, where appropriate.

Other standards in the series include the following group of interrelated standards for the specifications of factory made thermal insulation products, all of which come within the scope of CEN/TC 88:

- EN 14303, *Thermal insulation products for building equipment and industrial installations — Factory made mineral wool (MW) products — Specification*
- EN 14304, *Thermal insulation products for building equipment and industrial installations — Factory made flexible elastomeric foam (FEF) products — Specification*

EN 15501:2013 (E)

- EN 14305, *Thermal insulation products for building equipment and industrial installations — Factory made cellular glass (CG) products — Specification*
- EN 14306, *Thermal insulation products for building equipment and industrial installations — Factory made calcium silicate (CS) products — Specification*
- EN 14307, *Thermal insulation products for building equipment and industrial installations — Factory made extruded polystyrene foam (XPS) products — Specification*
- EN 14308, *Thermal insulation products for building equipment and industrial installations — Factory made rigid polyurethane foam (PUR) and polyisocyanurate foam (PIR) products — Specification*
- EN 14309, *Thermal insulation products for building equipment and industrial installations — Factory made products of expanded polystyrene (EPS) — Specification*
- EN 14313, *Thermal insulation products for building equipment and industrial installations — Factory made polyethylene foam (PEF) products — Specification*
- EN 14314, *Thermal insulation products for building equipment and industrial installations — Factory made phenolic foam (PF) products — Specification*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

(standards.iteh.ai)

SIST EN 15501:2013

<https://standards.iteh.ai/catalog/standards/sist/3ff28610-237c-4b5d-a727-1b9f8db04952/sist-en-15501-2013>

1 Scope

This European Standard specifies the requirements for factory made expanded perlite and exfoliated vermiculite products which are used for the thermal insulation of building equipment and industrial installations with an operating temperature in the range of approximately 0 °C to + 1 100 °C.

Expanded perlite and exfoliated vermiculite products can be used below 0 °C but special tests regarding the suitability of the product in the intended application are advised (e.g. liquefaction of oxygen). Manufacturer's advice should be heeded in all cases.

The products are manufactured in the form of boards, pipe sections, segments, prefabricated ware and special ware.

This European Standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

Products covered by this European Standard are also used in prefabricated thermal insulation systems and composite panels; the structural performance of systems incorporating these products is not covered.

This European Standard does not specify the required level of a given property that is achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application can be found in regulations and invitations to tender.

Products with a declared thermal conductivity greater than 0,6 W/(mK) at 10 °C are not covered by this European Standard.

This European Standard does not cover products intended to be used for the insulation of the building structure.

The European Standard does not cover the following acoustical aspects: direct airborne sound insulation and impact transmission noise index.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 822, *Thermal insulating products for building applications — Determination of length and width*

EN 823, *Thermal insulating products for building applications — Determination of thickness*

EN 824, *Thermal insulating products for building applications — Determination of squareness*

EN 825, *Thermal insulating products for building applications — Determination of flatness*

EN 826, *Thermal insulating products for building applications — Determination of compression behaviour*

EN 1094-6, *Insulating refractory products — Part 6: Determination of permanent change in dimensions of shaped products on heating (ISO 2477)*

EN 1604, *Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions*

EN 1609, *Thermal insulating products for building applications — Determination of short term water absorption by partial immersion*

EN 15501:2013 (E)

EN 12086, *Thermal insulating products for building applications — Determination of water vapour transmission properties*

EN 12667, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Products of high and medium thermal resistance*

EN 12939, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Thick products of high and medium thermal resistance*

EN 13172:2012, *Thermal insulation products — Evaluation of conformity*

EN 13467, *Thermal insulating products for building equipment and industrial installations — Determination of dimensions, squareness and linearity of preformed pipe insulation*

EN 13468, *Thermal insulating products for building equipment and industrial installations — Determination of trace quantities of water soluble chloride, fluoride, silicate and sodium ions and pH*

EN 13469, *Thermal insulating products for building equipment and industrial installations — Determination of water vapour transmission properties of preformed pipe insulation*

EN 13472, *Thermal insulating products for building equipment and industrial installations — Determination of short term water absorption by partial immersion of preformed pipe insulation*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13820, *Thermal insulating materials for building applications — Determination of organic content*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

EN 15715, *Thermal insulation products — Instructions for mounting and fixing for reaction to fire testing — Factory made products*

EN ISO 8497, *Thermal insulation — Determination of steady-state thermal transmission properties of thermal insulation for circular pipes (ISO 8497)*

EN ISO 8894-1, *Refractory materials — Determination of thermal conductivity — Part 1: Hot-wire methods (cross-array and resistance thermometer) (ISO 8894-1)*

EN ISO 13787, *Thermal insulation products for building equipment and industrial installations — Determination of declared thermal conductivity (ISO 13787)*

3 Terms, definitions, symbols, units and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1 Terms and definitions as given in EN ISO 9229:2007

3.1.1.1

expanded perlite

lightweight granular (insulation) material manufactured from naturally occurring volcanic rock expanded by heat to form a cellular structure

[SOURCE: EN ISO 9229:2007, 2.1.7, modified — removed alternative term "perlite"]

3.1.1.2**exfoliated vermiculite**

insulation material that results from expanding or exfoliating a natural micaceous mineral by heating

[SOURCE: EN ISO 9229:2007, 2.1.8, modified — removed alternative term "vermiculite"]

3.1.1.3**block**

(insulation) product generally of rectangular cross-section and with a thickness not significantly smaller than the width

[SOURCE: EN ISO 9229:2007, 2.3.1, modified — removed the Note and alternative term "billet"]

3.1.1.4**board**

slab

(insulation) rigid or semi-rigid product of rectangular shape and cross section in which the thickness is uniform and substantially smaller than the other dimensions

Note 1 to entry: Boards are usually thinner than slabs. They may also be supplied in tapered form.

[SOURCE: EN ISO 9229:2007, 2.3.2]

3.1.1.5**pipe section**

section

(insulation) product in the shape of a cylindrical annulus that may be split to facilitate application

[SOURCE: EN ISO 9229:2007, 2.3.9, modified — removed the Note]

3.1.1.6**lag**

segment

rigid or semi-rigid insulation product for application to large diameter cylindrical or spherical equipment

[SOURCE: EN ISO 9229:2007, 2.3.8]

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 15501:2013](https://standards.iteh.ai/catalog/standards/sist/3ff28610-237c-4b5d-a727-1b9f8db04952/sist-en-15501-2013)

<https://standards.iteh.ai/catalog/standards/sist/3ff28610-237c-4b5d-a727-1b9f8db04952/sist-en-15501-2013>

3.1.2 Additional terms and definitions**3.1.2.1****level**

given value which is the upper or lower limit of a requirement

Note 1 to entry: The level is given by the declared value of the characteristic concerned.

3.1.2.2**class**

combination of two levels of the same property between which the performance falls

3.1.2.3**prefabricated ware**

pieces cut, abraded or otherwise formed from a board or block of product e.g. elbows, T-pieces, etc.

3.1.2.4**production line**

assemblage of equipment that produces products in a continuous process

EN 15501:2013 (E)

3.1.2.5

production unit

assemblage of equipment that produces products in a discontinuous process

3.1.2.6

special ware

(insulation) product formed in a mould to a given shape and dimension

3.2 Symbols, units and abbreviated terms

3.2.1 Symbols and units

b	is the width	mm
D_i	is the inside diameter of pipe sections	mm
d	is the thickness	mm
d_D	is the declared thickness of the product	mm
$\Delta\varepsilon_b$	is the relative change in width	%
$\Delta\varepsilon_d$	is the relative change in thickness	%
$\Delta\varepsilon_l$	is the relative change in length	%
Li	is the deviation from linearity	mm
l	is the length	mm
λ	is the thermal conductivity	W/(m·K)
λ_D	is the declared thermal conductivity	W/(m·K)
μ	is the water vapour diffusion resistance factor	—
S_b	is the deviation from squareness of boards on length and width	mm/m
S_d	is the deviation from squareness of boards on thickness	mm
S_{max}	is the deviation from flatness	mm
σ_{10}	is the compressive stress at 10 % deformation	kPa
σ_m	is the compressive strength	kPa
v	is the deviation from squareness for pipe sections and segments	mm
ρ_a	is the apparent density	kg/m ³
BS	is the symbol of the declared level for bending strength	
CS(Y)	is the symbol of the declared level for compressive stress at Y % deformation	
CS(10)	is the symbol of the declared level for compressive stress at 10 % deformation	
CL	is the symbol of the declared level of soluble chloride ions	
F	is the symbol of the declared level of soluble fluoride ions	

ITeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15501:2013

<https://standards.iteh.ai/catalog/standards/sist/3ff28610-237c-4b5d-a727-1b9f8db04952/sist-en-15501-2013>

L	is the symbol of the declared class for length tolerances
MU	is the symbol of the declared value for water vapour diffusion resistance factor
Na	is the symbol of the declared level of soluble sodium ions
P	is the symbol of the declared value for flatness tolerances
pH	is the symbol of the declared level of the pH-value
S	is the symbol of the declared class for squareness tolerances
SI	declared level of soluble silicate ions
ST(+)	is the symbol of the declared level for maximum service temperature
ST(-)	is the symbol of the declared level for minimum service temperature
T	is the symbol of the declared class for thickness tolerances
W	is the symbol of the declared class for width tolerances

3.2.2 Abbreviated terms

EP	expanded perlite
EV	exfoliated vermiculite
ITT	initial type test
ML	manufacturer's literature
FPC	factory production control
RtF	reaction to fire

4 Requirements

4.1 General

Product properties shall be assessed in accordance with Clause 5. To comply with this standard, products shall meet the requirements of 4.2, and the requirements of 4.3 as appropriate.

NOTE Information on additional properties is given in Annex E.

One test result for a product property is the average of the measured values on the numbers of test specimens given in Table 4.