



SLOVENSKI STANDARD

SIST EN 13257:2014

01-marec-2014

Nadomešča:

SIST EN 13257:2001

SIST EN 13257:2001/A1:2005

SIST EN 13257:2001/AC:2003

Geotekstilije in geotekstilijam sorodni izdelki - Značilnosti, ki se zahtevajo pri odstranitvi trdnih odpadkov

Geotextiles and geotextile-related products - Characteristics required for use in solid waste disposals

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Geotextilien und geotextilverwandte Produkte - Geforderte Eigenschaften für die Anwendung bei der Entsorgung fester Abfallstoffe

[https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-](https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014)

Géotextiles et produits apparentés - Caractéristiques requises pour l'utilisation dans les ouvrages d'enfouissement des déchets solides

Ta slovenski standard je istoveten z: EN 13257:2014

ICS:

13.030.10	Trdni odpadki	Solid wastes
59.080.70	Geotekstilije	Geotextiles

SIST EN 13257:2014

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13257:2014

<https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014>

EUROPEAN STANDARD

EN 13257

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2014

ICS 59.080.70

Supersedes EN 13257:2000

English Version

Geotextiles and geotextile-related products - Characteristics required for use in solid waste disposals

Géotextiles et produits apparentés - Caractéristiques requises pour l'utilisation dans les ouvrages d'enfouissement des déchets solides

Geotextilien und geotextilverwandte Produkte - Geforderte Eigenschaften für die Anwendung in Deponien für feste Abfallstoffe

This European Standard was approved by CEN on 9 November 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 13257:2014](https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014)

<https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms, definitions and abbreviations	7
3.1 Terms and definitions	7
3.2 Abbreviations	8
4 Required characteristics and corresponding methods of test	8
4.1 General.....	8
4.2 Selection of the appropriate standard in a specific application	8
4.3 Characteristics relevant to specific conditions of use	11
4.3.1 Stiffness at 2 %, 5 % and 10 %	11
4.3.2 Tensile strength of seams and joints	11
4.3.3 Static puncture.....	11
4.3.4 Friction characteristics	11
4.3.5 Tensile creep	11
4.3.6 Protection efficiency (EN 14574).....	11
4.3.7 Water permeability normal to the plane	11
4.4 Release of dangerous substances.....	11
5 Assessment and verification of constancy of performance (AVCP).....	12
5.1 General.....	12
5.2 Presentation of characteristics	12
5.3 Product type determination (PTD).....	12
5.4 Factory production control (FPC)	13
5.5 Verification of values.....	13
5.6 Initial inspection of factory and of FPC	13
5.7 Continuous surveillance of FPC	14
6 Marking	14
Annex A (normative) Factory production control	15
A.1 Factory production control scheme	15
A.1.1 General.....	15
A.1.2 Product design.....	15
A.1.3 Production	15
A.1.4 Finished products.....	15
A.1.5 Provisions applicable to A.1.2, A.1.3 and A.1.4 (to be used where appropriate).....	16
A.2 Assessment of a factory production control (FPC) system	17
A.2.1 General.....	17
A.2.2 Checklist	17
A.2.3 Test frequency	20
Annex B (normative) Durability aspects.....	22
B.1 General.....	22
B.1.1 Service life	22

B.1.2	Initial and repeat testing of durability	22
B.1.3	Use of rework material (RWM)	23
B.2	Weathering (all products)	23
B.3	Products used in non-reinforcing applications and with service lives up to 5 years	23
B.4	Other applications and service lives up to 25 years, 50 years and 100 years	24
B.4.1	General	24
B.4.2	Tests for specific materials	24
Annex C (informative)	Guidelines for the selection of the appropriate standard in a specific application.....	28
Annex D (informative)	Significant technical changes to the superseded standard.....	30
Annex ZA (informative)	Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation.....	31
ZA.1	Scope and relevant characteristics	31
ZA.2	Procedure for AVCP of Geotextiles and geotextiles-related products for the use in the construction of solid waste disposals	35
ZA.2.1	Systems of AVCP	35
ZA.2.2	Declaration of performance (DoP)	38
ZA.3	CE marking and labelling	41
Bibliography	44

iTeh STANDARD PREVIEW

(standards.iteh.ai)

SIST EN 13257:2014

<https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014>

EN 13257:2014 (E)**Foreword**

This document (EN 13257:2014) has been prepared by Technical Committee CEN/TC 189 "Geosynthetics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2014, and conflicting national standards shall be withdrawn at the latest by January 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13257:2000.

Annex D provides details of significant technical changes between this European Standard and the previous edition.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU).

For relationship with Regulation (EU), see informative Annex ZA, which is an integral part of this document.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

SIST EN 13257:2014

<https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014>

Introduction

This European Standard allows manufacturers to describe geotextiles and geotextile-related products on the basis of declared values for characteristics relevant to the intended use and if tested to the specified method. It also includes procedures for the assessment and verification of constancy of performance and factory production control.

This European Standard may also be used by designers, end-users and other interested parties to define which functions and conditions of use are relevant.

The term “product” used in this European Standard refers to a geotextile or geotextile-related product.

This European Standard is part of a series of standards, addressing the requirements for geotextiles and geotextile-related products when used in a specific application. Annex C provides guidance on how to select the appropriate standard.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13257:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014>

EN 13257:2014 (E)**1 Scope**

This European Standard specifies the relevant characteristics of geotextiles and geotextile-related products used in solid waste disposals, and the appropriate test methods to determine these characteristics.

The intended use of these geotextiles or geotextile-related products is to fulfil one or more of the following functions: filtration, separation, reinforcement and protection. The separation function will always occur in conjunction with filtration or reinforcement, and hence will not be specified alone.

This European Standard is not applicable to geosynthetic barriers, as defined in EN ISO 10318.

This European Standard provides for the assessment and verification of constancy of performance of the product to this European Standard and for factory production control procedures.

NOTE Particular application cases may contain requirements regarding additional properties and – preferably standardized – test methods, if they are technically relevant.

This European Standard may be used to derive design values by taking into account factors within the context of the definitions given in EN 1997-1 (Eurocode 7), e.g. factors of safety. The design life of the product should be determined, since its function may be temporary, as a construction expediency, or permanent, for the lifetime of the structure.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12224, *Geotextiles and geotextile-related products - Determination of the resistance to weathering*

EN 12226, *Geosynthetics - General tests for evaluation following durability testing*

EN 12447, *Geotextiles and geotextile-related products - Screening test method for determining the resistance to hydrolysis in water*

EN 13719, *Geotextiles and geotextile-related products - Determination of the long term protection efficiency of geotextiles in contact with geosynthetic barriers*

EN 14574, *Geosynthetics - Determination of the pyramid puncture resistance of supported geosynthetics*

EN ISO 1043-1, *Plastics - Symbols and abbreviated terms - Part 1: Basic polymers and their special characteristics (ISO 1043-1)*

EN ISO 9862, *Geosynthetics - Sampling and preparation of test specimens (ISO 9862)*

EN ISO 10318, *Geosynthetics - Terms and definitions (ISO 10318)*

EN ISO 10319, *Geosynthetics - Wide-width tensile test (ISO 10319)*

EN ISO 10320, *Geotextiles and geotextile-related products - Identification on site (ISO 10320)*

EN ISO 10321, *Geosynthetics - Tensile test for joints/seams by wide-width strip method (ISO 10321)*

EN ISO 10722, *Geosynthetics - Index test procedure for the evaluation of mechanical damage under repeated loading - Damage caused by granular material (ISO 10722)*

EN ISO 11058, *Geotextiles and geotextile-related products - Determination of water permeability characteristics normal to the plane, without load (ISO 11058)*

EN ISO 12236, *Geosynthetics - Static puncture test (CBR test) (ISO 12236)*

EN ISO 12956, *Geotextiles and geotextile-related products - Determination of the characteristic opening size (ISO 12956)*

EN ISO 12957-1, *Geosynthetics - Determination of friction characteristics - Part 1: Direct shear test (ISO 12957-1)*

EN ISO 12957-2, *Geosynthetics - Determination of friction characteristics - Part 2: Inclined plane test (ISO 12957-2)*

EN ISO 13426-1, *Geotextiles and geotextile-related products - Strength of internal structural junctions - Part 1: Geocells (ISO 13426-1)*

EN ISO 13426-2, *Geotextiles and geotextile-related products - Strength of internal structural junctions - Part 2: Geocomposites (ISO 13426-2)*

EN ISO 13431, *Geotextiles and geotextile-related products - Determination of tensile creep and creep rupture behaviour (ISO 13431)*

EN ISO 13433, *Geosynthetics - Dynamic perforation test (cone drop test) (ISO 13433)*

EN ISO 13438, *Geotextiles and geotextile-related products - Screening test method for determining the resistance to oxidation (ISO 13438)*

ISO 10390, *Soil quality - Determination of pH*

ASTM D7409 - 07e1, *Standard Test Method for Carboxyl End Group Content of Polyethylene Terephthalate (PET) Yarns*

ASTM D4603 - 03(2011)e1, *Standard Test Method for Determining Inherent Viscosity of Poly(Ethylene Terephthalate) (PET) by Glass Capillary Viscometer*

3 Terms, definitions and abbreviations

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 10318 and the following apply.

3.1.1

product

geotextile or geotextile-related product

3.1.2

specification

any document in which the work, functions and specific conditions of use of the product are described

3.1.3

rework material (RWM)

material that is generated in a process and capable of being reclaimed within the same process that generated it

3.1.4

post-consumer material (PCM)

material generated by households or by commercial, industrial and institutional facilities in their role as end-users of the product which can no longer be used for its intended purpose. This includes returns of material from the distribution chain

EN 13257:2014 (E)**3.1.5****post-industrial material (PIM)**

material diverted from the waste stream during a manufacturing process

3.2 Abbreviations

For the purposes of this document, the abbreviations given in EN ISO 1043-1 and EN ISO 10318 and the following apply.

- AR: aramid
- GCO-R: geocomposite reinforcement

4 Required characteristics and corresponding methods of test**4.1 General**

The main functions of geotextiles and geotextile-related products used in solid waste disposals are filtration, separation reinforcement and protection. If a drainage or erosion control system is integrated in the construction, the requirements of the appropriate standards shall also be fulfilled. As the separation function is always used in conjunction with another function, the separation function shall never be specified alone.

The specification shall define which functions and conditions of use are relevant (see Table 1). The producer shall provide the necessary data based on the requirements and test methods specified in this European Standard, as described in 5.1.

The characteristics, their relevance to the conditions of use, and the test methods to be used, are specified in Table 1. The list of characteristics in Table 1 includes those needed for regulatory purposes (H), those relevant to all conditions of use (A), and those relevant to specific conditions of use (S). The indication “–” means that the characteristic is not relevant for that function.

Where, for the same property, data for more than one function shall be provided, the following ranking order shall be observed: H overrules A, A overrules S, and S overrules “–”.

The functions and conditions of use, corresponding with the S-coded characteristics in Table 1, are specified in 4.3.

Durability shall be assessed in accordance with the requirements of Annex B.

4.2 Selection of the appropriate standard in a specific application

Guidelines for the selection of the appropriate standard in a specific application are given in Annex C.

Table 1 — Geotextiles and geotextile-related products used in solid waste disposals – Functions, function-related characteristics and test methods to be used

Characteristic	Test method	Functions			
		Filtration	Separation	Reinforcement	Protection
(1) Tensile strength ^{b)}	EN ISO 10319	H	H	H	H
(2) Elongation at maximum load	EN ISO 10319	H	H	H	H
(3) Stiffness at 2 %, 5 % and 10 % ^{c)}	EN ISO 10319	–	–	S	–
(4) Tensile strength of seams and joints ^{c) d)}	EN ISO 10321	S	S	S	S
(5) Static puncture resistance (CBR test) ^{a), b)}	EN ISO 12236	S	H	H	see (10)
(6) Dynamic perforation resistance (cone drop test) ^{a)}	EN ISO 13433	H	A	H	H
(7) Friction	EN ISO 12957-1; EN ISO 12957-2	S	S	S	S
(8) Tensile creep	EN ISO 13431	–	–	S	--
(9) Damage during installation resistance	EN ISO 10722	A	A	A	A
(10) Protection characteristics	EN 13719 EN 14574	-- –	-- –	-- –	H S
(11) Characteristic opening size	EN ISO 12956	H	H	–	--
(12) Water permeability normal to the plane (velocity index)	EN ISO 11058	H	H	S	--
(13) Durability	According to Annex B	H	H	H	H
<p><u>Relevance of codes:</u></p> <p>H: required for regulatory purposes A: relevant to all conditions of use S: relevant to specific conditions of use “–”: indicates that the characteristic is not relevant for that function.</p>					

EN 13257:2014 (E)

^a Static puncture resistance may not be relevant for some types of products, e. g. GGR, GCO-R or GST.

^b If the mechanical properties (tensile strength and static puncture) are coded "H" in this Table, the producer shall provide data for both. The use of only one, either tensile strength or static puncture, is sufficient in a tender specification.

^c The strength of internal structural junctions of geocells shall be tested in accordance with EN ISO 13426-1.

^d The strength of internal structural junctions of geocomposites shall be tested in accordance with EN ISO 13426-2.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13257:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/65743e5d-3625-4639-bed1-de85fde1f522/sist-en-13257-2014>

4.3 Characteristics relevant to specific conditions of use

4.3.1 Stiffness at 2 %, 5 % and 10 %

Data on stiffness are necessary for the reinforcement function if the deformation of the structure needs to be evaluated.

4.3.2 Tensile strength of seams and joints

Data on tensile strength of seams and joints are necessary for all functions if the product is to be mechanically jointed and if load is transferred across the seams and joints.

4.3.3 Static puncture

Data on static puncture or - as an alternative - on tensile strength, are necessary for the filtration function if required by the specification, i.e. when the site loading conditions are such that there is a potential risk of static puncture of the filter layer.

4.3.4 Friction characteristics

Data on friction characteristics are necessary for the functions separation and filtration when the product is used in a situation where a differential movement can take place between the product and adjacent material that may endanger the stability of the works. The friction characteristics can be measured, using site specific materials, by a direct shear test according to EN ISO 12957-1 or, in the case of loads up to 5 kPa, by an inclined plane test according to EN ISO 12957-2.

Friction behaviour with the adjacent construction materials, e.g. the soil or the geosynthetic barrier, should also be considered.

4.3.5 Tensile creep

Data on tensile creep may be used to give an indication of the resistance to sustained loading, when the product fulfils a reinforcement function.

4.3.6 Protection efficiency (EN 14574)

Data on protection efficiency in accordance with EN 14574 are necessary when there is a risk that the barrier material be punctured by sharp objects or materials.

4.3.7 Water permeability normal to the plane

Data on water permeability are necessary when the reinforced structure is subject to water flow.

4.4 Release of dangerous substances

National regulations on dangerous substances may require verification and declaration on release, and sometimes content, when construction products covered by this European Standard are placed on those markets.

In the absence of European harmonized test methods, verification and declaration on release/content should be done taking into account national provisions in the place of use.

NOTE An informative database covering European and national provisions on dangerous substances is available at the Construction website on EUROPA accessed through: <http://ec.europa.eu/enterprise/construction/cpd-ds/>.