

**SLOVENSKI STANDARD****SIST EN 12914:2013****01-december-2013****Nadomešča:****SIST EN 12914:2006****Proizvodi, ki se uporabljajo za pripravo pitne vode - Prašnati perlit**

Products used treatment of water intended for human consumption - Powdered perlite

Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch - Perlit, pulverförmig

**iTeh STANDARD PREVIEW**

Produits utilisés pour le traitement de l'eau destinée à la consommation humaine - Perlite en poudre

[SIST EN 12914:2013](#)[https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-0112c9ef7/sist\\_en\\_12914\\_2013.pdf](https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-0112c9ef7/sist_en_12914_2013.pdf)**Ta slovenski standard je istoveten: EN 12914:2012****ICS:**

13.060.20	Pitna voda	Drinking water
71.100.80	Kemikalije za čiščenje vode	Chemicals for purification of water

**SIST EN 12914:2013****en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 12914:2013

<https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

EN 12914

October 2012

ICS 71.100.80

Supersedes EN 12914:2005

English Version

Products used for treatment of water intended for human  
consumption - Powdered perlite

Produits utilisés pour le traitement de l'eau destinée à la  
consommation humaine - Perlite en poudre

Produkte zur Aufbereitung von Wasser für den  
menschlichen Gebrauch - Perlit, pulverförmig

This European Standard was approved by CEN on 9 September 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

**iTeh STANDARD PREVIEW**

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[SIST EN 12914:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

	Page
<b>Foreword.....</b>	<b>3</b>
<b>Introduction .....</b>	<b>4</b>
<b>1 Scope .....</b>	<b>5</b>
<b>2 Normative references .....</b>	<b>5</b>
<b>3 Terms, definitions and symbols.....</b>	<b>5</b>
<b>4 Description .....</b>	<b>5</b>
<b>5 Physical properties.....</b>	<b>6</b>
<b>6 Chemical properties .....</b>	<b>6</b>
<b>7 Specific properties.....</b>	<b>7</b>
<b>8 Test methods.....</b>	<b>7</b>
<b>9 Labelling, transportation and storage .....</b>	<b>8</b>
<b>Annex A (informative) General information on powdered perlite .....</b>	<b>10</b>
<b>Bibliography .....</b>	<b>12</b>

**iTeh STANDARD PREVIEW**

**(standards.iteh.ai)**

SIST EN 12914:2013

https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-  
9268192c9ef7/sist-en-12914-2013

## Foreword

This document (EN 12914:2012) has been prepared by Technical Committee CEN/TC 164 "Water supply", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2013, and conflicting national standards shall be withdrawn at the latest by April 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12914:2005.

The significant technical difference between this edition and EN 12914:2005 is as follows:

- Updating of 9.2 in line with current legislation.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

[SIST EN 12914:2013](https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013)

<https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013>

## Introduction

In respect of potential adverse effects on the quality of water intended for human consumption caused by the product covered by this European Standard:

- a) this European Standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- b) it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

NOTE Conformity with this European Standard does not confer or imply acceptance or approval of the product in any of the Member States of the EU or EFTA. The use of the product covered by this European Standard is subject to regulation or control by National Authorities.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 12914:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013>

## 1 Scope

This European Standard is applicable to powdered perlite used for treatment of water intended for human consumption. It describes the characteristics of powdered perlite and specifies the requirements and the corresponding test methods for powdered perlite and gives information on its use in water treatment.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12901:1999, *Products used for treatment of water intended for human consumption — Inorganic supporting and filtering materials — Definitions*

EN 12902, *Products used for treatment of water intended for human consumption — Inorganic supporting and filtering materials — Methods of test*

EN ISO 10058 (all parts), *Chemical analysis of magnesite and dolomite refractory products (alternative to the X-ray fluorescence method) (ISO 10058)*

## 3 Terms, definitions and symbols

## STANDARD PREVIEW

For the purposes of this document, the terms, definitions and symbols given in EN 12901:1999 apply.

SIST EN 12914:2013

## 4 Description

<https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013>

### 4.1 Identification

#### 4.1.1 Chemical name

Not applicable.

#### 4.1.2 Synonym or common names

Perlite, expanded perlite.

#### 4.1.3 Chemical formula

Not applicable.

#### 4.1.4 CAS Registry number <sup>1)</sup>

Not available.

---

1) Chemical Abstracts Service Registry Number.

## EN 12914:2012 (E)

**4.1.5 EINECS Reference <sup>2)</sup>**

Not available.

**4.2 Commercial form**

The product is available in white powder forms in grades differing in permeability.

**5 Physical properties****5.1 Appearance**

White powder.

**5.2 Particle size distribution****5.2.1 Particle size**

A mass fraction of at least 95 % shall have a particle size less than 1 000 µm.

NOTE Other values can be necessary for certain applications. The particle size distribution is commonly specified as a mass fraction of 95 % less than a given particle size.

**iTeh STANDARD PREVIEW**  
 The particle size distribution shall be within the manufacturer's declared values.  
**(standards.iteh.ai)**

**5.2.2 Uniformity coefficient**

Not relevant.

[SIST EN 12914:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013>

**5.2.3 Oversize and undersize particles**

The proportion of oversize and undersize particles shall be within the manufacturer's declared values.

**5.3 Density**

The bulk density packed shall be in the range of 200 kg/m<sup>3</sup> to 700 kg/m<sup>3</sup>.

**6 Chemical properties**

This European Standard specifies the minimum purity requirements for powdered perlite used for the treatment of water intended for human consumption. Limits are given for impurities commonly present in the product. Depending on the raw material and the manufacturing process other impurities may be present and, if so, this shall be notified to the user and when necessary to relevant authorities.

Users of this product should check the national regulations in order to clarify whether it is of appropriate purity for treatment of water intended for human consumption, taking into account raw water quality, contents of other impurities and additives used in the products not stated in this product standard.

Limits have been given for impurities and chemical parameters where these are likely to be present in significant quantities from the current production process and raw materials. If the production process or raw

---

2) European Inventory of Existing Commercial Chemical Substances.

materials lead to significant quantities of impurities, by-products or additives being present, this shall be notified to the user.

The composition of the commercial product shall conform to Table 1.

**Table 1 — Composition of commercial product**

Parameter		Limit in mass fraction in% of the product
SiO <sub>2</sub>	min	70
Al <sub>2</sub> O <sub>3</sub>	min	10
Na <sub>2</sub> O + K <sub>2</sub> O	min	5
Mass loss at 150 °C	max	5

After filling, washing and commissioning of a filter system producing drinking water, powdered perlite should not increase the concentrations of chemical parameters (see [1]).

NOTE Water extractable substances, determined in accordance with the method for powdered materials given in EN 12902, can be used to estimate the leaching of the chemicals specified in EN 12902.

## iTeh STANDARD PREVIEW

### 7 Specific properties (standards.iteh.ai)

The permeability shall be within 15 % of the manufacturer's declared value and the cake density shall be within 5 % of the manufacturer's declared value EN 12914:2013

<https://standards.iteh.ai/catalog/standards/sist/a28b8032-c409-4fd9-bacc-9268192c9ef7/sist-en-12914-2013>

## 8 Test methods

### 8.1 Sampling

Prepare the laboratory sample(s) required by the relevant procedures described in EN 12902.

### 8.2 Analysis

#### 8.2.1 Particle size distribution

The particle size distribution shall be determined in accordance with EN 12902.

#### 8.2.2 Bulk density packed

The bulk density packed shall be determined in accordance with EN 12902.

#### 8.2.3 Content of silica

The content of silica shall be determined in accordance with EN 12902.

#### 8.2.4 Content of aluminium oxide

The content of Al<sub>2</sub>O<sub>3</sub> shall be determined in accordance with EN ISO 10058.