



SLOVENSKI STANDARD
oSIST prEN 10253-2:2018
01-januar-2018

Cevni fittingi za soležne zware - 2. del: Nelegirana in feritna legirana jekla s posebnimi zahtevami kontrole

Butt-welding pipe fittings - Part 2: Non alloy and ferritic alloy steels with specific inspection requirements

Formstücke zum Einschweißen - Teil 2: Unlegierte und legierte ferritische Stähle mit besonderen Prüfanforderungen

Raccords à souder bout à bout - Partie 2 : Aciers non alliés et aciers ferritiques alliés avec contrôle spécifique

ITIH STANDARD PREVIEW
(standards.iteh.ai)
[kSIST FprEN 10253-2:2021](https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fprEN-10253-2-2021)
<https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fprEN-10253-2-2021>

Ta slovenski standard je istoveten z: prEN 10253-2

ICS:

23.040.40	Kovinski fittingi	Metal fittings
77.140.20	Visokokakovostna jekla	Stainless steels
77.140.45	Nelegirana jekla	Non-alloyed steels

oSIST prEN 10253-2:2018

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[kSIST FprEN 10253-2:2021](https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fpren-10253-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fpren-10253-2-2021>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 10253-2

November 2017

ICS 77.140.20; 23.040.40; 77.140.45

Will supersede EN 10253-2:2007

English Version

Butt-welding pipe fittings - Part 2: Non alloy and ferritic alloy steels with specific inspection requirements

Raccords à souder bout à bout - Partie 2 : Aciers non alliés et aciers ferritiques alliés avec contrôle spécifique

Formstücke zum Einschweißen - Teil 2: Unlegierte und legierte ferritische Stähle mit besonderen Prüfanforderungen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ECISS/TC 110.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
European foreword.....		5
Introduction		6
1	Scope.....	7
2	Normative references.....	7
3	Terms and definitions	10
4	Symbols and abbreviations	11
5	Classification of grades and designation	12
5.1	Classification of grades	12
5.2	Designation of steel grades.....	12
5.3	Designation of fittings	12
5.3.1	General.....	12
5.3.2	Elbows and return bends	12
5.3.3	Reducers.....	12
5.3.4	Tees	13
5.3.5	Caps.....	13
6	Information to be supplied by the purchaser	13
6.1	Mandatory information	13
6.2	Options.....	13
6.3	Examples of an order	15
6.3.1	Example 1.....	15
6.3.2	Example 2.....	15
6.3.3	Example 3.....	15
6.3.4	Example 4.....	15
6.3.5	Example 5.....	15
7	Resistance to internal pressure	15
7.1	General.....	15
7.2	Fittings of type A.....	16
7.3	Fittings of type B.....	16
8	Manufacturing process.....	16
8.1	Steelmaking process	16
8.2	Product making process for fittings and heat treatment	16
8.2.1	Product making process	16
8.2.2	Welding as part of the manufacturing process of the fitting.....	17
8.2.3	Heat treatment condition.....	18
9	Technical requirements.....	19
9.1	General.....	19
9.2	Chemical composition	20
9.2.1	Cast analysis.....	20
9.2.2	Product analysis	20
9.3	Mechanical properties.....	25
9.4	Creep rupture strength values	34
9.5	Weldability	34
10	Appearance and internal soundness (delivery conditions)	34

10.1	Definitions of imperfections.....	34
10.2	Appearance	36
10.3	Internal soundness	36
11	Dimensions and tolerances.....	36
11.1	Dimensions	36
11.1.1	General	36
11.1.2	Elbows.....	37
11.1.3	Tees.....	37
11.1.4	Reducers	38
11.1.5	Caps.....	39
11.1.6	Preferred diameters and wall thicknesses.....	39
11.2	Dimensional tolerances.....	41
11.2.1	Diameter	41
11.2.2	Out of roundness.....	42
11.2.3	Wall thickness tolerances.....	42
11.2.4	Tolerances on specific dimensions and form	42
11.2.5	Corrugation.....	43
11.3	Performance of the end bevelling.....	44
12	Inspection.....	45
12.1	Type of inspection	45
12.2	Inspection documents.....	45
12.2.1	Type of inspection documents.....	45
12.2.2	Content of inspection documents.....	45
12.3	Summary of inspection and testing.....	46
13	Sampling	47
13.1	Frequency of tests.....	47
13.1.1	Test unit	47
13.1.2	Number of test pieces per test unit.....	49
13.2	Preparation of samples and test pieces.....	49
13.2.1	Samples for product analysis	49
13.2.2	Samples and test pieces for mechanical tests.....	49
13.2.3	Test piece for the tensile test on the base material.....	49
13.2.4	Test piece for the tensile test transverse to the weld.....	49
13.2.5	Test piece for the weld bend test	49
13.2.6	Test piece for the impact test	49
14	Test methods.....	50
14.1	Chemical analysis	50
14.2	Tensile test on the base material.....	50
14.2.1	At room temperature	50
14.2.2	At elevated temperature	50
14.3	Transverse tensile test on the weld	51
14.4	Hardness test.....	51
14.5	Weld bend test.....	51
14.6	Impact testing	51
14.7	Dimensional testing.....	52
14.8	Visual testing (VT).....	52
14.9	Non-destructive testing (NDT).....	52
14.9.1	Personnel.....	52
14.9.2	NDT of the weld	52
14.9.3	NDT of cold formed tees	53
14.9.4	Detection of laminar imperfections.....	53

prEN 10253-2:2017 (E)

14.9.5	NDT for the detection of longitudinal imperfections.....	53
14.9.6	NDT for the detection of transverse imperfections.....	53
14.9.7	NDT of bars and forgings.....	53
14.10	Positive material identification (PMI).....	54
15	Marking.....	54
16	Protection and packaging.....	55
Annex A	(normative) Dimensions.....	56
A.1	General.....	56
A.2	Elbows.....	56
A.3	Tees.....	58
A.4	Reducers.....	60
A.5	Caps.....	62
Annex B	(normative) Determination of pressure factors and wall thickness.....	64
B.1	General.....	64
B.2	Symbols and units.....	64
B.3	Minimal and nominal wall thickness.....	67
B.4	Pressure factors of fittings of type A.....	67
B.4.1	Pressure factor.....	67
B.4.2	Elbows.....	68
B.4.3	Tees.....	68
B.4.4	Reducers.....	71
B.4.5	Caps.....	75
B.5	Wall thicknesses of fittings of type B.....	77
B.5.1	Elbows.....	77
B.5.2	Tees.....	79
B.5.3	Reducers.....	81
B.5.4	Caps.....	86
Annex C	(normative) Pressure factor tables for Fittings of type A.....	88
C.1	General.....	88
C.2	Elbows.....	88
C.3	Tees.....	91
C.4	Reducers.....	100
C.5	Caps.....	111
Annex D	(informative) Wall thickness tables for fittings of type B.....	112
D.1	General.....	112
D.2	Elbows.....	112
D.3	Tees.....	115
D.4	Reducers.....	122
D.5	Caps.....	138
Annex E	(informative) Recommended heat treatment temperatures.....	140
Annex F	(informative) Creep rupture strength values.....	141
Annex ZA	(informative) Relationship between this European Standard and the Essential Requirements of EU Directive 2014/68/EU.....	147
Bibliography	149

European foreword

This document (prEN 10253-2:2017) has been prepared by Technical Committee ECISS/TC 110 "Steel tubes, and iron and steel fittings", the secretariat of which is held by UNI.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 10253-2:2007.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 2014/68/EU.

For relationship with EU Directive, see informative Annex ZA, which is an integral part of this document.

EN 10253 comprises a series of European Standards about *Butt-welding pipe fittings*, namely:

- *Part 1: Wrought carbon steel for general use and without specific inspection requirements;*
- *Part 2: Non alloy and ferritic alloy steels with specific inspection requirements;*
- *Part 3: Wrought austenitic and austenitic-ferritic (duplex) stainless steels without specific inspection requirements;*
- *Part 4: Wrought austenitic and austenitic-ferritic (duplex) stainless steels with specific inspection requirements.*

[kSIST FprEN 10253-2:2021
https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fpren-10253-2-2021](https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fpren-10253-2-2021)

prEN 10253-2:2017 (E)**Introduction**

In writing this European Standard the competent committee recognized that there are two broad types of products commonly used, and decided to reflect these in the standard by differentiating between two parts.

EN 10253-1 describes fittings without formal reference to the pressure resistance, which are not intended to be used in applications, covered by the Pressure Equipment Directive (2014/68/EU) classes I to IV.

EN 10253-2 defines two types of fittings: Type A fittings have the same wall thickness at the welding ends and at the body of the fitting than a pipe having the same specified wall thickness. Their resistance to internal pressure is, in general, less than that of a straight pipe with the same dimensions. Type B fittings showing increased wall thickness at the body of the fitting are designed to resist the same internal pressure as a straight pipe with same dimensions. These two types of fittings are intended to be used in applications covered by the EU Directive 2014/68/EU. According to this Directive and further interpretation guidelines (e.g. guideline 7/19), seamless fittings are considered as materials whereas welded fittings are considered as components. Therefore, in some areas of this European Standard, provisions for seamless and welded fittings are different.

The selection of steel type and requirement level depend on many factors; the properties of the fluid to be conveyed, the service conditions, the design code and any statutory requirements should all be taken into consideration. Therefore this standard gives no detailed guidelines for the application of different parts. It is the ultimate responsibility of the user to select the appropriate part for the intended application.

IMPORTANT — This document contains, in Annexes B, C and D, tables which have to be re-examined with regard to their correctness before publication of the standard. In the context of this CEN-Enquiry readers of this draft are therefore invited to comment on any amendments that may be required, particularly with regard to the tables in Annexes B, C and D.

1 Scope

This draft European Standard specifies the technical delivery requirements for seamless and welded butt-welding fittings (elbows, concentric and eccentric reducers, equal and reducing tees, caps) made of carbon and alloy steel in two test-categories which are intended for pressure purposes at room temperature, at low temperature or at elevated temperatures, and for the transmission and distribution of fluids and gases.

It specifies:

- a) type of fittings;
 - 1) type A: Butt-welding fittings with reduced pressure factor;
 - 2) type B: Butt-welding fittings for use at full service pressure;
- b) steel grades and their chemical compositions;
- c) mechanical properties;
- d) dimensions and tolerances;
- e) requirements for inspection and testing;
- f) inspection documents;
- g) marking;
- h) protection and packaging.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[kSIST FprEN 10253-2:2021](https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-40280127000a/pr-en-10253-2-2021)

[https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-](https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-40280127000a/pr-en-10253-2-2021)

NOTE In the case of a harmonised supporting standard for materials, presumption of conformity to the ESRs is limited to technical data of materials in the standard and does not presume adequacy of the material to a specific item of equipment. Consequently it is essential that the technical data stated in the material standard be assessed against the design requirements of this specific item of equipment to verify that the ESRs of the PED are satisfied.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10028-2, *Flat products made of steels for pressure purposes — Part 2: Non-alloy and alloy steels with specified elevated temperature properties*

EN 10028-3, *Flat products made of steels for pressure purposes — Part 3: Weldable fine grain steels, normalized*

prEN 10253-2:2017 (E)

EN 10028-4, *Flat products made of steels for pressure purposes — Part 4: Nickel alloy steels with specified low temperature properties*

EN 10052:1993, *Vocabulary of heat treatment terms for ferrous products*

EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

EN 10168, *Steel products — Inspection documents — List of information and description*

EN 10204, *Metallic products — Types of inspection documents*

EN 10217-1, *Welded steel tubes for pressure purposes — Technical delivery conditions*

EN 10217-2, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties*

EN 10217-3, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties*

EN 10217-4, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 4: Electric welded non-alloy steel tubes with specified low temperature properties*

EN 10217-5, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 5: Submerged arc welded non alloy and alloy steel tubes with specified elevated temperature properties*

EN 10217-6, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties*

EN 10220, *Seamless and welded steel tubes — Dimensions and masses per unit length*

EN 10222-2, *Steel forgings for pressure purposes — Part 2: Ferritic and martensitic steels with specified elevated temperatures properties*

EN 10222-3, *Steel forgings for pressure purposes — Part 3: Nickel steels with specified low temperature properties*

EN 10222-4, *Steel forgings for pressure purposes — Part 4: Weldable fine grain steels with high proof strength*

EN 10228-3, *Non-destructive testing of steel forgings — Part 3: Ultrasonic testing of ferritic or martensitic steel forgings*

EN 10266, *Steel tubes, fittings and structural hollow sections — Symbols and definitions of terms for use in product standards*

EN 10273, *Hot rolled weldable steel bars for pressure purposes with specified elevated temperature properties*

EN 13480 (all parts), *Metallic industrial piping*

EN 13480-3:2012, *Metallic industrial piping — Part 3: Design and calculation*

- EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*
- EN ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377)*
- EN ISO 2566-1, *Steel - Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1)*
- EN ISO 3166-1, *Codes for the representation of names of countries and their subdivisions — Part 1: Country codes (ISO 3166-1)*
- EN ISO 3183, *Petroleum and natural gas industries — Steel pipe for pipeline transportation systems (ISO 3183)*
- EN ISO 4136, *Destructive tests on welds in metallic materials — Transverse tensile test (ISO 4136)*
- EN ISO 5173, *Destructive tests on welds in metallic materials — Bend tests (ISO 5173)*
- EN ISO 5817, *Welding — Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) — Quality levels for imperfections (ISO 5817)*
- EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1)*
- EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1)*
- EN ISO 6892-2, *Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature (ISO 6892-2)*
- EN ISO 9606-1, *Qualification testing of welders — Fusion welding — Part 1: Steels (ISO 9606-1)*
- EN ISO 10893-4, *Non-destructive testing of steel tubes — Part 4: Liquid penetrant inspection of seamless and welded steel tubes for the detection of surface imperfections (ISO 10893-4)*
- EN ISO 10893-5, *Non-destructive testing of steel tubes — Part 5: Magnetic particle inspection of seamless and welded ferromagnetic steel tubes for the detection of surface imperfections (ISO 10893-5)*
- EN ISO 10893-8, *Non-destructive testing of steel tubes — Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8)*
- EN ISO 10893-10, *Non-destructive testing of steel tubes — Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10)*
- EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*
- EN ISO 14732, *Welding personnel — Qualification testing of welding operators and weld setters for mechanized and automatic welding of metallic materials (ISO 14732)*
- CEN ISO/TR 15608, *Welding — Guidelines for a metallic materials grouping system (ISO/TR 15608)*
- EN ISO 15614-1, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1)*

prEN 10253-2:2017 (E)

EN ISO 18265, *Metallic materials — Conversion of hardness values (ISO 18265)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10020, EN 10021, EN 10052:1993 and EN ISO 377 and the following apply.

3.1**employer**

organisation for which a person works on a regular basis

Note 1 to entry: The employer may be either the fitting manufacturer or supplier or a third party organisation providing a service, e.g. NDT.

3.2**model****3.2.1****model for elbows and return bends**

bending radius of the piece

3.2.2**model for reducers**

concentric or eccentric shape of the piece

3.3**purchaser**

person or organisation that orders products in accordance with this European Standard

Note 1 to entry: The purchaser is not necessarily, but may be, a manufacturer of pressure equipment in accordance with the EU Directive listed in Annex ZA.

Note 2 to entry: Where a purchaser has responsibilities under this EU Directive, this standard will provide a presumption of conformity with the essential requirements of the Directive so identified in Annex ZA.

3.4**weld during manufacture**

weld made for obtaining a fitting

Note 1 to entry: This term does not include the tube welds when a tube is used as starting material.

3.5**seamless fitting**

fitting manufactured without welding from starting material which is not welded

3.6**welded fitting****3.6.1****fitting made from welded tubes**

3.6.2**fitting made from sheet/plate or strip where welding is a part of the manufacturing process****3.7****test category**

classification that indicates their extent and level of inspection and testing

4 Symbols and abbreviations

For the purposes of this document, the symbols defined in EN 10266 and the following apply:

<i>A</i>	Percentage of elongation at rupture, with reference to gauge length of $5,65 \sqrt{S_0}$
<i>B</i>	Back to face distance for return bends, expressed in millimetres
<i>C</i>	Centre to centre distance for return bends ($C \approx 2R$), expressed in millimetres
<i>D</i>	Specified outside diameter for elbows, return ends, equal tees, caps and the major outside diameter for reducers and reducing tees, expressed in millimetres
<i>D₁</i>	Specified minor outside diameter for reducers and reducing tees, expressed in millimetres
<i>D_{max}</i>	Bigger diameter in one section, expressed in millimetres
<i>D_{min}</i>	Smaller diameter in the same section, expressed in millimetres
<i>F</i>	Distance from the axis of the branch outlet to the face of the centre body of tees, expressed in millimetres
<i>G</i>	Distance from the axis of the centre line to the face of the branch outlet of reducing tees, expressed in millimetres
<i>ID</i>	Inside diameter at the welding ends of elbows, return bends, equal tees and at the major welding end of reducers and reducing tees ($ID = D - 2T$)
<i>ID₁</i>	Inside diameter at the minor welding end of reducers and reducing tees ($ID_1 = D_1 - 2T_1$)
<i>K</i>	Total height for caps, expressed in millimetres
<i>L</i>	Face to face distance for reducers, expressed in millimetres
<i>P</i>	Tolerance on the form of elbows
<i>R</i>	Bending radius of elbows and return bends, expressed in millimetres
<i>R₁</i>	Inside spherical radius of cap
<i>R₂</i>	Inside knuckle radius of cap
<i>R_m</i>	Tensile strength, expressed in megapascals
<i>R_{p0,2}</i>	Minimum 0,2 % proof strength, expressed in megapascals
<i>R_{t0,5}</i>	Minimum 0,5 % proof strength, expressed in megapascals
<i>T</i>	Specified wall thickness at the welding ends for elbows, return bends, equal tees and bends or on the <i>D</i> end for reducers and reducing tees, expressed in millimetres
<i>T₁</i>	Specified wall thickness on the <i>D₁</i> welding end of reducers and reducing tees, expressed in millimetres

prEN 10253-2:2017 (E)

TC	Test category
W	Distance from the extrados to the centre of a 90° elbow at the welding ends
X	Tolerance on the form of fittings
Z	Distance from the extrados to the centre of a 45° elbow at the welding ends

5 Classification of grades and designation**5.1 Classification of grades**

In accordance with the classification system in EN 10020, the steel grades P235TR2, P265TR2, P235GH, P265GH, P215NL and P265NL are non-alloy quality steels, P355N, P355NH and P355NL1 alloy quality steels and the other steel grades are classified as alloy special steels.

The steel grades P235GH, P265GH, P355N, P355NH and P355NL1 can be provided in accordance to test category TC1 or TC2. Any other steel grade given in Table 2 shall be provided only in accordance to TC2.

5.2 Designation of steel grades

For the fittings covered by this European Standard the steel designation consists of:

— the number of this European Standard (EN 10253-2),

plus either

— steel name in accordance with EN 10027-1,

or

— steel number allocated in accordance with EN 10027-2.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fpren-10253-2-2021>

5.3 Designation of fittings**5.3.1 General**

Fittings are designated by their name and the following parameters.

5.3.2 Elbows and return bends

Elbows and return bends are designated by the following parameters:

- model (2D, 3D or 5D);
- type (type A or type B);
- angle;
- outside diameter (D);
- wall-thickness (T).

5.3.3 Reducers

Reducers are designated by the following parameters:

- model (concentric (con) or eccentric (ecc));
- type (type A or type B);

- c) major diameter (D) and wall-thickness (T);
- d) minor diameter (D_1) and wall-thickness (T_1).

5.3.4 Tees

Equal tees are designated by the following parameters:

- a) type (type A or type B),
- b) outside diameter (D)
- c) wall-thickness (T).

Reducing tees are designated by the following parameters:

- a) type (type A or type B),
- b) major diameter (D) and wall-thickness (T)
- c) minor diameter (D_1) and wall-thickness (T_1).

5.3.5 Caps

Caps are designated by the following parameters:

- a) the type (type A or type B),
- b) the outside diameter (D)
- c) the wall-thickness (T).

ITEN STANDARD PREVIEW

(standards.iteh.ai)

kSIST FprEN 10253-2:2021

<http://standards.iteh.ai/catalog/standards/sist/94ef347c-24c9-488d-8f66-4bb286fb2790/ksist-fpren-10253-2-2021>

6 Information to be supplied by the purchaser

6.1 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) quantity required (number of pieces);
- b) reference to this European Standard;
- c) designation of fittings (clause 5.3);
- d) designation of the steel grade (see 5.2);
- e) test category 1 or 2 (TC1/TC2) for unalloyed steels (see 12.3).

6.2 Options

A number of options are specified in this European Standard and these are listed below. In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the fittings shall be supplied in accordance with the basic specification (see 6.1).

- 1) Steelmaking process (see 8.1);
- 2) Method of manufacture of the fitting (see 8.2.1);