



Designation: A 701 – 96 (Reapproved 2004)

Standard Specification for Ferromanganese-Silicon¹

This standard is issued under the fixed designation A 701; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a manganese-silicon alloy designated as ferromanganese-silicon.

2. Referenced Documents

2.1 *ASTM Standards:*²

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 31 Methods for Chemical Analysis of Ferroalloys³

E 32 Practices for Sampling Ferroalloys and Steel Additives for Determination of Chemical Composition

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity,

3.1.2 Name of material,

3.1.3 ASTM designation and year of issue,

3.1.4 Size desired,

3.1.5 Requirement for packaging, and

3.1.6 Reports requested with shipment.

3.2 The basis of payment shall be per pound of alloy.

4. Chemical Requirements

4.1 The alloy shall conform to the chemical requirements as shown in Table 1.

4.2 The manufacturer shall furnish an analysis of each shipment as requested by the customer.

4.3 The values shown in Table 2 are expected maximums for the elements listed.

5. Size

5.1 The alloy is available in the sizes shown in Table 3.

5.2 The sizes listed in Table 3 are typical of the product as shipped from the seller's plant. Some deterioration of size can

TABLE 1 Recommended Specification for Ferromanganese-Silicon

Element	Composition, %
Manganese	63 to 66
Carbon, max	0.08
Silicon	28 to 32
Phosphorus, max	0.05

be expected in transit. This system is based on the relative friability as indicated in the Appendix.

6. Sampling

6.1 The material shall be sampled in accordance with Practices E 32.

6.2 Other methods of sampling may be used if mutually agreed upon between the purchaser and the seller. In case of discrepancies, Practices E 32 shall be used as the referee.

7. Chemical Analysis

7.1 Chemical procedures for analysis of ferroalloy components are not standardized. The chemical content procedures

TABLE 2 Recommended Supplementary Chemical Requirements for Ferromanganese-Silicon

Element	Composition, max, %
Arsenic	0.15
Tin	0.010
Lead	0.050
Chromium	0.50

TABLE 3 Ferromanganese-Silicon Sizes

Sizes	Tolerance
75 lb by 2 in. (34.0 kg by 50.8 mm)	
50 lb by 1 in. (22.7 kg by 25.4 mm)	
6 by ½ in. (152.4 mm by 12.70 mm)	
3 in. by down (76.2 mm by down)	10 % passing ¼ in. (6.3 mm) screen, max
2 in. by down (50.8 mm by down)	10 % passing ¼ in. (6.3 mm) screen, max

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Oct. 1, 2004. Published October 2004. Originally approved in 1974. Last previous edition approved in 2000 as A 701 – 96 (2000).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.