
**Cylindrical cork stoppers — Physical
tests —**

Part 3:
Determination of humidity content

Bouchons cylindriques en liège — Essais physiques —

Partie 3: Détermination du taux d'humidité

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9727-3:2007

<https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599fbfaf127a/iso-9727-3-2007>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 9727-3:2007](https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599fbfaf127a/iso-9727-3-2007)

<https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599fbfaf127a/iso-9727-3-2007>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9727-3 was prepared by Technical Committee ISO/TC 87, *Cork*.

This first edition of ISO 9727-3, together with the other parts of ISO 9727:2007, cancels and replaces ISO 9727:1991, which has been technically revised.

ISO 9727 consists of the following parts, under the general title *Cylindrical cork stoppers — Physical tests*:

- *Part 1: Determination of dimensions* [ISO 9727-3:2007](https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599fb6f127a/iso-9727-3-2007)
- *Part 2: Determination of mass and apparent density for agglomerated cork stoppers*
- *Part 3: Determination of humidity content*
- *Part 4: Determination of dimensional recovery after compression*
- *Part 5: Determination of extraction force*
- *Part 6: Determination of liquid tightness*
- *Part 7: Determination of dust content*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9727-3:2007

<https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599fbfaf127a/iso-9727-3-2007>

Cylindrical cork stoppers — Physical tests —

Part 3: Determination of humidity content

1 Scope

This part of ISO 9727 specifies a test method for determining the humidity content of cylindrical cork stoppers, ready for use or semi-worked.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 633, *Cork — Vocabulary*

(standards.iteh.ai)

3 Terms and definitions

[ISO 9727-3:2007](https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599bfaf127a/iso-9727-3-2007)

<https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599bfaf127a/iso-9727-3-2007>

For the purposes of this document, the terms and definitions given in ISO 633 and the following apply.

3.1

constant mass

mass of a stopper submitted to a drying operation is called constant when the difference between two consecutive weighings does not differ by more than 10 mg

4 Apparatus

4.1 Long method

4.1.1 **Balance**, with a resolution less than or equal to 0,001 g.

4.1.2 **Desiccator**, with a hygroscopic salt and a saturation indicator.

4.1.3 **Ventilated oven**, at $103\text{ °C} \pm 4\text{ °C}$.

4.2 Quick method

4.2.1 **Specific device to measure resistivity**, with two electrodes adapted to the cork material and that can be checked through a standard resistance (4.2.2).

4.2.2 **Standard resistance**.

5 Test conditions

5.1 Environment

The test shall be carried out in an environment with the following characteristics:

- temperature $21\text{ °C} \pm 4\text{ °C}$;
- relative humidity of air $60\% \pm 20\%$.

5.2 Cork stoppers

At the beginning of the test, and using the quick method (7.2) confirm that the stoppers of the test sample are at a temperature of $21\text{ °C} \pm 4\text{ °C}$.

6 Sampling

From each lot, take the quantity of stoppers that correspond to the sampling plan previously agreed between the interested parties.

7 Procedure

7.1 Long method

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Identify each stopper. Weigh each stopper with the balance (4.1.1). Register the result.

Place the unbroken stoppers in the oven regulated to $103\text{ °C} \pm 4\text{ °C}$ (4.1.3) for 24 h. Agglomerated cork stoppers with one or more discs of natural cork glued onto one end shall be separated into their parts, agglomerated body and discs, before going into the oven.

Take the stoppers (or parts of stoppers) out of the oven and place them in the desiccator (4.1.2) for, at a minimum, 30 min.

Weigh each stopper (or part of the stopper whenever it is an agglomerated cork stopper with one or more discs of natural cork glued onto one end). Register the result.

Put the stoppers (or parts of stoppers) back in the oven for 2 h.

Take the stoppers (or parts of stoppers) out of the oven and place them in the desiccator for 30 min.

Weigh each stopper (or part of a stopper).

If the difference between the mass obtained and the previous one is superior to 10 mg, repeat the procedure until two consecutive weighing do not differ by more than 10 mg.

7.2 Quick method

The test is described for each stopper. Repeat the test with each stopper from the global sample.

Regulate the scale of the device (4.2.1) to "cork", if several options are available.

Thrust the electrodes once, in the middle of the stoppers, 4 mm to 6 mm deep into the cylinder, in the cross-direction to the cork-layer growth of natural cork stoppers, the two electrodes defining a plan parallel to the stopper length.

Do not thrust electrodes into visible defects of the stopper, as the measurement performance may be affected.

When the measurement is carried out inside discs of agglomerated cork stoppers with one or more discs glued onto one end, the method used to thrust the electrodes in shall be included in the test report.

Read either the value, if it is shown on the device, or the measurement, reported from the device standard curve. Register the result.

8 Results

8.1 Long method

The humidity content, H , of a stopper, expressed in percentage, is given by the equation:

$$H = \frac{(m_1 - m_2)}{m_1} \times 100$$

where

m_1 is the initial mass of the stopper, before drying;

m_2 is the mass of the stopper, after drying.

The result per stopper is rounded off to the nearest 0,1 %.

8.2 Quick method

Humidity, read on or determined from the curve of the device to measure resistivity, is expressed in percentage, rounded off in accordance with the following principle:

EXAMPLE 6 to 6,4 = 6;

6,5 to 7 = 7.

8.3 Final result

Whatever the method used, the test result is the arithmetic average of the results obtained with each stopper of the test sample, expressed in percentage, rounded off to 0,1 %, and also the standard deviation and the maximum and minimum results rounded off to 0,1.

9 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 9727, specifying which of the two described methods was used;
- b) complete identification of the sample, including its type and origin;
- c) sampling report;
- d) results obtained;
- e) any deviation from this part of ISO 9727 that may have affected the results.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9727-3:2007

<https://standards.iteh.ai/catalog/standards/sist/79a6f2be-cf6d-4a0a-9c05-599fbfaf127a/iso-9727-3-2007>

ICS 55.100; 79.100

Price based on 3 pages