



Standard Specification for Solvent Cement for Acrylonitrile-Butadiene-Styrene (ABS) Plastic Pipe and Fittings¹

This standard is issued under the fixed designation D2235; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers solvent cement for joining acrylonitrile-butadiene styrene (ABS) plastic pipe and fittings for pressure and nonpressure systems.

1.2 Recommendation for using solvent cement for joining acrylonitrile-butadiene-styrene (ABS) plastic pipe and fittings is given in **Appendix X1**. Satisfactory joining of pipe and fittings cannot be made in the presence of water, as water destroys the bonding ability of solvent cement; therefore, all materials must be dry for satisfactory joining.

1.3 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 The following safety hazards caveat pertains only to the test methods portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

- D329 Specification for Acetone
- D618 Practice for Conditioning Plastics for Testing
- D740 Specification for Methyl Ethyl Ketone
- D883 Terminology Relating to Plastics
- D1084 Test Methods for Viscosity of Adhesives

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.20 on Joining. Current edition approved Oct. 1, 2004. Published October 2004. Originally approved in 1963. Last previous edition approved 2001 as D2235 – 01. DOI: 10.1520/D2235-04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D3965 Specification for Rigid Acrylonitrile-Butadiene-Styrene (ABS) Materials for Pipe and Fittings
- F402 Practice for Safe Handling of Solvent Cements, Primers, and Cleaners Used for Joining Thermoplastic Pipe and Fittings
- F412 Terminology Relating to Plastic Piping Systems
- F493 Specification for Solvent Cements for Chlorinated Poly(Vinyl Chloride) (CPVC) Plastic Pipe and Fittings
- 2.2 *Federal Standard*:
- Fed. Std. 123 Marking for Shipment (Civil Agencies)³
- 2.3 *Military Standard*:
- MIL STD-129 Marking for Shipment and Storage³
- 2.4 *National Sanitation Foundation Standards*:
- Standard No. 14 Plastic Piping Components and Related Materials⁴
- Standard No. 61 for Drinking Water Systems Components—Health Effects⁴

3. Terminology

3.1 Definitions are in accordance with Terminologies D883 and F412. Abbreviations are in accordance with Terminology D1600 unless otherwise indicated. The abbreviation for Acrylonitrile-Butadiene-Styrene plastic is ABS.

3.2 *Definition of Term Specific to This Standard*:

3.2.1 *solvent cement*—adhesive made by dissolving a plastic resin or compound in a suitable solvent or mixture of solvents. The solvent cement dissolves the surfaces of the pipe and fittings to form a bond between the mating surfaces provided the proper cement is used for the particular materials and proper techniques are followed.

4. Classification

4.1 Solvent Cement shall be acrylonitrile-butadiene-styrene plastic resin dissolved in either of the following solvents:

³ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁴ Available from the National Sanitation Foundation, P.O. Box 1468, Ann Arbor, MI, 48106.

- (1) methyl ethyl ketone
- (2) a blend of methyl ethyl ketone and acetone, with acetone constituting no more than 25 % of the solvent blend by weight.

NOTE 1—It is recommended that solvent cements made to this specification *not* be orange since that color is recommended for use with CPVC solvent cement under Specification F493.

5. Materials

5.1 *Material Specification*—Virgin ABS material shall conform to the requirements prescribed in Specification D3965 with a minimum cell classification of 1-1-2-2-2 or equivalent to the cell classification for the material being joined.

5.2 *Acrylonitrile-Butadiene-Styrene (ABS) Plastic*—Plastic containing polymers in which the minimum butadiene content is 6 %, the minimum acrylonitrile content is 15 %, the minimum styrene or substituted styrene content, or both, is 15 %, and the maximum content of all other monomers is not more than 5 %.

5.3 *Rework Material*—Only clean regrind material conforming to the requirements of this specification may be used.

5.4 *Methyl Ethyl-Ketone*—Commercial or industrial grade of MEK shall be used which complies with Specification D740.

5.5 *Acetone*—Commercial or industrial grade of acetone shall be used which complies with Specification D329.

6. Requirements

6.1 *Resin Content*—The ABS resin content shall be 15 % minimum when tested in accordance with 7.3.

6.2 *Dissolution*—The cement shall be capable of dissolving 10 % by weight of the plastic compound used in the pipe or fitting, and still be free flowing and not contain lumps or undissolved resin particles.

6.3 The cement shall be free flowing and shall not contain lumps, undissolved particles, or foreign matter. It shall show no gelation or separation that cannot be removed by stirring.

6.4 *Viscosity*—The minimum viscosity shall be 100 cP (100 mPa·s) when tested in accordance with 7.2.2.

6.5 *Lap Shear Strength*—The minimum average lap shear strength shall be 800 psi (5.5 MPa) when tested in accordance with 7.4.

NOTE 2—The specified shear strength value is used to evaluate the cement and should not be used for designing pipe joints.

7. Test Methods

7.1 The properties enumerated in this specification shall be determined in accordance with the following methods:

7.1.1 *Conditioning*—Condition the test specimens at 73.4 ± 3.6°F (23 ± 2°C) for not less than 40 h prior to test in accordance with Procedure A of Practice D618, for those tests where conditioning is required.

7.1.2 *Test Conditions*—Conduct tests at 73.4 ± 3.6°F (23 ± 2°C), unless otherwise specified in the test methods or in this specification.

7.2 Viscosity:

7.2.1 The samples for test shall be representative of the material under consideration. One sample for every batch shall be tested in accordance with 7.2.2.

7.2.2 Measure the viscosity in accordance with Method B of Test Methods D1084, except that conditioning to temperature equilibrium only is required. For qualification purposes, use a Model RVF viscometer, a speed of 10 r/min, and the spindle that, by trial, gives the closest reading to center range of scale for the cement being tested. Other speeds are used for qualification purposes.

7.3 Total Solids:

7.3.1 Apparatus:

7.3.1.1 *Ointment Tins*—Style No. 12, 1 oz (30 mL) all metal.

7.3.1.2 *Vacuum Oven*.⁵

7.3.1.3 *Desiccator*.

7.3.1.4 *Analytical Balance*.

7.3.2 *Procedure*—Stir the sample thoroughly with a spatula before weighing. Weigh 3.0 ± 0.5 g of the sample into a tared ointment tin. Place tin into the vacuum oven and heat at 248°F (120°C) for 45 min. Vacuum must be continually in operation to draw off flammable solvents and should be maintained at 0.6 in. Hg (15 mm Hg) minimum. Remove the tin from the oven and cap immediately. Place in a desiccator until cooled to room temperature. Weigh the tin and dried sample to the nearest 0.015 grains (1 mg).

NOTE 3—This material is usually nonhomogeneous and shall be thoroughly stirred before weighing. The weighing shall also be accomplished quickly to avoid loss of solvent by volatilization.

7.3.3 The use of a vacuum oven is mandatory for drying the specimen because it has no exposed heating surface nor an open flame, thus avoiding the danger of flashing. The oven also provides an open vacuum to exhaust solvent fumes.

7.3.4 The specimen shall be left in the oven for 45 min and no longer. Specimens left in for 1 h or more show a definite increase in weight.

7.3.5 *Calculation*—Calculate the percentage total solids, TS, as follows:

$$TS, \% = ((B - A)/(C - A)) \times 100$$

where:

A = weight of ointment tin,

B = weight of tin and specimen after drying, and

C = weight of tin and specimen before drying.

7.3.6 *Precision*—Duplicate samples shall be tested for best results. Duplicate results obtained by the same analyst, on the same material, on the same day, in the same laboratory are suspect if they differ by more than 0.52 % absolute. This procedure has a standard deviation of 0.13.

7.4 Lap Shear Strength (Qualification Tests):

7.4.1 *Number of Specimens*—A minimum of seven specimens shall be tested for the requirement specified in 6.5.

7.4.2 Cut sections 1 by 1 in. (25 by 25 mm) and 1 by 2 in. (25 by 50 mm) from 0.25-in. (6-mm) thick ABS sheets. One section of each size is required for each specimen (Fig. 1).

7.4.3 Clean the surfaces to be adhered with a cloth dampened with methyl ethyl ketone (MEK).

⁵ Labline Duo-Vac vacuum oven, or equivalent, has been found satisfactory for this purpose.