



Designation: A844/A844M – 04

Standard Specification for Steel Plates, 9 % Nickel Alloy, for Pressure Vessels, Produced by the Direct-Quenching Process¹

This standard is issued under the fixed designation A844/A844M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers 9 % nickel-alloy steel plates produced by the direct-quenching process. The plates are intended primarily for use in welded pressure vessels.

1.2 The direct-quenching process consists of quenching the plates directly after rolling, without permitting the plates to cool below the critical temperature prior to initiation of the quenching operation, and subsequently tempering the plates. (This differs from the “conventional” process in which the plates are permitted to cool to a temperature significantly below the critical temperature, usually to ambient temperature, prior to reheating to a temperature above the upper critical temperature, then quenching, and subsequently tempering.)

1.3 The maximum nominal thickness of plates furnished under this specification shall not exceed 2 in. [50 mm].

1.4 This material is susceptible to magnetization. Use of magnets in handling after heat treatment should be avoided if residual magnetism would be detrimental to subsequent fabrication or service.

1.5 The values stated in either inch-pound or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 *ASTM Standards*:²

[A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels](#)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Oct. 1, 2004. Published October 2004. Originally approved in 1985. Last previous edition approved in 1999 as A844/A844M – 93 (1999). DOI: 10.1520/A0844_A0844M-04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

[A435/A435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates](#)

[A577/A577M Specification for Ultrasonic Angle-Beam Examination of Steel Plates](#)

[A578/A578M Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications](#)

3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification [A20/A20M](#). These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions, quality and repair of defects, marking, loading, etc.

3.2 Specification [A20/A20M](#) also establishes the rules for ordering information that should be complied with when purchasing material to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

3.3.1 Vacuum treatment,

3.3.2 Additional or special tension testing, [a844m-04](#)

3.3.3 Additional or special impact testing, and

3.3.4 Nondestructive examination.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification [A20/A20M](#).

3.5 If the requirements of this specification are in conflict with the requirements of Specification [A20/A20M](#), the requirements of this specification shall prevail.

4. Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification [A20/A20M](#).

4.2 *Heat Treatment*:

4.2.1 The plates shall be quenched directly after rolling, without being allowed to cool below 1205°F [650°C]. The quenching shall be initiated from a temperature within the

*A Summary of Changes section appears at the end of this standard.