



Designation: B 137 – 95 (Reapproved 2004)

Endorsed by American
Electroplaters' Society
Endorsed by National
Association of Metal Finishers

Standard Test Method for Measurement of Coating Mass Per Unit Area on Anodically Coated Aluminum¹

This standard is issued under the fixed designation B 137; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers determination of the mass per unit area of coating on anodically coated aluminum and its alloys.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

D 1193 Specification for Reagent Water²

3. Significance and Use

3.1 This test method is a destructive test procedure suitable for quality control within manufacturing operations for coating mass on anodically coated aluminum and aluminum alloys. The mass of the coating is an approximation of its thickness provided the conditions under which the coating was applied, or the density of the coating, are known. An anodic coating's protective value and amenability to coloring by dyeing or electrolytic methods are related to mass of coating per unit area.

4. Reagents

4.1 The test solution shall have the following makeup:

Chromic acid anhydride (CrO ₃)	20 ± 0.5 g
Orthophosphoric acid of 85 mass %, density 1.69	35 ± 0.5 mL

¹ This test method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.07 on Chromate Conversion Coatings.

Current edition approved Oct. 1, 2004. Published October 2004. Originally approved in 1940. Last previous edition approved in 2000 as B 137 – 95 (2000).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Distilled or deionized water conforming with

Type III Reagent Water of Specification

D 1193, to make up to

1000 mL

NOTE 1—This solution is commonly referred to as a nondestructive “stripping solution” for anodic coatings. This solution dissolves the anodic coating with no significant attack of the substrate metal.

5. Test Specimen

5.1 Prepare a test specimen of known surface area, preferably a piece about 75 mm square. If the anodic coating is contaminated or impregnated with oil, grease, lacquer, etc., remove as much as possible of this material before determining the mass of the coating. It is not usually practicable to remove these materials from the pores of the coating, but surface films can frequently be removed by wiping the sample with a cloth wet with a suitable solvent.

5.2 In cases where it is required to measure the mass of coating on only one side of a specimen where both sides have anodic coatings, the following procedure may be used:

5.2.1 Prepare a specimen somewhat larger than required for 5.1.

5.2.2 Apply a suitable stop off around the edges of the specimen so that the area on the side of the specimen that is not to be tested is about 75 mm square. Paraffin wax has been used for this purpose, but any stop off that resists warm sodium hydroxide is suitable.

5.2.3 Swab the area with a warm solution of sodium hydroxide (10 mass %, 100 g/L) until bare metal is exposed, which is indicated by uniform bubbling over the entire exposed surface.

5.2.4 Swab with warm distilled water.

5.2.5 Dry with a clean cloth.

5.2.6 Swab with diluted nitric acid (1 part HNO₃, density 1.41, plus 1 part water).

5.2.7 Rinse with warm deionized or distilled water.

5.2.8 Dry at approximately 100°C until dry.

5.2.9 Cool and shear off the area covered with stop off, so that the coated area is the desired size, preferably at least 75 mm square.