
**Pulps — Determination of water retention
value (WRV)**

Pâtes — Détermination de la valeur de rétention d'eau (VRE)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 23714:2007](https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007)

<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 23714:2007](https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007)

<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007>

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

| | |
|--|----|
| Foreword..... | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions..... | 1 |
| 4 Principle | 1 |
| 5 Reagents | 2 |
| 6 Apparatus | 2 |
| 7 Sampling..... | 3 |
| 8 Preparation of sample | 3 |
| 9 Procedure | 3 |
| 10 Calculation..... | 4 |
| 11 Precision..... | 4 |
| 12 Test report..... | 6 |
| Annex A (informative) Test-pad-holding units | 7 |

[ISO 23714:2007](https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-cc3c-42c3-80ec-f38e127ebb27/iso-23714-2007)
<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-cc3c-42c3-80ec-f38e127ebb27/iso-23714-2007>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 23714 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test methods and quality specifications for pulps*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 23714:2007](https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007)

<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007>

Introduction

The water retention value (WRV) is an empirical measure of the capacity of a test pad of fibres to hold water. The WRV-value increases with increasing beating because of internal fibrillation, a widening of the small internal pores and delaminations, which has been called “swelling” and which occurs concurrently with the development of external fibrils, which also serve to hold additional water.

This test may be useful for the pulp producer as a guide to the influence of the pulping process on the fibre produced and the papermaking potential of the pulp. It is also useful for the papermaker as a measure of the efficiency of pulping and refining.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 23714:2007](https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007)

<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 23714:2007

<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007>

Pulps — Determination of water retention value (WRV)

1 Scope

This International Standard specifies a procedure for the determination of the water retention value (WRV) of all kinds of pulp.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5263-1, *Pulps — Laboratory wet disintegration — Part 1: Disintegration of chemical pulps*

ISO 5263-2, *Pulps — Laboratory wet disintegration — Part 2: Disintegration of mechanical pulps at 20 °C*

ISO 5263-3, *Pulps — Laboratory wet disintegration — Part 3: Disintegration of mechanical pulps at ≥ 85 °C*

ISO 7213, *Pulps — Sampling for testing*

[ISO 23714:2007](https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-b38e127ebb27/iso-23714-2007)

ISO 14487, *Pulps — Standard water for physical testing*

<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-b38e127ebb27/iso-23714-2007>

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

water retention value

ratio of the mass of water retained after centrifugation under specified conditions by a wet pulp sample to the oven-dry mass of the same pulp sample

4 Principle

A test pad consisting of pulp fibres is formed by dewatering a pulp suspension on a glass-fibre filter. The test pad is centrifuged under a specified centrifugal force for a specified time, weighed, dried and weighed again. The water retention value (WRV) is calculated from the wet mass of the centrifuged test pad and the dry mass of the test pad.

NOTE The results obtained from a rewetted pulp will not be the same as those from a corresponding never-dried pulp.

5 Reagents

5.1 **Standard water**, as specified in ISO 14487.

If any other type of water is used, this shall be reported.

6 Apparatus

6.1 **Laboratory centrifuge** with a swing-out head and buckets, made of an inert material such as steel or anodized aluminium, about 100 ml in volume and about 45 mm in inner diameter. The centrifugal force shall be $(3\,000 \pm 50)g$ (g is the acceleration due to gravity, i.e. 9.81 m/s^2) at the position of the test pad, approximately 15 mm from the bottom of the bucket. The centrifuge shall be equipped with a timer and a brake.

It is desirable that the centrifuge should maintain a working temperature of $(23 \pm 3)^\circ\text{C}$.

NOTE If g is the acceleration due to gravity, i.e. 9.81 m/s^2 , then the rotational frequency is obtained using the equation:

$$N = \left(\frac{Z \times 896}{r} \right)^{\frac{1}{2}} \quad (1)$$

where

N is the rotational frequency, in min^{-1} or r/min ;

Z is the centrifugal force, $(3\,000 \pm 50)g$;

r is the distance between the centre of rotation and the filtration plane of the glass filter (radius of gyration), in metres.

6.2 **Büchner funnel** or **similar funnel**, made of non-corrosive material, the perforated bottom of which shall be flat, and having an internal diameter larger than 30 mm.

6.3 **Wire cloth** of glass-fibre filter, e.g. Whatman grade GF/C filter or equivalent.

6.4 **Suction flask**, connected to a water suction pump or similar device for vacuum filtration applied to the Büchner funnel.

6.5 **Set of test-pad-holding units**. The holding unit is a metal tube, (30 ± 5) mm in inner diameter, with a phosphor-bronze wire-screen attached to one end. The wire-screen shall have a nominal size of aperture of $125\ \mu\text{m}$ and a preferred diameter of the wire of $90\ \mu\text{m}$. The centrifuge tube should be capped with a hole in the centre to prevent moisture loss.

The design of the holding unit depends on the design of the centrifuge and is therefore not specified in this International Standard. The unit shall fit into the centrifuge buckets in such a way that the test pad in the test-pad-holding unit will not be rewetted after centrifugation. Two examples of test-pad-holding units are described in Annex A.

The number of test-pad-holding units required depends on the design of the centrifuge. All units shall have the same mass.

6.6 **Weighing bottles with lids**, having a volume of 25 ml.

6.7 **Oven**, capable of maintaining $(105 \pm 2)^\circ\text{C}$.

7 Sampling

If the test is being carried out to evaluate a pulp lot, the sample shall be selected in accordance with ISO 7213. If the test is made on another type of sample, report the source of the sample and, if possible, the sampling procedure used.

Make sure that the test portions taken are representative of the pulp sample.

8 Preparation of sample

If the pulp sample is in dried form, disintegrate the pulp in standard water (5.1) in accordance with ISO 5263-1 or ISO 5263-2.

If a mechanical pulp has been disintegrated at a temperature higher than 85 °C, in accordance with ISO 5263-3 to remove latency effects, then before proceeding further, the diluted stock sample must be allowed to cool to (23 ± 3) °C.

If the sample has been disintegrated, the disintegration method shall be stated in the test report.

Dilute the stock in standard water (5.1) to give a concentration in the range from 2 g/l to 5 g/l. For samples that drain slowly, use the highest concentration.

It shall be stated in the test report whether the sample is rewetted or never-dried, since there could be significant differences in the results.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

9 Procedure

9.1 General

<https://standards.iteh.ai/catalog/standards/sist/6f2ad6ea-ce3c-42c3-80ec-f38e127ebb27/iso-23714-2007>

From the diluted and well-stirred stock, take samples and carry out WRV determinations at (23 ± 3) °C in duplicate. Carry out all determinations as soon as possible after sampling.

If, for practical reasons, WRV determinations are carried out a day or more after sampling, the WRV-value will be somewhat higher (normally less than 0,03 g/g) than it would have been if the determination had been carried out the same day. Any significant delay in carrying out the WRV tests shall be reported.

9.2 Forming in a Büchner funnel

Connect the Büchner funnel (6.2) to the suction flask (6.4). Put the glass-fibre filter in the funnel, moisten and then start the suction. Add to the Büchner funnel a volume of the stock, so chosen that the test pad formed will have an oven-dry grammage of $(1\ 700 \pm 100)$ g/m², when placed in the test-pad-holding unit (6.5).

For the volume of stock chosen, 100 ml of this volume should be filtered and then the suction stopped. If necessary (if the retention of fines is too low), add this initial filtrate to the remainder of the stock volume to be filtered.

Stop the suction when all the surface water has directly disappeared. The dry-matter content of the test pad should then be between 5 % and 15 %.

Remove the pad from the Büchner funnel and place it in a test-pad holder.