



SLOVENSKI STANDARD
kSIST FprEN 16345:2012

01-marec-2012

Bitumen in bitumenska veziva - Ugotavljanje viskoznosti bitumenskih emulzij z viskozimetrom po Redwoodu, št. II

Bitumen and bituminous binders - Determination of efflux time of bituminous emulsions using the Redwood No. II Viscometer

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Ausflusszeit von Bitumenemulsionen mit dem Redwood Nr. II-Viskosimeter

Bitumes et liants bitumineux - Mesure du temps d'écoulement des émulsions bitumineuses avec le Viscosimètre Redwood No. II

Ta slovenski standard je istoveten z: FprEN 16345

ICS:

75.140	Voski, bitumni in drugi naftni proizvodi	Waxes, bituminous materials and other petroleum products
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

kSIST FprEN 16345:2012

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

FINAL DRAFT
FprEN 16345

November 2011

ICS 75.140; 91.100.50

English Version

Bitumen and bituminous binders - Determination of efflux time of bituminous emulsions using the Redwood No. II Viscometer

Bitumes et liants bitumineux - Mesure du temps d'écoulement des émulsions bitumineuses avec le Viscosimètre Redwood No. II

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Ausflusszeit von Bitumenemulsionen mit dem Redwood Nr. II-Viskosimeter

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 336.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Principle.....	4
5	Reagents and materials	4
6	Apparatus	4
7	Sampling and preparation of sample.....	6
8	Procedure	6
9	Expression of results	7
10	Precision	7
11	Test report	7
Annex A (normative) Specifications of thermometer		8
Bibliography		9

Foreword

This document (FprEN 16345:2011) has been prepared by Technical Committee CEN/TC 336 "Bituminous Binders", the secretariat of which is held by AFNOR.

This document is currently submitted to the Unique Acceptance Procedure.

FprEN 16345:2011 (E)

1 Scope

This European Standard specifies a method for the determination of the efflux time (in seconds) at 85 °C using the Redwood No. II Viscometer.

WARNING – The use of this European Standard can involve hazardous materials, operations and equipment. This European Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this European Standard to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders — Sampling bituminous binders*

EN 12594, *Bitumen and bituminous binders — Preparation of test samples*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

viscosity

internal resistance of a fluid to flow

3.2

efflux time

time needed for a specified volume of a material to flow through a specified orifice at a specified temperature

NOTE The efflux time is an indirect measure of the viscosity and is also referred to as “pseudo-viscosity”.

4 Principle

The efflux time of a bituminous emulsion is determined using the Redwood No. II Viscometer which determines the time of efflux of a 50 ml sample through a 3,8 mm orifice at 85 °C.

5 Reagents and materials

5.1 **Spirit level.**


5.2 **Soft tissue paper** or other material suitable for drying the oil cup, which will not leave residue.

6 Apparatus

Usual laboratory apparatus and glassware, together with the following:

6.1 **Standard Redwood No. II Viscometer**, of the dimensions given in Figure 1, complete with ball-valve, oil cup cover, thermometer clip, stand and screen.

Dimensions in millimetres

**Key**

- 1 oil cup
- 2 stirrer body cut away between vanes
- 3 stirrer
- 4 brass tube
- 5 agate jet
- 6 bottom of heating bath
- 7 washer
- 8 minimum bore

Figure 1 — Redwood No. II Viscometer: section of cup**6.2 Thermometer**, one, conforming to the requirements described in Annex A.

Other temperature measuring devices may be used instead of mercury stem thermometers. However, the mercury stem thermometer is the reference device. Therefore any alternative device employed shall be calibrated so as to provide the same readings as would be provided by the mercury stem thermometer, recognising and allowing for the fact of changed thermal response times compared with the mercury thermometer.

6.3 Receiver, that is a Kohrausch type flask, of $(50 \pm 0,5)$ ml capacity at 20 °C or a 100 ml cylinder with graduations at 25 ml and 75 ml.

FprEN 16345:2011 (E)

6.4 Timing device / stopwatch, capable of reading to 0,2 s or less and accurate to 0,1 % over a period of not less than 15 min.

6.5 Loosely stoppered container, of at least 200 ml capacity.

6.6 Water/oil bath.

7 Sampling and preparation of sample

The material under test shall be sampled in accordance with EN 58 and prepared in accordance with EN 12594.

Place approximately 200 ml of the specimen in a suitable clean, loosely stoppered container and bring to a temperature a little over the test temperature (85 °C) by immersing in a hot water or oil bath; do not heat the specimen over a flame or by the immersion of hot bodies in it.

8 Procedure

8.1 General

Carry out the procedure in laboratory at room temperature between 18 °C and 28 °C.

8.2 Preparation of apparatus

Clean the oil cup with suitable solvents and dry thoroughly with soft tissue paper or other material which will not leave residue.

Set up the viscometer, level by using a spirit level and fill the bath with water or oil to not less than 10 mm below the rim of the oil cup at test temperature.

8.3 Measurement

Heat the viscometer bath to a few degrees above the test temperature. Homogenize the specimen by stirring and pour the prepared specimen into the oil cup. Adjust the temperature of the bath until the specimen in the cup is maintained at the test temperature of 85 °C, stirring the contents of the bath and cup during the process. Stir the specimen with the thermometer during the preliminary period. Do not stir the specimen during the actual determination.

When the temperature of the specimen has become steady at the test temperature, adjust the liquid level, if necessary, by removing any excess until the surface of the specimen touches the filling point. This should be achieved within 15 min of pouring the specimen into the oil cup in order to minimize loss of water by evaporation.

Slightly warm the oil cup cover, place it in position on the oil cup and swing the oil cup thermometer towards the closed end of the curved slot in the cover. Place the clean, dry standard 50 ml flask or 100 ml cylinder containing 25 ml of water below the jet with the neck a few millimetres from the bottom of the jet. Do not insulate the flask in any way.

Lift the ball-valve and simultaneously start the time recorder. Suspend the valve from the clip supporting the oil cup thermometer by means of the hook in the wire stem. Stop the timing device at the instant the specimen reaches the 50 ml graduation mark on the flask or the 75 ml graduation on the cylinder and note the final reading of the oil cup thermometer.

Reject any determination if the temperature of the specimen in the oil cup varies during the run by more than 0,3 °C.