
Aeronavtika - Kabli, električni, za splošne namene, eno- in večžilni - Družina XLETFE - 006. del: Posrebreni baker - Delovne temperature med -65 °C in 150 °C - Dvojno ekstrudirana izolacija za zunanjo uporabo - Možnost UV-laserskega tiskanja - Standard za izdelek

Aerospace series - Cables, electrical, for general purpose, single and multicore assembly - XLETFE Family - Part 006: Silver plated copper - Operating temperatures, between – 65 °C and 150 °C - Dual extruded wall for open applications - UV laser printable - Product standard

STANDARD PREVIEW
(standards.iteh.ai)

Luft- und Raumfahrt - Ein- und mehradrige elektrische Leitungen für allgemeine Verwendung - XLETFE Familie - Teil 006: Kupferversilbert - Betriebstemperaturen zwischen – 65 °C und 150 °C - Doppelt extrudierte Isolierung für externe Verwendung - UV-Laser bedruckbar - Produktnorm

Série aérospatiale - Câbles, électriques, d'usage général, mono et multiconducteurs - Famille XLETFE - Partie 006 : Cuivre argenté - Températures de fonctionnement comprises entre – 65 °C et 150 °C - Fil double isolé pour applications externes - Marquable au laser UV - Norme de produit

Ta slovenski standard je istoveten z: EN 4611-006:2012

ICS:

49.060	Letalska in vesoljska električna oprema in sistemi	Aerospace electric equipment and systems
--------	--	--

SIST EN 4611-006:2012

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4611-006:2012

<https://standards.iteh.ai/catalog/standards/sist/5603e17e-7a9d-49d8-83ec-ef5a4003bd00/sist-en-4611-006-2012>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 4611-006

February 2012

ICS 49.060

English Version

**Aerospace series - Cables, electrical, for general purpose,
single and multicore assembly - XLETFE Family - Part 006:
Silver plated copper - Operating temperatures, between -65 °C
and 150 °C - Dual extruded wall for open applications - UV laser
printable - Product standard**

Série aérospatiale - Câbles, électriques, d'usage général,
mono et multiconducteurs - Famille XLETFE - Partie 006:
Cuivre argenté - Températures de fonctionnement
comprises entre -65 °C et 150 °C - Fil double isolé pour
applications externes - Marquable au laser UV - Norme de
produit

Luft- und Raumfahrt - Ein- und mehradrige elektrische
Leitungen zur allgemeinen Verwendung, XLETFE-Familie -
Teil 006: Kupfer versilbert, Betriebstemperaturen zwischen
-65 °C und 150 °C, doppelt extrudierte Isolierung für offene
Anwendungen, UV-Laser bedruckbar - Produktnorm

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This European Standard was approved by CEN on 17 September 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Definitions and symbols	4
4 Materials and construction	5
4.1 Materials	5
4.2 Construction.....	5
4.3 Number of cores	6
4.4 Colour coding of cores	6
5 Required characteristics	6
6 Quality assurance	10
7 Designation	10
8 Identification and marking	10
9 Packaging, labelling and delivery lengths	10
10 Technical specification	10

ITeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4611-006:2012

<https://standards.iteh.ai/catalog/standards/sist/5603e17e-7a9d-49d8-83ec-ef5a4003bd00/sist-en-4611-006-2012>

Foreword

This document (EN 4611-006:2012) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2012, and conflicting national standards shall be withdrawn at the latest by August 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 4611-006:2012

<https://standards.iteh.ai/catalog/standards/sist/5603e17e-7a9d-49d8-83ec-ef5a4003bd00/sist-en-4611-006-2012>

EN 4611-006:2012 (E)

1 Scope

This European Standard specifies the characteristics of UV laser printable, silver plated copper conductor, electrical cables Crosslinked Ethylene Tetra Fluoro Ethylene co-polymer XLETFE family for use in the on-board electrical systems of aircraft at operating temperatures between – 65 °C and 150 °C, operating at voltages not exceeding 600 V r.m.s and frequencies not exceeding 2 000 Hz. These cables are suitable for airframe use without additional protection. In case of conflict between this European Standard and other referenced documents the requirements of this European Standard should take precedence.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies..

EN 2083, *Aerospace series – Copper or copper alloys conductors for electrical cables – Product standard*

EN 2084, *Aerospace series – Cables, electric, single-core, general purpose, with conductors in copper or copper alloy – Technical specification*

EN 2235, *Aerospace series – Single and multicore electrical cables, screened and jacketed*

EN 3475-100¹, *Aerospace series – Cables, electrical, aircraft use – Test methods – Part 100: General*

EN 4611-002, *Aerospace series – Cables, electrical, for general purpose, single and multicore assembly – XLETFE Family – Part 002: General*

EN 9133, *Aerospace series – Quality management systems – Qualification procedure for aerospace standard parts*

3 Terms, definitions, symbols and abbreviations

For the purposes of this document, the terms, definitions, symbols and abbreviations given in EN 3475-100 apply.

¹ And all its parts

4 Materials and construction

4.1 Materials

Conductor

The cable conductors shall be made of silver plated copper according to EN 4611-002 and EN 2083 code C.

Insulation for conductor all size codes

- first insulator extruded XLETFE, coloured blue or a contrasting colour if the second is blue;
- second insulator extruded XLETFE.

For single core, it shall be possible to mark the outer insulation by UV laser printing.

4.2 Construction

See EN 4611-002, Table1 and Table 2.

Table 1 – Single core cables

Code for nominal section	Nominal section mm ²	AWG ^a	Linear resistance at 20 °C	Maximum external diameter	Mass	Minimum insulation thickness
			Ω/km max.	mm	kg/km max.	mm
001 ^b	0,15	26	149,0	1,00	2,31	0,20
002 ^b	0,25	24	106,0	1,16	3,28	0,20
004	0,4	22	55,3	1,26	4,57	0,20
006	0,6	20	31,0	1,50	7,15	0,20
010	1	18	19,6	1,74	10,54	0,20
012	1,2	16	14,9	1,87	13,48	0,20
020	2	14	10,2	2,44	20,63	0,20
030	3	12	6,4	2,95	31,51	0,20
050	5	10	4,0	3,61	48,80	0,20
090	9	8	1,37	5,16	92,12	0,20
140	14	6	0,87	6,38	140,63	0,20
220	22	4	0,56	8,13	235,13	0,20
340	34	3	0,46	10,67	370,55	0,20
530	53	1	0,28	13,36	601,22	0,20
680	68	0	0,22	14,88	744,08	0,20

^a AWG = Closest American Wire Gauge.

^b Silver plated copper alloy conductor

EN 4611-006:2012 (E)

Table 2 – Multicore without screen or jacket

Size	AWG ^a	2 core			3 core			4 core		
		Max. dia. mm	Mass max. kg/km	DC Res. Ω /km max.	Max. dia. mm	Mass max. kg/km	DC Res. Ω /km max.	Max. dia. mm	Mass max. kg/km	DC Res. Ω /km max.
001 ^b	26	2,00	4,69	153,5	2,16	7,04	153,5	2,42	9,39	153,5
002 ^b	24	2,32	6,65	109,2	2,51	9,97	109,2	2,81	13,30	109,2
004	22	2,52	9,23	60,0	2,72	13,85	60,0	3,05	18,47	60,0
006	20	3,00	14,49	31,9	3,24	21,74	31,9	3,63	28,98	31,9
010	18	3,48	21,29	20,2	3,76	31,93	20,2	4,21	42,57	20,2
012	16	3,74	27,37	15,3	4,41	41,05	15,3	4,53	54,74	15,3
020	14	4,88	41,67	10,5	5,27	62,51	10,5	5,90	83,34	10,5
030	12	5,90	63,64	6,6	6,37	95,46	6,6	7,14	127,29	6,6
050	10	7,22	98,57	4,1	7,80	147,86	4,1	8,74	197,14	4,1

^a AWG = Closest American Wire Gauge.

^b Silver plated copper alloy conductor

iTeh STANDARD PREVIEW

(standards.iteh.ai)

4.3 Number of cores

See EN 4611-002.

See EN 2235 for cabling. <https://standards.iteh.ai/catalog/standards/sist/5603e17e-7a9d-49d8-83ec-ef5a4003bd00/sist-en-4611-006-2012>

4.4 Colour coding of cores

See EN 4611-002.

5 Required characteristics

According to EN 2084 and EN 3475-100

See Table 3.

NOTE Tests EN 3475-302 to EN 3475-706 should be performed on the single core cables.

Table 3

EN 3475-	Test	Details
201	Visual examination	Applicable
202	Mass	Applicable; see Table 1 and Table 2.
203	Dimensions	Applicable; see Table 1 and Table 2.
301	Ohmic resistance per unit length	Applicable; see Table 1 and Table 2.
302	Voltage proof test	Applicable
303	Insulation resistance	Applicable (20 ± 2) °C, 500 MΩ.km minimum (95 ± 2) °C, 1 MΩ.km minimum
304	Surface resistance	Applicable 12 500 MΩ.mm minimum
305	Overload resistance	Applicable $T_1 = (250 \pm 5) ^\circ\text{C}$; $T_2 = (380 \pm 5) ^\circ\text{C}$
401	Accelerated ageing	Applicable Temperature (200 ± 3) °C
402	Shrinkage and delamination	Applicable Temperature (150 ± 5) °C Maximum shrinkage at each end of cable: 0,80 mm on size code 001 to 006 1,00 mm on size code 010 to 012 1,20 mm on size code 020 to 050
403	Delamination and blocking	Applicable Temperature (150 ± 5) °C
404	Thermal shock	Applicable Temperatures (– 65 ± 2) °C and (260 ± 5) °C Maximum shrinkage at each end of cable: 1,00 mm on size code 001 to 050
405	Bending at ambient temperature	Applicable
406	Cold bend test	Applicable Temperature (– 65 ± 2) °C
407	Flammability	Applicable Methods 1 and 2 Flame application 15 s Extinguishing time: 3 s max.
408	Fire resistance	Not applicable
409	Air-excluded ageing	Not applicable
410	Thermal endurance	Applicable 50 000 hours Temperature 150 °C
411	Resistance to fluids	Applicable
412	Humidity resistance	Applicable Method B Temperature (90 ± 2) °C Duration 672 hours
413	Wrap back test	Not applicable
414	Differential scanning calorimeter (DSC test)	Not applicable

(continued)