

---

---

**Rubber hoses and hose assemblies —  
Wire-braid-reinforced compact types for  
hydraulic applications — Specification —**

Part 1:

**Oil-based fluid applications**

iTeh STANDARD PREVIEW

(standards.iteh.ai)  
*Tuyaux et flexibles en caoutchouc — Types hydrauliques compacts  
avec armature de fils métalliques — Spécifications —*

*Partie 1: Applications pour fluides à base d'huile*

ISO 11237-1:2004

<https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-15f412dc9186/iso-11237-1-2004>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 11237-1:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-15f412dc9186/iso-11237-1-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Classification</b> .....	<b>2</b>
<b>4 Materials and construction</b> .....	<b>2</b>
4.1 Hoses.....	2
4.2 Hose assemblies .....	2
<b>5 Dimensions</b> .....	<b>2</b>
<b>6 Hose requirements</b> .....	<b>3</b>
6.1 Hydrostatic requirements.....	3
6.2 Minimum bend radius .....	3
6.3 Resistance to impulse .....	4
6.4 Leakage of hose assemblies .....	4
6.5 Cold flexibility.....	4
6.6 Adhesion between components.....	4
6.7 Vacuum resistance.....	5
6.8 Abrasion resistance.....	5
6.9 Fluid resistance.....	5
6.10 Ozone resistance .....	6
<b>7 Designation</b> .....	<b>6</b>
8 <b>Marking</b> .....	<b>6</b>
8.1 Hoses.....	6
8.2 Hose assemblies .....	6
<b>Annex A (informative) Recommendations for lengths of supplied hoses and hose assemblies</b> .....	<b>7</b>
<b>Bibliography</b> .....	<b>8</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11237-1 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Hoses (rubber and plastics)*.

ISO 11237 consists of the following parts, under the general title *Rubber hoses and hose assemblies — Wire-braid-reinforced compact types for hydraulic applications — Specification:*

— *Part 1: Oil-based fluid applications*

[ISO 11237-1:2004](https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-15f412dc9186/iso-11237-1-2004)

— *Part 2 : Water-based fluid applications*

<https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-15f412dc9186/iso-11237-1-2004>

# Rubber hoses and hose assemblies — Wire-braid-reinforced compact types for hydraulic applications — Specification —

## Part 1: Oil-based fluid applications

### 1 Scope

This part of ISO 11237 specifies requirements for three types of wire-braid-reinforced compact hose and hose assembly of nominal bore from 6,3 to 31,5. They are suitable for use with hydraulic fluids HH, HL, HM, HR and HV in accordance with ISO 6743-4 at temperatures ranging from –40 °C to +100 °C.

This part of ISO 11237 does not include requirements for end fittings. It is limited to the performance of hoses and hose assemblies.

NOTE It is the responsibility of the user, in consultation with the hose manufacturer, to establish compatibility of the hose with the fluid to be used.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

### 2 Normative references

ISO 11237-1:2004

[https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-](https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-15f112dc9186/iso-11237-1-2004)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 1817, *Rubber, vulcanized — Determination of the effect of liquids*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of dimensions*

ISO 4672:1997, *Rubber and plastics hoses — Sub-ambient temperature flexibility tests*

ISO 6803, *Rubber or plastics hoses and hose assemblies — Hydraulic pressure impulse test without flexing*

ISO 6945, *Rubber hoses — Determination of abrasion resistance of the outer cover*

ISO 7233, *Rubber and plastics hoses and hose assemblies — Determination of suction resistance*

ISO 7326:1991, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions*

ISO 8033:1991, *Rubber and plastics hose — Determination of adhesion between components*

### 3 Classification

Three types of hose are specified, distinguished by their construction, working pressure, minimum bend radius and oil resistance:

- a) Type 1SC, hoses with a single braid of wire reinforcement;
- b) Type 2SC, hoses with two braids of wire reinforcement;
- c) Type R16, hoses with one or two braids of wire reinforcement;
- d) Type R17, 210 bar constant-pressure hoses with one or two braids of wire reinforcement.

NOTE Type R16 and R17 are not subjected to the vacuum resistance or abrasion resistance tests.

### 4 Materials and construction

#### 4.1 Hoses

Hoses shall consist of a hydraulic fluid resistant rubber lining, one or two layers of high tensile steel wire and an oil and weather resistant rubber cover.

#### 4.2 Hose assemblies

Hose assemblies shall only be manufactured with those hose fittings whose functionality conforms to the requirements of 6.1, 6.3 and 6.4 of this part of ISO 11237.

The manufacturer's instructions for proper preparation and fabrication of hose assemblies shall be followed.

iTech STANDARD PREVIEW  
(standards.iteh.ai)  
ISO 11237-1:2004  
<https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-15f412dc9186/iso-11237-1-2004>

### 5 Dimensions

When measured in accordance with ISO 4671, the dimensions of the hoses shall conform to the values given in Table 1.

Table 1 — Dimensions of hoses

Nominal bore	All types		Type 1SC			Type 2SC			Type R16		Type R17	
	Inside diameter		Diameter over reinforcement		Outside diameter of hose	Diameter over reinforcement		Outside diameter of hose	Diameter over reinforcement		Outside diameter of hose	
	mm		mm		mm	mm		mm	mm		mm	
	min.	max.	min.	max.	max.	min.	max.	max.	max.	max.	max.	max.
6,3	6,1	6,9	9,6	10,8	13,5	10,6	11,7	14,2	12,3	14,5	11,0	13,2
8	7,7	8,5	10,9	12,1	14,5	12,1	13,3	16,0	13,3	15,8	13,0	15,0
10	9,3	10,1	12,7	14,5	16,9	14,4	15,6	18,3	15,9	18,8	15,0	17,0
12,5	12,3	13,5	15,9	18,1	20,4	17,5	19,1	21,5	19,1	22,0	18,8	21,1
16	15,5	16,7	19,8	21,0	23,0	20,5	22,3	24,7	22,5	25,4	23,6	25,9
19	18,6	19,8	23,2	24,4	26,7	24,6	26,4	28,6	26,3	29,0	27,7	30,3
25	25,0	26,4	30,7	31,9	34,9	32,5	34,3	36,6	34,0	36,6	35,6	38,6
31,5	31,4	33,0	37,8	39,0	42,2	39,3	41,7	44,3	41,9	44,3	—	—

NOTE Inside diameters are in accordance with ISO 4397.

When measured in accordance with ISO 4671, the concentricity of the hoses shall conform to the values given in Table 2.

Table 2 — Concentricity of hoses

Nominal bore	Maximum variation in wall thickness	
	Between internal diameter and outside diameter mm	Between internal diameter and reinforcement diameter mm
6,3	0,8	0,5
over 6,3 and including 19	1,0	0,6
over 19	1,3	0,8

## 6 Hose requirements

### 6.1 Hydrostatic requirements

6.1.1 When determined in accordance with ISO 1402, the maximum working pressure, the proof pressure and minimum burst pressure of the hoses and hose assemblies shall conform to the values given in Table 3.

Table 3 — Maximum working pressure, proof pressure and minimum burst pressure

Nominal bore	Maximum working pressure bar <sup>a</sup>				Proof pressure bar				Minimum burst pressure bar			
	Type				Type				Type			
	1SC	2SC	R16	R17	1SC	2SC	R16	R17	1SC	2SC	R16	R17
6,3	225	400	350	210	450	800	700	420	900	1 600	1 400	840
8	215	350	298	210	430	700	595	420	860	1 400	1 190	840
10	180	330	280	210	360	660	560	420	720	1 320	1 120	840
12,5	160	275	245	210	320	550	490	420	640	1 100	980	840
16	130	250	192	210	260	500	385	420	520	1 000	770	840
19	105	215	158	210	210	430	315	420	420	860	630	840
25	88	165	140	210	176	330	280	420	352	660	560	840
31,5	63	125	110	—	125	250	228	—	250	500	455	—

<sup>a</sup> 1 bar = 0,1 MPa

6.1.2 When determined in accordance with ISO 1402, the change in length of hoses at their maximum working pressure shall not exceed +2 % or –4 %.

### 6.2 Minimum bend radius

Use test pieces having a length at least four times the minimum bend radius. Measure the hose outside diameter with callipers in the straight lay position before bending the hose. Bend the hose through 180° to the minimum bend radius and measure the flatness with the callipers.

When bent to the minimum bend radius given in Table 4, measured on the inside of the bend, the flatness shall not exceed 10 % of the original outside diameter.

**Table 4 — Minimum bend radius**

Nominal bore	Minimum bend radius mm			
	mm			
	Type 1SC	Type 2SC	Type R16	Type R17
6,3	75	75	50	50
8	85	85	55	55
10	90	90	65	65
12,5	130	130	90	90
16	150	170	100	100
19	180	200	120	120
25	230	250	150	150
31,5	250	280	210	—

**6.3 Resistance to impulse**

**6.3.1** The impulse test shall be in accordance with ISO 6803. The test fluid temperature shall be 100 °C.

**6.3.2** For type 1SC hoses, when tested at an impulse pressure equal to 125 % of the maximum working pressure, the hose shall withstand a minimum of 150 000 impulse cycles.

For type 2SC, R16 and R17 hoses, when tested at an impulse pressure equal to 133 % of the maximum working pressure, the hose shall withstand a minimum of 200 000 impulse cycles.

**6.3.3** There shall be no leakage or other malfunction before reaching the specified number of cycles.

**6.3.4** This test shall be considered a destructive test and the test piece shall be destroyed after the test.

**6.4 Leakage of hose assemblies**

When tested in accordance with ISO 1402, there shall be no leakage or evidence of failure. This test shall be considered a destructive test and the test piece shall be destroyed after the test.

**6.5 Cold flexibility**

When tested in accordance with method B of ISO 4672:1997 at a temperature of -40 °C, there shall be no cracking of the lining or cover. The test piece shall not leak or crack when subjected to a proof-pressure test in accordance with ISO 1402 after regaining ambient temperature.

**6.6 Adhesion between components**

When determined in accordance with ISO 8033, the adhesion between lining and reinforcement, and between cover and reinforcement, shall not be less than 2,5 kN/m for type 1SC and 2SC hoses, and not less than 1,8 kN/m for type R16 and R17 hoses.

Test pieces shall be type 5 for lining and reinforcement and type 2 or type 6 for cover and reinforcement as described in Table 1 of ISO 8033:1991.



## 6.7 Vacuum resistance

When tested in accordance with ISO 7233, hoses and hose assemblies shall conform to the values given in Table 5.

Table 5 — Degree of vacuum

Nominal bore	Negative gauge pressure kPa <sup>a</sup> max.	
	Type 1SC	Type 2SC
6,3	-80,0	-95,0
8		
10		
12,5		
16		
19	—	
25		
31,5		

<sup>a</sup> 1 kPa = 0,01 bar

NOTE Type R16 and R17 are not subjected to this test.

## 6.8 Abrasion resistance

ISO 11237-1:2004

<https://standards.iteh.ai/catalog/standards/sist/a36398a0-8ccd-422b-bebd-15f112dc9186/iso-11237-1-2004>

When determined in accordance with ISO 6945, with a vertical force of  $(25 \pm 0,5)$  N, the loss in mass after 2 000 cycles shall not be greater than 0,5 g.

NOTE Type R16 and R17 are not subjected to this test.

## 6.9 Fluid resistance

### 6.9.1 Test pieces

The fluid resistance tests shall be carried out on moulded sheets of lining and cover compound of cure state equivalent to that of the hose and having a minimum thickness of 2 mm.

### 6.9.2 Oil resistance

For type 1SC and 2SC, when determined in accordance with ISO 1817, by immersion in IRM 903 oil for 168 h at a temperature of 100 °C, the percentage change in volume of the lining  $\Delta V_{100}$  shall be between 0 and +25 %.

For type R16 and R17, when determined in accordance with ISO 1817, by immersion in IRM 903 oil for 72 h at a temperature of 100 °C, the percentage change in volume of the lining  $\Delta V_{100}$  shall be between 0 and +100 %.

For types 1SC and 2SC, when determined in accordance with ISO 1817, by immersion in IRM 903 oil for 168 h at a temperature of 70 °C, the percentage change in volume of the cover  $\Delta V_{100}$  shall be between 0 and +100 %.