
**Metallic coatings — Electrodeposited
coatings of chromium for engineering
purposes**

*Revêtements métalliques — Dépôts électrolytiques de chrome pour
usages industriels*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 6158:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/e5783b50-fc35-475c-a716-13c98be00240/iso-6158-2004>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 6158:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/e5783b50-fe35-475c-a716-13c98be00240/iso-6158-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Information to be supplied to the electroplater	2
5 Designation	3
6 Requirements	5
7 Sampling	8
Annex A (informative) Typical thickness of chromium specified in engineering applications	9
Annex B (informative) Thickness test methods for electroplated chromium and other metallic coatings	10
Annex C (normative) Determination of cracks and pores in chromium coatings	11
Bibliography	12

ITIH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 6158:2004](https://standards.iteh.ai/catalog/standards/sist/e5783b50-fe35-475c-a716-13c98be00240/iso-6158-2004)

<https://standards.iteh.ai/catalog/standards/sist/e5783b50-fe35-475c-a716-13c98be00240/iso-6158-2004>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 6158 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 3, *Electrodeposited coatings and related finishes*.

This second edition cancels and replaces the first edition (ISO 6158:1984), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
ISO 6158:2004
<https://standards.iteh.ai/catalog/standards/sist/e5783b50-fe35-475c-a716-13c98be00240/iso-6158-2004>

Introduction

Electrodeposited chromium coatings are frequently deposited from hexavalent chromium solutions similar to those used for decorative electroplating. Engineering chromium coatings, however, are generally thicker than decorative ones. Regular or conventional chromium is the type most frequently specified, but porous, cracked or specially profiled surfaces and duplex chromium are also applied to achieve oil-retaining or non-sticking surfaces, or to improve corrosion resistance.

Electrodeposited chromium coatings for engineering applications are most often applied directly to the basis metal to increase wear and abrasion resistance, to increase fretting resistance, to reduce static and kinetic friction, to reduce galling and seizing, to increase corrosion resistance, and to build up undersize or worn parts. For protection against severe corrosion, nickel and other metallic undercoats may be applied prior to the electrodeposition of chromium, or the corrosion resistance of the chromium coating may be increased by alloying, e.g., with molybdenum.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 6158:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/e5783b50-fc35-475c-a716-13c98be00240/iso-6158-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 6158:2004

<https://standards.iteh.ai/catalog/standards/sist/e5783b50-f35-475c-a716-13c98be00240/iso-6158-2004>

Metallic coatings — Electrodeposited coatings of chromium for engineering purposes

1 Scope

This International Standard specifies requirements for electroplated coatings of chromium, with or without undercoats, on ferrous and non-ferrous metals for engineering purposes. The coating designation provides a means of specifying the thickness of chromium appropriate for typical engineering applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2064, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*

ISO 2079, *Surface treatment and metallic coatings — General classification of terms*

ISO 2080, *Electroplating and related processes — Vocabulary*

ISO 2177, *Metallic coatings — Measurement of coating thickness — Coulometric measurement by anodic dissolution*

ISO 2178, *Non-magnetic coatings on magnetic substrates — Measurement of coating thickness — Magnetic method*

ISO 2819, *Metallic coatings on metallic substrates — Electrodeposited and chemically deposited coatings — Review of methods available for testing adhesion*

ISO 3543, *Metallic and non-metallic coatings — Measurement of thickness — Beta backscatter method*

ISO 3882, *Metallic and other inorganic coatings — Review of methods of measurement of thickness*

ISO 4516, *Metallic and other inorganic coatings — Vickers and Knoop microhardness tests*

ISO 4519, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*

ISO 4526, *Metallic coatings — Electroplated coatings of nickel for engineering purposes*

ISO 9220, *Metallic coatings — Measurement of coating thickness — Scanning electron microscope method*

ISO 9587, *Metallic and other inorganic coatings — Pretreatments of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 6158:2004(E)

ISO 9588, *Metallic and other inorganic coatings — Post-coating treatments of iron or steel to reduce the risk of hydrogen embrittlement*

ISO 10309, *Metallic coatings — Porosity tests — Ferroxy test*

ISO 10587, *Metallic and other inorganic coatings — Test for residual embrittlement in both metallic-coated and uncoated externally-threaded articles and rods — Inclined wedge method*

ISO 12686, *Metallic and other inorganic coatings — Automated controlled shot-peening of metallic articles prior to nickel, autocatalytic nickel or chromium plating, or as a final finish*

ISO 15724, *Metallic and other inorganic coatings — Electrochemical measurement of diffusible hydrogen in steels — Barnacle electrode method*

EN 12508, *Corrosion protection of metals and alloys — Surface treatment, metallic and other inorganic coatings — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2064, ISO 2079, ISO 2080 and EN 12508 apply.

4 Information to be supplied to the electroplater

4.1 Essential information

When ordering articles to be electroplated in accordance with this International Standard, the purchaser shall provide the following information in writing, e.g., in the contract or purchase order, or on engineering drawings.

- a) The designation (see Clause 5).
- b) The requirements for special test specimens (see 6.1).
- c) The significant surface, indicated by drawings of the articles or by suitably marked samples (see 6.2).
- d) The appearance and surface finish of the chromium coating, e.g., as-plated, ground or machined (see 6.2 and 6.3). Alternatively, samples showing the appearance and required finish shall be supplied or approved by the purchaser, and used for comparison purposes (see 6.2).
- e) The type, size and number of defects that can be tolerated (see 6.2).
- f) Additional portions of the surface where minimum thickness requirements apply (see 6.4).
- g) The test method to be used to measure thickness (see 6.4).
- h) The adhesion and porosity requirements, and test methods (see 6.6 and 6.7, respectively).
- i) The tensile strength of parts and the requirement for stress-relief heat treatment before electroplating (see 6.8).
- j) Requirements for any embrittlement relief heat treatment after electroplating, and for hydrogen embrittlement testing (see 6.9).
- k) The sampling plan and acceptance levels (see Clause 7).

4.2 Additional information

The following additional information may be provided, when appropriate:

- a) the nominal composition or specification, and metallurgical condition of the basis metal including hardness (see 5.3);

NOTE In the case of reclaimed articles, it may not be possible to supply this information, and it may, therefore, be difficult to guarantee the quality of the coating.

- b) any special requirements for, or restrictions on, pre-treatment, e.g., vapour blasting instead of acid pre-treatment;
- c) where applicable, any special requirements for adhesion (see 6.6);
- d) the necessity for any treatment to induce compressive stress, e.g.; peening before or after electroplating (see 6.10);
- e) requirements for undercoats (see 5.5 and 6.11) and stripping (see 6.12).

5 Designation

5.1 General

The designation shall appear on engineering drawings, in the purchase order, the contract or in the detailed product specification.

The designation specifies, **in the order given**, the basis metal, the specific alloy (optional), stress relief requirements, the type and thickness of undercoats, the type and thickness of the electroplated chromium coating, and post-treatments such as heat treatment to reduce susceptibility to hydrogen embrittlement.

5.2 Components

The designation shall comprise the following:

- a) the term, "Electrodeposited coating";
- b) the number of this International Standard, i.e. ISO 6158;
- c) a hyphen;
- d) the chemical symbol of the basis metal (see 5.3);
- e) a solidus (/);
- f) symbols for the chromium coating, as well as coatings applied prior to chromium electroplating, separated by solidi for each stage in the coating sequence in the order of application. The coating designation shall include the thicknesses of the coatings in micrometres, as well as heat treatment requirements (see 5.4). Double solidi or separators (//) shall be used to indicate that a step has been omitted or is not a requirement.

NOTE It is recommended that the specific alloy be identified by its standard designation following the chemical symbol of the basis metal; e.g., its UNS number, or the national or regional equivalent may be placed between the symbols < >.

EXAMPLE Fe<G43400> is the UNS designation for a high-strength steel.

See [1] to [7].

5.3 Designating the basis metal

The basis metal shall be designated by its chemical symbol or, if an alloy, its principal constituent.

For example:

- a) Fe for iron and steel;
- b) Zn for zinc alloys;
- c) Cu for copper and copper alloys;
- d) Al for aluminium and aluminium alloys.

NOTE To ensure proper surface preparation and hence adherence of the coating to the substrate, it is important to identify the specific alloy and its metallurgical condition (tempered, nitrided, etc.).

5.4 Designation of heat treatment requirements

The heat treatment requirements shall be in brackets and designated as follows:

- a) the letters SR, for heat treatment for stress relief purposes; the letters ER, for heat treatment for the purpose of reducing susceptibility to hydrogen embrittlement; the letters, HT, for heat treatment for other purposes;
- b) in parenthesis, the minimum temperature, in degrees centigrade;
- c) the duration of the heat treatment, in hours.

EXAMPLE [SR(210)1] designates stress relief heat treatment at 210 °C for 1 h.

When heat treatment is specified, the requirements shall be included in the designation (see 5.6).

5.5 Type and thickness of metal layers

The electrodeposited chromium coating shall be designated by the symbols given in Table 1 placed after a number giving the specified minimum local thickness of the coating in micrometres. Annex A provides information on typical thickness of chromium specified in engineering applications.

EXAMPLE Cr50hr designates a regular hard chromium coating that is 50 µm thick.

Table 1 — Symbols for different types of chromium

Type of chromium	Symbol
Regular hard chromium	hr
Hard chromium from mixed acid solutions	hm
Microcracked hard chromium	hc
Microporous hard chromium	hp
Duplex chromium	hd
Special types of chromium	hs

Nickel undercoats shall be designated in accordance with ISO 4526, i.e., the symbol, sf for sulfur-free nickel coatings, sc for sulfur-containing nickel coatings, or the symbol pd, for sulfur-free nickel coatings containing submicron particles dispersed throughout the nickel matrix shall be used to designate the type of nickel undercoat by placing the appropriate symbol after the number giving the specified minimum local thickness of the coating in micrometres.

EXAMPLE Ni10sf designates an electrodeposited nickel undercoat 10 µm thick prepared from a solution that does not introduce sulfur into the deposit.

5.6 Examples of designations

An electrodeposited coating of regular hard chromium 50 µm thick (Cr50hr) deposited on mild steel (Fe) is designated as follows:

Electrodeposited coating ISO 6158 – Fe//Cr50hr

An electrodeposited coating of porous, electrodeposited chromium that is 250 µm thick (Cr250hp) on an aluminium alloy (Al) is designated as follows:

Electrodeposited coating ISO 6158 – Al//Cr250hp

An electrodeposited coating of regular hard chromium 50 µm thick (Cr50hr) deposited on steel (Fe) over an undercoat of sulfur-free nickel 10 µm thick (Ni10sf) is designated as follows:

Electrodeposited coating ISO 6158 – Fe//Ni10sf/Cr50hr

An electrodeposited coating of regular hard chromium 50 µm thick (Cr50hr) deposited on steel that is stress relieved prior to electroplating at 210 °C for 2 h and heat-treated after electroplating for embrittlement relief purposes at 210 °C for 22 h is designated as follows:

Electrodeposited coating ISO 6158 – Fe/[SR(210)2]/Cr50hr/[ER(210)22]

For ordering purposes, the detailed product specification shall not only comprise the designation, but shall also include clear written statements of other requirements that are essential for the serviceability of a particular product (see Clause 4).

6 Requirements

6.1 Special test specimens

Special test specimens are often used to measure adhesion, thickness, porosity, corrosion, hardness, and other properties when the coated articles are not suitable for the test, or if it is not practical to submit the coated articles to destructive tests because the parts are few in number or too expensive. Special test specimens shall be of the same material, shall be in the same metallurgical condition, and shall have the same surface condition as the coated articles, and shall be processed along with the coated articles that they represent.

The use of special or representative test specimens to determine that the requirements of this International Standard have been met, the number of test specimens to be used, the material from which they shall be made, and their shape and size shall be specified by the purchaser [see 4.1 b)].

6.2 Appearance

The chromium coating on the significant surface shall be bright or lustrous and, when visually inspected shall be free from pits, blisters, exfoliation and other defects detrimental to the final finish. Nodular growths elsewhere than at the extreme edges of coatings are not permitted on articles used in the as-plated condition, or on the surface of ground articles. Imperfections and variations that arise from surface conditions of the