
**Graphic technology — Prints and printing
inks — Assessment of resistance to
various agents**

*Technologie graphique — Impressions et encres d'imprimerie —
Évaluation de la résistance des impressions à divers agents*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2836:2004](https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004)

[https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-
b831d8261e46/iso-2836-2004](https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2836:2004

<https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
4.1 Liquid and solid agents	2
4.2 Solvents and varnishes	2
4.3 Acids.....	2
5 Agents	2
5.1 General	2
5.2 Water	2
5.3 Alkali.....	2
5.4 Oils and fats.....	2
5.5 Cheese.....	3
5.6 Detergents.....	3
5.7 Soaps.....	3
5.8 Waxes	3
5.9 Spices.....	3
5.10 Solvents and varnishes	3
5.11 Acids.....	3
5.12 Other agents	4
6 Apparatus and reagents	4
6.1 Equipment and apparatus	4
6.2 Solvents and varnishes	5
7 Preparation of test pieces	5
8 Test methods	5
8.1 Liquid agents	5
8.2 Solid agents	5
8.3 Meltable solid agents (waxes)	6
8.4 Solid spices	6
8.5 Solvents and varnishes	6
8.6 Acids.....	6
9 Evaluation of results	7
9.1 Liquid and solid agents	7
9.2 Solvents and varnishes	7
9.3 Acids.....	7
10 Test report.....	8
11 Test conditions.....	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2836 was prepared by Technical Committee ISO/TC 130, *Graphic technology*.

This third edition cancels and replaces the second edition (ISO 2836:1999). It also incorporated the requirements of, and cancels, ISO 2837:1996 *Graphic technology — Prints and printing inks — Assessment of resistance to solvents* and ISO 11628:1995 *Graphic technology — Prints and printing inks — Determination of resistance of prints to acids*.

[ISO 2836:2004](https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004)

<https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004>

Graphic technology — Prints and printing inks — Assessment of resistance to various agents

1 Scope

This International Standard specifies methods of assessing the resistance of printed materials to liquid and solid agents, solvents, varnishes, and acids.

It applies to printing on all substrates by all of the traditional printing processes and digital imaging processes such as ink-jet, electrophotography, etc. using marking materials appropriate to the printing process used.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2834:1999, *Graphic technology — Test print preparation for offset and letterpress inks*

ISO 105-A03:1993, *Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining*

<https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004>

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

agent

liquid or solid to which a sample of printed material is exposed for the purpose of determining the resistance characteristics of that printed sample

3.2

resistance

ability of a printed material to withstand exposure to a specified agent as determined by the tests defined in this International Standard

4 Principle

4.1 Liquid and solid agents

A test piece cut from the print is brought into contact with the agent used. Assessment is made of any changes in the print and in the receptor surface which has been in contact with the print.

4.2 Solvents and varnishes

A test piece cut from the print is immersed in the prescribed solvent or test varnish for a given time. The colour change of the solvent or varnish and the discoloration and any change of the test piece are noted and reported.

4.3 Acids

A test piece cut from the print is pressed between two sheets of filter paper previously wetted with a solution of the relevant acid. An assessment is made of any change to the print and any bleeding of the colour onto the filter paper.

NOTE 1 The type and concentration of the acid and the duration of exposure are not standardized, but should be chosen according to the intended application of the print. Table 1 gives a list of commonly used types, concentrations and exposure durations.

NOTE 2 The test piece includes both printing ink and substrate, because resistance may be affected by ink, substrate or the interaction between them.

Test samples may be taken from existing printed material, or may be prepared to be representative of a planned printed product.

ISO 2836:2004
<https://standards.itech.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004>

5 Agents

5.1 General

The type of agent used and its concentration shall be reported.

5.2 Water

This International Standard does not specify the type of water used for the assessment of resistance of prints. It may be tap water, distilled water, deionized water, natural water, carbonated water, sea water, etc.

5.3 Alkali

This International Standard specifies a 1 % by mass solution of sodium hydroxide in distilled water used for the assessment of resistance of prints.

5.4 Oils and fats

This International Standard does not specify the oil or the fat to be used for the assessment of resistance of prints. It may be animal, vegetable, mineral, essential or synthetic, e.g. fish oil, olive oil, liquid paraffin, lavender oil, silicone oil, butter, margarine, lanolin, grease.

5.5 Cheese

This International Standard does not specify the type of cheese, e.g. soft cheese or hard cheese, used for the assessment of resistance of prints. However, the cheese shall be used as a solid agent in a natural state, i.e. not liquefied.

5.6 Detergents

This International Standard does not specify the type of detergent, e.g. liquid or solid, used for the assessment of resistance of prints, only its concentration: 1 % by mass.

5.7 Soaps

This International Standard does not specify the type of soap, hard or soft, used for the assessment of resistance of prints, only its concentration: 1 % by mass.

5.8 Waxes

This International Standard does not specify the type of wax to be used for the assessment of resistance of prints, i.e. animal, vegetable, mineral or synthetic, e.g. beeswax, carnauba wax, paraffin wax, Fischer Tropsch wax.

5.9 Spices

This International Standard does not specify the spice to be used for the assessment of resistance of prints.

5.10 Solvents and varnishes

This International Standard specifies solvents and varnishes, e.g. denatured ethanol, a mixture of ethanol, ethyl acetate and 1-methoxy-propanol-2, or any other solvent or varnish for assessing the resistance of prints.

5.11 Acids

This International Standard does not specify any particular acid or concentration, but does give examples of acids that are commonly found in commerce and in the home which can be used for the assessment of resistance of prints. The acid and concentration should be chosen according to the intended application of the print. The following acids are mentioned in this International Standard:

- lactic acid to simulate cheese and cheese products;
- citric acid to simulate the juice of citrus fruits;
- acetic acid to simulate pickles and vinegars;
- hydrochloric acid to simulate products with pH values < 2;
- sulfuric acid.

5.12 Other agents

The test methods set out in this International Standard may be used in the assessment of the resistance of prints to other agents such as the following:

- hydraulic fluids;
- perfumes, deodorants;
- beverages: coffee, tea, beer, spirits;
- cosmetics: lipstick; skin cream.

6 Apparatus and reagents

This clause lists supplies and equipment necessary to perform resistance tests.

6.1 Equipment and apparatus

6.1.1 Glass plates, 2, 60 mm × 90 mm × 2 mm.

6.1.2 Laboratory filter paper, for qualitative chemical analysis, white, neutral, with a very smooth and soft surface, cut into strips 60 mm × 90 mm.

6.1.3 Petri dish, ≥100 mm in diameter.

6.1.4 Test tubes, 2, of colourless glass, with inside diameter of approximately 16 mm and a height of approximately 160 mm.

6.1.5 Mass, 1 kg.

6.1.6 Time-piece.

6.1.7 Thermometer, capable of measuring from 20 °C to 30 °C.

6.1.8 Oven, capable of heating to 40 °C.

6.1.9 Oven, capable of maintaining a temperature of (50 ± 2) °C.

6.1.10 Hot plate, capable of heating to 40 °C above melting point of the wax.

6.1.11 Depth gauge, rule, etc.

6.1.12 Surface, white, illuminated.

6.1.13 Grey scale for colour evaluation (see ISO 105-A03).

6.1.14 pH measuring device, e.g. test strip or meter.

ISO STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2836:2004](https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004)

<https://standards.iteh.ai/catalog/standards/sist/568bebed-66b5-40f7-b11a-b831d8261e46/iso-2836-2004>

6.2 Solvents and varnishes

6.2.1 Water, deionized.

6.2.2 Ethanol, denatured.

6.2.3 Denatured ethanol — ethyl acetate — 1-methoxy-propanol-2 mixture, 60 % by volume; 30 % by volume; 10 % by volume.

6.2.4 Solvent, any provided that it is identified in the test report.

6.2.5 Acid, for test.

6.2.6 Varnish, for test.

7 Preparation of test pieces

Prepare production prints or test prints using any suitable method that allows a uniform distribution of ink to be formed on a specified substrate and dried in an appropriate manner, e.g. prepared in accordance with ISO 2834.

8 Test methods

8.1 Liquid agents

Test conditions for various liquid agents are summarized in Table 2.

Immerse the four strips of filter paper (6.1.2) to be used for the test totally in the liquid agent being tested and then drain them until no free agent drips from the filter paper.

Place two saturated strips of filter paper on the lower glass plate (6.1.1).

Place the 20 mm × 50 mm test piece being evaluated on the filter paper and cover it with the other two strips of saturated filter paper.

Cover with the other glass plate and place a 1 kg mass on top. Leave the package for the test duration specified in Table 2.

Rinse the test pieces being tested for alkali, detergent or soap resistance with deionized water until the rinse water has a neutral pH and dry test pieces (except those for oil resistance) in an oven for 30 min at a temperature of about 40 °C.

8.2 Solid agents

Test conditions for various solid agents are summarized in Table 2.

Place a 20 mm × 50 mm test piece with its printed side in contact with the freshly prepared smooth surface of the agent being tested.

Exert sufficient pressure on the test piece to ensure optimum contact with the solid agent.

Store this package for the test duration under the conditions specified in Table 2.

Carefully remove the test piece and, if required, allow to dry naturally.