

INTERNATIONAL STANDARD

**ISO
9125**

First edition
1990-12-15

AMENDMENT 1
2004-08-15

Fibre-cement slates and fittings **AMENDMENT 1**

Ardoises et leurs accessoires en fibres-ciment

AMENDEMENT 1

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9125:1990/Amd 1:2004

<https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004>



Reference number
ISO 9125:1990/Amd.1:2004(E)

© ISO 2004

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 9125:1990/Amd 1:2004](https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 9125:1990 was prepared by Technical Committee ISO/TC 77, *Products in fibre reinforced cement*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9125:1990/Amd 1:2004](https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 9125:1990/Amd 1:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004>

Fibre-cement slates and fittings

AMENDMENT 1

Page 1, Clause 2

Replace the contents of Clause 2 with the following:

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 390:1993, *Products in fibre reinforced cement — Sampling and inspection*

ISO 395:1983, *Asbestos-cement slates*

ISO 2602:1980, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

HIGH STANDARD PREVIEW
(standards.iteh.ai)

Page 2

ISO 9125:1990/Amd 1:2004

Add a new subclause, 3.3.3.6. <https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004>

3.3.3.6 Soak dry

When slates are tested as specified in 3.5.6, the limit L_i of the average ratio \bar{r} , as defined in 3.5.6.4, shall be greater than 0,75.

Page 2

Add a new subclause, 3.3.4.

3.3.4 Reaction to fire

The details of the specifications and acceptance criteria of reaction to fire may be defined by national standards.

Page 2, subclause 3.4.1

Replace the text by:

3.4.1 General

The objective of an acceptance test is to establish whether a batch of products conforms to a specification. The tests are performed on samples drawn either from continuous production or from a consignment.

NOTE Test methods and specification limit values are defined in this International Standard. Sampling levels and acceptance criteria are defined in national documents or by default in ISO 390.

Acceptance tests as described in 3.4.2. to 3.4.5. shall be performed on as-delivered slates.

Page 3, subclause 3.4.4

Renumber the paragraphs and replace the text of the first of these as follows:

3.4.4 Bending test (obligatory)

3.4.4.1 General

The test shall be carried out on full size slates or cut specimens. These specimens shall be preconditioned in ambient (above 5 °C) or wet conditions or as specified by national standards.

In the absence of national standards, this test shall be carried out on wet preconditioned specimens, immersed in water for 24 h (except for slates of category 1 where the time of immersion shall be reduced to 2 h). Specimens shall be tested immediately after removal from the water.

Page 3, subclause 3.4.4.1

Renumber as 3.4.4.2.

Page 3, subclause 3.4.4.1.1

Renumber as 3.4.4.2.1.

Page 3, subclause 3.4.4.1.2

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.4.4.2.2 **Micrometer**, reading to 0,05 mm with flat metal jaws between 6 mm to 15 mm diameter.

Page 3, subclause 3.4.4.2

ISO 9125:1990/Amd.1:2004
<https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004>

Renumber as 3.4.4.3.

Page 4, subclause 3.4.4.3

Renumber as 3.4.4.4.

Page 4, subclause 3.5.1

Replace the text by:

3.5.1 General

A type test is concerned with the approval of a new product and/or a fundamental change in formulation and/or method of manufacture.

The test is performed on the as-delivered product.

The test is required to demonstrate conformity of a generic product to a specification but is not required for each production batch.

Page 5, subclause 3.5.2.1

Replace the text by:

3.5.2.1 Preparation of specimens

The water permeability shall be checked on three slates. The specimen shall be kept in a laboratory atmosphere at a temperature which is constantly above 5 °C.

Page 5, subclause 3.5.2.2.1

Replace the text by:

3.5.2.2.1 Vertical transparent water column, minimum 300 mm long. The internal dimension of the column in contact with the surface of the test piece shall be a minimum of 35 mm in diameter or 31 mm square.

Page 5, subclause 3.5.2.3

Replace the text by:

3.5.2.3 Procedure

The vertical transparent water column is sealed to the middle of a test piece placed horizontally on a transparent container. The column is filled with water and maintained at a minimum height of 250 mm, measured from the upper surface of the test piece. The specimen is placed in a laboratory atmosphere at a temperature above 5 °C. The duration of the test shall be 24 h. The result of the test is considered to be satisfactory if it conforms to the requirements of 3.3.3.1.

Page 5, subclause 3.5.4.1

ISO 9125:1990/Amd 1:2004

Replace the text by: <https://standards.iteh.ai/catalog/standards/sist/f66257f9-db4b-43ee-ae64-476508870322/iso-9125-1990-amd-1-2004>

3.5.4.1 Apparatus

The apparatus shall consist of any suitable construction with an inclined frame into which the slates shall be mounted and alternately heated uniformly by radiant heat and sprayed with water.

The total area of the slate to be tested shall be approximately square, from 1 m² to 5 m² depending on the slate size and shall contain not less than 11 full slates.

The specimen shall be tested at 90° pitch for façades, and at any angle defined by national standards for roofs.

Quantity of water:

- 2,5 l/min/m² for roofing;
- 1 l/min/m² for façades.

The heating device shall be calibrated in order to maintain a uniform black body⁶⁾ surface temperature equal to 70 °C ± 5 °C for roofs and to 60 °C ± 5 °C for façades, during the heating period.

It should provide an approximately uniform power output during this period.

6) For the definition of a black body see ASTM E 638-78. For this test an aluminium plate of 1 mm thickness painted with a matt black paint is used as a black body.

The measurement device is a thermocouple or a similar device fixed on the surface of the aluminium plate.

Add a new subclause, 3.5.6.

3.5.6 Soak dry (optional)

3.5.6.1 Preparation of specimens

Sample 10 slates as delivered by the producer. Cut 10 sets of paired specimens to suit the bending test in 3.4.4. Each pair of specimens shall be given the same number for later comparison of results.

3.5.6.2 Apparatus

The apparatus includes the following items.

3.5.6.2.1 Ventilated oven, capable of achieving a temperature of $60\text{ °C} \pm 5\text{ °C}$ and a relative humidity of $\leq 20\%$ with a full load of specimens.

3.5.6.2.2 Bath, filled with water at ambient temperature of more than 5 °C .

3.5.6.2.3 Testing equipment, for determination of bending strength as defined in 3.4.4.1.1.

3.5.6.3 Procedure

Divide the paired specimens to form two lots of 10 specimens each. After the conditioning procedure, submit the first lot of 10 specimens to the bending tests as described in 3.4.4.

At the same time submit the second lot to 25 soak dry cycles consisting of

- immersion in water at ambient temperature (above 5 °C) for 18 h;
- drying in a ventilated oven at $60\text{ °C} \pm 5\text{ °C}$ and relative humidity $< 20\%$ for 6 h.

If necessary, an interval of up to 72 h between cycles is allowed. During this interval, the specimens shall be stored in immersed conditions.

After 25 cycles, place the specimens in a laboratory atmosphere for 7 d.

At the end of this period, carry out the wet bending test as specified in 3.4.4.2.

3.5.6.4 Expression and interpretation of results

For each pair of specimens i ($i = 1$ to 10), calculate the individual ratio, r_i , as follows:

$$r_i = M_{fi} / M_{fci}$$

where

M_{fi} is the modulus of rupture of the i th test specimen after the soak-dry cycling;

M_{fci} is the modulus of rupture of the i th reference test specimen (from the first lot).

Calculate the average, \bar{r} , and standard deviation, s , of the individual ratios, r_i (see ISO 2602). Calculate the 95 % lower confidence limit, L_i , of the average ratio \bar{r} , as follows:

$$L_i = \bar{r} - 0,58s$$

Assess the ratio against the specifications of 3.3.3.6.

Page 7, subclause 5.1

Replace the text by:

5.1 Conformity with requirements

The manufacturer shall establish and maintain an effective documented quality control system, developed, e.g., on the basis of the standards of the series ISO 9000.

For the acceptance tests, 90 % of the delivered products shall fulfil the requirements of 3.3.1 to 3.3.3. In the absence of national documents, the sampling schemes provided in ISO 390 with an AQL of 4 % and an inspection level S_3 ensure that, for large batches, approximately 90 % of the items fulfil these requirements. Other methods may be used provided they give the same level of quality.

For each type-test, in the absence of a fundamental change to the formulation and/or method of manufacture, results from one test performed should be taken as a reference of conformity to the specification.

Page 7, subclause 5.2

Replace the text by:

5.2 Evidence of conformity of consignment of finished products

When tenders and/or orders do not specify receiving inspection, the lots delivered are presumed to be in conformity with this International Standard.

Inspection of a consignment of finished products should take place only where there is no third-party certification.

It is conducted, e.g., in accordance with ISO 390, which gives an AQL of 4 % with an inspection level S_3 and in accordance with Annex A.

For special applications, different levels of quality may be applied after agreement between manufacturer and purchaser.