



SLOVENSKI STANDARD SIST-TP CEN/TR 14473:2014

01-julij-2014

Nadomešča:
SIST CR 14473:2002

Premične plinske jeklenke - Porozne mase za jeklenke za acetilen

Transportable gas cylinders - Porous materials for acetylene cylinders

Ortsbewegliche Gasflaschen - Poröse Materialien für Acetylenflaschen

iTeh STANDARD PREVIEW
Bouteilles à gaz transportables - Matières poreuses pour bouteilles à acétylène
(standards.iteh.ai)

Ta slovenski standard je istoveten z: CEN/TR 14473:2014

<https://standards.iteh.ai/catalog/standards/sist/317bf6b2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014>

ICS:

23.020.30	Tlačne posode, plinske jeklenke	Pressure vessels, gas cylinders
-----------	---------------------------------	---------------------------------

SIST-TP CEN/TR 14473:2014

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN/TR 14473:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/317bf2b2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014>

English Version

Transportable gas cylinders - Porous materials for acetylene
cylindersBouteilles à gaz transportables - Matières poreuses pour
bouteilles à acétylèneOrtsbewegliche Gasflaschen - Poröse Materialien für
Acetylenflaschen

This Technical Report was approved by CEN on 6 January 2014. It has been drawn up by the Technical Committee CEN/TC 23.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)[SIST-TP CEN/TR 14473:2014](https://standards.iteh.ai/catalog/standards/sist/317bf2b2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014)<https://standards.iteh.ai/catalog/standards/sist/317bf2b2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014>EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

Contents		Page
Foreword.....		3
Introduction		4
1	Scope	5
2	Source and nature of the data about the listed porous materials	5
3	Country codes.....	5
4	Data for porous materials for individual acetylene cylinders type tested in accordance with EN ISO 3807.....	6
5	Data for porous materials for individual acetylene cylinders and that are type approved based on national regulations.....	10
6	Data for porous materials for acetylene cylinders used in bundles and that are type approved according to national regulations.....	18
Bibliography.....		25

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN/TR 14473:2014](https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014)
<https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014>

Foreword

This document (CEN/TR 14473:2014) has been prepared by Technical Committee CEN/TC 23 “Transportable gas cylinders”, the secretariat of which is held by BSI.

This document supersedes CR 14473:2002.

This second edition supersedes the first edition (CR 14473:2002) with the following main technical revisions:

- a) changes in the legal background are taken into account by introducing new tables for porous materials with filling conditions based on a new European standard (EN ISO 3807) for type testing of porous materials for acetylene cylinders);
- b) entries for porous materials that are no longer used or for which the filling conditions could not be verified were deleted;
- c) the report was amended with regard to porous materials which have been newly placed on the market since the last edition of this report.

For amendments or changes to this report, an application shall be made to the CEN/TC 23 Secretariat with a copy of the documentation based on which the acetylene cylinders are placed on the market (type approval by the competent authority or conformity assessment in accordance with Directive 2010/35/EU (TPED)).

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST-TP CEN/TR 14473:2014](https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014)

<https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014>

CEN/TR 14473:2014 (E)**Introduction**

This report contains data and information about monolithic porous materials for acetylene cylinders.

This report does not contain information about non-monolithic porous materials.

Where there is any conflict between this European Technical Report and any applicable regulation, the regulation always takes precedence.

In International Standards, weight is equivalent to a force, expressed in Newton. However, in common parlance the word "weight" continues to be used to mean "mass", but this practice is deprecated (ISO 80000-4).

In this European Technical Report the unit bar is used, due to its universal use in the field of technical gases. It should, however, be noted that bar is not an SI unit, and that the according SI unit for pressure is Pa.

Pressure values given in this European Technical Report are given as gauge pressure (pressure exceeding atmospheric pressure) unless noted otherwise.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN/TR 14473:2014](https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014)

<https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014>

1 Scope

This Technical Report contains information about monolithic porous materials used in individual acetylene cylinders and in acetylene cylinder bundles. It does not claim to be exhaustive.

2 Source and nature of the data about the listed porous materials

The data contained in the tables in Clauses 4, 5 and 6 are derived from the documentation based on which the acetylene cylinders were or still are placed on the market (type approval by the competent authority or conformity assessment in accordance with TPED) and according to which they are operated (in some cases a type approval with regard to newly manufacturing a porous material has been withdrawn or a TPED-certificate is no longer valid but the cylinders that were already on the market still may be used).

NOTE The documentation provided was examined carefully before including the according information into this Report. Nevertheless, there might be discrepancies to the actual approval, e.g. because more recent amendments exist which were not made available at the time of preparing this Report. In some cases not all information was available in the documents provided and consequently the according information is missing (for example the maximum top clearance or the working pressure).

Acetylene cylinders that were reassessed in accordance with TPED may be filled with the filling values conforming to the reassessment certificate throughout the EU. It should be noted that these values might deviate from those of prior national approvals which still apply to those cylinders that were not reassessed according to TPED.

If no reliable documentation could be made available to the working group, no information is included in this Report. However, this does not necessarily mean that no approval or certification exists.

Clause 4 contains information on porous materials for acetylene cylinders which are placed on the market in accordance with type tests according to EN ISO 3807. It also contains information on filling conditions for acetylene cylinder bundles in accordance with EN ISO 13088.

Clause 5 contains information on porous materials used in individual acetylene cylinders that were type approved based on national regulations and/or standards.

Clause 6 contains information on porous materials used in acetylene cylinder bundles that were approved based on national regulations and/or standards.

If several years are indicated for the approval or certification they refer to according amendments in addition.

3 Country codes

In this Technical Report countries are identified in accordance with their distinguishing signs for motor vehicles according to the Vienna Convention on Road Traffic which is also the basis for marking of cylinders according to the ADR (see Annex A to the ADR, 6.2.2.7) as follows:

A	Austria	F	France	L	Luxembourg
B	Belgium	GB	United Kingdom	NL	Netherlands
CH	Switzerland	GR	Greece	N	Norway
CZ	Czech Republic	HR	Croatia	P	Portugal
D	Germany	HU	Hungary	S	Sweden
DK	Denmark	IRL	Ireland	SK	Slovakia
E	Spain	I	Italy		
FIN	Finland	IS	Iceland		

CEN/TR 14473:2014 (E)**4 Data for porous materials for individual acetylene cylinders type tested in accordance with EN ISO 3807**

Clause 4 contains information on porous materials for acetylene cylinders which were or still are placed on the market in accordance with type testing according to EN ISO 3807. It also contains information on filling conditions for acetylene cylinder bundles in accordance with EN ISO 13088.

The following tables are ordered alphabetically according to the name of the porous material.

Column 1 gives the cylinder water capacities, in l, to which the filling conditions (solvent content, acetylene content, working pressure) as given in the subsequent columns are applicable.

Column 2 lists the specified solvent content, in kg/l, that the acetylene cylinder shall contain per litre water capacity in accordance with the type tests according to EN ISO 3807.

Column 3 lists the maximum acetylene content (including saturation acetylene), in kg/l, that the acetylene cylinder shall contain per litre water capacity in accordance with the type tests according to EN ISO 3807.

Column 4 lists the working pressure of the acetylene cylinder as calculated in accordance with EN ISO 3807. For bundles it gives the maximum no. of consecutive fillings before the bundle has to be dismantled and solvent has to be replenished in the individual cylinders.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TP CEN/TR 14473:2014](https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014)

<https://standards.iteh.ai/catalog/standards/sist/317bfeb2-7203-4521-8e06-d03ab0ca56af/sist-tp-cen-tr-14473-2014>

Identification	A-10W ECO		
Manufacturer	Worthington Cylinders GmbH Beim Flaschenwerk 1, 3291 Kienberg bei Gaming, Austria		
Year and no. of type approval or EU-Certificate	2005, 2006 BAM-05-M01		
Time of manufacture	since 2006		
Type of porous material	Monolithic, asbestos-free		
Density in kg/l	0,270 ± 0,015		
Porosity in %	90,5 ± 1,5		
Maximum top clearance in mm	2		
Solvent	Acetone		
Individual cylinders with acetone			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Working pressure in bar
< 20	0,310	0,180	18
20 to 60	0,310	0,200	19
Individual cylinders without solvent			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Working pressure in bar
	-	0,020	19
Bundle cylinders based on EN ISO 13088			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Maximum no. of consecutive fillings
20 to 60	0,289 to 0,331	0,180	6

CEN/TR 14473:2014 (E)

Identification	A-10W ECO DMF		
Manufacturer	Worthington Cylinders GmbH Beim Flaschenwerk 1, 3291 Kienberg bei Gaming, Austria		
Year and no. of type approval or EU-Certificate	2005, 2006, 2009 BAM-05-M02		
Time of manufacture	since 2006		
Type of porous material	Monolithic, asbestos-free		
Density in kg/l	0,270 ± 0,015		
Porosity in %	90,5 ± 1,5		
Maximum top clearance in mm	2		
Solvent	DMF		
Individual cylinders with DMF			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Working pressure in bar
40 to 60	0,400	0,209	18
Bundle cylinders based on EN ISO 13088			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Maximum no. of consecutive fillings
40 to 60	0,385 to 0,410	0,189	100

Identification	UL 1		
Manufacturer	Linde Vitkovice a.s. Hrbovická 155, 400 01 Ústí nad Labem, Czech Republic		
Year and no. of type approval or EU-Certificate	2012 (valid until 2022) 05.624.115		
Time of manufacture	since 1997		
Type of porous material	Monolithic, asbestos-free		
Density in kg/l	0,264 ± 0,010		
Porosity in %	90,0 ± 1,5		
Maximum top clearance in mm	3		
Solvent	Acetone		
Individual cylinders with acetone			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Working pressure in bar
< 20	0,3125	0,180	18
20 to 55,5	0,3125	0,200	19
Individual cylinders without solvent			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Working pressure in bar
50, 55	–	0,020	19
Bundle cylinders based on EN ISO 13088			
Cylinder water capacity in l	Solvent content in kg/l	Acetylene content in kg/l	Maximum no. of consecutive fillings
20 to 55,5	0,2914 to 0,333	0,180	6