
**Plastics — Polytetrafluoroethylene
(PTFE) semi-finished products —**

**Part 1:
Requirements and designation**

Plastiques — Semi-produits en polytétrafluoroéthylène (PTFE) —

Partie 1: Spécifications et désignation

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 13000-1:2005

<https://standards.iteh.ai/catalog/standards/sist/cb92369c-7109-4d47-bf24-11a02549cf96/iso-13000-1-2005>



Reference number
ISO 13000-1:2005(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 13000-1:2005

<https://standards.iteh.ai/catalog/standards/sist/cb92369c-7109-4d47-bf24-11a02549cf96/iso-13000-1-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terminology	1
3.1 Terms and definitions.....	1
3.2 Abbreviated terms and symbols	2
4 Requirements for PTFE semi-finished products	2
4.1 General.....	2
4.2 Dimensions and dimensional tolerances	2
4.3 Tensile strength and percentage elongation at break	4
4.4 Dimensional stability	4
4.5 Density	5
4.6 Hardness.....	5
4.7 Colour	5
4.8 Dielectric strength (DS), breakdown voltage and electrical flaws	5
4.9 Requirements that may be specified depending on the specific application	7
5 Format for presenting a specification	7
5.1 General.....	7
5.2 Order of presenting codes.....	7
5.3 Examples of coding a specification.....	8
Annex A (informative) Standard specifications for semi-finished products of polytetrafluoroethylene	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13000-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This second edition cancels and replaces the first edition (ISO 13000-1:1997), which has been technically revised.

ISO 13000 consists of the following parts, under the general title *Plastics — Polytetrafluoroethylene (PTFE) semi-finished products*:

- *Part 1: Requirements and designation*
- *Part 2: Preparation of test specimens and determination of properties*

In this corrected version of ISO 13000-1:2005, the tolerance on the inner diameter corresponding to code-letter “a” in the first table in 4.2.6 has been changed from $-\frac{0}{6}$ mm to $-\frac{0}{0,6}$ mm.

Plastics — Polytetrafluoroethylene (PTFE) semi-finished products —

Part 1: Requirements and designation

1 Scope

This part of ISO 13000 specifies the requirements for processed unfilled polytetrafluoroethylene (PTFE) products, which may occur in several forms. The PTFE used to make the semi-finished product is described in ISO 12086-1 and, as provided in ISO 12086-1, may contain up to 1 % of a comonomer. The PTFE used to make the semi-finished product may be virgin, reprocessed or recycled resin. The addition of up to 1,5 % by mass of pigment or colorant is permitted. This part of ISO 13000 allows for four grades based on tensile strength and elongation at break. The semi-finished products can be as-processed (type P) or dimensionally stabilized (type S) and may also have specified electrical properties or other properties when they are required for an application.

NOTE References to other standard specifications for semi-finished products made from polytetrafluoroethylene are listed in Annex A for information.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 12086-1, *Plastics — Fluoropolymer dispersions and moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 13000-2, *Plastics — Polytetrafluoroethylene (PTFE) semi-finished products — Part 2: Preparation of test specimens and determination of properties*

3 Terminology

3.1 Terms and definitions

For the purposes of this part of ISO 13000, the terms and definitions given in ISO 472 and ISO 12086-1 and the following terms and definitions apply.

3.1.1

moulded basic shape

〈PTFE〉 semi-finished product made by preforming and sintering without additional processing

3.1.2

semi-finished product

material, in the form of skived tape, sheets, rods, tubes, tubing, moulded basic shapes or special shapes, that is produced for use either directly without further fabrication or in fabricating end use products, or both

3.1.3

skived tape

film or sheet prepared by cutting, slicing or shaving

NOTE The term “veneered tape” is deprecated.

3.2 Abbreviated terms and symbols

The abbreviated terms given in ISO 1043-1 are applicable to this part of ISO 13000.

4 Requirements for PTFE semi-finished products

4.1 General

After considering the specific shape, dimensions and dimensional tolerances, the primary basis for specifying a semi-finished product of PTFE is the tensile strength and percentage elongation at break of the product. Tests to determine the values for specification shall be run in accordance with the methods in ISO 13000-2. The semi-finished product is identified as “type P” for as-processed or “type S” for stabilized and also may be designated as “type E” with specified electrical properties when required for a particular application. The exclusion of the use of reprocessed or recycled material shall be specified if needed in order to meet special customer requirements. The values required for other properties are given in their respective subclauses.

4.2 Dimensions and dimensional tolerances

4.2.1 General

Dimensional tolerances shall be measured at $23\text{ °C} \pm 2\text{ °C}$.

4.2.2 Skived tape, skived sheet and film

Code-letter	Thickness	Tolerance
a	< 0,1 mm	$\begin{smallmatrix} +0,01 \\ 0 \end{smallmatrix}$ mm
b	$\geq 0,1$ mm	$\begin{smallmatrix} +10 \\ 0 \end{smallmatrix}$ %

The standard tolerance for width is $\begin{smallmatrix} +3 \\ 0 \end{smallmatrix}$ %, with a maximum of 30 mm. For slit skived tape, the exact width shall be agreed upon between purchaser and supplier.

The standard tolerance for length is $\begin{smallmatrix} +2 \\ 0 \end{smallmatrix}$ %.

4.2.3 Moulded sheet

Code-letter	Thickness	Tolerance
a	< 5 mm	$+0,75_0$ mm
b	≥ 5 mm	$+15_0$ %

The length and width tolerance shall be $+3_0$ %.

4.2.4 Extruded or moulded rods

As extruded or moulded:

Code-letter	Diameter	Tolerance
a	< 10 mm	$+0,6_0$ mm
b	≥ 10 mm	$+6_0$ %

The standard tolerance for length is:

Code-letter	Length	Tolerance
a	≤ 500 mm	$+10_0$ mm
b	> 500 mm	$+2_0$ %

<https://standards.iteh.ai/catalog/standards/sist/cb92369c-7109-4d47-bf24-11a02549cf96/iso-13000-1-2005>

Centreless ground:

Tolerance on diameter for all diameters: $+0,04_0$ mm.

Tolerance on length:

Code-letter	Length	Tolerance
a	≤ 500 mm	$+10_0$ mm
b	> 500 mm	$+2_0$ %

4.2.5 Thin-walled tube extruded from coagulated dispersion powder

The standard tolerance on inner diameter and wall thickness is:

Code-letter	Dimension	Tolerance
a	Inner diameter < 5 mm	$\pm 0,25$ mm
b	Inner diameter ≥ 5 mm	± 5 %
c	Wall thickness < 1,0 mm	$\pm 0,1$ mm
d	Wall thickness $\geq 1,0$ mm	± 10 %

The standard tolerance for length is $+2_0$ %.

4.2.6 Extruded and moulded tubes

Code-letter	Outer diameter	Tolerance on	
		inner diameter	outer diameter
a	< 10 mm	$\begin{smallmatrix} 0 \\ -0,6 \end{smallmatrix}$ mm	$\begin{smallmatrix} +0,6 \\ 0 \end{smallmatrix}$ mm
b	≥ 10 mm	$\begin{smallmatrix} 0 \\ -6 \end{smallmatrix}$ %	$\begin{smallmatrix} +6 \\ 0 \end{smallmatrix}$ %

The standard tolerance for length is:

Code-letter	Length	Tolerance
a	≤ 500 mm	$\begin{smallmatrix} +10 \\ 0 \end{smallmatrix}$ mm
b	> 500 mm	$\begin{smallmatrix} +2 \\ 0 \end{smallmatrix}$ %

The tube shall be capable of being machined concentrically to the required nominal dimensions and the eccentricity of the bore shall not exceed 4,0 % of the nominal inside diameter.

NOTE The machining of the tube to the nominal dimensions with the inner and outer surfaces concentric is feasible if the maximum inner diameter, calculated by difference between the outer diameter and two times the minimum wall thickness, is within the specified tolerance.

For a moulded tube, the tolerance on the outer diameter shall be a minimum value. A larger diameter than is provided for by the plus tolerance is acceptable for moulded tube, either type P or S, that is to be machined to the final dimension.

4.3 Tensile strength and percentage elongation at break

The grade for semi-finished products is determined by the minimum values of tensile strength and percentage elongation at break shown in Table 1, determined as specified in ISO 13000-2.

NOTE There are some configurations of PTFE that might not be able to be produced with a high grade classification.

Table 1

Grade	1	2	3	4
Tensile strength, MPa	25	20	15	10
Elongation at break, %	280	200	150	75

4.4 Dimensional stability

This requirement applies only to type S (stabilized) material.

The maximum change in any dimension shall not exceed 0,5 %, determined as specified in ISO 13000-2.

4.5 Density

All semi-finished products shall have a density in the range of 2,13 g/cm³ to 2,19 g/cm³ except that:

- a) products made from reprocessed material or blends with reprocessed material shall have a density in the range of 2,14 g/cm³ to 2,23 g/cm³;
- b) tubing extruded from coagulated dispersion powders shall have a density in the range of 2,13 g/cm³ to 2,23 g/cm³.

4.6 Hardness

All products that have a shape or dimensions such that measurements can be made precisely shall have a ball indentation hardness of more than 23 MPa or the hardness determined using the Shore D test shall have a value greater than 54. Both of the hardness tests are described in ISO 13000-2.

4.7 Colour

PTFE that does not contain a colorant shall be white to transparent after sintering. Visual perception of whiteness is usually adequate to appraise this characteristic of semi-finished products. If a quantitative value is required for whiteness, the test procedure in ISO 13000-2 shall be used. The value required shall be as agreed upon between producer and purchaser. If pigment or colorant has been added, its presence shall be reported in all documentation related to a particular product.

NOTE The presence of pigments or colorants may affect some properties of the material, e.g. chemical resistance and electrical properties, and it is advisable for the purchaser and supplier to agree upon the type and grade of pigment to be used.

4.8 Dielectric strength (DS), breakdown voltage and electrical flaws

4.8.1 General

This requirement applies only to materials coded E with specified electrical properties required for an application. The required values for the various shapes reflect the same dielectric strength when corrected for thickness by the standard relationship.

NOTE The IEC has responsibility for standards related to electrical properties. Since there are, however, no IEC standards that are pertinent to the scope and needs of this part of ISO 13000, provisions for electrical properties are included in this part of ISO 13000. Some references to general IEC standards and specific references to IEC standards for heat-shrinkable tubing of PTFE are included in Annex A.

4.8.2 Skived tape, skived sheet and film

4.8.2.1 The minimum values required for dielectric strength DS (expressed in kV/mm) shall be computed for applicable thicknesses of materials in accordance with the following formulae, where t is the thickness of the tape in millimetres:

Type	Minimum DS (kV/mm)
E1	$37 \sqrt{0,5/t}$
E2	$30 \sqrt{0,5/t}$
E3	$20 \sqrt{0,5/t}$

4.8.2.2 The number of electrical flaws shall be as agreed between the purchaser and the seller.