



SLOVENSKI STANDARD

SIST EN 1015-3:2001

01-februar-2001

A YrcXY'dfYg_i ýUb^UnjXUfg_Y'a UHr!" "XY.'8c`c Yj Ub^Y_cbgjghYbWW'gj YyY'a UHr
fb'ghfYgUbc'a]ncŁ

Methods of test for mortar for masonry - Part 3: Determination of consistence of fresh mortar (by flow table)

Prüfverfahren für Mörtel für Mauerwerk - Teil 3: Bestimmung der Konsistenz von Frischmörtel (mit Ausbreittisch)

Méthodes d'essai des mortiers pour maçonnerie - Partie 3: Détermination de la consistance du mortier frais (à la table à secousses)

[https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-](https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-beaed18e669f/sist-en-1015-3-2001)

Ta slovenski standard je istoveten z: EN 1015-3:1999

ICS:

91.100.10 Cement. Mavec. Apno. Malta Cement. Gypsum. Lime.
Mortar

SIST EN 1015-3:2001

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1015-3:2001](#)

<https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-beaed18e669f/sist-en-1015-3-2001>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1015-3

February 1999

ICS 91.100.10

English version

Methods of test for mortar for masonry - Part 3: Determination of
consistence of fresh mortar (by flow table)

Méthodes d'essai des mortiers pour maçonnerie - Partie 3:
Détermination de la consistance du mortier frais (à la table
à secousses)

Prüfverfahren für Mörtel für Mauerwerk - Teil 3:
Bestimmung der Konsistenz von Frischmörtel (mit
Ausbreittisch)

This European Standard was approved by CEN on 4 September 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-beaed18e669f/sist-en-1015-3-2001>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents	Page
Foreword	3
Introduction	4
1 Scope	4
2 Normative references	4
3 Principle	4
4 Apparatus	5
5 Sampling, preparation and storage of test samples	5
6 Procedure	6
7 Calculation and expression of results	6
8 Test report	6
Annex A (normative) Details of flow table	8
Annex B Bibliography (informative)	9

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1015-3:2001](https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-bcaed18c669f/sist-en-1015-3-2001)

<https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-bcaed18c669f/sist-en-1015-3-2001>

ALTERNATIVE APPROACHES
TO THE TESTING OF
SYSTEMS OF
ANALYSIS

1998 25
INTERNATIONAL CENTER FOR TESTING

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 125 "Masonry", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 1999, and conflicting national standards shall be withdrawn at the latest by December 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1015-3:2001

<https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-beaed18e669f/sist-en-1015-3-2001>

Introduction

Fresh mortar is brought to a defined level of consistence as measured using the flow table prior to the assessment of those properties which are used to characterise it.

Consistence is a measure of the fluidity and/or wetness of the fresh mortar and gives a measure of the deformability of the fresh mortar when subjected to a certain type of stress. The consistence however is not directly associated with the manner in which the fresh mortar handles when used by a craftsman.

Normally there will be a linear correlation between flow value, measured in accordance with this test method, and the plunger penetration value measured in accordance with EN 1015-4, for the same type of mortar with increasing water content, but the slope will differ with different type of mortars.

1 Scope

This European Standard specifies a method for determining the consistence of freshly mixed mortars (in the following briefly referred to as fresh mortars) including those containing mineral binders and both normal weight and lightweight aggregates, which is by means of the flow value.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

prEN 998-1	Specification for mortar for masonry - Part 1: Rendering and plastering mortar with inorganic binding agents
prEN 998-2	Specification for mortar for masonry - Part 2: Masonry mortar
EN 1015-2	Methods of test for mortar for masonry - Part 2: Sampling of mortars and preparation of test mortars

3 Principle

The flow value is measured by the mean diameter of a test sample of the fresh mortar which has been placed on a defined flow table disc by means of a defined mould, and given a number of vertical impacts by raising the flow table and allowing it to fall freely through a given height.

4 Apparatus

4.1 A **flow table**, as described in annex A, consisting of the following main parts:

- stand
- rigid table plate and disc
- horizontal shaft and lifting cam
- lifting spindle

4.2 A **truncated conical mould** made of stainless steel or brass, 60 mm \pm 0,5 mm in height and with internal diameter of 100 mm \pm 0,5 mm at the bottom and 70 mm \pm 0,5 mm at the top. The inside surface and the edges of the mould are smooth. The planes containing the top and bottom edges are at right angles to its axis. The minimum thickness of the mould wall is 2,0 mm.

4.3 A **tamper** consisting of a rigid, non-absorptive rod of circular cross-section, approximately 40 mm in diameter and approximately 200 mm long. The tamping face is flat and at right angles to the length of the tamper. The mass of the tamper is 0,250 kg \pm 0,015 kg.

4.4 **Calipers** capable of measuring diameters up to 300 mm with an accuracy of 1 mm.

4.5 **Trowel**

4.6 **Palette knife**

SIST EN 1015-3:2001
<https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-beaed18e669f/sist-en-1015-3-2001>

5 Sampling, preparation and storage of test samples

The fresh mortar for this test shall have a minimum volume of 1,5 l and shall be obtained by reduction of the bulk test sample (see EN 1015-2) using a sample divider or by quartering.

Ready to use mortars (factory-made wet mortars which are retarded), and pre-batched air-lime/sand wet mortars when not gauged with hydraulic binders, shall be tested within their specified workable life.

Mortars that are made from dry constituents and water shall be mixed in accordance with EN 1015-2 unless otherwise specified.

The length of mixing period shall be measured from the moment all the constituents are introduced into the mixer.

Before testing, the batch shall be gently stirred by hand using a trowel or palette knife in 5 -10 seconds to counteract any false setting etc., but without any additional mixing of the batch.

Any deviation from the mixing procedure shall be noted.

Two test samples shall be tested.

6 Procedure

Before each test, wipe the disc and the inner surface and edges of the mould (4.2) clean with a damp cloth, let dry and lightly lubricate the surfaces with very low viscosity non-resin mineral oil. If the table has not been used within the last 24 h, operate for ten revolutions before use.

Place the mould centrally on the disc of the flow table (4.1) and introduce the mortar in two layers, each layer being compacted by at least 10 short strokes of the tamper (4.3) to ensure uniform filling of the mould. During filling, hold the mould firmly on the disc, using one hand.

Skim off the excess mortar with a palette knife and wipe the free area of disc clean and dry, being especially careful to remove any water from around the bottom edge of the mould. After approximately 15 s, slowly raise the mould vertically and spread out the mortar on the disc by jolting the flow table 15 times at a constant frequency of approximately one per second.

Measure the diameter of the mortar in two directions at right angles to one another using calipers (4.4). State the results in mm to the nearest mm.

7 Calculation and expression of results

Calculate the mean value of the two measurements. This mean value is the flow value for the test sample. If the individual flow values from the two test samples deviate from their mean value by less than 10 %, use this mean value as the flow value of the mortar. If the two individual flow values deviate from their mean value by more than 10 %, repeat the test using further mortar from the reduced bulk test sample (see Clause 5) and if the results deviate from the mean value by less than 10% use the mean value from the repeat test as the flow value of the mortar. If the results differ by more than 10% consider the measurements unsatisfactory and take fresh test samples from the bulk test sample or laboratory prepared mortar and repeat the test.

8 Test report

The test report shall include the following information :

- a) the number, title and date of issue of this European Standard;
- b) the place, date and time of taking the bulk test sample¹;

Note : This is the sample taken from the bulk supply that is to be used for all of the tests in EN 1015.

- c) the method used for taking the bulk test sample (if known) and the name of the organization that took it;
- d) the type, origin and designation of the mortar by reference to the relevant part of prEN 998;

¹ This information is contained on the certificate of sampling (see EN 1015-2)

- e) preparation (mixing, casting) and storage (curing) conditions;
- f) the date and time of preparing test samples for test (i.e. date and time of any mixing, casting, moulding, or demoulding procedure, if appropriate);
- g) the date and time of testing;
- h) test results (individual measurements and the flow values in mm for each test sample)
- i) remarks, if any;

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1015-3:2001

<https://standards.iteh.ai/catalog/standards/sist/fdc3a65b-0f2c-408d-9bcd-beaed18e669f/sist-en-1015-3-2001>