



Standard Test Method for Dust Control Material on Calcined Petroleum Coke¹

This standard is issued under the fixed designation D 4930; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Warning notes were moved into text editorially in November 2004.

1. Scope

1.1 This test method covers the determination of the amount of material applied to calcined coke to control dust associated with coke handling and transportation.

1.2 This test method is limited to those materials that are soluble in a solvent that can be used in a Soxhlet extraction type of apparatus such as methylene chloride (dichloromethane).

NOTE 1—Methylene chloride is the most popular solvent for removing dust control oil at the time this procedure is being written. Toluene and methyl chloroform, however, have been used with equal results on all cokes tested which have included only those sprayed with aromatic or waxy materials.

1.3 The values stated in SI units are to be regarded as the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 8.

2. Referenced Documents

2.1 ASTM Standards:²

D 346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis

D 2013 Practice for Preparing Coal Samples for Analysis

D 2234 Test Methods for Collection of a Gross Sample of Coal

D 4057 Practice for Manual Sampling of Petroleum and Petroleum Products

E 11 Specification for Wire Cloth and Sieves for Testing Purposes

3. Terminology

3.1 Definitions:

3.1.1 *analysis sample*—the reduced and divided representative portion of the bulk sample, prepared for use in the laboratory.

3.1.2 *bulk sample*—the reduced and divided representative portion of the gross sample as prepared for shipment and received by a laboratory.

3.1.3 *test sample*—the weighed portion of the analysis sample actually used in a test.

3.2 Descriptions of Term Specific to This Standard:

3.2.1 *de-dusting material*—a substance, such as a petroleum oil, a petroleum wax, an aqueous latex emulsion, and the like, that is applied to (sprayed on) calcined petroleum coke to control dust associated with coke handling and transport.

4. Summary of Test Method

4.1 The dust control material is dissolved from a weighed dry representative sample of 6.3-mm maximum sized coke by methylene chloride in a Soxhlet extraction apparatus. The mass of the residue remaining after distilling and evaporating the solvent is the mass of dust control material. The amount of residue as a percent of the original mass is calculated.

5. Significance and Use

5.1 The test is designed to quantify the amount of dust control material added to calcined coke. The dust control material is applied to calcined coke to help maintain a dust-free environment. It generally serves no other useful purpose. It adds weight to the coke and can have a negative effect on the

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.05 on Properties of Fuels, Petroleum Coke and Carbon Material.

Current edition approved Nov. 1, 2004. Published November 2004. Originally approved in 1989. Last previous edition approved in 1999 as D 4930 – 94 (1999).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.