



**SLOVENSKI STANDARD**  
**SIST EN 1052-2:2000**  
**01-september-2000**

---

**Metode preskušanja za zidovje - 2. del: Ugotavljanje upogibne trdnosti**

Methods of test for masonry - Part 2: Determination of flexural strength

Prüfverfahren für Mauerwerk - Teil 2: Bestimmung der Biegezugfestigkeit

Méthodes d'essai de la maçonnerie - Partie 2: Détermination de la résistance a la flexion

**Ta slovenski standard je istoveten z: EN 1052-2:1999**

[SIST EN 1052-2:2000](https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000)

<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>

**ICS:**

91.080.30      Zidane konstrukcije      Masonry

**SIST EN 1052-2:2000**      **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 1052-2:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

EN 1052-2

August 1999

ICS 91.080.30

English version

## Methods of test for masonry - Part 2: Determination of flexural strength

Méthodes d'essai de la maçonnerie - Partie 2:  
Détermination de la résistance à la flexion

Prüfverfahren für Mauerwerk - Teil 2: Bestimmung der  
Biegezugfestigkeit

This European Standard was approved by CEN on 8 July 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

**iTeh STANDARD PREVIEW**  
<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Contents	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Principle	4
4 Symbols	4
5 Materials	5
6 Apparatus	6
7 Preparation of specimens	6
8 Procedure	7
9 Calculations	10
10 Evaluation of results	10
11 Test report	11

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 1052-2:2000](https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000)  
<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>

**Foreword**

This European Standard has been prepared by Technical Committee CEN/TC 125 "Masonry", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2000, and conflicting national standards shall be withdrawn at the latest by February 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 1052-2:2000

<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>

## 1 Scope

This European standard specifies a method for determining the flexural strength of small masonry specimens for the two principal axes of loading. Guidance is given on the preparation of the specimens, the conditioning required before testing, the testing machine, the method of test, the method of calculation and the contents of the test report.

## 2 Normative references

This European standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

prEN 772-1	Methods of test for masonry units - Part 1 : Determination of compressive strength.
EN 772-10	Methods of test for masonry units - Part 10 : Determination of moisture content of calcium silicate and autoclaved aerated concrete masonry units.
prEN 998-2	Specification for mortar for masonry - Part 2 : Masonry mortar
EN 1015-3	Methods of test for mortar for masonry - Part 3 : Determination of consistence of fresh mortar (by flow table)
EN 1015-7	Methods of test for mortar for masonry - Part 7 : Determination of air content of fresh mortar
EN 1015-11	Methods of test for mortar - Part 11 : Determination of flexural and compressive strength of hardened mortar.

## 3 Principle

The flexural strength of masonry is derived from the strength of small specimens tested to destruction under four point loading. The maximum load achieved is recorded. The characteristic value, calculated from the maximum stresses achieved by the samples is considered to be the flexural strength of the masonry

## 4 Symbols

### 4.1 Definitions

**4.1.1 Masonry.** An assemblage of masonry units laid in a specified pattern and jointed together with mortar.

**4.1.2 Flexural strength of masonry.** The strength of masonry in pure bending assuming a linear stress distribution of internal stresses.

### 4.2 Symbols

*b* is the height or width of a masonry specimen perpendicular to the direction of span, (mm)

$F_{i,max}$	is the maximum load applied to an individual masonry specimen, (N)
$f_{xi}$	is the flexural strength of an individual masonry specimen, (N/mm <sup>2</sup> )
$f_{mean}$	is the mean flexural strength of the masonry specimens, (N/mm <sup>2</sup> )
$f_{sk}$	is the characteristic flexural strength of masonry, (N/mm <sup>2</sup> )
$h_u$	is the height of masonry unit, (mm)
$k$	is the numerical factor
$l_s$	is the length of a masonry specimen in the direction of span, (mm)
$l_u$	is the length of masonry unit, (mm)
$l_1$	is the spacing of the outer bearings, (mm)
$l_2$	is the spacing of the inner bearings, (mm)
$n$	is the number of specimens
$s$	is the standard deviation of the log values
$t_u$	is the width of masonry unit, (mm)

ITeH STANDARD PREVIEW  
(standards.iteh.ai)

## 5 Materials

SIST EN 1052-2:2000  
<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>

### 5.1 Masonry units

#### 5.1.1 Conditioning of the units

The conditioning of masonry units shall be as specified:

Record the method of conditioning the units prior to laying. Measure the moisture content by mass of autoclaved aerated concrete and calcium silicate masonry units in accordance with EN 772-10. Record the age of non autoclaved concrete units at the time of testing the masonry specimens.

#### 5.1.2 Testing

Determine the compressive strength of a sample of masonry units, using the method given in prEN 772-1. For non-autoclaved concrete units determine the compressive strength at the time of testing the masonry specimens.

### 5.2 Mortar

The mortar, its mixing procedure and its flow value shall conform to the requirements of prEN 998-2, unless otherwise specified, and these shall be reported in the test report.

Take representative samples of fresh mortar from the mason's board to make mortar prisms, to determine the flow value in accordance with **EN 1015-3**, and to determine the air content in accordance with **EN 1015-7**. Use the prism specimens to determine the mean compressive strength at the time of testing of the masonry specimens in accordance with **EN 1015-11**.

## 6 Apparatus

A testing machine complying with the requirements given in **table 1**, and accommodating variations of plane. The testing machine shall have adequate capacity but the scale used shall be such that the ultimate load on the specimen exceeds one fifth of the full scale reading. The machine shall be provided with a load pacer or equivalent means to enable the load to be applied at the rate specified. The bearings shall be designed to ensure that contact is provided over the full width of the masonry, for example by using a hollow rubber bolster of at least 7 mm wall thickness and a 10 mm bore containing an 8 mm diameter steel rod.

**Table 1 : Requirements for testing machines**

Maximum permissible repeatability of forces as percentage of indicated force	Maximum permissible mean error of forces as percentage of indicated force	Maximum permissible error of zero force as percentage of maximum force of range
2,0	± 2,0	± 0,4

(standards.iteh.ai)

## 7 Preparation of specimens

SIST EN 1052-2:2000

### 7.1 Masonry specimens

<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>

For each of the two principal axes of loading use at least five specimens according to **figure 1** having the sizes given in **table 2**. The size of the masonry specimens shall be chosen so that the distance between the inner and outer bearings shall be not less than the thickness of the masonry specimen. The thickness of the specimen shall be equal to  $t_u$  unless otherwise specified.

**Table 2 : Specimen sizes for testing the flexural strength of masonry**

Direction	$h_u$ (mm)	$b$ (mm)	Additional conditions
Flexural strength for a plane of failure parallel to the bed joints	any	$\geq 400$ and $\geq 1,5 l_u$	minimum 2 bed joints within $l_2$
Flexural strength for a plane of failure perpendicular to the bed joints	$\leq 250$	$\geq 240$ and $\geq 3h_u$	minimum 1 head joint every course within $l_2$
	$>250$	$\geq 1000$	minimum 1 bed joint and minimum 1 head joint every course within $l_2$

### 7.2 Construction and curing of the specimens

Build the specimens within 30 min after completion of the conditioning of the units, using mortar mixed not more than one hour beforehand unless the mortar is designed to be used over a more prolonged period. Construct the specimens to the bond specified. Do not allow the work to be interrupted before completion.



Immediately after building, pre-compress each specimen using a uniformly distributed mass to give a vertical stress between  $2,5 \cdot 10^{-3} \text{ N/mm}^2$  and  $5,0 \cdot 10^{-3} \text{ N/mm}^2$ ; then cure the specimens, and maintain them undisturbed until testing. For other than lime-based mortar prevent the test specimens from drying out during the curing period by close covering with polyethylene sheet, and maintain the specimens undisturbed until testing unless otherwise specified. Test each specimen at an age of 28 days  $\pm$  1 day, unless otherwise specified, and determine the compressive strength of the mortar at the same age, following **EN 1015-11**. For lime-based mortars an alternative curing regime and period may be necessary and this should be specified.

## 8 Procedure

### 8.1 Placing the specimens in the testing equipment

Test the masonry specimen in the vertical attitude under four-point loading (see **figure 1**). The distance between the outer bearings and the end of the specimen shall be greater than or equal to 50 mm. The distance between the inner bearings may be varied to suit the format of the masonry but shall be 0,4 to 0,6 times the spacing of the outer bearings. The inner bearings shall be located so that they are, as far as practicable, midway between the nearest mortar joints which are parallel to the bearings.

Ensure that the base of each masonry specimen is free from frictional restraint, for example by setting it on two layers of polytetrafluoroethylene with grease between them or on ball, needle or roller bearings.

### 8.2 Loading

Increase the flexural stress at a rate between  $0,03 \text{ N/mm}^2/\text{min}$  and  $0,3 \text{ N/mm}^2/\text{min}$ .

iteh STANDARD PREVIEW  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/ab1278ae-8557-44ed-bedc-495384dc50ac/sist-en-1052-2-2000>