

---

---

**Rubber- or plastics-coated fabrics —  
Determination of resistance to liquids**

*Supports textiles revêtus de caoutchouc ou de plastique —  
Détermination de la résistance aux liquides*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 6450:2005](https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005)

<https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 6450:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword.....	iv
1 Scope .....	1
2 Normative references .....	1
3 Principle .....	1
4 Test liquids for methods 1 and 2.....	1
5 Test conditions for methods 1 and 2.....	2
6 Conditioning atmosphere for methods 1 and 2.....	2
7 Apparatus for methods 1 and 2.....	2
8 Method 1 — Immersion and subsequent removal of excess liquid by wiping.....	3
9 Method 2 — Immersion in a volatile test liquid and subsequent drying of the test pieces .....	4
10 Test report .....	4
Annex A (informative) Reference liquids .....	5
Annex B (informative) Standard temperatures of immersion .....	9
Bibliography .....	10

[ISO 6450:2005](https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005)

<https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 6450 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 4, *Products (other than hoses)*.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 6450:2005](https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005)

<https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005>

# Rubber- or plastics-coated fabrics — Determination of resistance to liquids

## 1 Scope

This International Standard specifies two methods (methods 1 and 2) of evaluating the resistance of fabrics coated with plastics or with vulcanized rubber to the action of liquids by measurement of selected properties of the materials before and after immersion in selected liquids.

The difference between the two methods is as follows:

- In method 1, excess liquid is removed from the test pieces, after immersion, by wiping.
- In method 2, the test pieces are immersed in a volatile liquid and excess liquid is subsequently removed by drying in an oven.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2231, *Rubber- or plastics-coated fabrics — Standard atmospheres for conditioning and testing*

ISO 2286-1, *Rubber- or plastics-coated fabrics — Determination of roll characteristics — Part 1: Methods for determination of length, width and net mass*

## 3 Principle

This International Standard provides a procedure for exposing test pieces to the influence of liquids under defined conditions of temperature and time. Selected properties are determined in accordance with the relevant test method standards. Test pieces are then immersed in selected liquid(s) and the properties determined again. The percentage change or the values before and after immersion are measures of the resistance of the material to the selected liquid(s).

## 4 Test liquids for methods 1 and 2

**SAFETY PRECAUTIONS** — Appropriate safety precautions should be taken when preparing and handling test liquids, especially those known to be toxic, corrosive or flammable. Products giving off fumes should be handled only under an efficiently ventilated hood, corrosive products should not be allowed to come into contact with the skin or ordinary clothing, and flammable products should be kept away from any source of ignition.

In addition, attention is drawn to the damage which can be caused by corrosive test liquids to test equipment (e.g. clamps or jaws).

As commercial liquids may not have an entirely constant composition, a standard immersion liquid consisting of a well-defined chemical compound or a mixture of such compounds should preferably be used. Suitable liquids are given in Annex A.

If a commercial liquid is used, the test report shall mention all the available information about its origin, composition, properties, e.g. viscosity, aniline point, etc., and batch number.

NOTE For test purposes, it is usually desirable to use the liquid(s) with which the coated fabric will come into contact during use. When determining the effect of solutions of chemicals, the concentration of the solution should be appropriate to the proposed application.

## 5 Test conditions for methods 1 and 2

### 5.1 Temperature

Where appropriate, use an immersion temperature  $T$  approximating to that encountered during use. Maintain the immersion temperature at  $T \pm 2$  °C.

Preferred immersion temperatures are given in Annex B.

### 5.2 Immersion period

The following immersion periods are recommended:

22 h  $\pm$  0,25 h; 46 h  $\pm$  0,25 h; 72 h  $\pm$  2 h; 168 h  $\pm$  2 h; multiples of 7 days  $\pm$  2 h

NOTE When determining changes in physical properties, it is advisable to use a period of immersion which is long enough to ensure that equilibrium is reached. To determine this equilibrium point, it is recommended that preliminary measurements be carried out using several different periods of immersion, recording the results as a function of time. Whenever practicable, the total period of immersion should extend well beyond the point at which the change in a property reaches its maximum value.

### 5.3 Light

Immersion tests shall be conducted in the absence of direct light.

### 5.4 Time lapse between manufacturing and testing

The minimum time lapse between manufacturing and testing shall be 16 h.

## 6 Conditioning atmosphere for methods 1 and 2

Before immersion, test pieces shall be conditioned in one of the atmospheres defined in ISO 2231, unless otherwise specified in the standard relevant to the property to be determined.

## 7 Apparatus for methods 1 and 2

The apparatus to be used is determined by the temperature of immersion, the volatility of the test liquid, the dimensions of the test pieces and the number required for determining the selected property. At temperatures appreciably below the boiling point of the test liquid, use a stoppered vessel, e.g. a glass bottle or tube, of such dimensions that the test pieces remain completely immersed in the specified volume of test liquid and all surfaces are completely exposed to the liquid without any restriction. At temperatures near the boiling point of the test liquid, fit the vessel with a reflux condenser, or other suitable means of minimizing evaporation of the test liquid, instead of the stopper.

## 8 Method 1 — Immersion and subsequent removal of excess liquid by wiping

### 8.1 Preparation of test pieces

Select properties that are considered relevant to the end-use (for example, tensile strength, coating adhesion, mass per unit area, tear resistance and/or low-temperature properties).

For each property, cut from the usable width of the roll (as defined in ISO 2286-1) two sets of test pieces as specified in the relevant test method standard (some commonly used test method standards are given in the Bibliography).

Condition all the test pieces in accordance with Clause 6.

### 8.2 Determination of original properties before immersion

Determine the selected properties on the first set of test pieces using the relevant test method standards.

### 8.3 Immersion

Place the test pieces, suitably separated, in a vessel as described in Clause 7, with a volume of test liquid (see Clause 4) that is at least 15 times the combined volume of the test pieces and sufficient to keep them totally immersed. If the conditions of the test do not necessitate the use of a reflux condenser, stopper the vessel. Maintain the test liquid at the test temperature  $T$ , within a tolerance of  $\pm 2$  °C, during the whole of the exposure period.

iTeh STANDARD PREVIEW

### 8.4 Preparation of test pieces for redetermination of properties

At the end of the immersion period, bring the test pieces, if necessary, to the test temperature, preferably by quickly transferring them to a fresh portion of test liquid at this temperature and allowing to stand for 5 min to 10 min.

<https://standards.iteh.ai/catalog/standards/sist/4493404f-0009-49fd-8f39-8ae8116601cd/iso-6450-2005>

Take the test pieces out of the test liquid and remove any liquid remaining on the surface of the test pieces using a suitable method. The method of removing the liquid may vary with the nature of the liquid. When mobile, volatile liquids like iso-octane and toluene are used, wipe the test pieces with a filter paper or a piece of lint-free fabric. Some difficulty may be experienced in removing viscous, non-volatile liquids completely by this method, and it may be necessary to dip the test pieces quickly in a suitable volatile liquid such as methanol and wipe them again with filter paper or lint-free fabric.

Visually assess the appearance of the test pieces against a piece of non-immersed material. Note whether any change has occurred or not and describe any changes observed.

### 8.5 Determination of properties after immersion

Immediately after removal of the liquid, measure the selected physical properties in accordance with the relevant standards.

### 8.6 Expression of results

Report the values measured before and after immersion or report the change in the values as a percentage of the original value determined before immersion.

## 9 Method 2 — Immersion in a volatile test liquid and subsequent drying of the test pieces

### 9.1 Preparation of test pieces

Prepare the test pieces as specified in 8.1.

### 9.2 Determination of original properties before immersion

Determine the original properties as specified in 8.2.

### 9.3 Immersion

Immerse the test pieces as specified in 8.3.

### 9.4 Drying of test pieces

At the end of the specified immersion period, remove the test pieces and hang them in a circulating-air oven at a temperature of  $70\text{ °C} \pm 2\text{ °C}$  for a period of  $2\text{ h} \pm 0,1\text{ h}$ . At the end of this drying period, remove the test pieces from the oven and allow them to cool to room temperature.

### 9.5 Determination of properties after immersion and drying

The time interval between removal of the test pieces from the oven and testing shall not be less than 1 h and not more than 2 h. Measure the selected physical property in accordance with the relevant standard.

### 9.6 Expression of results

Report the values measured before and after immersion or report the change in the values as a percentage of the original value determined before immersion.

## 10 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) the date of the test;
- c) the conditioning and test atmosphere;
- d) all details necessary for identification of the coated fabric tested;
- e) a description of the test liquid (see Clause 4);
- f) the method used (method 1 or method 2);
- g) the immersion temperature;
- h) the immersion period;
- i) a description of the appearance of the test pieces after immersion;
- j) the values of the measured properties before and after immersion, or the percentage changes in the properties;
- k) any deviation from the specified procedure.



## Annex A (informative)

### Reference liquids

**WARNING** — Appropriate safety precautions should be taken when preparing and handling test liquids, especially those known to be toxic, corrosive or flammable. Products giving off fumes should be handled only under an efficiently ventilated hood, corrosive products should not be allowed to come into contact with the skin or ordinary clothing, and flammable products should be kept away from any source of ignition.

#### A.1 Standard simulated fuels

Commercial fuels vary widely in composition even within the same grade (i.e. knock rating) and from the same source. There are hydrocarbon-based fuels with and without oxygen compounds as well as alcohol-based fuels. The grade of gasoline is improved by adding aromatic or oxygen-containing compounds, but these additives increase the effect of fuels on normally fuel-resistant rubbers. The composition varies with the situation on the gasoline market and with the geographical area and can change rapidly. Hence, several test liquids which are used in practice are recommended in Tables A.1 and A.2 to cover the range of different compositions. They may also serve as guidelines for the formulation of other suitable test liquids. Analytical reagent quality materials shall be used in making up the test liquids. Test liquids containing alcohol shall not be used if the fuels involved are known to be free of alcohol.

**Table A.1 — Standard simulated fuels without oxygen compounds**

Liquid	Constituents	Content % (by volume)
A	2,2,4-Trimethylpentane	100
B	2,2,4-Trimethylpentane Toluene	70 30
C	2,2,4-Trimethylpentane Toluene	50 50
D	2,2,4-Trimethylpentane Toluene	60 40
E	Toluene	100
F	Straight-chain paraffins (C <sub>12</sub> to C <sub>18</sub> ) 1-Methylnaphthalene	80 20

NOTE      Liquids B, C and D simulate petroleum-derived fuels without oxygen compounds. Liquid F is intended to simulate diesel fuel, domestic heating oils and similar light furnace oils.