

SLOVENSKI STANDARD

SIST EN 3456:2012

01-oktober-2012

Nadomešča:

SIST EN 3456:2010

Aeronavtika - Titanova zlitina TI-P64001 (Ti-6Al-4V) - Žarjena - Pločevina in trakovi, vroče valjani - $a \leq 6$ mm

Aerospace series - Titanium alloy TI-P64001 (Ti-6Al-4V) - Annealed - Sheet and strip, hot rolled - $a \leq 6$ mm

Luft- und Raumfahrt - Titanlegierung TI-P64001 (Ti-6Al-4V) - Geglüht - Bleche und Bänder, warmgewalzt - $a \leq 6$ mm

Série aérospatiale - Alliage de titane TI-P64001 (Ti-6Al-4V) - Recuit - Tôles et bandes, laminées à chaud - $a \leq 6$ mm

Ta slovenski standard je istoveten z: EN 3456:2012

ICS:

49.025.30 Titan

Titanium

SIST EN 3456:2012

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 3456:2012

<https://standards.iteh.ai/catalog/standards/sist/f9a6ab97-151b-4e62-a64d-f321d55b6933/sist-en-3456-2012>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 3456

July 2012

ICS 49.025.30

Supersedes EN 3456:2009

English Version

**Aerospace series - Titanium alloy TI-P64001 (Ti-6Al-4V) -
Annealed - Sheet and strip, hot rolled - $a \leq 6$ mm**

Série aérospatiale - Alliage de titane TI-P64001 (Ti-6Al-4V)
- Recuit - Tôles et bandes, laminées à chaud - $a \leq 6$ mm

Luft- und Raumfahrt - Titanlegierung TI-P64001 (Ti-6Al-4V)
- Geglüht - Bleche und Bänder, warmgewalzt - $a \leq 6$ mm

This European Standard was approved by CEN on 23 March 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

SIST EN 3456:2012

<https://standards.iteh.ai/catalog/standards/sist/9a6ab97-151b-4e62-a64d-f321d55b6933/sist-en-3456-2012>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword	3
Introduction	4
1 Scope	4
2 Normative references	4

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

SIST EN 3456:2012

<https://standards.iteh.ai/catalog/standards/sist/f9a6ab97-151b-4e62-a64d-f321d55b6933/sist-en-3456-2012>

Foreword

This document (EN 3456:2012) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2013, and conflicting national standards shall be withdrawn at the latest by January 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 3456:2009.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

(standards.iteh.ai)

SIST EN 3456:2012

<https://standards.iteh.ai/catalog/standards/sist/9a6ab97-151b-4e62-a64d-f321d55b6933/sist-en-3456-2012>

Introduction

This document is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-004.

1 Scope

This European Standard specifies the requirements relating to:

Titanium alloy Ti-P64001 (Ti-6Al-4V)
Annealed
Sheet and strip, hot rolled
 $a \leq 6 \text{ mm}$

for aerospace applications.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2002-8, *Aerospace series — Metallic materials — Test methods — Part 8: Micrographic determination of grain size* ¹⁾

SIST EN 3456:2012

<https://standards.iteh.ai/catalog/standards/sist/9a6ab97-151b-4e62-a64d-69338c6c3456/en-2002-8>

EN 2032-2, *Aerospace series — Metallic materials — Part 2: Coding of metallurgical condition in delivery condition*

EN 2338, *Aerospace series — Sheets, hot rolled in titanium and titanium alloys — Thickness $0,8 \text{ mm} \leq a \leq 6 \text{ mm}$ — Dimensions*

EN 3114-004, *Aerospace series — Test method — Microstructure of $(\alpha + \beta)$ titanium alloy wrought products — Part 004: Microstructure of sheet for superplastic forming*

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*

EN 4500-004, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 004: Specific rules for titanium and titanium alloys* ¹⁾

EN 4800-001, *Aerospace series — Titanium and titanium alloys — Technical specification — Part 001: Plate, sheet and strip*

¹⁾ Published as ASD-STAN Prestandard at the date of publication of this standard by Aerospace and Defence Industries Association of Europe-Standardization (ASD-STAN), (www.asd-stan.org).

1	Material designation		Titanium alloy Ti-P64001 (Ti-6Al-4V)										
2	Chemical composition %	Element	Al	V	O+2N	N	H	Fe	C	Y	Others		Ti
		min.	5,50	3,50	–	–	–	–	–	–	–	–	Base
		max.	6,75	4,50	0,25	0,03	0,012 5	0,30	0,08	0,005 0	0,10	0,40	
3	Method of melting		See EN 4800-001.										
4.1	Form		Sheet and strip										
4.2	Method of production		Hot rolled										
4.3	Limit dimension(s)	mm	$a \leq 6$										
5	Technical specification		EN 4800-001 - EN 2338										

6.1	Delivery condition	Annealed											
	Heat treatment	$700\text{ }^{\circ}\text{C} \leq \theta \leq 840\text{ }^{\circ}\text{C} / t \geq 30\text{ min} / \text{AC in inert atmosphere}$											
6.2	Delivery condition code	U ^a											
7	Use condition	Delivery condition											
	Heat treatment	—											

iTeh STANDARD PREVIEW
Characteristics
(standards.iteh.ai)

8.1	Test sample(s)			See EN 4800-001.		
8.2	Test piece(s)			SIST EN 3456:2012 See EN 4800-001.		
8.3	Heat treatment			Use condition		
9	Dimensions concerned	mm	$a \leq 5$		$5 < a \leq 6$	
10	Thickness of cladding on each face	%	—			
11	Direction of test piece			See EN 4800-001.		
12	Temperature	θ	°C	Ambient		
13	Proof stress	$R_{p0,2}$	MPa	≥ 870		
14	T Strength	R_m	MPa	$920 \leq R_m \leq 1\ 180$		
15	Elongation	A	%	$A_{50\text{ mm}} \geq 8$		
16	Reduction of area	Z	%	—		
17	Hardness			—		
18	Shear strength	R_c	MPa	—		
19	Bending	k	—	$5; \alpha = 105^\circ$		—
20	Impact strength			—		
21	Temperature	θ	°C	—		
22	Time		h	—		
23	Stress	σ_a	MPa	—		
24	Elongation	a	%	—		
25	Rupture stress	σ_R	MPa	—		
26	Elongation at rupture	A	%	—		
27	Notes (see line 98)			a		

