

INTERNATIONAL
STANDARD

ISO
105-A05

First edition
1996-04-01

**Textiles — Tests for colour fastness —
Part A05:**

Instrumental assessment of change in colour
for determination of grey scale rating

ISO 105-A05:1996
Textiles — Essais de solidité des teintures —
Partie A05: Évaluation instrumentale de la dégradation pour la
détermination du degré de l'échelle de gris



Reference number
ISO 105-A05:1996(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

(standards.iteh.ai)

International Standard ISO 105-A05 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

[https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-](https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-bd2f352af9ba/iso-105-a05-1996)

ISO 105 was previously published in thirteen "parts", each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections", each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Textiles — Tests for colour fastness —

Part A05:

Instrumental assessment of change in colour for determination of grey scale rating

1 Scope

This part of ISO 105 specifies an instrumental method for assessing the change in colour of a test specimen in comparison to an identical untreated reference, and the calculations undertaken to convert the instrumental measurements into a grey scale rating.

This method is intended as an alternative to the many national methods for visual evaluation of the effect of a colour fastness test on any textile material.

NOTE 1 There may be a difference between instrumental and visual assessments of specimens due to fluorescence, and/or other factors.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 105. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 105 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 105-J03:1995, *Textiles — Tests for colour fastness — Part J03: Calculation of colour differences*.

CIE Publication No. 5.2, *Colorimetry*, 2nd ed., 1986.¹⁾

3 Principle

The colour of the specimen which has been subjected to the colour fastness test and the colour of an identical untreated specimen are measured instrumentally. The CIELAB coordinates for lightness L^* , chroma C_{ab}^* and hue h_{ab} are determined for both specimens, and the CIELAB differences ΔL^* , ΔC_{ab}^* and ΔH_{ab}^* are calculated and converted to a grey scale rating by means of a series of equations.

1) Available from the CIE Central Bureau, Kegelgasse 27, A-1030 Vienna, Austria.

4 Apparatus

4.1 Spectrophotometer or colorimeter, meeting any one of the illuminating and viewing conditions for reflecting specimens as described in CIE Publication 15.2, subclause 1.4.

5 Test specimen

Choose a representative sample of material which has been subjected to a colour fastness test, of adequate size to fit the sample holder of the instrument used and having no visible defects. Back a single layer of the test specimen with an opaque white material containing no fluorescent whitening agents (FWA). Both the test specimen and the untreated reference shall be backed in an identical manner.

NOTE 2 Alternatively, back the test specimen with a number of thicknesses of the identical untreated material sufficient to give an acceptably opaque specimen.

6 Test procedure

6.1 From the untreated material, prepare a reference consisting of the same number of thicknesses of material as that used to prepare the test specimen (see clause 5). Mount the reference in the sample holder and measure its colour values with the instrument (see 4.1). From the instrument system, obtain CIE tristimulus values using CIE illuminant D65 and 10° observer. Calculate the CIELAB L^* , C_{ab}^* and h_{ab} values using the data obtained, as specified in ISO 105-J03.

NOTE 3 Permitted illuminant/observer alternatives for colorimetric calculations are: D65/2°; C/2°; C/10°.

6.2 Measure the colour of the specimen (see clause 5) in the same manner and calculate the CIELAB L^* , C_{ab}^* and h_{ab} values.

ISO 105-A05:1996

[https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-](https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-bd2f352af9ba/iso-105-a05-1996)

7 Calculation of change in colour [bd2f352af9ba/iso-105-a05-1996](https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-bd2f352af9ba/iso-105-a05-1996)

7.1 Calculate the differences in lightness ΔL^* , chroma ΔC_{ab}^* and hue ΔH_{ab}^* between the reference and specimen from the data obtained in clause 6.

7.2 Calculate the change in colour ΔE_F using the following equations, where:

the subscripts S and R refer to test Specimen and Reference respectively;

the subscript N is used to indicate functions of the means of the values of the specimen and reference;

the subscript K is used to indicate corrected hue and chroma functions;

the subscript F is used to indicate special colorimetric values, to distinguish them from the CIELAB colorimetric values in common usage.

$$\Delta E_F = [(\Delta L^*)^2 + (\Delta C_F)^2 + (\Delta H_F)^2]^{1/2}$$

$$\Delta H_F = \Delta H_K / [1 + (10C_M / 1\ 000)^2]$$

$$\Delta C_F = \Delta C_K / [1 + (20C_M / 1\ 000)^2]$$

$$\Delta H_K = \Delta H_{ab}^* - D$$

$$\Delta C_K = \Delta C_{ab}^* - D$$

$$D = (\Delta C_{ab}^* \cdot C_M \cdot e^{-x}) / 100$$

$$C_M = (C_{ab,S}^* + C_{ab,R}^*)/2$$

$$x = [(h_M - 280)/30]^2 \text{ if } |h_M - 280| \leq 180$$

$$x = [(360 - |h_M - 280|)/30]^2 \text{ if } |h_M - 280| > 180$$

$$h_M = (h_{ab,S} + h_{ab,R})/2 \text{ if } |h_{ab,S} - h_{ab,R}| \leq 180$$

$$h_M = (h_{ab,S} + h_{ab,R})/2 + 180 \text{ if } |h_{ab,S} - h_{ab,R}| > 180 \text{ and } |h_{ab,S} + h_{ab,R}| < 360$$

$$h_M = (h_{ab,S} + h_{ab,R})/2 - 180 \text{ if } |h_{ab,S} - h_{ab,R}| > 180 \text{ and } |h_{ab,S} + h_{ab,R}| \geq 360$$

L_S^* , $C_{ab,S}^*$, $h_{ab,S}$ = lightness, chroma and hue of Specimen

L_R^* , $C_{ab,R}^*$, $h_{ab,R}$ = lightness, chroma and hue of Reference

ΔL^* , ΔC_{ab}^* and ΔH_{ab}^* are calculated in accordance with ISO 105-J03:1995, subclause 3.2.

8 Determination of grey scale rating for colour change

Using ΔE_F calculated in 7.2, determine the grey scale rating for colour change (GS_C), expressed to the nearest half-point (e.g. 5; 4,5; 4; etc.), either from table 1 or from equation (1) or equation (2).

NOTE 4 Use of equation (1) or equation (2) produces a continuous function, yielding a decimal value of GS_C compared to the stepwise value obtained from table 1.

$$GS = 5 - [\Delta E_F/1,7] \text{ if } \Delta E_F \leq 3,4 \quad \dots (1)$$

$$GS = 5 - [\log_{10}(\Delta E_F/0,85)/\log_2 2] \text{ if } \Delta E_F > 3,4 \quad \dots (2)$$

Table 1

Range of ΔE_F	GS_C
< 0,40	5
$0,40 \leq \Delta E_F < 1,25$	4,5
$1,25 \leq \Delta E_F < 2,10$	4
$2,10 \leq \Delta E_F < 2,95$	3,5
$2,95 \leq \Delta E_F < 4,10$	3
$4,10 \leq \Delta E_F < 5,80$	2,5
$5,80 \leq \Delta E_F < 8,20$	2
$8,20 \leq \Delta E_F < 11,60$	1,5
$\geq 11,60$	1

9 Test report

The test report shall contain at least the following information:

- a) the number and year of publication of this part of ISO 105, i.e. ISO 105-A05:1996;
- b) all details necessary for complete identification of the specimen(s) tested;
- c) identification of the spectrophotometer or colorimeter used, including the CIE geometry type;
- d) test conditions, including illuminant and observer used;
- e) grey scale rating GS_C determined for each test specimen, expressed to the nearest half-point (e.g. 5; 4,5; 4; etc.);
- f) date of the test.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 105-A05:1996](https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-bd2f352af9ba/iso-105-a05-1996)

<https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-bd2f352af9ba/iso-105-a05-1996>

iTeh STANDARD PREVIEW
This page intentionally left blank
(standards.iteh.ai)

ISO 105-A05:1996

<https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-bd2f352af9ba/iso-105-a05-1996>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 105-A05:1996

<https://standards.iteh.ai/catalog/standards/sist/d34bfe4-b378-43b2-a121-bd2f352af9ba/iso-105-a05-1996>

ICS 59.080.10

Descriptors: textiles, dyes, colour fastness, tests, colour-fastness tests, determination, colour differences, grey scale.

Price based on 4 pages
