

SLOVENSKI STANDARD
kSIST FprEN 12165:2015

01-december-2015

Baker in bakrove zlitine - Palice (lite in izstiskane) za izkovke

Copper and copper alloys - Wrought and unwrought forging stock

Kupfer und Kupferlegierungen - Vormaterial für Schmiedestücke

Ta slovenski standard je istoveten z: FprEN 12165

ICS:

77.150.30 Bakreni izdelki Copper products

kSIST FprEN 12165:2015 en,fr,de

**EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM**

**FINAL DRAFT
FprEN 12165**

October 2015

ICS 77.150.30

Will supersede EN 12165:2011

English Version

**Copper and copper alloys - Wrought and unwrought
forging stock**

Kupfer und Kupferlegierungen - Vormaterial für
Schmiedestücke

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 133.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
European foreword.....	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	6
4 Designations.....	7
4.1 Material.....	7
4.1.1 General.....	7
4.1.2 Symbol.....	7
4.1.3 Number	7
4.2 Material condition	7
4.3 Product.....	7
5 Ordering information	9
6 Requirements	10
6.1 Composition	10
6.2 Mechanical properties.....	10
6.3 Resistance to dezincification	10
6.4 Dimensions and tolerances	11
6.4.1 Diameter.....	11
6.4.2 Deviation from circular form.....	11
6.4.3 Length.....	11
6.4.4 Straightness.....	11
6.5 Surface quality.....	11
7 Sampling.....	11
7.1 General.....	11
7.2 Analysis.....	11
7.3 Hardness and dezincification resistance tests	12
8 Test methods	12
8.1 Analysis.....	12
8.2 Hardness test	12
8.2.1 General.....	12
8.2.2 Preparation of samples.....	12
8.2.3 Procedure for testing.....	12
8.3 Dezincification resistance test	12
8.4 Retests for analysis, hardness and dezincification resistance	12
8.5 Rounding of results	13
9 Declaration of conformity and inspection documentation.....	13
9.1 Declaration of conformity	13
9.2 Inspection documentation.....	13
10 Marking, packaging, labelling.....	13
Bibliography.....	28

Tables

Table 1 — Composition of copper	14
Table 2 — Composition of low alloyed copper alloys	15
Table 3 — Composition of copper-aluminium alloys.....	16
Table 4 — Composition of copper-nickel alloys	17
Table 5 — Composition of copper-nickel-zinc alloys.....	17
Table 6 — Composition of copper-zinc alloys.....	18
Table 7 — Composition of copper-zinc-lead alloys	19
Table 8 — Composition of complex copper-zinc alloys.....	21
Table 9 — Mechanical properties of round forging stock of copper	23
Table 10 — Mechanical properties of round forging stock of low alloyed copper alloys.....	23
Table 11 — Mechanical properties of round forging stock of copper-aluminium alloys	24
Table 12 — Mechanical properties of round forging stock of copper-nickel alloys	24
Table 13 — Mechanical properties of round forging stock of copper-nickel-zinc alloys	24
Table 14 — Mechanical properties of round forging stock of copper-zinc alloys	25
Table 15 — Mechanical properties of round forging stock of copper-zinc-lead alloys.....	25
Table 16 — Mechanical properties of round forging stock of complex copper-zinc alloys	26
Table 17 — Tolerances on diameter of round forging stock.....	27
Table 18 — Tolerances on straightness of round forging stock	27
Table 19 — Sampling rate.....	27

European foreword

This document (FprEN 12165:2015) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 12165:2011.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 4 "Extruded and drawn products, forgings and scrap" to revise the following standard:

- EN 12165:2011, *Copper and copper alloys — Wrought and unwrought forging stock*.

This document is one of a series of European Standards for the copper and copper alloy products rod, wire, profile and forgings. Other products are specified as follows:

- EN 12163, *Copper and copper alloys — Rod for general purposes*;
- EN 12164, *Copper and copper alloys — Rod for free machining purposes*;
- EN 12166, *Copper and copper alloys — Wire for general purposes*;
- EN 12167, *Copper and copper alloys — Profiles and bars for general purposes*;
- EN 12168, *Copper and copper alloys — Hollow rod for free machining purposes*;
- EN 12420, *Copper and copper alloys — Forgings*;
- EN 13601, *Copper and copper alloys — Copper rod, bar and wire for general electrical purposes*;
- EN 13602, *Copper and copper alloys — Drawn round copper wire for the manufacture of electrical conductors*;
- EN 13605, *Copper and copper alloys — Copper profiles and profiled wires for electrical purposes*.

In comparison with EN 12165:2011, the following significant technical changes were made:

- a) addition of three new materials: CuZn35Pb1,5AlAs (CW625N), CuZn33Pb1,5AlAs (CW626N) and CuZn33Pb1AlSiAs (CW725R) due to the market requirements on restriction of lead and modification of the chemical composition for CuZn39Pb1 (CW611N);
- b) introduction of an optional procedure how to refer to restrictions to the chemical composition imposed by the 4 MS Common Composition List for materials used for products accepted for contact with drinking water;
- c) requirements and test methods for resistance of dezincification modified;
- d) provisions for surface quality added;
- e) mechanical properties for CuZn21Si3P (CW724R) modified.