

SLOVENSKI STANDARD SIST EN 1608:2013

01-julij-2013

Nadomešča: SIST EN 1608:1997 SIST EN 1608:1997/AC:1999

Toplotnoizolacijski proizvodi za uporabo v gradbeništvu - Ugotavljanje natezne trdnosti v smeri dolžine

Thermal insulating products for building applications - Determination of tensile strength parallel to faces

iTeh STANDARD PREVIEW

Wärmedämmstoffe für das Bauwesen - Bestimmung der Zugfestigkeit in Plattenebene

Produits isolants thermiques destinés aux applications du bâtiment - Détermination de la résistance à la traction parallèlement aux faces

Ta slovenski standard je istoveten z: EN 1608:2013

ICS:

91.100.60 Materiali za toplotno in zvočno izolacijo

Thermal and sound insulating materials

SIST EN 1608:2013

en,fr,de



iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 1608:2013 https://standards.iteh.ai/catalog/standards/sist/7ba9e45b-6c99-4086-8736-412a5b6940ed/sist-en-1608-2013

SIST EN 1608:2013

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 1608

March 2013

ICS 91.100.60

Supersedes EN 1608:1996

English Version

Thermal insulating products for building applications -Determination of tensile strength parallel to faces

Produits isolants thermiques destinés aux applications du bâtiment - Détermination de la résistance à la traction parallèlement aux faces Wärmedämmstoffe für das Bauwesen - Bestimmung der Zugfestigkeit in Plattenebene

This European Standard was approved by CEN on 15 December 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

https://standards.iteh.ai/catalog/standards/sist/7ba9e45b-6c99-4086-8736-412a5b6940ed/sist-en-1608-2013



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

SIST EN 1608:2013

EN 1608:2013 (E)

Contents

Foreword3		.3
1	Scope	.5
2	Normative references	5
3	Terms and definitions	5
4	Principle	5
5	Apparatus	5
6	Test specimens	6
7	Procedure	.7
8	Calculation and expression of results	8
9	Accuracy of measurement	.8
10	Test report	9

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 1608:2013 https://standards.iteh.ai/catalog/standards/sist/7ba9e45b-6c99-4086-8736-412a5b6940ed/sist-en-1608-2013

Foreword

This document (EN 1608:2013) has been prepared by Technical Committee CEN/TC 88 "Thermal insulating materials and products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2013, and conflicting national standards shall be withdrawn at the latest by September 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1608:1996.

The revision of this standard contains no major changes, only minor corrections and clarifications of an editorial nature.

This European Standard is one of a series of standards which specify test methods for determining dimensions and properties of thermal insulating materials and products. It supports a series of product standards for thermal insulating materials and products which derive from the Council Directive of 21 December 1988 on the approximation of laws, regulations and administrative provisions of the Member States relating to construction products (Directive 89/106/EEC) through the consideration of the essential requirements.

This European Standard has been drafted for applications in building, but it may also be used in other areas where it is relevant.

https://standards.iteh.ai/catalog/standards/sist/7ba9e45b-6c99-4086-8736-

This European test standard is one of the following group of interrelated standards on test methods for determining dimensions and properties of thermal insulation materials and products, all of which fall within the scope of CEN/TC 88:

- EN 822, Thermal insulating products for building applications Determination of length and width
- EN 823, Thermal insulating products for building applications Determination of thickness
- EN 824, Thermal insulating products for building applications Determination of squareness
- EN 825, Thermal insulating products for building applications Determination of flatness
- EN 826, Thermal insulating products for building applications Determination of compression behaviour
- EN 1602, Thermal insulating products for building applications Determination of the apparent density
- EN 1603, Thermal insulating products for building applications Determination of dimensional stability under constant normal laboratory conditions (23 °C/50 % relative humidity)
- EN 1604, Thermal insulating products for building applications Determination of dimensional stability under specified temperature and humidity conditions
- EN 1605, Thermal insulating products for building applications Determination of deformation under specified compressive load and temperature conditions
- EN 1606, Thermal insulating products for building applications Determination of compressive creep

- EN 1607, Thermal insulating products for building applications Determination of tensile strength perpendicular to faces
- EN 1608, Thermal insulating products for building applications Determination of tensile strength parallel to faces
- EN 1609, Thermal insulating products for building applications Determination of short-term water absorption by partial immersion
- EN 12085, Thermal insulating products for building applications Determination of linear dimensions of test specimens
- EN 12086, Thermal insulating products for building applications Determination of water vapour transmission properties
- EN 12087, Thermal insulating products for building applications Determination of long-term water absorption by immersion
- EN 12088, Thermal insulating products for building applications Determination of long-term water absorption by diffusion
- EN 12089, Thermal insulating products for building applications Determination of bending behaviour
- EN 12090, Thermal insulating products for building applications Determination of shear behaviour
- EN 12091, Thermal insulating products for building applications Determination of freeze-thaw (standards.iteh.ai)
- EN 12429, Thermal insulating products for building applications Conditioning to moisture equilibrium under specified temperature and humidity conditions <u>1608:2013</u> https://standards.iteh.ai/catalog/standards/sist/7ba9e45b-6c99-4086-8736-
- EN 12430, Thermal insulating products⁴ for 5 building sapplications¹³ Determination of behaviour under point load
- EN 12431, Thermal insulating products for building applications Determination of thickness for floating floor insulating products
- EN 13793, Thermal insulating products for building applications Determination of behaviour under cyclic loading
- EN 13820, Thermal insulating materials for building applications Determination of organic content

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the equipment and procedures for determining the tensile strength of a product parallel to its faces. It is applicable to thermal insulating products.

This European Standard can be used to determine whether the product has sufficient strength to withstand stresses during transportation and application.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 823, Thermal insulating products for building applications — Determination of thickness

EN 12085, Thermal insulating products for building applications — Determination of linear dimensions of test specimens

ISO 5725-1, Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions

ISO 5725-2, Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method

(standards.iteh.ai)

3 Terms and definitions

SIST EN 1608:2013

For the purposes of this document, the following term and definition applies.

3.1

tensile strength parallel to faces

 $\sigma_{\rm t}$

maximum recorded tensile force parallel to the product faces during the pulling operation, divided by the cross-sectional testing area of the test specimen

4 Principle

A test specimen is attached to two clamps which are fastened in a tensile testing machine and pulled apart at a given speed.

The maximum tensile force is recorded and the tensile strength of the test specimen is calculated.

5 Apparatus

5.1 Tensile testing machine, appropriate for the range of force and displacement involved, capable of having a constant crosshead speed adjusted to (10 ± 1) mm/min and capable of measuring the force to an accuracy of ± 1 %.

5.2 Two clamps, designed so as to avoid failure of the test specimen in the area of the clamps.

The clamps shall be positioned so that the tensile stress is uniformly distributed during the test.

An example of suitable equipment is shown in Figure 1.

Any test equipment or method which provides the same result with at least the same accuracy may be used.

6 Test specimens

6.1 Dimensions of test specimens

The thickness of the test specimens shall be the original product thickness including any skins, facings, and/or coatings. The test specimens shall be cut with the shape and with the dimensions shown in Figure 2. For small products or because of equipment limitations, the test specimen length and width shall be adjusted proportionally, but with a minimum length of 500 mm.

Other specimen shapes which provide the same result to at least the same accuracy may be used.

6.2 Number of test specimens

The number of test specimens shall be as specified in the relevant product standard. If the number is not specified, then at least three test specimens shall be used.

In the absence of a product standard or any other European Technical Specification, the number of test specimens may be agreed between parties.



Figure 1 — Example of suitable clamps

6.3 Preparation of test specimens

The test specimens shall be cut from the full size product so that the length direction corresponds to the direction in which the tensile force is applied to the product in its application.

Test specimens shall be prepared by methods that do not change the original structure of the product.

Special methods of preparation, when needed, are given in the relevant product standard or any other European Technical Specification.

6.4 Conditioning of test specimens

The test specimens shall be conditioned for at least 6 h at (23 ± 5) °C. In case of dispute, they shall be conditioned at (23 ± 2) °C and (50 ± 5) % relative humidity for the time stated in the relevant product standard.

7 Procedure

7.1 Test conditions

Testing shall be carried out at (23 ± 5) °C. In case of dispute, it shall be carried out at (23 ± 2) °C and (50 ± 5) % relative humidity.

7.2 Test procedure

Measure the thickness of the testing area, d, to the nearest millimetre, in accordance with EN 823.

Measure the length of the test specimen, *l*, and the width of the testing area, *b*, to the nearest millimetre, in accordance with EN 12085 ch STANDARD PREVIEW

Attach the test specimen centrally between two clamps to distribute the stress uniformly. Place it carefully in the tensile testing machine and increase the tensile force with a constant speed of the crosshead (see 5.1) until failure occurs.

SIST EN 1608:2013

Record the maximum tensile force the kilonewtons lards/sist/7ba9e45b-6c99-4086-8736-

412a5b6940ed/sist-en-1608-2013

Note the way in which the product failed. Discard any test specimens that failed outside the testing area (see Figure 2).