
**Paper, board and pulps — Measurement
of diffuse blue reflectance factor —**

Part 2:
**Outdoor daylight conditions
(D65 brightness)**

iTeh STANDARD PREVIEW
(standards.iteh.ai)
*Papier, carton et pâtes — Mesurage du facteur de réflectance diffuse
dans le bleu —*
*Partie 2: Conditions de lumière du jour extérieure (degré de blancheur
D65)*

[ISO 2470-2:2008](https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2470-2:2008

<https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle.....	3
5 Apparatus	3
6 Sampling and conditioning	4
7 Preparation of test pieces.....	4
8 Procedure	4
9 Expression of results	5
10 Precision.....	5
11 Test report	5
Annex A (normative) Spectral characteristics of instruments for measuring D65 brightness	6
Bibliography	8

[ISO 2470-2:2008](https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008)
<https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2470-2 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

ISO 2470 consists of the following parts, under the general title *Paper, board and pulps — Measurement of diffuse blue reflectance factor*:

— *Part 1: Indoor daylight conditions (ISO brightness)*

— *Part 2: Outdoor daylight conditions (D65 brightness)*

ISO 2470-2:2008
<https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008>

Introduction

The reflectance factor (radiance factor) depends on the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This part of ISO 2470 should therefore be read in conjunction with ISO 2469, which defines the geometric characteristics of the instrument and also defines the photometric calibration procedure to be adopted.

The radiance factor of fluorescent materials, for which this property is most interesting, is also dependent on the ultraviolet (UV content) of the illumination falling upon the sample. This part of ISO 2470 should therefore be read in conjunction with ISO 11475, which describes the procedure for adjusting the UV content in this type of instrument to match the CIE standard illuminant D65.

It is important to ensure that the property defined in this part of ISO 2470 is not confused with the property known as ISO brightness, which is determined under conditions corresponding to the CIE-illuminant C, where the UV content is much lower, approximating UV levels encountered in indoor viewing conditions.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 2470-2:2008](https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2470-2:2008

<https://standards.iteh.ai/catalog/standards/sist/ae81057e-bac6-4377-8caf-88a172d4ed61/iso-2470-2-2008>

Paper, board and pulps — Measurement of diffuse blue reflectance factor —

Part 2: Outdoor daylight conditions (D65 brightness)

1 Scope

This part of ISO 2470 specifies a method for measuring the D65 brightness of pulps, papers and boards.

This part of ISO 2470 is limited in its scope to white and near-white pulps, papers and boards, particularly those exhibiting fluorescence which promotes the appearance of whiteness. The measurement can only be made in an instrument in which the ultraviolet energy level of the illumination has been adjusted to correspond to the CIE standard illuminant D65 using a fluorescent reference standard.

The source employed in this part of ISO 2470 excites almost twice as much fluorescence as the illuminant in ISO 2470-1. Consequently, this part of ISO 2470 is better suited for measuring the fluorescent contribution to the brightness. However, D65 brightness should not be confused with ISO brightness which closely approximates the brightness of papers viewed under indoor conditions.

NOTE The property called ISO brightness is measured with an instrument adjusted to a much lower UV content than that specified in this part of ISO 2470. The measurement of ISO brightness is described in ISO 2470-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469:2007, *Paper, board and pulps — Measurement of diffuse radiance factor*

ISO 3688, *Pulps — Preparation of laboratory sheets for the measurement of diffuse blue reflectance factor (ISO brightness)*

ISO 7213, *Pulps — Sampling for testing*

ISO 11475:2004, *Paper and board — Determination of CIE whiteness, D65/10° (outdoor daylight)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 radiance factor

β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone with its apex at the surface element to that of the perfect reflecting diffuser under the same conditions of illumination

NOTE For fluorescent (luminescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_S , and the luminescent radiance factor, β_L , so that:

$$\beta = \beta_S + \beta_L$$

For non-fluorescent materials, the reflected radiance factor, β_S , is numerically equal to the reflectance factor R .

3.2 diffuse radiance [reflectance] factor

R

ratio of the radiation reflected and emitted from a body to that reflected from the perfect reflecting diffuser under the same conditions of diffuse illumination and normal detection

NOTE 1 The ratio is often expressed as a percentage.

NOTE 2 The diffuse radiance [reflectance] factor is influenced by the backing if the body is translucent.

NOTE 3 This part of ISO 2470 prescribes diffuse illumination and normal detection in an instrument calibrated in accordance with the provisions of this part of ISO 2470.

3.3 intrinsic radiance [reflectance] factor

R_∞

diffuse radiance [reflectance] factor of a layer or pad of material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance [reflectance] factor

NOTE The radiance [reflectance] factor of a single non-opaque sheet is dependent on the background and is not a material property.

3.4 D65 brightness

$R_{457,D65}$

intrinsic radiance [reflectance] factor measured with a reflectometer having the characteristics described in ISO 2469, equipped with a filter or corresponding function having an effective wavelength of 457 nm and a half-peak bandwidth of 44 nm, and adjusted so that the UV content of the irradiation incident upon the test piece corresponds to that of the CIE standard illuminant D65

NOTE The filter function is described more fully by the weighting function factors given in Annex A and Table A.1.

4 Principle

A test piece is illuminated diffusely in a standard instrument and the light reflected normal to the surface is either allowed to pass through a defined optical filter and then measured by a photodetector or measured by an array of photosensitive diodes, where each diode responds to a different effective wavelength. The brightness is then determined directly from the output from the photodetector or by calculation from the photosensitive diode outputs using the appropriate weighting function.

5 Apparatus

5.1 Reflectometer, having the geometric, spectral and photometric characteristics described in ISO 2469 and calibrated in accordance with the provisions of ISO 2469, and equipped for the measurement of blue reflectance factor as defined in Annex A.

5.1.1 In the case of a filter reflectometer, the radiation falling upon the test piece shall have a UV content corresponding to that of the CIE standard illuminant D65, adjusted or verified by the help of the fluorescent reference standard (5.2.2).

5.1.2 In the case of an abridged spectrophotometer, the instrument shall have a UV-adjustable filter with a cut-off wavelength of 395 nm or some other system for adjustment and control, and this filter shall be adjusted or the system shall be calibrated with the help of the fluorescence reference standard (5.2.2), so that the UV content of the illumination falling upon the sample corresponds to that of the CIE standard illuminant D65.

5.2 Reference standards for calibration of the instrument and the working standards, to be used sufficiently frequently to ensure satisfactory calibration and UV adjustment.

5.2.1 Non-fluorescent reference standard for photometric calibration, issued by an ISO/TC 6 authorized laboratory in accordance with the provisions of ISO 2469.

5.2.2 Fluorescent reference standard for use in adjusting the UV content of the radiation incident upon the sample, having a CIE whiteness (D65/10°) value assigned by an ISO/TC6 authorized laboratory as prescribed in ISO 11475:2004, Annex B.

NOTE Greater precision in the D65 brightness measurement would be attained if a fluorescent reference standard having an assigned D65 brightness value were used. It is, however, important for the industry to have only one UV-filter adjustment for all measurements under CIE standard illuminant D65 conditions. For this reason, a reference standard having an assigned CIE whiteness (D65/10°) value as prescribed in ISO 11475 is preferred.

5.3 Working standards, as follows.

5.3.1 Two plates of flat opal glass, ceramic or other suitable non-fluorescent material, cleaned and calibrated as described in ISO 2469.

NOTE In some instruments, the function of the primary working standard may be taken over by a built-in internal standard.

5.3.2 Stable plastic or other tablet, incorporating a fluorescent whitening agent.

5.4 Black cavity, having a reflectance factor which does not differ from its nominal value by more than 0,2 %, at all wavelengths. The black cavity should be stored upside down in a dust-free environment or with a protective cover.

NOTE The condition of the black cavity can be checked by reference to the instrument maker.