

SLOVENSKI STANDARD oSIST prEN 10210-2:2018

01-oktober-2018

Vroče izdelani votli konstrukcijski profili iz jekla - 2. del: Mere, mejni odstopki in značilnosti profilov

Hot finished structural steel hollow sections - Part 2: Tolerances, dimensions and sectional properties

Warmgefertigte Hohlprofile für den Stahlbau - Teil 2: Grenzabmaße, Masse und statische Werte

Profils creux de construction finis à chaud en aciers - Partie 2 : Tolérances, dimensions et caractéristiques du profil

Ta slovenski standard je istoveten z: prEN 10210-2

https://standards.iteh.ai/catalog/standards/sist/e7ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019

ICS:

77.140.45Nelegirana jekla77.140.70Jekleni profili

Non-alloyed steels Steel profiles

oSIST prEN 10210-2:2018

en,fr,de



iTeh Standards (https://standards.iteh.ai) Document Preview

SIST EN 10210-2:2019

https://standards.iteh.ai/catalog/standards/sist/e7ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019



EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

DRAFT prEN 10210-2

August 2018

ICS 77.140.75

Will supersede EN 10210-2:2006

English Version

Hot finished steel structural hollow sections - Part 2: Tolerances, dimensions and sectional properties

Profils creux de construction finis à chaud en aciers -Partie 3 : Tolérances, dimensions et caractéristiques du profil Warmgefertigte Hohlprofile für den Stahlbau - Teil 3: Grenzabmaße, Maße und statische Werte

This draft European Standard is submitted to CEN members for second enquiry. It has been drawn up by the Technical Committee ECISS/TC 103.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2018 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. prEN 10210-2:2018 E

oSIST prEN 10210-2:2018

prEN 10210-2:2018 (E)

Contents

Page

Europe	ean foreword3
1	Scope
2	Normative references
3	Terms and definitions
4	Symbols
5	Information to be obtained by the manufacturer
6	Tolerances
7	Measurement of size and shape
8	Dimensions and sectional properties
Annex	A (normative) Formulae for the calculation of sectional properties
A.1	General14
A.2	Circular hollow sections
A.3	Rectangular, including square, hollow sections
A.4	Elliptical hollow sections
Annex	B (normative) Sectional properties for a limited range of standard sizes 19

SIST EN 10210-2:2019

https://standards.iteh.ai/catalog/standards/sist/e7ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019

European foreword

This document (prEN 10210-2:2018) has been prepared by Technical Committee ECISS/TC 103 "Structural steels other than reinforcements", the secretariat of which is held by DIN.

This document is currently submitted to the second CEN Enquiry.

This document will supersede EN 10210-2:2006.

This standard consists of the following parts:

- EN 103xx, Steel structural hollow sections General (Characteristics, evaluation of conformity and *marking*) in preparation
- EN 10210-1, Hot finished steel structural hollow sections Part 1: Technical delivery conditions
- EN 10210-2, Hot finished steel structural hollow sections Part 2: Tolerances, dimensions and sectional properties

It forms part of a series of standards on hollow sections together with EN 10219-1 and EN 10219-2.

iTeh Standards (https://standards.iteh.ai) Document Preview

SIST EN 10210-2:2019

https://standards.iteh.ai/catalog/standards/sist/e7ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019

prEN 10210-2:2018 (E)

1 Scope

This part of this European standard specifies tolerances for hot finished circular, square, rectangular and elliptical structural hollow sections, manufactured in wall thicknesses up to 120 mm, in the following size ranges:

- Circular: Outside diameters up to 2 500 mm;
- Square: Outside dimensions up to 800 mm × 800 mm;
- Rectangular: Outside dimensions up to 750 mm × 500 mm;
- Elliptical: Outside dimensions up to 500 mm × 250 mm.

The formulae for calculating sectional properties of sections manufactured to the dimensional tolerances of this standard, to be used for the purposes of structural design, are given in Annex A.

Dimensions and sectional properties for a limited range covering the more common sizes are given in Annex B.

NOTE The designation of the sections' major axis (yy) and its minor axis (zz) align with the axis designation used for structural design in the structural Eurocodes.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10210-1:2006, Hot finished structural hollow sections of non-alloy and fine grain steels — Part 1: Technical delivery conditions

3 Terms and definitions

SIST EN 10210-2:2019

https://standards.iteh.ai/catalog/standards/sist/e7ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019 For the purposes of this document, the terms and definitions given in EN 10210-1 apply.

4 Symbols

For the purposes of this document, the symbols defined in Table 1 apply.

Symbol	Unit	Definition
Α	cm ²	Cross-sectional area
$A_{ m m}$	mm ²	Area of the surface delimited by the perimeter at mid- thickness
As	m²/m	Superficial area per metre length
В	mm	Specified side dimension of a square hollow section. Specified dimension of the shorter side of a rectangular hollow section. Specified outside dimension of an elliptical section on its minor axis
<i>C</i> ₁ / <i>C</i> ₂	mm	Length of corner region of a square or rectangular hollow section

Table 1 — Symbols and definitions

Symbol	Unit	Definition
Ct	cm ³	Torsional modulus constant
D	mm	Specified outside diameter of a circular hollow section
$D_{\rm max}/D_{\rm min}$	mm	The maximum and minimum outside diameter of a circular hollow section measured in the same plane
е	mm	Deviation from straightness
Н	mm	Specified dimension of the longer side of a rectangular hollow section. Specified outside dimension of an elliptical section on its major axis
I	cm ⁴	Second moment of area
It	cm ⁴	Torsional inertia constant (polar moment of inertia in the case of circular hollow sections only)
i	cm	Radius of gyration
L	mm	Length
М	kg/m	Mass per unit length
0	%	Out-of-roundness
Р	mm Teh S	External perimeter of an elliptical hollow section
R	(httpm://sta	External corner radius of a square or rectangular hollow section
	Tmm cum	Specified thickness
U	mm	Perimeter of an elliptical hollow section at mid-thickness
V	mm <u>SIST E</u>	Total measured twist
/standard viteh.ai/cat	alog/standards/sist/e7ec	Twist measured at one end of a section st-en-10210-2-2019
$W_{ m el}$	cm ³	Elastic section modulus
$W_{ m pl}$	cm ³	Plastic section modulus
<i>x</i> ₁	mm	Concavity of a side of a square or rectangular hollow section
X2	mm	Convexity of a side of a square or rectangular hollow section
уу	_	Axis of cross-section, major axis of a rectangular hollow section
ZZ		Axis of cross-section, minor axis of a rectangular hollow section
θ	0	Angle between adjacent sides of a square or rectangular hollow section

5 Information to be obtained by the manufacturer

5.1 Mandatory information

The following mandatory information from this part of EN 10210 shall be obtained by the manufacturer at the time of enquiry and order:

- a) the dimensions (see Clause 8);
- b) the type of length, length range or length (see Table 3).

NOTE This Information is included in the list of information to be obtained by the manufacturer contained in EN 10210-1:2006, Clause 5.

5.2 Options

Options are specified in this part of EN 10210. In the event that the purchaser does not indicate a wish to implement one of these options at the time of enquiry and order, the manufacturer shall supply in accordance with the basic specification.

Option 2.1 The tolerance on approximate length shall be $^{+150}_{0}$ mm (see Table 3).

- Option 2.2 Tolerance of external corner radius of 2T maximum at each corner.
- Option 2.3 Out-of-roundness tolerances for diameter to thickness ratio exceeding 100 (see Table 2, footnote d).

6 Tolerances

6.1 Tolerances shall not exceed the values given in Table 2 for shape, straightness and mass, Table 3 for manufacturer's delivered length and Table 4 for the height of the internal and external weld bead of submerged arc welded hollow sections.

6.2 The internal corners of square and rectangular hollow sections shall be rounded, except in the case of EW sections for a corner containing the weld, should the weld be located in the corner region.

NOTE The internal corner profile is not specified.

Characteristic	Circular hollow sections	Square and rectangular hollow sections	Elliptical hollow sections	
Outside dimensions (D, B, H)	±1 % with a minimum of ± 0,5 mm and a maximum of ± 10 mm	±1 ª % with a minimum of ± 0,5 mm		
Thickness (T)	- 10 % ^{b c}			
Out-of-roundness (<i>O</i>)	2 % for hollow sections having a diameter to thickness ratio not exceeding 100 ^d	_		
Concavity/Convexity $(x_1, x_2)^{e}$	_	1 %	—	
Squareness of side (θ)		90° ± 1°		
External corner profile $(C_1, C_2 \text{ or } R)^{\text{f}}$		3 <i>T</i> maximum at each corner	—	
Twist (V)		2 mm ª plus 0,	5 mm/m length ^a	
Straightness (e)	0,2 ° % of total length and 3 mm over any 1 m length			
Mass (M)	- 6 %/+ 8 % on individual delivered lengths			
^a For elliptical hollow sections of sizes $H < 250$ mm, the permitted tolerance is twice the value given in this table				

Table 2 — Tolerances on shape, straightness and mass

^b The positive deviation is limited by the tolerance on mass.

^c For seamless sections thicknesses of less than 10 % but not less than 12,5 % of the nominal thickness may occur in smooth transition areas over not more than 25 % of the circumference.

^d When the diameter to thickness ratio exceeds 100, application of tolerance on out-of-roundness is not required, unless specifically agreed (see 5.2).

^e The tolerance on convexity and concavity is independent of the tolerance on outside dimensions.

^f The sides need not be tangential to the corner arcs.

Table 3 — Tolerances on manufacturer's delivered length

Dimensions in millimetres

Type of length ^a	Range of length or length <i>L</i>	Tolerance
Random length	4 000 ≤ <i>L</i> ≤ 16 000 with a range of 2 000 per order item	10 % of sections supplied may be below the minimum for the ordered range but not shorter than 75 % of the minimum range length
Approximate length	$4\ 000 \le L \le 16\ 000$	±500 mm ^b
Exact length	2 000 ≤ <i>L</i> ≤ 6 000 6 000 < <i>L</i> °	⁺¹⁰ ₀ mm ⁺¹⁵ ₀ mm

^a The manufacturer shall establish at the time of enquiry and order the type of length required and the length range or length.

^b Option 3.1 the tolerance on approximate length is $^{+150}_{-0}$ mm.

^c Common lengths available are 6 m and 12 m.

Table 4 — Tolerance on height of internal and external weld seam for submerged arc welded hollow sections

Dimensions in mill			
Thickness, T	Maximum weld bead height		
≤ 14,2 OCUMEI	t Prevl _{3,5} v		
> 14,2	4,8		
> 14,2	4,8		

7 Measurement of size and shape 107ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019

7.1 General

All external dimensions, including out-of-roundness, shall be measured at a distance from the end of the hollow section of not less than D for circular sections, B for square sections or H for rectangular and elliptical sections, with a minimum of 100 mm.

7.2 Outside dimensions

For circular hollow sections the diameter (D) and for elliptical hollow sections the outside dimensions (B and H) shall be measured either directly, e.g. using a calliper gauge, or for circular tubes by circumference tape at the discretion of the manufacturer.

The limiting cross-sectional positions for measuring *B* and *H* for square and rectangular hollow sections are shown in Figure 1.

7.3 Thickness

The thickness (T) of welded hollow sections shall be measured at a position not less than 2T from the weld.

The limiting cross-sectional positions for measuring the thickness of square and rectangular hollow sections are shown in Figure 1.

prEN 10210-2:2018 (E)

NOTE Thickness is normally measured within a distance of half the outside diameter or half the dimension of the longer side from the end of the section.

Dimensions in millimetres



Key

^a This dimension is a maximum when measuring B or H and a minimum when measuring T

Figure 1 — Limiting cross-sectional positions for measuring the dimensions *B*, *H* and *T* for square or rectangular hollow sections

7.4 Out-of-roundness ttps://standards.iteh.ai)

The out-of-roundness (*O*) of a circular hollow section shall be calculated from the following formula:

$$O(\%) = \frac{D_{\max} - D_{\min}}{D} \times 100$$
 SIST EN

ps://standards.iteh.ai/catalog/standards/sist/e7ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019 7.5 Concavity and convexity

The concavity (x_1) or the convexity (x_2) of the sides of a square or rectangular hollow section shall be measured as shown in Figure 2.

The percentage concavity or convexity shall be calculated as follows:

$$\frac{x_1}{B} \times 100 \%; \frac{x_2}{B} \times 100 \%; \frac{x_1}{H} \times 100 \%; \frac{x_2}{H} \times 100 \%$$

where *B* and *H* are the dimensions of the sides containing the concavity x_1 or the convexity x_2 .



Figure 2 — Measurement of concavity/convexity of square or rectangular hollow sections

7.6 Squareness of sides

The deviation from squareness of the sides of a square or rectangular hollow section shall be measured as the difference between 90° and θ as shown in Figure 3.

<u>SIST EN 10210-2:2019</u>

https://standards.iteh.ai/catalog/standards/sist/e7ec6b6e-62e6-457a-8c90-92713f61d609/sist-en-10210-2-2019





7.7 External corner profile

7.7.1 The external corner profile of a square or rectangular hollow section shall be measured according to 7.7.2 or 7.7.3 at the discretion of the manufacturer.

7.7.2 The corner arc shall be measured with a radius gauge.