



Designation: D6705 – 04

Standard Guide for Repair and Recoat of Spray Polyurethane Foam Roofing Systems¹

This standard is issued under the fixed designation D6705; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide covers the procedures for the repair and recoating of existing spray polyurethane roofing systems.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C1029 Specification for Spray-Applied Rigid Cellular Polyurethane Thermal Insulation

D5469 Guide for Application of New Spray Applied Polyurethane Foam and Coated Roofing Systems

D6083 Specification for Liquid Applied Acrylic Coating Used in Roofing

2.2 *SPFA Standards:*³

AY 102 A Guide for Selection of Elastomeric Protective Coatings Over Sprayed Polyurethane Foam

AY 107 Spray Polyurethane Foam Blisters, Their Causes, Types, Prevention and Repair

2.3 *API Standard:*⁴

Alliance for The Polyurethane Industry (API), Bulletin AX 119 Guide for Safe Handling and Use of Polyurethane and Polyisocyanurate Foam Systems

¹ This guide is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.06 on Spray Polyurethane Foam Roof Systems.

Current edition approved Dec. 1, 2004. Published December 2004. Originally approved in 2001. Last previous edition approved in 2001 as D6705 – 01. DOI: 10.1520/D6705-04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Spray Polyurethane Foam Alliance, 4400 Fair Lakes Ct., Suite 105, Fairfax, VA 22033.

⁴ Available from The Alliance for the Polyurethanes Industry, 1300 Wilson Blvd., Arlington, VA 22209.

3. Terminology

3.1 *Definitions:*

3.1.1 *recoat*—to apply a new protective coating over an existing coated SPF (spray polyurethane foam) roof system to extend the performance life of the roofing system.

3.1.2 *scarfing*—to shave or grind an SPF foam surface mechanically to remove a coating, or UV deteriorated SPF, or both, to refoam or recoat the surface.

4. Significance and Use

4.1 This guide outlines general procedures and precautions necessary for correct and safe repair and recoat of SPF roofing systems.

4.2 This guide is not all inclusive; this guide is intended to supplement detailed instructions from manufacturers and safety requirements required by law.

5. Roof Inspection Procedures and Considerations

5.1 *General Considerations:*

5.1.1 The performance of a sprayed-in-place polyurethane foam roof system can be affected by all the component parts of the roof structure, as well as the atmospheric conditions inside and outside the structure. Structural design, code compliance, specification review, contractor, and material selection should be considered in the repair and recoat of a spray polyurethane foam roof system.

5.1.2 A range of spray polyurethane foam systems exists with various physical properties, exhibiting different temperature limitations, and different combustibility characteristics. Most published data are obtained from testing of laboratory samples. The thickness of the polyurethane foam sprayed, number of passes, temperature of substrate, ambient temperature, and so forth will have an effect on all polyurethane foam properties.

5.1.3 The specifier should consult with the respective material manufacturer of the sprayed-in-place polyurethane foam roof system. This should include, but not be limited to, materials selection, expansion joints, flashing details, and other items.