

INTERNATIONAL STANDARD

ISO 14555

Second edition
2006-10-01

Welding — Arc stud welding of metallic materials

Soudage — Soudage à l'arc des goujons sur les matériaux métalliques

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 14555:2006](https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006)

<https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006>



Reference number
ISO 14555:2006(E)

© ISO 2006

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 14555:2006

<https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols and abbreviated terms	4
4.1 Symbols	4
4.2 Abbreviated terms	4
5 Technical review	5
6 Welding personnel	5
6.1 Stud-welding operators	5
6.2 Welding coordination	5
7 Equipment	6
7.1 Production equipment	6
7.2 Description of the equipment	6
7.3 Maintenance	6
8 Production planning	7
9 Welding procedure specification (WPS)	7
9.1 General	7
9.2 Information related to the manufacturer	7
9.3 Information related to the parent material	7
9.4 Welding process	7
9.5 Joint	8
9.6 Studs	8
9.7 Auxiliaries	8
9.8 Power source	9
9.9 Movable fixtures	9
9.10 Welding variables	9
9.11 Thermal conditions	10
9.12 Post-weld heat-treatment	10
9.13 Non-thermal treatment after welding	10
10 Welding procedure qualification	10
10.1 Principles	10
10.2 Welding procedure tests	10
10.3 Pre-production tests	14
10.4 Previous experience	14
10.5 Welding procedure qualification record (WPQR)	15
11 Examination and testing	15
11.1 General	15
11.2 Visual examination	15
11.3 Bend testing	15
11.4 Tensile testing	18
11.5 Torque test	21
11.6 Macro examination	22
11.7 Radiographic examination	22

12	Acceptance criteria	22
12.1	General	22
12.2	Acceptance criteria for visual examination	23
12.3	Acceptance criteria for bend testing	23
12.4	Acceptance criteria for tensile testing	23
12.5	Acceptance criteria for torque testing	23
12.6	Acceptance criteria for macro examination	23
12.7	Acceptance criteria for radiographic examination	23
12.8	Acceptance criteria for additional tests	24
13	Workmanship	24
14	Process control	24
14.1	General	24
14.2	Production test	25
14.3	Simplified production test	25
14.4	Re-testing for production test or simplified production test	26
14.5	Production surveillance	26
14.6	Production surveillance record	26
14.7	Non-conformance and corrective actions	26
14.8	Calibration of the measuring and testing equipment	27
Annex A (informative) Processing of stud welding		28
Annex B (normative) Quality requirements for stud welding		48
Annex C (informative) Manufacturer's welding procedure specification (WPS)		49
Annex D (informative) Welding procedure qualification record form (WPQR) (for drawn-arc stud welding with ceramic ferrule or shielding gas and short-cycle drawn-arc stud welding)		50
Annex E (informative) Welding procedure qualification record form (WPQR) (for capacitor discharge stud welding with tip ignition and capacitor discharge drawn-arc stud welding)		54
Annex F (informative) Test results — Production test (for drawn-arc stud welding with ceramic ferrule or shielding gas and short-cycle drawn-arc stud welding)		57
Annex G (informative) Test results — Production test (for capacitor discharge stud welding with tip ignition and capacitor discharge drawn-arc stud welding)		59
Annex H (informative) Example for production surveillance record		61
Bibliography		62

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14555 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*.

This second edition cancels and replaces the first edition (ISO 14555:1998), which has been technically revised.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 10 via your national standards body. A complete listing of these bodies can be found at <http://www.iso.org>.

Introduction

The purpose of arc stud welding is to weld predominantly pin-shaped metal parts to metal workpieces. In this International Standard it is referred to simply as stud welding. Amongst other things, stud welding is used in bridge building (especially in composite structures), steel structures, shipbuilding, facade-wall fabrication, vehicle manufacture, equipment design, steam-boiler construction, and the manufacture of household appliances.

The quality of a stud weld depends not only on strict compliance with the welding procedure specification but also on the correct function of the actuating mechanism (e.g. welding guns), and on the condition of the components, of the accessories and of the power supply.

This International Standard does not invalidate former specifications, providing the technical requirements are equivalent and satisfied.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 14555:2006](https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006)

<https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006>

Welding — Arc stud welding of metallic materials

1 Scope

This International Standard covers arc stud welding of metallic materials subject to static and dynamic loading. It specifies requirements that are particular to stud welding, in relation to welding knowledge, quality requirements, welding procedure specification, welding procedure qualification, qualification testing of operators and testing of production welds.

This International Standard is appropriate where it is necessary to demonstrate the capability of a manufacturer to produce welded construction of a specified quality.

NOTE General quality requirements for fusion welding of metallic materials are given in ISO 3834-1, ISO 3834-2, ISO 3834-3, ISO 3834-4 and ISO 3834-5.

This International Standard has been prepared in a comprehensive manner, with a view to its being used as a reference in contracts. The requirements contained within it can be adopted in full, or partially, if certain requirements are not relevant to a particular construction (see Annex B).

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 857-1, *Welding and allied processes — Vocabulary — Part 1: Metal welding processes*

ISO 3834-1, *Quality requirements for fusion welding of metallic materials — Part 1: Criteria for the selection of the appropriate level of quality requirements*

ISO 3834-2, *Quality requirements for fusion welding of metallic materials — Part 2: Comprehensive quality requirements*

ISO 3834-3, *Quality requirements for fusion welding of metallic materials — Part 3: Standard quality requirements*

ISO 3834-4, *Quality requirements for fusion welding of metallic materials — Part 4: Elementary quality requirements*

ISO 4063, *Welding and allied processes — Nomenclature of processes and reference numbers*

ISO 6947, *Welds — Working positions — Definitions of angles of slope and rotation*

ISO 9606-1, *Approval testing of welders — Fusion welding — Part 1: Steels*

ISO 9606-2, *Qualification test of welders — Fusion welding — Part 2: Aluminium and aluminium alloys*

ISO 13918:—¹⁾, *Welding — Studs and ceramic ferrules for arc stud welding*

1) To be published. (Revision of ISO 13918:1998)

ISO 14555:2006(E)

ISO 14175, *Welding consumables — Shielding gases for arc welding and cutting*

ISO 14731, *Welding coordination — Tasks and responsibilities*

ISO 14732:1998, *Welding personnel — Approval testing of welding operators for fusion welding and of resistance weld setters for fully mechanized and automatic welding of metallic materials*

ISO 15607:2003, *Specification and qualification of welding procedures for metallic materials — General rules*

ISO/TR 15608, *Welding — Guidelines for a metallic materials grouping system*

ISO 15611, *Specification and qualification of welding procedures for metallic materials — Qualification based on previous welding experience*

ISO 15613, *Specification and qualification of welding procedures for metallic materials — Qualification based on pre-production welding test*

ISO 15614-1:2004, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys*

ISO 15614-2, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 2: Arc welding of aluminium and its alloys*

ISO 17636, *Non-destructive testing of welds — Radiographic testing of fusion-welded joints*

ISO 17662, *Welding — Calibration, verification and validation of equipment used for welding, including ancillary activities*

ITeH STANDARD PREVIEW
(standards.iteh.ai)

3 Terms and definitions

ISO 14555:2006

<https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c->

For the purposes of this document, the terms and definitions given in ISO 857-1, ISO 3834-1, ISO 4063, ISO 14731, ISO 14732 and ISO 15607 and the following apply.

3.1

stud

fastener to be attached by stud welding

3.2

auxiliaries

ceramic ferrules and shielding gases

3.3

stud-welding operator

operating personnel for stud-welding equipment

NOTE In special cases (e.g. mass production at the manufacturer's factory) the welding can be carried out by suitable auxiliary personnel, appropriately trained and supervised.

3.4

stud diameter

d

stud nominal diameter

NOTE See ISO 13918.

3.5

welding diameter

d_w

diameter at the weld base

3.6**weld zone**

welded area underneath the welding diameter

3.7**current intensity**

root-mean-square (RMS) value of the welding current in the steady state during the burning time of the arc

NOTE Current intensity is not applicable to capacitor discharge.

3.8**welding time**

time difference between the ignition and the final extinction of the main arc

3.9**lift**

L

distance between the stud tip and the work piece surface with the stud-lifting mechanism in position and activated

NOTE 1 For tip ignition, this definition applies to the ignition gap.

NOTE 2 See Figure A.1.

3.10**plunge**

axial movement of the stud towards the surface of the work piece

3.11**protrusion**

P

(unregulated lifting mechanism) distance between the tip of the stud and the face of the support device in their initial positions, where the support device faces the work piece

NOTE 1 A spring-loaded lifting mechanism is an unregulated lifting mechanism.

NOTE 2 See Figure A.1.

3.12**arc blow**

magnetic deflection of the arc from the axial direction of the stud

3.13**flux**

aluminium additive on the weld end of the stud, which improves the ignition and de-oxidizes the weld pool

3.14**dual-material stud**

two-material stud composed of a material at the weld tip, similar to that of the parent material, and a dissimilar material outside the weld tip, which are joined by a friction weld, thus avoiding a mixed structure in the weld zone when stud welding

3.15**structure subjected to fatigue loading**

structure subject to a set of typical load events described by the positions or movements of loads, their variation in intensity and their frequency and sequence of occurrence

4 Symbols and abbreviated terms

4.1 Symbols

For the purposes of this International Standard, the following symbols apply.

<i>C</i>	capacitance (expressed in mF)
<i>d</i>	stud diameter (expressed in mm)
<i>d_w</i>	welding diameter (expressed in mm)
<i>h</i>	length of the threaded part of the nut
<i>I</i>	current intensity (expressed in A)
<i>L</i>	lift
<i>P</i>	protrusion
<i>t</i>	thickness of plate
<i>t_w</i>	welding time (expressed in ms or s)
<i>T</i>	torque (expressed in Nm)
<i>U</i>	charging voltage (expressed in V)
<i>W</i>	charging energy (expressed in Ws)
<i>a</i>	bending angle (expressed in °)

ITeH STANDARD PREVIEW
(standards.iteh.ai)

ISO 14555:2006

<https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006>

4.2 Abbreviated terms

For the purposes of this International Standard, the following abbreviated terms apply.

CF	ceramic ferrule
HAZ	heat-affected zone
NP	no protection
PA	flat welding position
PC	horizontal welding position
PE	overhead welding position
pWPS	preliminary welding procedure specification
SG	shielding gas
WPS	welding procedure specification
WPQR	welding procedure qualification record

5 Technical review

When a technical review is required by an application standard, by specification or by use of ISO 3834-2, ISO 3834-3 or ISO 3834-4, the manufacturer shall check, as appropriate, the following aspects:

- a) the accessibility and welding position of the stud weld;
- b) the nature of the surface and the collar shape of the welded joint;
- c) materials and combinations of materials (see Tables A.3 and A.4);
- d) the ratio of stud diameter to sheet metal thickness (avoidance of damage on the reverse side of the sheet);
- e) dimensions and details of the weld preparation and of the finished weld, including the nature of the stud and sheet-metal surfaces, positional and angular accuracy and the length tolerance of the welded stud;
- f) the use of special techniques to avoid damage to the reverse side of the sheet;
- g) techniques to assure the angular position of the welded stud.

NOTE Consideration is paid to the multi-axial stress state arising from localized heating/cooling. This stress concentration reduces the dynamic strength of a component with welded studs.

6 Welding personnel

iTeH STANDARD PREVIEW
(standards.iteh.ai)

6.1 Stud-welding operators

Stud-welding operators shall be qualified in accordance with ISO 14732:1998, 4.2.1 or 4.2.2. They shall have appropriate knowledge to operate the equipment, to adjust it properly, to carry out the welding correctly and, while doing so, to pay attention to good contact and suitable connection between the work piece cables and uniform distribution of ferromagnetic materials (see Table A.8).

The qualification shall include testing in accordance with the acceptance criteria specified in 12.2.

A test of job knowledge is required for all qualification methods. This test shall cover, as a minimum:

- a) setting up the welding equipment in accordance with the welding procedure specification;
- b) basic knowledge of the way in which suitable connection of work piece cables, the polarity of the stud, and arc blowing can influence the weld result (see Table A.8);
- c) basic assessment of the welded joint for imperfections (see Tables A.5, A.6 and A.7);
- d) safe execution of the welding operations, i.e. good contact of the stud in the stud holder, no movement during the welding process, operation checking and correct positioning of the guns).

6.2 Welding coordination

Welding coordination shall be performed in accordance with ISO 14731.

Welding coordination personnel for stud welding shall have knowledge of and experience in the relevant stud-welding process, and shall be able to select and set the correct parameters, e.g. lift, protrusion (plunge), current intensity, and welding time.

A welding coordinator is not required for stud welding to structures subjected to unspecified static loading (see Annex B).

7 Equipment

7.1 Production equipment

Suitable stud-welding equipment shall be used, with power supplies of sufficient capacity to weld the stud properly to the parent material when the equipment is correctly set up. The following equipment shall be available, as required:

- a) power sources, control unit and movable fixtures;
- b) cables with sufficient cross-section, solid connection terminals and sufficient earth connection;
- c) handling equipment for the technical aspects of welding fabrication (jigs, fixtures);
- d) weld data monitoring equipment;
- e) post-drying equipment for ceramic ferrules;
- f) cleaning facilities for contact points and welding points;
- g) measuring and testing equipment;
- h) equipment for pre- and post-treatment;
- i) equipment and welding plant for retouching.

7.2 Description of the equipment

iTeh STANDARD PREVIEW
(standards.iteh.ai)

A list of the stud-welding equipment shall be maintained, which shall serve as evidence of the performance and stud-welding application field. It shall include:

- a) details of the smallest and largest weldable stud diameter;
- b) the maximum number of studs to be welded per unit of time;
- c) the regulating range of the power supply;
- d) the mode of operation and performance of mechanized or automatic stud-welding equipment;
- e) details of the available test equipment.

7.3 Maintenance

The correct functioning of the equipment shall be ensured. During production, a function check of the actuation mechanisms shall be performed at fixed intervals. Cables, terminals, stud and ceramic ferrule holders shall be regularly checked and replaced at the appropriate time. For mass production and comprehensive quality requirements in accordance with ISO 3834-2, a maintenance plan for additional essential systems shall be drawn up. Examples of such systems are:

- a) stud sorting and feeding systems;
- b) stud and ceramic ferrule holders;
- c) mechanical guides and fixtures;
- d) measuring equipment;
- e) cables, hoses, connecting elements;
- f) a monitoring system.

8 Production planning

For stud welding, the production planning shall also contain the following elements:

- a) a definition of the required stud-welding procedures and equipment;
- b) details of which jigs and fixtures are used;
- c) the surface preparation method.

9 Welding procedure specification (WPS)

9.1 General

The welding procedure specification (WPS) shall give details of how a welding operation shall be performed and shall contain all relevant information about the welding work.

Information listed in 9.2 to 9.13 is adequate for most welding operations. For some applications, it may be necessary to supplement or reduce the list. The relevant information shall be specified in the WPS.

Ranges and tolerances shall be specified when appropriate. An example of the WPS format is given in Annex C.

9.2 Information related to the manufacturer

9.2.1 Identification of the manufacturer

- unambiguous identification.

ISO 14555:2006

9.2.2 Identification of the WPS

<https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006>

- alphanumeric designation (reference code).

9.2.3 Reference to the welding procedure qualification record (WPQR) or other relevant documents

- alphanumeric designation (reference code).

9.3 Information related to the parent material

9.3.1 Parent material type

- identification of material, preferably by reference to an appropriate standard;
- parent material(s) delivery condition.

NOTE A WPS can cover a material group in accordance with ISO/TR 15608. See also ISO/TR 20172, ISO/TR 20173 and ISO/TR 20174.

9.3.2 Dimensions

- the thickness or range of thickness of the parent material;
- other relevant dimensions.

9.4 Welding process

- designation in accordance with ISO 4063.

9.5 Joint

9.5.1 Joint design

- sketch of the joint design showing the relative positions of studs and tolerances;
- the sequence of the welding of studs shall be indicated on the sketch if essential for application.

9.5.2 Welding position

- welding positions shall be specified in accordance with ISO 6947.

9.5.3 Preparation of parent material surface

- method of surface preparation, if necessary (e.g. cleaning, degreasing, pickling);
- maximum time permitted between preparation and welding (if required).

9.5.4 Jigs and fixtures

- the methods to be used (if required);
- fixture details, templates, etc.

9.5.5 Support

- the method of support;
- specification of supporting material: <https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006>
- dimensions of support (when welding thin plates).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

9.6 Studs

9.6.1 Designation

- Designation according to standard, supplier or trade name; non-standard studs shall be specified.

9.6.2 Handling

- if the studs are to be treated (e.g. by cleaning) before use, this shall be specified.

9.7 Auxiliaries

9.7.1 Ceramic ferrules (if any)

- designation according to standard, supplier or trade name; non-standard ceramic ferrules shall be specified;
- if the ceramic ferrules are to be treated (e.g. by rebaking) before use, this shall be specified.

9.7.2 Protective gas (if any)

- designation in accordance with ISO 14175.

9.8 Power source

— manufacturer, type.

9.9 Movable fixtures**9.9.1 Welding gun/head**

— manufacturer, type;

— damper.

9.9.2 Shielding gas system (if used)

— gas flow rate;

— (schematic) description showing nozzle dimensions and position of nozzle(s) in relation to stud and work piece.

9.9.3 Stud feeding system (if any)

— description of stud feeding system including sketch.

9.10 Welding variables

STANDARD PREVIEW
(standards.iteh.ai)

9.10.1 Drawn arc stud welding with ceramic ferrule or shielding gas and short-cycle drawn arc stud welding

ISO 14555:2006

- a) polarity; <https://standards.iteh.ai/catalog/standards/sist/1a9b6b9c-491b-4ba8-889c-9dbb0525d3ee/iso-14555-2006>
- b) welding current;
- c) welding time;
- d) lift;
- e) protrusion;
- f) damper;
- g) number and position of earth clamps.

9.10.2 Capacitor discharge drawn arc stud welding or capacitor discharge stud welding with tip ignition

- a) polarity;
- b) capacitance;
- c) charging voltage;
- d) spring force and/or gap length;
- e) number and position of earth clamps;
- f) welding cable configuration (if used for current control).