
**Glass in building — Forced-entry security
glazing —**

Part 1:

**Test and classification by repetitive ball
drop**

iTeh STANDARD PREVIEW
*Verre dans la construction — Vitrages de sécurité contre infractions —
(standards.iteh.ai) Partie 1: Essai et classification par balle lancée répétée*

[ISO 16936-1:2005](https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16936-1:2005

<https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Sampling	2
5 Apparatus	2
6 Required characteristics	3
7 Test method	3
8 Classification and designation	5
9 Test report	5
10 Marking	6
Annex A (informative) Testing by repetitive ball drop at extreme temperatures	7
Bibliography	8

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 16936-1:2005](https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16936-1 was prepared by Technical Committee ISO/TC 160, *Glass in building*, Subcommittee SC 2, *Use considerations*.

ISO 16936 consists of the following parts, under the general title *Glass in building — Forced-entry security glazing*:

- Part 1: Test and classification by repetitive ball drop
- Part 2: Test and classification by repetitive impact of a hammer and axe at room temperature
- Part 3: Test and classification by manual attack
- Part 4: Test and classification by pendulum impact under thermally and fire stressed conditions

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16936-1:2005
<https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-374b1fc125b/iso-16936-1-2005>

Introduction

This part of ISO 16936 assesses security-glazing products that are more familiarly known as “anti-vandal”, “anti-bandit” and “detention” glazing products. Because there is no single test that will cover the wide range of resistances to attack, four separate test methods are provided to assess the forced entry resistant properties of security glazing. It is not intended that any particular test method be associated with the terms “anti-vandal” or “anti-bandit”, since these terms can be only loosely defined and there is considerable overlap in their definition.

It is important that security glazing products be installed in a frame which can give appropriate resistance to impact and which also provides a suitable support for the security-glazing product. It is important that cutouts and holes in security glazing products be avoided where possible, as these can affect the resistance of the product.

The test method specified in this part of ISO 16936 does not reproduce the conditions of real human attack, but is intended to give a classification of comparative resistance.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 16936-1:2005

<https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16936-1:2005

<https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005>

Glass in building — Forced-entry security glazing —

Part 1: Test and classification by repetitive ball drop

1 Scope

This part of ISO 16936 specifies requirements and a test method for security glazing designed to resist impacts of a hard body by delaying access of objects and/or persons to a protected space for a short period of time. This part of ISO 16936 classifies security-glazing products into categories of resistance to repetitive impacts of a steel sphere.

In this part of ISO 16936, the categories of resistance have not been assigned to special applications. Glazing classification should be specified on an individual basis for every application.

This part of ISO 16936 deals with mechanical resistance to impact only. Other properties can also be important.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 48:1994, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

action of force

deliberate action on the part of a person made with the intention of creating a hole in the security glazing product, by the use of manually held implements or by the use of thrown objects

3.2

asymmetric construction

product in which, from both outer surfaces, the sequence of glass panes, plastic glazing sheet material and interlayer(s) by type, thickness, finish and/or general characteristics is different

3.3

category of resistance

classification of the capability of a security-glazing product to resist actions of force

3.4

protected space

space protected against access by the completed installation

3.5

sample

specified number of test pieces which together are representative of the security glazing product intended to comply with a particular category of resistance in this part of ISO 16936

3.6

security glazing composition

specific construction of a glazing product

NOTE A product is deemed to be of the same or superior security glazing composition if individual plies are exchanged with others of a different colour, but without significant effect on the resistance to actions of force, and/or additional glazing products are installed on either face of the security glazing product, laminated to it or with an air space, and/or additional equipment such as alarm wires, heating wires, printing, or surface coatings (on part or all of the surface) are incorporated into the security glazing product, provided that this does not significantly affect the resistance to actions of force.

3.7

security glazing product

product based on glass with or without plastics with a single or multiple ply construction, where the individual plies are of uniform thickness over the whole area of the product

NOTE A security-glazing product is usually transparent or translucent, and provides a specific resistance to the actions of force.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.8

test piece

specified piece of security glazing product submitted to a specified test procedure

ISO 16936-1:2005
<https://standards.iteh.ai/catalog/standards/sist/3f372e45-a360-43d8-afbb-37ff01fe125b/iso-16936-1-2005>

4 Sampling

The sample submitted for testing shall consist of three test pieces for each category for which testing is required.

To ensure against invalid test results because of errors during the test, it is advisable to submit at least one extra test piece.

If the test pieces are of an asymmetric material, their number shall be doubled.

Each test piece shall be $(1\,100 \pm 5)$ mm long \times (900 ± 5) mm wide. The edges shall be free from visible chips, cracks and flaws. Glass samples should be lightly arressed for ease of handling.

Each test piece shall be stored vertically and self-supporting at (18 ± 3) °C, for at least 12 h immediately prior to the test.

For exterior uses under extreme conditions, the influence of the outside temperature should be considered.

5 Apparatus

5.1 Impactor, consisting of a steel sphere with a diameter of $(100 \pm 0,2)$ mm and a mass of $(4,11 \pm 0,06)$ kg. The sphere shall be manufactured from polished steel with a hardness of 60 HRC to 65 HRC on the Rockwell C scale, in accordance with ISO 6508-1.

5.2 Impactor-holding equipment, with a drop height adjustable to the required tolerance (see Table 1).

The equipment for holding the impactor and the mechanism for releasing the impactor shall not induce any momentum or rotation in the impactor, so that the impactor is accelerated only by gravitational forces and falls vertically.

Table 1 — Drop heights

Category of resistance	Drop height mm
P1A	1 500 ± 50
P2A	3 000 ± 50
P3A	6 000 ± 50
P4A	9 000 ± 50
P5A	9 000 ± 50

5.3 Test piece support apparatus, consisting of a steel frame to clamp the edge of the test piece and a receiving box to collect fragments and the impactor (see Figure 1).

The support apparatus shall

- be inherently rigid;
- have an unyielding connection to a solid base;
- ensure plane and parallel clamping of the test piece in a horizontal position;
- be designed in such a way that the test piece touches only the clamping frame during the test;
- ensure clamping of the test piece on all four edges with an edge cover of (30 ± 5) mm;
- have the clamping frame covered on the contact area of the test piece with rubber strips 30 mm wide and 4 mm thick of hardness 40 IHRD to 60 IHRD, according to method N of ISO 48:1994;
- ensure that the edges of the test piece are clamped with a uniform pressure of (140 ± 20) kN/m²;
- ensure that the impactor is not damaged and does not rebound when hitting the bottom of the receiving box;
- ensure that air cannot be trapped in the support apparatus in such a way that it may cushion the effects of the impact.

6 Required characteristics

The security-glazing product shall be submitted to testing for a particular category of resistance.

The security glazing product shall be classified in that particular category of resistance if all three test pieces (or all six test pieces in the case of an asymmetric material) prevent penetration by the impacting body when tested by the method described in Clause 7.

7 Test method

7.1 Room temperature test

The test room temperature shall be (18 ± 5) °C.

If the glass is tested at extreme temperatures, i.e. at -20 °C or at $+40$ °C, it shall be tested according to the specifications given in Annex A.