

---

---

**Plastics — Polyethylene (PE) moulding  
and extrusion materials —**

Part 2:

**Preparation of test specimens and  
determination of properties**

**iTeh STANDARD PREVIEW**  
*Plastiques — Polyéthylène (PE) pour moulage et extrusion —*  
*Partie 2: Préparation des éprouvettes et détermination des propriétés*  
**(standards.iteh.ai)**

ISO 1872-2:2007

<https://standards.iteh.ai/catalog/standards/sist/61c5fae4-758b-461f-a994-ab750654e170/iso-1872-2-2007>



Reference number  
ISO 1872-2:2007(E)

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 1872-2:2007](https://standards.iteh.ai/catalog/standards/sist/61c5fae4-758b-461f-a994-ab750654e170/iso-1872-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/61c5fae4-758b-461f-a994-ab750654e170/iso-1872-2-2007>

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1872-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This third edition cancels and replaces the second edition (ISO 1872-2:1997), which has been technically revised, and incorporates Amendment 1:2000.

ISO 1872 consists of the following parts, under the general title *Plastics — Polyethylene (PE) moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 1872-2:2007

<https://standards.iteh.ai/catalog/standards/sist/61c5fae4-758b-461f-a994-ab750654e170/iso-1872-2-2007>

# Plastics — Polyethylene (PE) moulding and extrusion materials —

## Part 2: Preparation of test specimens and determination of properties

### 1 Scope

This part of ISO 1872 specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of polyethylene (PE) moulding and extrusion materials. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given.

Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are also given. Properties and test methods that are suitable and necessary to characterize PE moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for or of particular significance to these moulding and extrusion materials are also included in this part of ISO 1872, as are the designatory properties specified in ISO 1872-1.

In order to obtain reproducible and comparable test results, it is necessary to use the methods of preparation and conditioning, the specimen dimensions and the test procedures specified herein. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

## ISO 1872-2:2007(E)

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 294-4, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 4: Determination of moulding shrinkage*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*

ISO 1133:2005, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 1183-3, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method*

ISO 1628-3, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 3: Polyethylenes and polypropylenes*

ISO 1872-1:1993, *Plastics — Polyethylene (PE) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 6603-2, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing*

ISO 8256, *Plastics — Determination of tensile-impact strength*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials (Under revision)*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 11359-2, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 16770, *Plastics — Determination of environmental stress cracking (ESC) of polyethylene — Full-notch creep test (FNCT)*

IEC 60093, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies*

IEC 60250, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgears*

IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*

ASTM D 638, *Standard test method for tensile properties of plastics*

ASTM D 1693, *Standard test method for environmental stress-cracking of ethylene plastics*

### 3 Preparation of test specimens

It is essential that specimens are always prepared by the same procedure (either injection moulding or compression moulding), using the same processing conditions.

The procedure to be used for each test method is indicated in Tables 3 and 4 (M = injection moulding, Q = compression moulding).

#### 3.1 Treatment of the material before moulding

No pre-treatment of the material (sample) is normally necessary before processing.

#### 3.2 Injection moulding

Injection moulding of test specimens is used for PE moulding materials having a melt mass-flow rate of  $\geq 1$  g/10 min, determined in accordance with ISO 1133:2005 using set of test conditions D (190 °C/2, 16 kg).

Injection-moulded specimens shall be prepared in accordance with ISO 294-1 or ISO 294-3, using the conditions specified in Table 1. It has been found that type A bar test specimens (prepared in accordance with ISO 3167) give better precision than type B (injection-moulded directly to their final dimensions) and so the use of this geometry is preferable.

NOTE Details of the work can be found at: <http://isotc.iso.ch/livelink/livelink?func=ll&objid=927134&objAction=browse&> on the SC9 server. (11 Round-robin test results: Technical report. Comparison of precision data for two types of bar test specimens formed in PP and PE.)

An appropriate hold pressure, consistent with the production of blemish-free mouldings, shall be used.

**Table 1 — Conditions for injection moulding of test specimens**

Material	Melt temperature °C	Mould temperature °C	Average injection velocity mm/s	Cooling time s	Total cycle time s
MFR $\geq 1$ g/10 min	210	40	100 $\pm$ 20	35 $\pm$ 5	40 $\pm$ 5

### 3.3 Compression moulding

Compression moulding is used for materials with a melt mass-flow rate of < 1 g/10 min, determined in accordance with ISO 1133:2005 using set of test conditions D (190 °C/2,16 kg). For thinner specimens (≤ 2 mm thick) and where specifically prescribed in Tables 3 and 4, compression moulding shall be used for all materials.

Compression-moulded sheets shall be prepared in accordance with ISO 293 using the conditions specified in Table 2. The test specimens required for the determination of the properties shall be machined from the compression-moulded sheets in accordance with ISO 2818, or stamped

NOTE Stamping is suitable for specimens of lower thickness up to 4 mm. Compared with milling or sawing, it gives lower stress and deformation to the specimens.

**Table 2 — Conditions for compression moulding of test specimens**

Material	Moulding temperature °C	Average cooling rate °C/min	Demoulding temperature °C	Full pressure MPa	Full-pressure time min	Preheating pressure MPa	Preheating time min
All grades	180	15	≤ 40	5/10 <sup>a</sup>	5 ± 1	Contact	5 to 15

<sup>a</sup> Use 5 MPa for a frame mould and 10 MPa for a positive mould.

NOTE 1 Inconsistent cooling rates can lead to significant deviations in measured properties due to the effect on the crystallinity of the specimens. So, it is desirable to use a moulding machine that can keep a constant cooling rate.

NOTE 2 For a type 1 mould, since full pressure is only applied upon the frame, compression-moulded sheet may suffer from insufficient homogeneity and pellet boundaries may be preserved.

A type 1 (frame) mould may be used, but it is necessary to start the cooling cycle whilst simultaneously applying the full pressure. This avoids the melt being pressed out of the frame and also avoids sink marks.

For thicker sheet (≈ 4 mm), a type 2 (positive) mould has been found to work satisfactorily. The preheating time depends on the type of mould and the type of energy input (steam, electricity). For frame moulds, 5 min is usually sufficient but for positive moulds, due to the bigger mass, a preheating time of up to 15 min may be necessary, especially if electric heating is used.

### 4 Conditioning of test specimens

Unfilled PE test specimens shall be conditioned for at least 16 h at 23 °C ± 2 °C, with no relative humidity requirement. Specimens made from materials containing fillers or additives that are susceptible to moisture uptake shall be conditioned for at least 16 h at 23 °C ± 2 °C and (50 ± 10) % relative humidity.

### 5 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350-1 shall be applied. Unless specifically stated in Table 3 and 4, testing of unfilled PE test specimens shall be carried out in the standard atmosphere of 23 °C ± 2 °C with no relative humidity requirement. Specimens made from materials containing fillers and additives that are susceptible to moisture uptake shall be tested in the standard atmosphere of 23 °C ± 2 °C and (50 ± 10) % relative humidity.

Table 3 is compiled from ISO 10350-1, and the properties listed are those that are appropriate to polyethylene (PE) moulding and extrusion materials. These properties are those considered useful for comparisons of data generated for different thermoplastics.



Table 4 contains those properties not found specifically in Table 3 that are in wide use or of particular significance in the practical characterization of polyethylene (PE) moulding and extrusion materials.

**Table 3 — General properties and test conditions** (selected from ISO 10350-1)

Property	Symbol	International Standard	Specimen type (dimensions in mm)	Specimen preparation <sup>a</sup>	Unit	Test conditions and supplementary instructions	
<b>1 Rheological properties</b>							
1.1	Melt mass-flow rate	MFR	ISO 1133	Moulding compound	—	g/10 min	See conditions given in ISO 1872-1.
1.2	Melt volume-flow rate	MVR				cm <sup>3</sup> /10 min	See conditions given in ISO 1872-1. Use a value for the melt density of 763,6 kg/m <sup>3</sup> to calculate the mass-flow rate of unfilled materials. <sup>b</sup>
1.3	Moulding shrinkage	$S_{Mp}$	ISO 294-4	60 × 60 × 2	M	%	Parallel
1.4		$S_{Mn}$					Normal
<b>2 Mechanical properties</b>							
2.1	Tensile modulus	$E_t$	ISO 527-2	ISO 3167	M/Q	MPa	Test speed 1 mm/min
2.2	Yield stress	$\sigma_y$					%
2.3	Yield strain	$\epsilon_y$					
2.4	Nominal strain at break	$\epsilon_{tB}$				MPa	Failure without yielding $\epsilon_B \leq 10\%$ : test speed 5 mm/min $\epsilon_B > 10\%$ : test speed 50 mm/min
2.5	Stress at 50 % strain	$\sigma_{50}$					
2.6	Stress at break	$\sigma_B$				%	
2.7	Strain at break	$\epsilon_B$					
2.8	Tensile creep modulus	$E_{tc}^1$	ISO 899-1	MPa	At 1 h	Strain $\leq 0,5\%$	
2.9		$E_{tc} \cdot 10^3$			At 1 000 h		
2.10	Flexural modulus	$E_f$	ISO 178	80 × 10 × 4	MPa	Test speed 2 mm/min	
2.11	Charpy notched impact strength	$a_{cA}$	ISO 179-1 or ISO 179-2	80 × 10 × 4 Machined V-notch, $r = 0,25$	kJ/m <sup>2</sup>	Edgewise impact, method 1eA. Also record type of failure.	
2.12	Tensile notched impact strength	$a_{tI}$	ISO 8256	80 × 10 × 4 Machined double V-notch, $r = 1$		Only to be quoted if fracture cannot be obtained with notched Charpy test.	
2.13	Puncture energy	$W_P$	ISO 6603-2	60 × 60 × 2	J	Striker velocity 4,4 m/s Striker diameter 20 mm Support ring diameter 40 mm Lubricate the striker.	
2.14	Maximum puncture force	$F_M$			N	Clamp the specimen sufficiently to prevent any out of plane movement of its outer regions.	