

INTERNATIONAL STANDARD

ISO
105-E06

Second edition
1987-12-15



INTERNATIONAL ORGANIZATION FOR STANDARDIZATION
ORGANISATION INTERNATIONALE DE NORMALISATION
МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ

Textiles — Tests for colour fastness —

Part E06: Colour fastness to spotting: Alkali

Textiles — Essais de solidité des teintures —

Partie E06: Solidité des teintures aux alcalis

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 105-E06 was prepared by Technical Committee ISO/TC 38, *Textiles*.

This second edition cancels and replaces the first edition (included in ISO 105-E : 1978), of which it constitutes a minor revision.

ISO 105 was previously published in thirteen "parts", each designated by a letter (e.g. "Part A"), with publication dates between 1978 and 1985. Each part contained a series of "sections" each designated by the respective part letter and by a two-digit serial number (e.g. "Section A01"). These sections are now being republished as separate documents, themselves designated "parts" but retaining their earlier alphanumeric designations. A complete list of these parts is given in ISO 105-A01.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

Textiles — Tests for colour fastness —

Part E06:

Colour fastness to spotting: Akali

1 Scope and field of application

This part of ISO 105 specifies a method for determining the resistance of the colour of textiles of all kinds and in all forms to the action of dilute alkaline solutions.

2 References

ISO 105, *Textiles — Tests for colour fastness —*

Part A01: General principles of testing.

Part A02: Grey scale for assessing change in colour.

3 Principle

Drops of a solution of sodium carbonate are placed on the specimen, the surface of which is rubbed gently with a glass rod to ensure penetration. The change in colour of the textile is assessed with the grey scale.

4 Apparatus and reagent

4.1 Pipette or dropper.

4.2 Glass rod, with rounded end.

4.3 Grey scale for assessing change in colour (see clause 2).

4.4 Sodium carbonate, solution containing 100 g of anhydrous sodium carbonate per litre.

5 Test specimen

5.1 If the textile to be tested is fabric, use a specimen 10 cm × 4 cm.

5.2 If the textile to be tested is yarn, knit it into fabric and use a specimen 10 cm × 4 cm, or make a wick of parallel lengths 10 cm long and about 0,5 cm in diameter, tied near both ends.

5.3 If the textile to be tested is loose fibre, comb and compress enough of it to form a sheet 10 cm × 4 cm.

6 Procedure

6.1 Spot the specimen at room temperature with the sodium carbonate solution so that after working the solution into the specimen with the glass rod a spot of diameter approximately 20 mm is formed. In the case of water-repellent fabrics, the amount of solution should not exceed 0,5 ml.

6.2 Dry the specimen by hanging it in air at room temperature; brush it to remove sodium carbonate residues.

6.3 Assess the change in colour with the grey scale.

7 Test report

Report the numerical rating for change in colour.

8 Note

It is recommended that the test for resistance to water spotting, specified in ISO 105-E07, *Textiles — Tests for colour fastness — Part E07: Colour fastness to spotting: Water*, also be carried out to ascertain that the change in colour is not due to the action of water alone.