

**SLOVENSKI STANDARD****SIST EN 10305-3:2016****01-oktober-2016****Nadomešča:****SIST EN 10305-3:2010**

---

**Jeklene cevi za precizno uporabo - Tehnični dobavni pogoji - 3. del: Varjene hladno dimenzionirane cevi**

Steel tubes for precision applications - Technical delivery conditions - Part 3: Welded cold sized tubes

Präzisionsstahlrohre - Technische Lieferbedingungen - Teil 3: Geschweißte maßgewalzte Rohre  
**(standards.iteh.ai)**Tubes de précision en acier - Conditions techniques de livraison - Partie 3 : Tubes soudés calibrés à froid  
<https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869-62ba7261fc5/sist-en-10305-3-2016>**Ta slovenski standard je istoveten z: EN 10305-3:2016**

---

**ICS:**

77.140.75      Jeklene cevi in cevni profili za posebne namene      Steel pipes and tubes for specific use

**SIST EN 10305-3:2016****en,fr,de**

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

SIST EN 10305-3:2016

[https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869-  
62ba7261fc5/sist-en-10305-3-2016](https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869-62ba7261fc5/sist-en-10305-3-2016)

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

EN 10305-3

March 2016

ICS 77.140.75

Supersedes EN 10305-3:2010

English Version

**Steel tubes for precision applications - Technical delivery  
conditions - Part 3: Welded cold sized tubes**

Tubes de précision en acier - Conditions techniques de  
livraison - Partie 3 : Tubes soudés calibrés à froid

Präzisionsstahlrohre - Technische Lieferbedingungen -  
Teil 3: Geschweißte maßgewalzte Rohre

This European Standard was approved by CEN on 18 January 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

[https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869-  
62ba7261fc5/sist-en-10305-3-2016](https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869-62ba7261fc5/sist-en-10305-3-2016)



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

**Contents**

	Page
<b>European foreword.....</b>	<b>4</b>
<b>1 Scope.....</b>	<b>5</b>
<b>2 Normative references.....</b>	<b>5</b>
<b>3 Terms and definitions .....</b>	<b>6</b>
<b>4 Symbols.....</b>	<b>7</b>
<b>5 Classification and Designation .....</b>	<b>7</b>
<b>5.1 Classification.....</b>	7
<b>5.2 Designation.....</b>	7
<b>6 Information to be supplied by the purchaser.....</b>	<b>7</b>
<b>6.1 Mandatory information .....</b>	7
<b>6.2 Options.....</b>	7
<b>6.3 Example of an order .....</b>	8
<b>7 Manufacturing process.....</b>	<b>9</b>
<b>7.1 Steelmaking process.....</b>	9
<b>7.2 Tube manufacture and delivery conditions.....</b>	9
<b>8 Requirements .....</b>	<b>10</b>
<b>8.1 General.....</b>	10
<b>8.2 Chemical composition.....</b>	10
<b>8.3 Mechanical properties.....</b>	12
<b>8.4 Appearance and internal soundness.....</b>	13
<b>8.5 Dimensions and tolerances .....</b>	14
<b>8.5.1 Outside diameter and wall thickness.....</b>	14
<b>8.5.2 Lengths.....</b>	16
<b>8.5.3 Straightness.....</b>	17
<b>8.5.4 Preparation of ends.....</b>	17
<b>9 Inspection .....</b>	17
<b>9.1 Types of inspection.....</b>	17
<b>9.2 Inspection documents .....</b>	17
<b>9.2.1 Types of inspection documents.....</b>	17
<b>9.2.2 Content of inspection documents.....</b>	18
<b>9.3 Summary of inspection and testing .....</b>	18
<b>10 Sampling.....</b>	<b>19</b>
<b>10.1 Test unit.....</b>	19
<b>10.2 Preparation of samples and test pieces .....</b>	20
<b>10.2.1 Location, orientation and preparation of samples and test pieces for mechanical tests .....</b>	20
<b>10.2.2 Test pieces for roughness measurement.....</b>	20
<b>11 Test methods .....</b>	<b>20</b>
<b>11.1 Tensile test .....</b>	20
<b>11.2 Flattening test.....</b>	20
<b>11.3 Drift expanding test.....</b>	21

<b>11.4 Dimensional inspection.....</b>	<b>22</b>
<b>11.5 Roughness measurement .....</b>	<b>22</b>
<b>11.6 Visual examination .....</b>	<b>22</b>
<b>11.7 Non-destructive testing .....</b>	<b>22</b>
<b>11.7.1 Testing for longitudinal imperfections.....</b>	<b>22</b>
<b>11.7.2 Leak-tightness.....</b>	<b>22</b>
<b>11.7.3 Testing of transverse welds for imperfections .....</b>	<b>22</b>
<b>11.8 Retests, sorting and reprocessing.....</b>	<b>22</b>
<b>12 Marking .....</b>	<b>22</b>
<b>13 Protection and packaging.....</b>	<b>23</b>
<b>Bibliography .....</b>	<b>24</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 10305-3:2016

<https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869-62ba7261fc5/sist-en-10305-3-2016>

## European foreword

This document (EN 10305-3:2016) has been prepared by Technical Committee ECISS/TC 110 "Steel tubes and iron and steel fittings", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2016 and conflicting national standards shall be withdrawn at the latest by September 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10305-3:2010.

In comparison with the previous edition, the following technical changes have been made:

- a) References were adapted;
- b) The options were renumbered in such a way that now throughout all parts the number of options are the same;
- c) Addition of steel grades E460, E500, E550, E600 and E700;
- d) Editorial updates.

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

EN 10305, *Steel tubes for precision applications - Technical delivery conditions* consists of the following parts:  
<https://standards.iteh.ai/catalog/standards/sist/af14c488-048b-4eba-9869-62ba7261fc5/sist-en-10305-3-2016>

- Part 1: Seamless cold drawn tubes
- Part 2: Welded cold drawn tubes
- Part 3: Welded cold sized tubes
- Part 4: Seamless cold drawn tubes for hydraulic and pneumatic power systems
- Part 5: Welded cold sized square and rectangular tubes
- Part 6: Welded cold drawn tubes for hydraulic and pneumatic power systems

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard specifies the technical delivery conditions for welded cold sized steel tubes of circular cross section for precision applications with specified outside diameter  $D \leq 193,7$  mm.

This document may also be applied to other types (excluding square and rectangular) of cross section.

Tubes according to this document are characterized by having precisely defined tolerances on dimensions and a specified maximum surface roughness. Typical fields of application are in the vehicle, furniture and general engineering industries.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020:2000, *Definition and classification of grades of steel*

EN 10021:2006, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels - Part 1: Steel names*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system*

EN 10052:1993, *Vocabulary of heat treatment terms for ferrous products*

EN 10168, *Steel products - Inspection documents* (List of information and description)

<https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869>

EN 10204, *Metallic products - Types of inspection documents* (2016)

EN 10266:2003, *Steel tubes, fittings and structural hollow sections - Symbols and definitions of terms for use in product standards*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 3773)*

EN ISO 2566-1, *Steel - Conversion of elongation values - Part 1: Carbon and low alloy steels (ISO 2566-1)*

EN ISO 4287, *Geometrical product specifications (GPS) - Surface texture: Profile method - Terms, definitions and surface texture parameters (ISO 4287)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 8492, *Metallic materials - Tube - Flattening test (ISO 8492)*

EN ISO 8493, *Metallic materials - Tube - Drift-expanding test (ISO 8493)*

EN ISO 10893-1, *Non-destructive testing of steel tubes - Part 1: Automated electromagnetic testing of seamless and welded (except submerged arc-welded) steel tubes for the verification of hydraulic tightness (ISO 10893-1)*

**EN 10305-3:2016 (E)**

EN ISO 10893-2, *Non-destructive testing of steel tubes - Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2)*

EN ISO 10893-3, *Non-destructive testing of steel tubes - Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-3)*

EN ISO 10893-10, *Non-destructive testing of steel tubes - Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10)*

EN ISO 10893-11, *Non-destructive testing of steel tubes - Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-11)*

ISO 11484, *Steel products - Employer's qualification system for non-destructive testing (NDT) personnel*

### **3 Terms and definitions**

For the purposes of this document, the terms and definitions given in EN 10020:2000, EN 10021:2006, EN 10052:1993, EN 10266:2003 and the following apply.

## **iTeh STANDARD PREVIEW**

### **(standards.iteh.ai)**

**3.1 employer**  
organization for which a person works on a regular basis

Note 1 to entry: The employer may be either the tube manufacturer or a third party organization providing services, such as non-destructive testing (NDT).  
SIST EN 10305-3:2016  
<https://standards.iteh.ai/catalog/standards/sist/ai4c488-048b-4eba-9869-62ba7261fc5/sist-en-10305-3-2016>

**3.2 manufacturer**  
party to produce and to deliver tubes in accordance with this document

Note 1 to entry: Where tubes are delivered through an intermediary, see EN 10021:2006, Clause 6.

**3.3 imperfection**  
discontinuity in the wall or on the pipe surfaces detectable by methods described in this document

Note 1 to entry: Imperfections with a size complying with the acceptance criteria specified in this document are considered to have no practical implication on the intended use of the product.

**3.4 defect**  
imperfection of a size not complying with the acceptance criteria specified in this document

Note 1 to entry: Defects are considered to adversely affect or limit the intended use of the product.

**3.5 parent coil**  
coil originating from the hot rolling process prior to any subsequent operation (pickling, slitting, cold rolling or coating)

## 4 Symbols

For the purposes of this document, the symbols in EN 10266:2003 apply.

## 5 Classification and Designation

### 5.1 Classification

In accordance with the classification system in EN 10020 the steel grades given in Table 2 are non-alloy quality steels except steel grade E700 which is an alloy quality steel.

### 5.2 Designation

For the tubes covered by this document the steel designation consists of the number of this document (EN 10305-3) plus either:

- a) the steel name in accordance with EN 10027-1; or
- b) the steel number in accordance with EN 10027-2.

## 6 Information to be supplied by the purchaser

### 6.1 Mandatory information STANDARD PREVIEW (standards.iteh.ai)

The following information shall be obtained by the manufacturer at the time of enquiry and order:

- a) the quantity (mass or total length or number);  
SIST EN 10305-3:2016  
<https://standards.iteh.ai/catalog/standards/sist/aff4c488-048b-4eba-9869-62ba7261fc5/sist-en-10305-3-2016>
- b) the term "tube";
- c) the dimensions (see 8.5.1);
- d) the steel designation (see 5.2);
- e) the delivery condition including the surface condition (see 7.2.1 and 7.2.2);
- f) type of tube length and, where applicable, the length (see 8.5.2);
- g) type of inspection document (see 9.1).

### 6.2 Options

A number of options are specified in this document and these are listed below. In the event that the purchaser does not indicate his wish to implement any of these options at the time of enquiry and order, the tubes shall be supplied in accordance with the basic specification (see 6.1).

- Option 1: specification of a steel grade not specified in this document (see 8.2);
- Option 3: suitability for hot-dip galvanizing (see 8.2);
- Option 4: surface condition for further processing (see 8.4.1);
- Option 6: removal of internal weld bead (see 8.4.2);

**EN 10305-3:2016 (E)**

- Option 8: measurement of surface roughness (see 8.4.4);
- Option 9: specific surface roughness (see 8.4.4);
- Option 11: non-destructive testing of the weld seam for the detection of longitudinal imperfections (see 8.4.8);
- Option 12: non-destructive testing for the detection of longitudinal imperfections (see 8.4.8 and 11.7);
- Option 13: non-destructive testing for verification of leak-tightness (see 8.4.8);
- Option 14: specification of a procedure to test transverse welds for the detection of imperfections (see 8.4.8);
- Option 15: specification of a cross section other than circular (see 8.5.1.1);
- Option 16: reduced diameter tolerances (see 8.5.1.2);
- Option 17: unilateral diameter tolerance (see 8.5.1.2);
- Option 19: reduced wall thickness tolerance (see 8.5.1.3);
- Option 20: unilateral wall thickness tolerance (see 8.5.1.3);
- Option 21: another specified length and/or tolerance (see 8.5.2);
- Option 22: reduced maximum deviation from straightness (see 8.5.3);
- Option 23: specified end finishing (see 8.5.4);
- Option 25: flattening or drift expanding test for delivery condition +A or +N (see Table 9);
- Option 26: test unit with tubes from one cast only (see 10.1);
- Option 27: more restrictive requirement on flattening test (see 11.2);
- Option 28: alternative marking (see Clause 12);
- Option 29: delivery without corrosion protection (see Clause 13);
- Option 30: specified corrosion protection (see Clause 13);
- Option 38: unbundled tubes or specific method of packaging (see Clause 13).

**6.3 Example of an order**

12 000 m tube with an outside diameter of  $D = 40$  mm and a wall thickness of  $T = 1,5$  mm in accordance with this document, made of steel grade E235 in the normalized condition, pickled, to be delivered in standard lengths of 6 m with an 3.1 inspection certificate in accordance with EN 10204.

12 000 m tubes – D 40 x T 1,5 – EN 10305-3 –E235+N – S2 – standard length – inspection certificate 3.1

## 7 Manufacturing process

### 7.1 Steelmaking process

The steelmaking process is at the discretion of the manufacturer with the exception that the open hearth (Siemens-Martin) process shall not be employed unless in combination with a secondary steelmaking or ladle refining process.

Steels shall be fully killed.

NOTE This excludes the use of rimming, balanced or semi-killed steel.

### 7.2 Tube manufacture and delivery conditions

**7.2.1** The tubes shall be manufactured from strip by electric welding. The tubes shall not contain strip end welds except for tubes to be supplied coiled for which the delivery conditions +A or +N shall be specified.

Possible surface conditions are:

- a) S1 (black);
- b) S2 (pickled);
- c) S3 (cold rolled); **iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**
- d) S4 (coated to an agreed condition).

The surface conditions S1 and S3 apply for the strip. The surface condition S2 and S4 may apply for the strip or the tube; the purchaser should, where necessary, indicate the required condition at the time of enquiry and order. SIST EN 10305-3:2016  
<https://standards.iteh.ai/catalog/standards/sist/en/c488-0480-4eba-9859>

**7.2.2** Tubes made of the steel grades E155, E195, E235, E275 and E355 shall be supplied in the delivery condition +CR1 or +A or +N (see Table 1). Tubes made of the grades E190, E220, E260, E320, E370, E420, E460, E500, E550, E600 and E700 shall be supplied in the delivery condition +CR2.

**7.2.3** All non-destructive testing (NDT) activities shall be carried out by qualified and competent level 1, 2 and/or 3 personnel authorized to operate by the employer.

The qualification shall be in accordance with ISO 11484 or, at least, an equivalent to it.

It is recommended that the level 3 personnel be certified in accordance with EN ISO 9712 or, at least, an equivalent to it.

The operating authorization issued by the employer shall be in accordance with a written procedure. NDT operations shall be authorized by a level 3 NDT individual approved by the employer.

NOTE The definition of levels 1, 2 and 3 can be found in appropriate standards, e.g. EN ISO 9712 and ISO 11484.