



Designation: D705 – 99(Reapproved 2004)

Standard Specification for Urea-Formaldehyde Molding Compounds¹

This standard is issued under the fixed designation D705; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers compression molding thermosetting, urea-formaldehyde molding compounds as further defined in 3.1.

1.2 The values stated in SI units are to be regarded as the standard.

NOTE 1—The properties included in this specification are those required to identify the types of molding compounds covered. There may be other requirements necessary to identify particular characteristics. Transfer or injection molding will usually result in different physical and electrical characteristics than compression molding.

1.3 The following safety hazards caveat pertains only to the test method portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—ISO 2112-1977(E) is similar but not equivalent to this specification. Product classification and characterization are not the same.

2. Referenced Documents

- 2.1 *ASTM Standards*:²
- D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
 - D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics
 - D495 Test Method for High-Voltage, Low-Current, Dry Arc Resistance of Solid Electrical Insulation
 - D570 Test Method for Water Absorption of Plastics
 - D618 Practice for Conditioning Plastics for Testing
 - D790 Test Methods for Flexural Properties of Unreinforced

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.16 on Thermosetting Materials.

Current edition approved Oct. 1, 2004. Published December 2004. Originally approved in 1943. Last previous edition approved in 1999 as D705 - 99. DOI: 10.1520/D0705-99R04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

and Reinforced Plastics and Electrical Insulating Materials

D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement

D956 Practice for Compression Molding Specimens of Amino Molding Compounds (Withdrawn 1992)³

D3892 Practice for Packaging/Packing of Plastics

2.2 *ISO Standard*:

ISO 2112-1977(E) Plastics—Aminoplastic Moulding Materials—Specification⁴

3. Classification

3.1 The molding compounds covered by this specification shall be designated by types, based upon their principal characteristics and the fillers used.

3.1.1 *Type 1*—A general purpose molding compound with alpha-cellulose filler.

3.1.2 *Type 2*—A general purpose molding compound with cellulose filler other than alpha-cellulose.

4. General Requirements

4.1 The molding compounds shall be of uniform composition. The apparent density, bulk factor, plasticity, particle size, and color shall be compounded as to conform to the requirements prescribed in this specification.

5. Detail Requirements

5.1 Test specimens molded in accordance with Practice D956 shall conform to the requirements prescribed in Table 1.

6. Sampling

6.1 A batch of molding compound shall be considered as a unit of manufacture as prepared for shipment and may consist of a blend of two or more production runs.

6.2 Adequate statistical sampling shall be used.

7. Test Methods

7.1 The properties enumerated in this specification shall be determined in accordance with the following methods:

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

*A Summary of Changes section appears at the end of this standard