



SLOVENSKI STANDARD

SIST EN ISO 16891:2016

01-april-2016

Preskusne metode za ugotavljanje poslabšanja lastnosti filtrirnih sredstev, ki se lahko čistijo (ISO 16891:2016)

Test methods for evaluating degradation of characteristics of cleanable filter media (ISO 16891:2016)

Prüfmethode zur Ermittlung der Abnahme der Wirksamkeit von abreinigbaren Filtermedien (ISO 16891:2016)

Méthodes d'essais pour l'évaluation de la dégradation des propriétés des medias filtrants décolmatables (ISO 16891:2016)

ITIH STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>

Ta slovenski standard je istoveten z: EN ISO 16891:2016

ICS:

91.140.30	Prezračevalni in klimatski sistemi	Ventilation and air-conditioning
-----------	------------------------------------	----------------------------------

SIST EN ISO 16891:2016

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 16891:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>

EUROPEAN STANDARD

EN ISO 16891

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2016

ICS 91.140.30

English Version

Test methods for evaluating degradation of characteristics of cleanable filter media (ISO 16891:2016)

Méthodes d'essais pour l'évaluation de la dégradation
des propriétés des médias filtrants décolmatables (ISO
16891:2016)

Prüfmethode zur Ermittlung der Abnahme der
Wirksamkeit von abreinigbaren Filtermedien (ISO
16891:2016)

This European Standard was approved by CEN on 7 November 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 16891:2016](https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016)
<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>

European foreword

This document (EN ISO 16891:2016) has been prepared by Technical Committee ISO/TC 142 "Cleaning equipment for air and other gases" in collaboration with Technical Committee CEN/TC 195 "Air filters for general air cleaning" the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iteh STANDARD PREVIEW

(standards.iteh.ai)

Endorsement notice

SIST EN ISO 16891:2016

The text of ISO 16891:2016 has been approved by CEN as EN ISO 16891:2016 without any modification.

File: 2016/standards.iteh.ai/catalog/standards/cen/549.../16891-2016
6c87a7c87047/sist-en-iso-16891-2016

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 16891:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>

INTERNATIONAL
STANDARD

ISO
16891

First edition
2016-01-15

**Test methods for evaluating
degradation of characteristics of
cleanable filter media**

*Méthodes d'essais pour l'évaluation de la dégradation des propriétés
des medias filtrants décolmatables*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 16891:2016](https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016)

<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>



Reference number
ISO 16891:2016(E)

© ISO 2016

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 16891:2016

<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	4
5 Principle	5
6 Test specimen, equipment and test procedure	6
6.1 General.....	6
6.2 Preparation of sheets for gas exposure.....	7
6.2.1 Shape and size of tensile specimen.....	7
6.2.2 Sample sheet for exposure.....	7
6.2.3 Selection of sample sheet through air permeability measurement.....	8
6.2.4 Filter media for exposure.....	8
6.3 Sample preparation.....	9
6.3.1 Exposure system.....	9
6.3.2 Heating system.....	11
6.3.3 Test gas supply system.....	11
6.3.4 Gas analyzer.....	11
6.3.5 Gas treatment device.....	12
6.4 Exposure conditions and procedures.....	12
6.4.1 Exposure conditions.....	12
6.4.2 Exposure period and number of exposure.....	12
6.4.3 Attachment of filter sample sheets in the sample case.....	13
6.4.4 Implementation of the exposure.....	13
7 Tensile strength measurement of exposed specimen	14
7.1 Tensile test device.....	14
7.2 Preparation of a tensile test specimen.....	14
7.3 Method of tensile test.....	14
7.4 Characterization of the degradation.....	15
8 Test report	16
Annex A (informative) Causes and results of degradation of fabrics	17
Annex B (informative) Possible evaluation method for characteristic change of fabrics	18
Annex C (informative) Theoretical consideration of degradation mechanism	19
Annex D (informative) Determination of specimen size	22
Annex E (informative) Experimental setup for gas exposure	26
Annex F (informative) Service temperature of filter materials	30
Annex G (informative) Examples of measured data of fabric at different circumstances	31
Annex H (informative) Example of test report	37
Bibliography	41

ISO 16891:2016(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 142, *Cleaning equipment for air and other gases*.

SIST EN ISO 16891:2016

<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>

Introduction

The main purpose of using cleanable filter is, of course, to separate dust particles from dirty gases. They are usually designed to be usable for as long as two years to four years. However, it is very hard to design and/or select filter media properly, since their important characteristics of collection performance and residual pressure drop change with operation time. Physical and chemical properties of filter media, such as degradation in tensile strength, tenacity and so on, also change with time. Those changes can damage filter media and this can result in the breakage of bag filters and leakage of dust to the atmosphere. Hence the evaluation of these performances is also important for the rational design and the selection of appropriate filter media. ISO 11057:2011 has been published to meet the demand for the evaluation of filtration characteristics.

Changes in physical and chemical properties of filter media are caused by many factors, such as heat, corrosive gases, and mechanical reasons like clogging weave openings and increasing size of weave openings, the combination of those factors and so on (see [Annex A](#)). These changes are mostly adverse effects to filter media. Degradation proceeds very slowly, and thus, it takes a long time before recognizable and/or measurable change appears. Furthermore, the appearance of change depends on the combination of causes and fibre material. These facts are the main reason why mechanism of property changes has not been well understood despite its practical importance.^{[1]-[13]} Hence, the characterization or evaluation methods for filter media have not been established yet^{[14][15]} (see [Annex B](#)).

Nevertheless, there are demands for the establishment of a guideline for systematic characterization and evaluation of property change of filter media with respect to their relevant long-time operation not only from manufacturers of filter media, but also from producers and users of filter installations, especially the users treating combustion exhaust gases.

To evaluate degradation of filter media in a laboratory, it is important that experiment can be done in a relatively short time period by using controllable single or a small number of variables, i.e. causes of change.

Furthermore, it is important that the resulting effects are measurable. From this point of view, heat intensity is controllable by changing heating temperature and the intensity of corrosive gas is also controllable by changing gas concentration. Thus, their effect is expected to be accelerated. Of course, the effects can be evaluated by the degradation of tensile stress.

Evaluation of property change of filter media by corrosive gases can be done by contacting filter media with those corrosive materials in any phases, i.e. gas, liquid and solid state. Testing by dipping filter media into a solution of corrosive materials is easy and the resulting effects are expected to be obtained in a short period of time. Chinese Standard, GB/T 6719:2009 adopts this method.^[16] Solid state testing can be carried out by hard contact of filter media but it will take a long time and it is very hard to control the intensity of corrosiveness.

Testing under the gaseous state takes much longer than a liquid type test but the intensity of corrosiveness is controllable and it is much easier than the test under the solid state. Furthermore, test temperature and gas conditions except corrosive gas concentrations, are similar to the actual operation condition of filtration, which is suitable (see [Annex B](#)). Hence, in this International Standard, test methods for evaluating degradation characteristics of cleanable unwoven filter media with synthetic fibre by heat and corrosive gases are standardized because they are most widely used for bag filtration.

The major objective of this International Standard is to specify the testing method to assess the relative change of physical performances of new and used cleanable filter media for industrial application, by exposing it in hot and/or corrosive gas conditions ^{[17][18]}.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 16891:2016](#)

<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-6c87a7c87047/sist-en-iso-16891-2016>

Test methods for evaluating degradation of characteristics of cleanable filter media

1 Scope

This International Standard specifies a standard reference test method useful to assess the relative degradation characteristics of cleanable filter media for industrial applications under standardized simulated test conditions. The main purpose of testing is to obtain the information about relative change of properties of filter media due to exposure to the simulated gas conditions for a long time. The main target of this International Standard is the property change of nonwoven fabric filters because they are frequently used under similar circumstances to the test gas conditions described in this International Standard.

The results obtained from this test method are not intended for predicting the absolute properties of full scale filter facilities. However, they are helpful for the design of a bag filter and selection and development of appropriate cleanable filter media, and for the identification of suitable operating parameters.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4606, *Textile glass — Woven fabrics — Determination of tensile breaking force and elongation at breaking by strip method*

ISO 13934-1, *Textiles — Tensile properties of fabrics — Part 1: Determination of maximum force and elongation at maximum force using the strip method*¹⁾

ISO 29464:2011, *Cleaning equipment for air and other gases — Terminology*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 29464:2011 and the following apply.

3.1

aged filter sheet

filter sheet exposed under simulated hot and corrosive gas conditions for a preset period of time to evaluate the change of filter properties

3.2

air permeability

gas volume flow rate per unit filtration area at pressure drop of 124,5 Pa

3.3

average gas concentration

mean concentration of test gases during the exposure

1) This International Standard replaced ISO 5081, *Textiles — Woven fabrics — Determination of breaking strength and elongation (Strip method)*.

ISO 16891:2016(E)**3.4****batch type exposure chamber**

chamber in which filter sheets are exposed to stationary test gas mixture

3.5**chemical degradation**

degradation of chemical properties of filter media by the interaction with test gases

3.6**cleanable filter**

filter designed to enable the removal of collected dust by appropriate technique

[SOURCE: ISO 29464:2011; 3.1.77]

3.7**continuous-flow-method**

exposing method of filter sheet, which is exposed in a continuous flow of test gas mixture

3.8**corrosive gas**

chemicals which react with filter media and change its chemical and physical properties

3.9**degradation**

change in physical and chemical performances of filter media by the interaction with corrosive gases

3.10**elongation**

incremental change in length of test specimen by tensile test

3.11**elongation at maximum load**

incremental change in length of test specimen at maximum load in tensile test

3.12**elongation ratio**

ratio of elongation of test specimen to its initial length between holders or its percentage

3.13**elongation ratio at maximum load**

ratio of elongation of test specimen at maximum load in tensile test to its initial length between holders

3.14**exposure chamber**

chamber to expose test filter sheet to corrosive gases

3.15**filter media**

material separating particulate matter from gases and characterized by its separating structure and its structural and/or textile-technological characteristics

3.16**flow-through type replacement**

method to replace test gas in the batch type exposure chamber by introducing test gas continuously to the chamber

3.17**initial load**

initial load applied on the test specimen at the start of tensile test

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 16891:2016

<https://standards.iteh.ai/catalog/standards/sist/5c49ccc7-ac1b-453e-91a4-400000000000/iso-16891-2016>

3.18**length between holders**

length between holders of top and bottom holding chucks positioned at the start of the tensile test

Note 1 to entry: See [Figure 3](#).

3.19**load**

tensile strength of test specimen observed in the tensile test

3.20**non-continuous-flow-method**

exposing method of filter sheet, which is exposed in still test gas mixture

3.21**nonwoven fabric**

filter media using fabric made from long fibres, bonded together with each other by chemical, mechanical, heat or solvent treatment

3.22**number of replacement**

number of test gas replacement for whole heating space volume of the test chamber

3.23**replacement of gas**

exchange gas to maintain test gas concentration within certain concentration range

3.24**retention of tensile strength (standards.iteh.ai)**

ratio of tensile strength of the test specimen subjected to thermal and/or acid gas exposure to that of the test specimen without the exposure

3.25**strip method**

method of implementing tensile test with holding whole width of the test specimen with a holding device

3.26**tensile speed**

speed to pull a test specimen in tensile test

3.27**tensile strength**

value of the maximum load divided by the width of test specimen

3.28**test gas**

gas which may cause changes in physical properties of filter media to be used for tensile test

3.29**vacuum replacement**

method to replace test gas in the batch type exposure chamber by the use of vacuum

3.30**thermal exposure**

expose filter media at an elevated temperature to accelerate the change of its physical properties

3.31**woven fabric**

filter media using a fabric formed by weaving