



Designation: D 2208 – 00

Standard Test Method for Breaking Strength of Leather by the Grab Method¹

This standard is issued under the fixed designation D 2208; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the breaking strength of leather by the grab method. It is intended for use on light, soft leathers; boarded, sueded, or embossed leathers tested on a specimen in the form of a rectangle piece; narrow strap, welt, lace, and round belt leathers; or other leathers that cannot be accurately tested by Test Method D 2209. This test method does not apply to wet blue.

1.2 The test method is not recommended for breaking loads over 500 lbf (2200 N) because of slippage of the specimen in the jaws.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 1517 Terminology Relating to Leather²
- D 1610 Practice for Conditioning Leather and Leather Products for Testing²
- D 1813 Test Method for Measuring Thickness of Leather Test Specimens²
- D 2209 Test Method for Tensile Strength of Leather²
- D 2211 Test Method for Elongation of Leather²

3. Terminology

3.1 For definitions of leather terms used in this standard, refer to Terminology D 1517.

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of D31.04 on Apparel and Upholstery. This test method was developed in cooperation with the American Leather Chemists Assn. (Standards Method E 16–1965).

Current editions approved Sept. 10, 2000. Published October 2000. Originally published as D 2208–63T. Last previous edition D 2208–95.

² *Annual Book of ASTM Standards*, Vol 15.04.

4. Summary of Test Method

4.1 The leather specimen is clamped in the test machine as described in Test Method D 2209. The force required to rupture the leather at a jaw separation of 10 ± 2 in./min is measured, along with the percent elongation at rupture.

5. Significance and Use

5.1 The measurement of the strength of leather is often necessary in order to determine its suitability for its intended application. This test method is recommended for use on light, soft leathers, narrow strap, welt, lace and round belt leathers as well as others that cannot be accurately tested by Test Method D 2209.

6. Apparatus

6.1 *Testing Machine*, as described in Test Method D 2209.

NOTE 1—The face of one jaw of each clamp shall measure 1 by 1 in. (25.4 by 25.4 mm) and that of the other shall measure 1 by 1½ (25.4 by 38 mm) or more for testing specimens wider than the jaws only.

6.2 *Thickness Gage*—A dead-mass type of thickness gage as described in Test Method D 1813.

6.3 *Steel Scale*, graduated to read in 0.02 in. (0.5 mm).

7. Test Specimen

7.1 For testing specimens wider than the jaws, the specimen for wide, flat leathers shall be a small piece of leather 6 in. (152 mm) long and 3 in. (76 mm) wide. The direction of the long dimension relative to the backbone shall be noted.

7.2 For testing specimens cut from narrow strip, the specimen for narrow strap, welt, lace, and round belt leathers shall be a piece of leather 6 in. (152 mm) long.

8. Conditioning

8.1 All samples shall be conditioned for 48 h in standard atmospheric conditioning and tested under these conditions as described in Practice D 1610.

9. Procedure

9.1 *For Testing Specimens Wider than the Jaws:*