
**Road vehicles — Elastomeric boots for
cylinders for drum type hydraulic brake
wheel cylinders using a non-petroleum
base hydraulic brake fluid (Service
temperature 120 °C max.)**

iTeh STANDARD PREVIEW
*Véhicules routiers — Capuchons en caoutchouc pour cylindres de roue
pour freins hydrauliques à tambour utilisant un liquide de frein à base
(standards.iteh.ai) non pétrolière (température maximale d'utilisation 120 °C)*

[ISO 4927:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/b70752ea-7f57-477b-894b-9928821d7ee2/iso-4927-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4927:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/b70752ea-7f57-477b-894b-9928821d7ee2/iso-4927-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4927 was prepared by Technical Committee ISO/TC 22, *Road vehicles*, Subcommittee SC 2, *Braking systems and equipment*.

This second edition cancels and replaces the first edition (ISO 4927:1978), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4927:2005](https://standards.iteh.ai/catalog/standards/sist/b70752ea-7f57-477b-894b-9928821d7ee2/iso-4927-2005)

<https://standards.iteh.ai/catalog/standards/sist/b70752ea-7f57-477b-894b-9928821d7ee2/iso-4927-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4927:2005

<https://standards.iteh.ai/catalog/standards/sist/b70752ea-7f57-477b-894b-9928821d7ee2/iso-4927-2005>

Road vehicles — Elastomeric boots for cylinders for drum type hydraulic brake wheel cylinders using a non-petroleum base hydraulic brake fluid (Service temperature 120 °C max.)

1 Scope

This International Standard specifies performance tests for moulded rubber boots used at end closures on drum type wheel brake cylinders. These boots prevent the entrance of dirt and moisture which could cause corrosion and otherwise impair wheel brake operation.

This International Standard is applicable to boots of both plain and reinforcement insert types, for fitting in wheel cylinders using a fluid in accordance with ISO 4925. It does not include requirements relating to chemical composition, tensile strength or elongation at brake of the rubber compound. It does not cover the strength of adhesion of rubber to the reinforcement in the insert type.

The rubber material used in these boots shall be suitable for operation in a temperature range of – 40 °C to + 120 °C.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 48, *Rubber, vulcanized or thermoplastic — Determination of hardness (hardness between 10 IRHD and 100 IRHD)*

ISO 188:1998, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 1431-1:2004, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 4925, *Road vehicles — Specification of non-petroleum base brake fluids for hydraulic systems*

ISO 4926, *Road vehicles — Hydraulic brake system — Non-petroleum base reference fluids*

ISO 4928:1980, *Road vehicles — Elastomeric cups and seals for cylinders for hydraulic braking systems using a non-petroleum base hydraulic brake fluid (Service temperature 120 °C max.)*

3 General requirements

3.1 Workmanship and finish

The moulded boots shall be free from blisters, pin-holes, cracks, protuberances, embedded foreign material, or other physical defects, and shall conform to the dimensions specified on the drawings.

3.2 Marking

The identification mark of the manufacturer and other details as specified on the drawing shall be moulded into each boot where design permits. Each boot in conformity with this International Standard may also have the following mark: "ISO 4927".

3.3 Packaging

Boots shall be packaged to meet requirements specified by the purchaser.

3.4 Sampling

The minimum lot on which complete specification tests shall be conducted for quality control testing, or the frequency of any specific type test used to control production, shall be agreed upon by the manufacturer and the purchaser.

4 Test requirements

4.1 Resistance to fluid at elevated temperature

After the boots have been subjected to the test for resistance to fluids at elevated temperature as prescribed in 5.3, the change in volume and the change in hardness shall be within the following limits:

- change in volume: – 15 % to + 15 %;
- change in hardness: – 10 IHRD to + 10 IRHD.

4.2 High temperature stroking performance

After the high temperature stroking as specified in 5.4, a boot shall be free of flexure cracks which extend through the wall thickness, and shall fit tightly around the cylinder and push rod.

4.3 Low temperature stroking performance

During the low temperature stroking as specified in 5.5, a boot shall not crack or separate from its assembled position on the cylinder or become loose on the push rod.

4.4 Tension set performance

After the tension set test prescribed in 5.6, boots shall show no more than 75 % tension set.

4.5 Heat resistance performance (static)

After the heat resistance test as detailed in 5.7, a boot shall conform to the following requirements:

- a) no cracking shall occur when the boot is flexed similarly to service conditions;
- b) the change in hardness shall be within the limits – 5 IHRD to + 10 IRHD;
- c) no tackiness shall be evident after removal from the oven.

4.6 Ozone resistance performance

At the end of the 70 h exposure period as detailed in 5.8, test specimens shall be removed from the ozone chamber and examined under 2× magnification. The surface of the test specimens shall show no evidence of cracking, rupture or other deterioration.

5 Test procedures

5.1 Test specimens

Specimens prepared for all tests shall be cut from the same general area of sample. In addition, hardness test specimens shall be prepared according to ISO 48.

5.2 Determination of hardness

The method of determining rubber hardness shall be as described in ISO 48. Test each specimen submitted; record the range of IRHD. When the shape of the boot prevents using the method described in ISO 48, an alternative method agreed between manufacture and purchaser may be substituted. In this case, correlation of the results obtained shall be made to IRHD as in ISO 48.

5.3 Resistance to fluids at elevated temperature

5.3.1 Apparatus

5.3.1.1 Circulating air oven as specified in ISO 188 (3.2.2)

5.3.1.2 **Screw-top, straight-sided, round glass jar**, having a capacity of approximately 250 ml and inner dimensions of approximately 125 mm in height and 50 mm in diameter, and a tinned steel lid (no insert or organic coating).

5.3.2 Test specimens

A section weighing approximately 3 g to 5 g shall be cut from each of two boots.

5.3.3 Test fluid

The brake fluid used for the test shall be the compatibility fluid in accordance with ISO 4926.

5.3.4 Procedure

Rinse the specimens in isopropyl alcohol or its equivalent and wipe dry with a clean, lint-free cloth to remove dirt and packing debris. Do not allow the specimens to remain in the alcohol for more than 30 s.

Determine and record the initial hardness of the test specimens (see 5.2).

Determine the volume of each specimen in the following manner:

- Weigh each specimen in air (m_1) to the nearest 0,001 g and then weigh the specimen immersed in distilled water at room temperature (m_2). Quickly dip each specimen in alcohol and then wipe dry with a clean, lint-free cloth.
- Immerse two specimens completely in 75 ml of the test fluid in the glass jar and tightly cap the jar.
- Place the jar containing the specimen in the oven (5.3.1.1) at $120\text{ °C} \pm 2\text{ °C}$ for a period of $70\text{ h} \pm 2\text{ h}$. At the end of the heating period, remove the jar containing the specimen from the oven and allow to cool to

23 °C ± 5 °C for 60 m to 90 m. At the end of the cooling period, remove the specimens from the jar and rinse in isopropyl alcohol or its equivalent and wipe dry with a clean, lint-free cloth. Do not allow the specimens to remain in the alcohol for more than 30 s.

- After removing from the alcohol and drying, place each specimen in a separate, tarred, stoppered weighing bottle and weigh (m_3). Remove each specimen and weigh it immersed in distilled water (m_4) to determine water displacement after hot fluid immersion.

Determine the final volume and hardness of each specimen within 60 m after rinsing in alcohol.

5.3.5 Expression of results

5.3.5.1 Volume change shall be reported as a percentage of the original volume. The percentage change in volume is given by the formula:

$$\frac{(m_3 - m_4) - (m_1 - m_2)}{(m_1 - m_2)} \times 100$$

where

m_1 is the initial mass, in grams, in air;

m_2 is the initial apparent mass, in grams, in water;

m_3 is the mass, in grams, in air after immersion in test fluid;

m_4 is the apparent mass, in grams, in water after immersion in test fluid.

5.3.5.2 Change in hardness shall be determined and recorded.

5.3.5.3 The specimens shall be examined for disintegration as evidenced by blisters or sloughing (carbon black).

5.4 High temperature stroking test

5.4.1 Apparatus

5.4.1.1 **Circulating air oven** as specified in ISO 188 (3.2.2).

5.4.1.2 **Stroking fixtures** as shown in Figures 1 and 2 of ISO 4928.

5.4.2 Test specimen

Two boots shall be used as test specimens.

5.4.3 Procedure

Install two sample wheel cylinder boots on the cylinder for which they are designed, or equivalent. Then mount the cylinder in the actuator assembly, set to operate at (1000 ± 100) strokes per hour with a stroke length of 4,8 mm ± 0,5 mm.

Then place the cylinder assembly in the oven (5.4.1.1) and actuate for 70 h ± 2 h at 120 °C ± 2 °C. After the actuation of the assembly, remove it from the oven, allow to cool to room temperature, and examine the boots for flexure cracks and general appearance.

5.5 Low temperature stroking test

5.5.1 Apparatus

5.5.1.1 Cold chamber, in which the test specimens are exposed to the low temperature, of sufficient size to contain the apparatus assembled with test specimens and so arranged as to permit the operator to check and operate it without removal from the chamber.

It shall be capable of maintaining a uniform atmosphere of cold dry air within the specified temperature range of $-40\text{ }^{\circ}\text{C}$ to $-43\text{ }^{\circ}\text{C}$.

5.5.1.2 Stroking fixtures as shown in Figure 4 of ISO 4928.

5.5.2 Test specimens

Two boots shall be used as test specimens.

5.5.3 Procedure

Install the sample wheel cylinder boots on the cylinder for which they are designed, or equivalent. Place the test boots and the test apparatus in the cold chamber (see 5.5.1.1) and expose them to a temperature range of $-40\text{ }^{\circ}\text{C}$ to $-43\text{ }^{\circ}\text{C}$ for $22\text{ h} \pm 1\text{ h}$. After $22\text{ h} \pm 1\text{ h}$ of low temperature exposure, stroke them with the stroking test device for six strokes with a length of $4,8\text{ mm} \pm 0,5\text{ mm}$, at intervals of 30 s, without removal from the cold chamber.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.6 Tension set test

5.6.1 Apparatus

5.6.1.1 Circular stretching mandrels, having a diameter which will expand by $15_{-3}^0\%$ one or the other of the sealing ends attached to the wheel cylinder or to the actuating rod. The mandrel diameter (d_3) is calculated as 115 % of the moulded diameter of the chosen boot end. The moulded diameter shall be calculated from the average of two measurements made at right angles to one another on a contour projector. The mandrel shall be provided with a smooth lead-in chamfer to prevent cutting of the rubber and shall itself have a polished machine finished (16 Ra maximum).

5.6.1.2 Circulating air oven as specified in ISO 188 (3.2.2).

5.6.2 Test specimens

Three boots shall be used as test specimens.

5.6.3 Procedure

5.6.3.1 Measure accurately and record the inside diameter (d_1) of the ends of three specimen boots. Assemble on the stretching mandrels (5.6.1.1). Place the assemblies in the oven (5.6.1.2) and age for $70\text{ h} \pm 2\text{ h}$ at $120\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$. Remove the assemblies and cool at room temperature for 1 h. Remove the boots. Allow to recover for between 30 m and 1 h. Again measure and record the diameter (d_1).

5.6.3.2 The tension set as a percentage of the original stretch deflection is given by the formula:

$$\frac{d_2 - d_1}{d_3 - d_1} \times 100$$