



Designation: D 4122 – 05

Standard Practice for Carbon Black—Evaluation of an Industry Reference Black¹

This standard is issued under the fixed designation D 4122; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers guidelines for the production and testing for uniformity of a lot of carbon black to be used as an Industry Reference Black (IRB).

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- D 412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension
- D 1506 Test Methods for Carbon Black—Ash Content
- D 1508 Test Method for Carbon Black, Pelleted Fines and Attrition
- D 1509 Test Methods for Carbon Black—Heating Loss
- D 1510 Test Method for Carbon Black—Iodine Adsorption Number
- D 1513 Test Method for Carbon Black, Pelleted—Pour Density
- D 1514 Test Method for Carbon Black—Sieve Residue
- D 1618 Test Method for Carbon Extractables—Transmittance of Toluene Extract
- D 1765 Classification System for Carbon Blacks Used in Rubber Products
- D 2414 Test Method for Carbon Black—Oil Absorption Number (OAN)
- D 3182 Practice for Rubber—Materials, Equipment, and

Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets

- D 3191 Test Methods for Carbon Black in SBR (Styrene-Butadiene Rubber)—Recipe and Evaluation Procedures
- D 3192 Test Methods for Carbon Black Evaluation in NR (Natural Rubber)
- D 3265 Test Method for Carbon Black—Tint Strength
- D 3493 Test Method for Carbon Black—Oil Absorption Number of Compressed Sample (COAN)
- D 5230 Test Method for Carbon Black—Automated Individual Pellet Hardness
- D 6556 Test Methods for Carbon Black—Total and External Surface Area by Nitrogen Adsorption

3. Significance and Use

3.1 These guidelines are intended to ensure that IRBs are evaluated by a standard procedure.

3.2 These guidelines are to be used to establish the average physicochemical and physical rubber properties of a lot of carbon black to be used as an IRB.

4. Production, Quality Control, and Quality Assurance

4.1 It is assumed that the manufacturer of the IRB will use state-of-the-art techniques to ensure maximum uniformity throughout the entire production run. The production should be made in one continuous production lot run. The testing called for in this practice is not intended to be a substitute for in-process quality control. This interlaboratory study is only adequate to verify the quality of a homogeneous lot.

4.2 The size of the lot is determined by historical records on the rate of use. The lot should have an expected life of 8 to 10 years at the most recent rate of use.

4.3 The black should be bagged in 50-lb polyethylene bags to reduce moisture incursion. Each pallet of bagged black should be wrapped in plastic to reduce environmental exposure. The bagged black will be segregated into at least twelve equal sized sublots for uniformity testing.

5. Sampling

5.1 After a suitable time to allow the black to stabilize, a bag will be selected from the approximate middle of each of the sublots; the bags selected will be numbered from one through

¹ This practice is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.61 on Carbon Black Sampling and Statistical Analysis.

Current edition approved Jan. 1, 2005. Published January 2005. Originally approved in 1982. Last previous edition approved in 2002 as D 4122 – 02.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Industry Reference Black Test Data

Laboratory Number		Sample No.	Tensile Strength, MPa	Tensile Stress at 300 %, MPa	Elongation, %	Tensile Strength, MPa	300 % Modulus, MPa	Elongation, %	Iodine No., g/kg	STSA 10 ³ m ² /kg	NSA Multi-point Adsorption 10 ³ m ² /kg	Oil Absorption, No., 10 ⁻⁵ mg ³ /kg (cm ³ /100 g)	Compressed Oil No., 10 ⁻⁵ mg ³ /kg (cm ³ /100 g)	Tint Strength,	Pour Density, kg/m ³ (lb/ft ³)
Day of Mixing and Date	Day No.		D 3191	D 3191	D 3191	D 3192A	D 3192A	D 3192A	D 1510	D 6556	D 6556	D 2414	D 3493	D 3265	D 1513
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									
Day No. ___		50'				30'									
Date ___	Prev. IRB	50'				30'									

<https://standards.iteh.ai>

n, where *n* is the total number of sublots, in order to represent the corresponding production lot.

5.2 *n* 4-dm³ (1-gal) samples, numbered from one through *n*, and taken from the corresponding bags, will be sent to each participant in the interlaboratory study to evaluate the new IRB.

5.3 Additionally, a 4-dm³ (1-gal) sample of the *previous* IRB taken from a common blended source will also be sent to each participant.

6. Procedure

6.1 Test, in order, one of the *n* samples on each of the one to *n* days. These days shall be as near to consecutive as possible.

6.2 Each day a sample is tested, subject it to all of the test methods described in 6.3-6.5.

6.3 *Physicochemical Tests:*

6.3.1 Perform the following physicochemical tests on both the new and previous IRB:

6.3.1.1 *Iodine Adsorption Number (Test Method D 1510)*—Report the result obtained from an individual determination in grams of iodine per kilogram to the nearest 0.1 unit.

6.3.1.2 *Total and External NSA (Test Methods D 6556)*—Report total and external NSA from a single determination in 10³ m²/kg (m²/g) to the nearest 0.1 unit.

6.3.1.3 *Oil Absorption Number (Test Method D 2414)*—Report the result obtained from an individual determination in 10⁻⁵ m³kg (cm³/100 g) to the nearest 0.1 unit.

6.3.1.4 *Oil Absorption Number of Compressed Sample (Test Method D 3493)*—Report the result obtained from an individual determination in 10⁻⁵ m³kg (cm³/100 g) to the nearest 0.1 unit.

6.3.1.5 *Tint Strength (Test Method D 3265)*—Report the result obtained from an individual determination in percent of ITRB to the nearest 0.1 unit.

6.3.1.6 *Pour Density (Test Method D 1513)*—Report the result obtained from an individual determination in kg/m³ (lb/ft³) to the nearest whole unit.

6.3.2 Record data on **Table 1**.

6.4 *Rubber Physical Tests:*

6.4.1 Perform the following physical tests in rubber on both the new and previous IRB. Test samples mixed in accordance with Test Methods **D 3191** and cure for 50 min at 145°C as well as samples mixed in accordance with Test Methods **D 3192**, Test Method A, and cure for 30 min at 145°C.

6.4.1.1 In accordance with Test Methods **D 412**, Test Method A, test five dumbbells from each cured sheet and determine the median values of tensile stress at 300 % elongation, tensile strength, and ultimate elongation.

6.4.1.2 Record data in absolute numbers (not as differences from IRB) on **Table 1**, reporting tensile stress and tensile strength to the nearest 0.1 MPa and ultimate elongation to the nearest 5 %.

6.5 *Informational Physicochemical Tests:*

6.5.1 Perform the following physicochemical tests on the new IRB:

6.5.1.1 *Ash Content (Test Methods D 1506)*—Report results obtained from a single determination to the nearest 0.01 %.

TABLE 2 Statistical Analysis Form

NOTE 1—Experience so far has shown that neither a laboratory’s test values nor a sample’s test values are random values about the grand average, but tend to reflect a persistent bias typified by the average value for the laboratory or the sample. Consequently, it is not appropriate to divide the reproducibility by the square root of L or N as might otherwise be the case when comparing averages of L or N values to the grand average of $L \times N$ values.

Test Method: ASTM D _ _ _								
Sample No. ↓	Laboratory No. →	1	2	...	i	...	L	\bar{X}_R
1								
2								
...								
j								
...								
N								
\bar{X}_C								$\bar{X} =$

Row average $\bar{X}_R = \sum_j X_j / L$
 Grand average test value $\bar{X} = \sum_j \bar{X}_R / N$
 Upper and lower control limits for row averages = $\bar{X} \pm$ reproducibility of the test method.
 Column average $\bar{X}_C = \sum_j X_j / N$
 Upper and lower control limits for column averages = $\bar{X} \pm$ reproducibility of the test method.

6.5.1.2 *Fines and Attrition (Test Method D 1508)*—Report results obtained from a single determination to the nearest 0.1 %.

6.5.1.3 *Heating Loss (Test Methods D 1509)*—Report results obtained from a single determination to the nearest 0.1 %.

6.5.1.4 *Sieve Residue, 325 Mesh (Test Method D 1514)*—Report results obtained from a single determination to the nearest mg/kg (ppm).

6.5.1.5 *Transmittance of Toluene Extract (Test Method D 1618)*—Report results obtained from a single determination to the nearest 0.1 % transmittance.

6.5.1.6 *Pellet Hardness (Test Method D 5230)*—Report results obtained from a single determination to the nearest whole number for the maximum and average.

7. Statistical Analysis

7.1 For each test in **Table 1**, enter the results from each laboratory for each sample into the form shown in **Table 2**. Then calculate the statistics defined in **Table 2**.

NOTE 1—Rubber physical test data are to be entered as differences from the previous IRB. For example:

$$\text{Difference} = X_1 - X_2 \quad (1)$$

where:

- X_1 = measured value for new IRB, and
- X_2 = measured value for previous IRB.

7.2 If any row average test result falls outside the interval defined by the upper and lower control limits shown in **Table 2**, this will indicate that the subplot of IRB represented by that row average may be rejected by Committee D24 as being a nonhomogeneous portion of the production lot.

7.3 If any laboratory average test result (column average) falls outside the upper and lower control limits shown in **Table**

2, then that laboratory’s data for that test should be deleted and **Table 2** should be recalculated excluding that laboratory. Such data indicates that the laboratory has a significant reproducibility problem, which needs corrective action.

7.4 After deleting data, the remaining data for each test method can be averaged to provide typical values for tabulation in Classification **D 1765** and average differences between the new IRB and the previous one.

7.5 For each test in **Table 3**, enter the results from each laboratory for each sample in the form shown in **Table 2**. Then calculate the statistics defined in **Table 2**. The results are for information only and not to determine the uniformity of the lot.

8. Acceptance

8.1 All sublots tested as homogeneous by this practice will be considered acceptable by Committee D24 for use as the new IRB. The average values will be published in Classification **D 1765**.

9. Shelf Life

9.1 The shelf life of carbon black is indefinite when properly stored in a manner that protects it from exposure to wet weather or other sources of liquid water. Iodine number is the only property known to change over an extended period (years) and steps are being taken within ASTM Committee D24 to address this issue.

10. Keywords

10.1 blending; industry reference blacks (IRBs); lot size; physical properties; physicochemical properties; shelf life; statistical analysis form; table for IRB test data; uniformity guidelines for production and testing